BETA TESTING SERVICES

Tension test report - ASTM E8/E8M

Parameter	Value	Unit
Specimen	AL-004	
Alloy / grade	Al 6061-T6	
Date tested	09/18/2026	
0.2% offset yield strength	40.2	ksi
Ultimate tensile strength	45.1	ksi
Elongation in 2 in.	12.0	%
Notes	Normal ductile failure.	