BETA TESTING SERVICES

Tension test report - ASTM E8/E8M

Parameter	Value	Unit
Specimen	ST-103	
Alloy / grade	S355JR	
Date tested	09/18/2026	
0.2% offset yield strength	54.0	ksi
Ultimate tensile strength	76.3	ksi
Elongation in 2 in.		%
Notes	Extensometer slipped, elongation not recorded.	