BETA TESTING SERVICES

Tension test report - ASTM E8/E8M

Parameter	Value	Unit
Specimen	TI-201	
Alloy / grade	Ti-6Al-4V	
Date tested	09/21/2026	
0.2% offset yield strength	133.5	ksi
Ultimate tensile strength	143.0	ksi
Elongation in 2 in.	14.0	%
Notes	Normal ductile failure.	