Gamma Metrology

Mechanical testing - technician's report

On 6 October 2026 we tested AL-005, an Al 6061-T6 extrusion. Proof stress at 0.2% plastic strain came out at 288 MPa, while ultimate strength reached 322 MPa. Elongation measured on the broken halves was 10.9 percent.