Gamma Metrology

Mechanical testing - technician's report

Specimen ST-104 (structural steel, grade S355JR) was pulled to failure on 3 October 2026. The upper yield point was observed at 366 MPa; the curve then rose to a maximum of 502 MPa before necking. Total elongation after fracture: 25 percent. No anomalies.