Gamma Metrology

Mechanical testing - technician's report

Report on specimen TI-203, machined from Ti-6Al-4V bar stock. The test was carried out on 3 October 2026 at room temperature. Plastic deformation began at roughly 905 MPa (0.2% offset) and the specimen failed at a peak stress of 968 MPa, after stretching by 13.5 percent of its gauge length. The fracture surface showed a classic cup-and-cone pattern.