

Firefighters work in the harshest environments, and need gear that provide protection and comfort so they can focus on saving lives.

Firefighters are exposed to many hazards including smoke and soot particulate which are highly toxic carcinogens as they are absorbed through the skin.

The **KL200** is Life Liners second generation particulate blocking hood to provide additional protection against smoke and soot particulate.

Offering outstanding breathability, increase air permeability and a unique construction for ease of movement and flexibility, the KL200 minimizes heat stress while reducing exposure to particulates, providing additional protection for the firefighter.

#### CERTIFICATIONS

NFPA 1971-2018 UL Certified

#### FABRICS

Outer Layer: 49% Kermel/ 49% Lenzing FR/2% Spandex

Inner Layer: Stedair Prevent

#### WEIGHT

Outer layer: 8.4 oz. sq. yard Inner layer: 4.35 oz. sq. yard

#### CONSTRUCTION

Outer Layer 1x1 Rib Knit

#### COLOR

Navy

TAN

#### SIZES

Small, Medium, Large

#### THERMAL PROTECTIVE PERFORMANCE (TPP)

As received 29.6 Cal/cm<sup>2</sup>

After 5 washes 36.9 Cal/cm<sup>2</sup>

#### THERMAL Heat Loss (THL)

385.6 W/M<sup>2</sup>

#### HOOD MATERIAL BURST STRENGTH

Outer Layer 445

Inner Layer: 413 N

#### Particulate Blocking

As received 99%+

After 10 Conditionings 98.7%+

## Hood Specifications

Model: KL200

NFPA 1971-2018

TPP As Received: 29.6 Cal/cm<sup>2</sup>

TPP After 5 Washes: 36.9 Cal/cm<sup>2</sup>

THL: 385 W/M<sup>2</sup>



Issued: May 4, 2018

## FLAME RESISTANCE TEST

### Outer Layer

After Flame As received 0 seconds

After 5 washes 0 seconds

Char Length As received 28mm

After 5 washes 20mm

### Inner Layer

After Flame As received 0 seconds

After 5 washes 0 seconds

Char Length As received 73mm

After 5 washes 56mm

## DESIGN

Separate head with sewn on back and front bib, Back of head ends at the nape of the neck for improved fit and comfort.

Two piece design with 6" front with 8" back

## LAYERS

2 Layer

## CLEANING SHRINKAGE RESISTANCE TEST

Hood Measurement 0.34% avg.

## HEAT AND THERMAL SHRINKAGE RESISTANCE TEST

Hood MeasuAs received 0.4% avg.

After 5 washes 0.1% avg

## SEAM BREAKING STRENGTH TEST

644 N

## MELT, DRIP, IGNITE, SEPARATE WHEN EXPOSED TO FLAME

None

## FACE OPENING

Easy-Seal Face opening that goes on easy. Seals tight

Sewn with 1/2" elastic encapsulated in hood material

## CONSTRUCTION

Head Seams: All head and bib seams are sewn with a flat lock stitch

Binding: 1 1/2" binding sewn to hem through folder with a three thread cover stitch to create a 1/2" finished bound hem

## THREAD

100% Nomex

## LABELS

Each hood is labeled with an FR Label with all four label edges sewn

to the hood, identifying material contents and UL certification

## Hood Specifications

Model: KL200

NFPA 1971-2018

TPP As Received: 29.6 Cal/cm<sup>2</sup>

TPP After 5 Washes: 36.9Cal/cm<sup>2</sup>

THL: 385 W/M<sup>2</sup>



Fabric Performance Values in accordance with NFPA 1971-2018 test report dated 3/23/2018 preformed by Underwriters Laboratories

Issued: May 4, 2018