

Experiment No: 03
Determination of the Ten Percent Fines Value

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels/ Boulder/ Rock

Sample Size : 14 mm to 10 mm

Test Method : Bs 812 (part 3) 1975

Force required to produce T.F.V = $4000 \text{ KN} / A.I.V = 4000/18.11=221\text{KN}$.

Used Force = x = KN

Test No	1	2	3
Data			
Wt. of Sample (Surface Dry), A (gm)	3180	3230	3180
Wt. of materials retained on 2.36 mm sieve, C (gm)	2907	2930	2857
Wt. of materials passing 2.36 mm sieve, B (gm)	273	300	245
Percent Fines = $B/A \times 100\%$ (to the first decimal place)	8.5	9.2	7.9
Mean percentage fines (y), at x = 221 KN force	8.6		

Calculation:

Ten Percent Fines Value (T.F.V) = $14x / (y+4) =$
 (to the nearest 5 KN, if < 100 KN
 & 10KN, if $\geq 100 \text{ KN}$)

Ten Percent Fines Value (T.F.V): 246kN

Signature of the Course Teacher