

Experiment No: 02
Determination of Aggregate Crushing Value

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels/ Boulder/ Rock

Sample Size : 14 mm to 10 mm

Test Method : Bs 812 (part 3) 1975

Test No	1	2	3
Data			
Wt. of Sample (Surface Dry), A (gm)	2548		
Wt. of materials retained on 2.36 mm sieve, C (gm)	2060		
Wt. of materials passing 2.36 mm sieve, B (gm)	488		
Aggregate Crushing Value (%) = $B/A \times 100\%$ (to the first decimal place)	20		
Average Aggregate Crushing Value (ACV) = (to the nearest whole number)	20		

Average Aggregate Crushing Value: 20%