

Experiment No: 01
Determination of Aggregate Impact Value

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels/ Boulder/ Rock

Sample Size : 14 mm to 10 mm

Test Method : Bs 812 (part 3) 1975

Data	Test No	1	2	3
Wt. of Sample (Surface Dry), A (gm)		508		
Wt. of materials retained on 2.36 mm sieve, C (gm)		416		
Wt. of materials passing 2.36 mm sieve, B (gm)		92		
Aggregate Impact Value (%) = $B/A \times 100\%$ (to the first decimal place)		18.11		
Average Aggregate Impact Value (AIV) = (to the nearest whole number)		18%		

Average Aggregate Impact Value (AIV): **18%**

Signature of the Course Teacher