

Experiment No: 06
Determination of Angularity Number

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels

Test Method : Bs 812; Part 1 Clause: 7.5 & BS 812, Part 2 Clause: 5

Serial No.	Mass of Aggregate in Cylinder (gm)	Mean Mass of Aggregate in the Cylinder, (M) (gm)	Relative Density of the Aggregate (Oven dry basis) (G)	Water Required to Fill the Cylinder, (C) (gm)	Angularity Number (A.N)
1	5161	5161.67	2.68	3159	6.03
2	5159				
3	5165				

Calculation:

$$\text{Angularity Number (A.N)} = 67 - \frac{100 M}{CG} = 6 \text{ (almost) (to the nearest whole number)}$$