

Experiment No: 05
Determination of the Elongation Index

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels/ Boulder/ Rock

Test Method : Bs 812 (part 1) Clause 7.3 & 7.4

Sieve size (mm)	Gauge size used, (mm)	Wt. of the material retained (gm)	Percent of the material retained	Check if greater than 5% (ok/ not ok)	Elongated Particles (amount retained) gm
50.0	-	X	X		
37.5	78.0				
28.0	59.0				
20.0	43.2	681	45.52	Ok	153
14.0	30.6	635	42.44	Ok	144
10.0	21.6	51	3.40	Not ok	0
6.3	14.7	129	8.62	ok	34
		M ₁ =1496	M ₂ =1445		M ₃ =331

Calculation: $331/1445 = 0.229 \times 100\% = 22.9\%$

Elongation index (E.I) = $M_3/M_2 \times 100\% = 23\%$ (to the nearest whole number)

Signature of the Course Teacher