

Experiment No: 04
Determination of the Flakiness Index

Name :

Student No:

Type of material : Brick Chips/ Stone Chips/ Gravels/ Boulder/ Rock

Test Method : Bs 812 (part 1) Clause 7.3 & 7.4

Sieve size (mm)	Gauge size used, (mm)	Wt. of the material retained (gm)	Percent of the material retained	Check if greater than 5% (ok/ not ok)	Flaky Particles (amount passed) gm
63.0	-	x	x		
50.0	33.9				
37.5	26.3				
28.0	19.7				
20.0	14.4	681	45.52	Ok	58
14.0	10.2	635	42.44	Ok	118
10.0	7.2	51	3.40	Not ok	0
6.3	4.9	129	8.62	ok	39
		M ₁ =1496	M ₂ =1445		M ₃ =215

Calculation: (215/1445)*100%= 15% [almost]

Flakiness index (F.I) = $M_3/M_2 \times 100\%$ = 15% (to the nearest whole number)

Signature of the Course Teacher