TECHNICAL DATA SHEET



YIPIN® Iron Oxide Pigment Iron Oxide Brown S5237

Edition of2015-11-20TypeBrown PigmentDelivery FormPowder pigmentChemical ClassSynthetic Iron Oxide

Color Index Combination of C.I.77491,77492,77499

Use Recommendation Building Industry

COLOR VALUES AND TINTING STRENGTH							
Reference			Standard				
	<u>Min</u>	<u>Max</u>	Test Method				
Reduction with titanium dioxide (1:2)		R-706	Similar to ASTM D-387				
L*	-0.7	+0.7					
a*	-0.7	+0.7					
b*	-0.7	+0.7					
E*ab		1.0					
Binder		R-05					
Relative tinting strength [%]	95	105	Similar to ASTM D-387				

TECHNICAL DATA			
	<u>Min</u>	<u>Max</u>	Test Method
Water-Soluble Content [%]		1.0	ASTM 1208-96
Sieve Residue 0.045mm [%]		0.5	ASTM D 185
Fe ₂ O ₃ [%]	88.0		ASTM D 50
Moisture (After Production) [%]		1.0	ASTM D 280-01

TECHNICAL DATA SHEET





STANDARD PACKAGING	50LB/bag	

TRANSPORT AND STORAGE

Protect against weathering. Store in a dry place and avoid extreme fluctuations in temperature. Special conditions for opened packaging: Close bags after use to prevent the absorption of moisture and contamination.

SAFETY

The product is not classified as dangerous under the relevant EC directives and corresponding national regulations valid in the individual EU member states. It is not dangerous according to transport regulations. In countries outside the EU, compliance with the respective national legislation concerning the classification, packaging, labeling and transport of dangerous substances must be ensured.

The information contained in the safety data sheet should be observed.

This contains information on handing, product safety and ecology.

This information is given in good faith, without warranty. It is also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General conditions of sale and delivery.