BUY NOW

Copyright © 2001 ASM International®
All rights reserved
www.asminternational.org

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Aluminum, Unalloyed ingot															
USA															
AA Registration Record(00)	P0202A	For intermediate steps in smelting, casting, alloying only			0.02 max		0.02 max	0.02 max	0.01 max	0.02 max	As<=0.009; Ga<=0.02; V<=0.01; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0303A	For intermediate steps in smelting, casting, alloying only			0.03 max		0.03 max	0.03 max	0.01 max	0.02 max	As<=0.009; Ga<=0.03; V<=0.01; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0303B	For intermediate steps in smelting, casting, alloying only			0.03 max		0.03 max	0.03 max	0.01 max	0.02 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0304A	For intermediate steps in smelting, casting, alloying only			0.04 max		0.03 max	0.03 max	0.01 max	0.02 max	As<=0.009; Ga<=0.03; V<=0.01; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0305A	For intermediate steps in smelting, casting, alloying only			0.05 max		0.03 max	0.03 max	0.01 max	0.02 max	As<=0.009; Ga<=0.03; V<=0.01; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0404A	For intermediate steps in smelting, casting, alloying only			0.04 max		0.04 max	0.03 max	0.01 max	0.03 max	As<=0.009; Ga<=0.03; V<=0.01; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0404B	For intermediate steps in smelting, casting, alloying only			0.04 max		0.04 max	0.03 max	0.01 max	0.03 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0405A	For intermediate steps in smelting, casting, alloying only			0.05 max		0.04 max	0.03 max	0.02 max	0.03 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0406A	For intermediate steps in smelting, casting, alloying only			0.06 max		0.04 max	0.03 max	0.02 max	0.04 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0506A	For intermediate steps in smelting, casting, alloying only			0.06 max		0.05 max	0.03 max	0.02 max	0.05 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0506B	For intermediate steps in smelting, casting, alloying only			0.06 max		0.05 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0507A	For intermediate steps in smelting, casting, alloying only			0.05 max		0.07 max	0.03 max	0.02 max	0.05 max	As<=0.009; Ga<=0.03; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0507B	For intermediate steps in smelting, casting, alloying only			0.07 max		0.05 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0610A	For intermediate steps in smelting, casting, alloying only			0.10 max		0.06 max	0.03 max	0.02 max	0.05 max	As<=0.009; Ga<=0.04; V<=0.02; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0610B	For intermediate steps in smelting, casting, alloying only			0.10 max		0.06 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P0610C	For intermediate steps in smelting, casting, alloying only			0.10 max		0.06 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1015A	For intermediate steps in smelting, casting, alloying only			0.15 max		0.10 max	0.03 max	0.03 max	0.10 max	As<=0.009; Ga<=0.04; V<=0.03; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1015B	For intermediate steps in smelting, casting, alloying only			0.15 max		0.10 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1015C	For intermediate steps in smelting, casting, alloying only			0.15 max		0.10 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1015D	For intermediate steps in smelting, casting, alloying only			0.15 max		0.10 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				

UNS numbers and US grades are provided as a means of cross referencing chemically similar alloys. Exchangability is only possible after independent examination of specifications. Tensile properties are minimum or typical as specified. UTS and YS as MPa. El as %. OE=others each. OT=others total.

Aluminum, Unalloyed ingot (Continued from previous page)

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
USA															
AA Registration Record(00)	P1020A	For intermediate steps in smelting, casting, alloying only			0.20 max		0.10 max	0.03 max	0.03 max	0.10 max	As<=0.009; Ga<=0.04; V<=0.03; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1020B	For intermediate steps in smelting, casting, alloying only			0.20 max		0.10 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1020C	For intermediate steps in smelting, casting, alloying only			0.20 max		0.10 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1020D	For intermediate steps in smelting, casting, alloying only			0.20 max		0.10 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1020E	Inactive									base Al				
AA Registration Record(00)	P1020G	For intermediate steps in smelting, casting, alloying only			0.20 max		0.10 max	0.03 max	0.03 max	0.10 max	As<=0.009; Ga<=0.04; Li<=0.0001; Mg<=0.003; Na<=0.0010; V<=0.03; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1520A	For intermediate steps in smelting, casting, alloying only			0.20 max		0.15 max	0.03 max	0.03 max	0.10 max	As<=0.009; Ga<=0.04; V<=0.03; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1520B	For intermediate steps in smelting, casting, alloying only			0.20 max		0.15 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1520C	For intermediate steps in smelting, casting, alloying only			0.20 max		0.15 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1520D	For intermediate steps in smelting, casting, alloying only			0.20 max		0.15 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1535A	For intermediate steps in smelting, casting, alloying only			0.35 max		0.15 max	0.03 max	0.03 max	0.10 max	As<=0.009; Ga<=0.04; V<=0.03; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1535B	For intermediate steps in smelting, casting, alloying only			0.35 max		0.15 max		0.05 max	0.10 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1535C	For intermediate steps in smelting, casting, alloying only			0.35 max		0.15 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1535D	For intermediate steps in smelting, casting, alloying only			0.35 max		0.15 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P1535E	Inactive									base Al				
AA Registration Record(00)	P2055A	For intermediate steps in smelting, casting, alloying only			0.55 max		0.20 max	0.03 max	0.05 max	0.15 max	As<=0.009; Ga<=0.04; V<=0.04; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2055C	For intermediate steps in smelting, casting, alloying only			0.55 max		0.20 max		0.10 max	0.20 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2055D	For intermediate steps in smelting, casting, alloying only			0.55 max		0.20 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2055E	Inactive									base Al				
AA Registration Record(00)	P2070A	For intermediate steps in smelting, casting, alloying only			0.70 max		0.20 max	0.03 max	0.05 max	0.15 max	As<=0.009; Ga<=0.04; V<=0.04; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2070B	For intermediate steps in smelting, casting, alloying only			0.70 max		0.20 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2070E	Inactive									base Al				

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Aluminum, Unalloyed ingot (Continued from previous page)															
USA															
AA Registration Record(00)	P2585A	For intermediate steps in smelting, casting, alloying only			0.85 max		0.25 max	0.03 max	0.05 max	0.15 max	As<=0.009; Ga<=0.04; V<=0.04; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2585B	For intermediate steps in smelting, casting, alloying only			0.85 max		0.25 max		0.15 max	0.30 max	As<=0.009; Cd+Hg+Pb<=0.0095; bal Al; base Al				
AA Registration Record(00)	P2585E	Inactive									base Al				
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 100.x															
Czech Republic															
CSN	424109		99.0 min	0.02 max	0.6 max		0.5 max	0.08 max			Ti<=0.03; Fe+Si<=0.9; base Al				
Finland															
SFS 2563	G-Al99.0		99	0.03	0.8		0.5	0.08			base Al				
France															
NF A57-101	A4	Ingot	99.0 min	0.05 max	0.9 max	0.05 max	0.9 max	0.10 max	0.05 max	1.00 max	Ga<=0.05; Mg<=0.05; Ti<=0.05; V<=0.05; Si+Fe<=0.9; base Al				
India															
IS 202 or 617	1900	Sand, permanent mold, pressure die cast		0.2 max	0.6 max	0.2 max	0.5 max	0.1 max			Mg<=0.05; Ni<=0.1; Pb<=0.05; Sn<=0.05; bal Al; base Al				
IS 202 or 617	A-0	Former designation. See 1900									base Al				
International															
ISO/R 115(68)	Al99.0	Ingot, for remelting	99.00 min	0.03 max	0.80 max		0.50 max	0.08 max	0.03 max		Cu+Fe+Si+Zn<=1.00; base Al				
Japan															
JIS H2102(83)	Class 3	Virgin ingot	99.00 min	0.02 max	0.80 max	0.03 max	0.50 max				Ti<=0.03; base Al				
JIS H2103(71)	Class 1	Secondary ingot for mill product	99 min	0.2 max	0.5 max	0.1 max	0.4 max	0.1 max			Mg<=0.1; base Al				
South Africa															
SABS 711	Al99.0	Ingot for remelting	99 min	0.005 max	0.04	0.01 max	0.04 max	0.015 max		0.005 max	Ga<=0.03; Mg<=0.01; Ti<=0.005; base Al				
Sweden															
MNC 41E	4024	Ingot	99								base Al				
SIS 144024	4024-00		99	0.03	0.8		0.5	0.08			base Al				
USA															
	UNS A01001	Foundry alloy, ingot	99.00	0.10 max	0.6-0.8		0.15 max	0.05 max	0.03 max	0.10 max	Mn+Cr+Ti+V<=0.025; Al nominal; base Al				
AA Registration Record(99)	100.1	Ingot; conductivity 54% IACS min	99.00 min	0.10 max	0.6-0.8		0.15 max	0.05 max	0.03 max	0.10 max	Mn+Cr+Ti+V<=0.025; base Al				
ASTM B179(96)	100.1	Ingot for die casting	99.00	0.10 max	0.6-0.8		0.15 max	0.05 max	0.03 max	0.10 max	Mn+Cr+Ti+V<=0.025; base Al				
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 130.x															
USA															
	UNS A01301	Foundry alloy, ingot	99.30 min	0.10 max			0.15 max	0.05 max	0.03 max	0.10 max	Fe/Si>=2.5; Mn+Cr+Ti+V<=0.025; base Al				
AA Registration Record(99)	130.1	Ingot; conductivity 54% IACS min	99.30 min	0.10 max				0.05 max	0.03 max	0.10 max	Fe/Si>=2.5; Mn+Cr+Ti+V<=0.025; base Al				
ASTM B179(96)	130.1	Ingot for die casting	99.30	0.10 max				0.05 max	0.03 max	0.10 max	Fe/Si>=2.5; Mn+Cr+Ti+V<=0.025; base Al				
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 150.x															
Australia															
AS 1874(00)	AA150	Ingot	99.95 min		0.40 max		0.3 max		0.03 max	0.15 max	base Al				

UNS numbers and US grades are provided as a means of cross referencing chemically similar alloys. Exchangability is only possible after independent examination of specifications. Tensile properties are minimum or typical as specified. UTS and YS as MPa. El as %. OE=others each. OT=others total.

Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 150.x (Continued from previous page)

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Czech Republic															
CSN	424105		99.5 min								base Al				
CSN	424106		99.5 min	0.02 max	0.35 max		0.3 max	0.06 max			Ti<=0.03; Fe+Si<=0.45; base Al				
Europe															
CEN EN 576(96)	EN AB-10451	Unalloyed ingot for remelting		0.02 max	0.40 max	0.03 max	0.15 max	0.05 max	0.03 max	0.10 max	Mg<=0.03; Ti<=0.02; bal Al; base Al				
CEN EN 576(96)	EN AB-10501	Unalloyed ingot for remelting	99.50 min	0.02 max	0.30 max	0.03 max	0.15 max	0.05 max	0.03 max		Li<=0.0001; Mg<=0.0050; Na<=0.0010; Ti<=0.02; base Al				
CEN EN 576(96)	EN AB-10502	Unalloyed ingot for remelting	99.50 min	0.02 max	0.30 max	0.03 max	0.15 max	0.05 max	0.02 max		Mg<=0.03; Na<=0.003; Ti<=0.02; base Al				
Finland															
SFS 2562	G-Al99.5		99.5	0.03	0.4		0.3	0.07			base Al				
France															
NF A57-101	A5	Ingot	99.50 min	0.02 max	0.30 max	0.03 max	0.20 max	0.05 max	0.03 max	0.50 max	Ga<=0.03; Mg<=0.03; Ti<=0.02; V<=0.03; base Al				
Germany															
DIN 1712-3	3.0250/Al99.5H	Ingot. Inactive. Replaced by DIN EN 573-3	99.50 min	0.02 max	0.35 max		0.25 max	0.05 max	0.03 max	0.50 max	Ti<=0.02; base Al				
DIN 1712-3	3.0256/E-AlH	Ingot. Inactive. Replaced by DIN EN 573-3	99.50 min	0.02 max	0.35 max		0.20 max	0.04 max	0.03 max	0.50 max	Cr+Mn+Ti+V<=0.03; base Al				
India															
IS 202 or 617	1950	Sand, permanent mold, pressure die cast		0.03 max	0.40 max	0.03 max	0.30 max	0.07 max			Mg<=0.03; Ni<=0.03; Pb<=0.03; Sn<=0.03; bal Al; base Al				
International															
ISO/R 115(68)	Al99.5	Ingot, for remelting	99.50 min	0.03 max	0.40 max		0.30 max	0.07 max	0.03 max		Cu+Fe+Si+Zn<=0.50; base Al				
Japan															
JIS H2102(83)	Class 2	Virgin ingot	99.50 min	0.02 max	0.40 max	0.02 max	0.25 max				Ti<=0.02; base Al				
South Africa															
SABS 711	Al99.50	Ingot for remelting	99.5 min	0.02 max	0.3 max	0.03 max	0.15 max	0.05 max	0.03 max		Mg<=0.03; Ti<=0.02; base Al				
SABS 711	Al99.50E	Ingot for remelting	99.5 min		0.35 max	0.005 max	0.1 max	0.03 max	0.02 max		B<=0.02; Cr<=0.004; Ti<=0.004; V<=0.004; base Al				
SABS 989	SA2(Al-99.5A)	Sand, permanent mold, pressure die cast	99.50 min	0.03 max	0.40 max		0.30 max	0.07 max	0.03 max		base Al				
SABS 991	Al-99.5	Sand cast	99.5 min	0.03 max	0.4 max		0.3 max	0.07 max	0.03 max		base Al				
SABS 991	Al-99.5A		99.5	0.03	0.4		0.3	0.07			base Al				
SABS 992	Al 99.5	Pressure die cast	99.5 min	0.03 max	0.4 max		0.3 max	0.07 max	0.03 max		base Al				
SABS 992	Al-99.5A		99.5	0.03	0.4		0.3	0.07			base Al				
Spain															
UNE 38-125	L-2051	Ingot, casting			0.40 max		0.30 max	0.10 max	0.05 max		Ti<=0.10; bal Al; base Al				
UNE 38-203	L-2051	Ingot, casting			0.40 max		0.30 max	0.10 max	0.05 max		Ti<=0.10; bal Al; base Al				
Sweden															
MNC 41E	4022	Ingot	99.5								base Al				
SIS 144022	4022-00		99.5	0.03	0.4		0.3	0.07			base Al				
UK															
BS 1490	LM0			0.03 max	0.40 max	0.03 max	0.30 max	0.07 max			Mg<=0.03; Ni<=0.03; Pb<=0.03; Sn<=0.03; bal Al; base Al				

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 150.x (Continued from previous page)															
USA															
	UNS A01501	Foundry alloy, ingot	99.50 min	0.05 max				0.05 max	0.03 max	0.10 max	Fe/Si>=2.0; Mn+Cr+Ti+V<=0.025; base Al				
AA Registration Record(99)	150.1	Ingot; conductivity 57% IACS min	99.50 min	0.05 max				0.05 max	0.03 max	0.10 max	Fe/Si>=2.0; Mn+Cr+Ti+V<=0.025; base Al				
ASTM B179(96)	150.1	Ingot for die casting	99.50	0.05 max				0.05 max	0.03 max	0.10 max	Fe/Si>=2.0; Mn+Cr+Ti+V<=0.025; base Al				
ASTM B179(96)	99.5A	Ingot for die casting. Former designation. See 150.1									base Al				
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 160.x															
Australia															
AS 1874(00)	AA160	Ingot	99.60 min		0.3 max	0.01 max	0.10 max		0.02 max	0.10 max	Cr<=0.01; Ti<=0.01; V<=0.01; Fe>=2xSi; Cr+Mn+Ti+V<=0.01; base Al				
Czech Republic															
CSN	424104		99.6 min	0.01 max	0.25 max		0.20 max	0.05 max			Ti<=0.03; Fe+Si<=0.36; base Al				
Europe															
CEN EN 576(96)	EN AB-10601	Unalloyed ingot for remelting	99.60 min	0.01 max	0.30 max	0.007 max	0.10 max	0.04 max	0.03 max		B<=0.04; Cr<=0.005; Mg<=0.02; Cr+Mn+Ti+V<=0.030; base Al				
France															
NF A57-101	A6E	Ingot	99.60 min	0.01 max	0.30 max	0.005 max	0.10 max	0.05 max	0.03 max	0.40 max	B<=0.04; Cr<=0.005; Mg<=0.02; Ti<=0.02; V<=0.02; Ti+V<=0.02; base Al				
Japan															
JIS H2110(71)	Ingot	Virgin ingot for electrical use	99.65 min	0.005 max	0.25 max	0.005 max	0.10 max				Ti<=0.005; V<=0.005; Ti+V<=0.005; base Al				
South Africa															
SABS 711	Al-EC99.6	Ingot for remelting	99.6	0.02	0.3		0.15	0.07			base Al				
SABS 711	Al99.60E	Ingot for remelting	99.6 min	0.01 max	0.3 max	0.005 max	0.1 max	0.04 max	0.03 max		B<=0.04; Cr<=0.005; Mg<=0.02; Ti<=0.005; V<=0.005; base Al				
USA															
	UNS A01601	Foundry alloy, ingot	99.60 min		0.25 max		0.10 max	0.05 max	0.03 max	0.10 max	Fe/Si>=2.0; Mn+Cr+Ti+V<=0.025; base Al				
AA Registration Record(99)	160.1	Ingot	99.60 min		0.25 max		0.10 max	0.05 max	0.03 max	0.10 max	Fe/Si>=2.0; Mn+Cr+Ti+V<=0.025; base Al				
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 170.x															
Australia															
AS 1874(00)	AA170	Ingot	99.70 min		0.20 max		0.10 max	0.03 max	0.03 max	0.10 max	Ga<=0.04; V<=0.03; base Al				
AS 1874(00)	AA175	Ingot	99.75 min	0.02 max	0.20 max		0.20 max		0.03 max	0.10 max	base Al				
AS 1874(00)	BA170	Ingot	99.70 min			0.025 max			0.03 max	0.10 max	Cr<=0.025; Ti<=0.025; V<=0.025; Fe>=1.5xSi; Cr+Mn+Ti+V<=0.025; base Al				
Czech Republic															
CSN	424103		99.7 min	0.01 max	0.16 max		0.16 max	0.05 max			Ti<=0.02; Fe+Si<=0.26; base Al				
Europe															
CEN EN 576(96)	EN AB-10701	Unalloyed ingot for remelting	99.70 min	0.01 max	0.20 max	0.005 max	0.07 max	0.04 max	0.03 max		B<=0.04; Cr<=0.004; Mg<=0.02; Cr+Mn+Ti+V<=0.02; base Al				

UNS numbers and US grades are provided as a means of cross referencing chemically similar alloys. Exchangability is only possible after independent examination of specifications. Tensile properties are minimum or typical as specified. UTS and YS as MPa. El as %. OE=others each. OT=others total.

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, 170.x (Continued from previous page)															
Europe															
CEN EN 576(96)	EN AB-10702	Unalloyed ingot for remelting	99.70 min	0.01 max	0.20 max	0.03 max	0.10 max	0.04 max	0.03 max		Li<=0.0001; Mg<=0.0050; Na<=0.0010; Ti<=0.02; base Al				
CEN EN 576(96)	EN AB-10703	Unalloyed ingot for remelting	99.70 min	0.01 max	0.20 max	0.03 max	0.10 max	0.04 max	0.02 max		Mg<=0.02; Na<=0.003; Ti<=0.02; base Al				
CEN EN 576(96)	EN AB-10751	Unalloyed ingot for remelting		0.01 max	0.15 max	0.02 max	0.10 max	0.04 max	0.03 max	0.10 max	Ga<=0.03; Mg<=0.01; Ti<=0.02; bal Al; base Al				
CEN EN 576(96)	EN AB-10841	Unalloyed ingot for remelting		0.01 max	0.10 max	0.02 max	0.06 max	0.04 max	0.02 max	0.05 max	Ga<=0.03; Mg<=0.01; Ti<=0.02; bal Al; base Al				
CEN EN 576(96)	EN AB-10871	Unalloyed ingot for remelting		0.01 max	0.07 max	0.01 max	0.06 max	0.03 max	0.02 max	0.05 max	Ga<=0.02; Mg<=0.01; Ti<=0.01; bal Al; base Al				
Finland															
SFS 2561	G-Al99.7		99.7	0.02	0.25		0.2	0.06			base Al				
France															
NF A57-101	A7	Ingot	99.70 min	0.01 max	0.20 max	0.03 max	0.15 max	0.04 max	0.03 max	0.30 max	Ga<=0.03; Mg<=0.03; Ti<=0.02; V<=0.03; base Al				
Germany															
DIN 1712-3	3.0270/Al99.7H	Ingot. Inactive. Replaced by DIN EN 573-3	99.70 min	0.01 max	0.25 max		0.20 max	0.04 max	0.03 max	0.30 max	Ti<=0.02; base Al				
International															
ISO/R 115(68)	Al99.7	Ingot, for remelting	99.70 min	0.02 max	0.25 max		0.20 max	0.06 max	0.03 max		Cu+Fe+Si+Zn<=0.30; base Al				
Japan															
JIS H2102(83)	Class 1	Virgin ingot	99.70 min	0.01 max	0.20 max	0.02 max	0.15 max				Ti<=0.02; base Al				
South Africa															
SABS 711	Al99.65	Ingot for remelting	99.65 min	0.02 max	0.2 max	0.03 max	0.15 max	0.04 max	0.02 max		Cr<=0.03; Mg<=0.03; base Al				
SABS 711	Al99.65E	Ingot for remelting	99.65 min	0.01 max	0.25 max	0.003 max	0.1 max		0.02 max		B<=0.02; Cr<=0.003; Mg<=0.02; Ti<=0.003; V<=0.003; base Al				
SABS 711	Al99.7	Ingot for remelting	99.7 min	0.01 max	0.2	0.03 max	0.1 max	0.03 max		0.02 max	Mg<=0.02; Ti<=0.02; base Al				
SABS 711	Al99.70E	Ingot for remelting	99.7 min	0.01 max	0.2 max	0.003 max	0.08 max	0.02 max	0.02 max		B<=0.02; Cr<=0.003; Mg<=0.02; Ti<=0.003; V<=0.003; base Al				
SABS 711	Al99.75E	Ingot for remelting	99.75 min	0.01 max	0.15	0.002 max	0.08 max	0.02 max		0.02 max	B<=0.01; Cr<=0.002; Ga<=0.03; Mg<=0.01; Ti<=0.002; V<=0.002; base Al				
SABS 989	SA4(Al-99.7A)	Sand, permanent mold, pressure die cast	99.70 min	0.02 max	0.25 max		0.20 max	0.06 max	0.03 max		base Al				
SABS 991	Al-99.7A		99.7	0.02	0.25		0.2	0.06			base Al				
SABS 992	Al-99.7A		99.7	0.02	0.25		0.2	0.06			base Al				
Sweden															
MNC 41E	4021	Ingot	99.7								base Al				
SIS 144021	4021-00		99.7	0.02	0.25		0.2	0.06			base Al				
USA															
	UNS A01701	Foundry alloy, ingot	99.70 min					0.05 max	0.03 max	0.10 max	Fe/Si>=1.5; Mn+Cr+Ti+V<=0.025; base Al				
AA Registration Record(99)	170.1	Ingot; conductivity 59% IACS min	99.70 min					0.05 max	0.03 max	0.10 max	Fe/Si>=1.5; Mn+Cr+Ti+V<=0.025; base Al				
ASTM B179(96)	170.1	Ingot for die casting	99.70					0.05 max	0.03 max	0.10 max	Fe/Si>=1.5; Mn+Cr+Ti+V<=0.025; base Al				

BUY NOW

Cast Aluminum, (1xx.x series) Commercially Pure, 99.00% or greater, No equivalents identified

Specification	Designation	Notes	Al	Cu	Fe	Mn	Si	Zn	OE	OT	Other	UTS	YS	El	Hard
Australia															
AS 1874(00)	AA180	Ingot	99.80 min	0.02 max	0.10 max		0.10 max		0.03 max	0.10 max	base Al				
AS 1874(00)	AA185	Ingot	99.85 min	0.02 max	0.10 max		0.10 max		0.03 max	0.10 max	base Al				
AS 1874(00)	AA190	Ingot	99.90 min		0.07 max		0.05 max	0.03 max	0.02 max	0.05 max	Ga<=0.03; V<=0.02; base Al				
Europe															
CEN EN 576(96)	EN AB-10851	Unalloyed ingot for remelting	99.85 min	0.01 max	0.070 max	0.02 max	0.08 max	0.04 max	0.01 max		Ga<=0.03; Mg<=0.01; Ti<=0.010; base Al				
Finland															
SFS 2560	G-Al99.8		99.8	0.02	0.15		0.15	0.06			base Al				
France															
NF A57-101	A8	Ingot	99.80 min	0.01 max	0.15 max	0.02 max	0.10 max	0.04 max	0.02 max	0.20 max	Ga<=0.03; Mg<=0.02; Ti<=0.02; V<=0.02; base Al				
NF A57-101	A9	Ingot	99.90 min	0.005 max	0.050 max	0.010 max	0.050 max	0.030 max	0.010 max	0.10 max	Ga<=0.030; Mg<=0.010; Ti<=0.005; V<=0.010; base Al				
NF A57-101	A99	Ingot	99.99 min	0.003 max	0.005 max	0.002 max	0.006 max	0.005 max	0.001 max	0.010 max	Ga<=0.003; Mg<=0.005; Ti<=0.002; V<=0.003; base Al				
Germany															
DIN 1712-3	3.0280/Al99.8H	Ingot. Inactive. Replaced by DIN EN 573-3	99.80 min	0.01 max	0.15 max		0.15 max	0.04 max	0.02 max	0.20 max	Ga<=0.03; Ti<=0.02; base Al				
DIN 1712-3	3.0300/Al99.9H	Ingot. Inactive. Replaced by DIN EN 573-3	99.90 min	0.005 max	0.040 max		0.050 max	0.0030 max	0.010 max	0.10 max	Ga<=0.030; Ti<=0.005; base Al				
DIN 1712-3	3.0400/Al99.99R	Ingot. Inactive. Replaced by DIN EN 573-3	99.99 min	0.003 max	0.005 max		0.010 max	0.005 max	0.001 max	0.010 max	Ti<=0.002; base Al				
International															
ISO/R 115(68)	Al99.8	Ingot, for remelting	99.80 min	0.02 max	0.15 max		0.15 max	0.06 max	0.03 max		Cu+Fe+Si+Zn<=0.20; base Al				
Japan															
JIS H2102(83)	Special class 1	Virgin ingot	99.90 min	0.01 max	0.07 max	0.01 max	0.05 max				Ti<=0.01; base Al				
JIS H2102(83)	Special class 2	Virgin ingot	99.85 min	0.01 max	0.12 max	0.01 max	0.08 max				Ti<=0.01; base Al				
South Africa															
SABS 711	Al99.8	Ingot for remelting	99.8 min	0.01 max	0.1	0.02 max	0.1 max	0.03 max		0.01 max	Cr 0.02; Ga<=0.03; Mg<=0.01; Ti<=0.02; base Al				
SABS 711	Al99.85	Ingot for remelting	99.85	0.01 max	0.07	0.02 max	0.05 max	0.02 max		0.01 max	Cr 0.02; Ga<=0.03; Mg<=0.01; Ti<=0.01; base Al				
SABS 711	Al99.9	Ingot for remelting	99.9 min	0.005 max	0.04	0.01 max	0.04 max	0.015 max		0.005 max	Ga<=0.03; Mg<=0.01; Ti<=0.005; base Al				
Sweden															
MNC 41E	4020	Ingot	99.8								base Al				
SIS 144020	4020-00		99.8	0.02	0.15		0.15	0.06			base Al				

UNS numbers and US grades are provided as a means of cross referencing chemically similar alloys. Exchangability is only possible after independent examination of specifications. Tensile properties are minimum or typical as specified. UTS and YS as MPa. El as %. OE=others each. OT=others total.