Clinker Technical Datasheet

Manufacturer	Guangxi Jingan Cement Co., Ltd.	Standard	GB/T 21372-2024
Product	Cement Clinker	Grade	52.5
Origin	China	Batch No.	C0202

Key Highlights

Compressive Strength (28d)	60.5 MPa	$C_3S + C_2S$	75.05%
CaO/SiO_2 Ratio	3.04	Initial Setting Time	115 min

Technical Properties

Physical Properties

Item	Value
Initial Setting Time	115 min
Final Setting Time	148 min
Soundness	Qualified

Chemical Composition

Component	Value
Loss on Ignition (LOI)	0.07%
Insoluble Matter	0.28%
MgO	1.92%
SO_3	0.32%
Free CaO	1.06%
Cl^-	0.009%

Mineralogical Composition

Mineral Phase	Value
$C_3S + C_2S$	75.05%
C_3A	8.02%
CaO/SiO_2 Ratio	3.04

Mechanical Strength

Test Item	Unit	Result	Standard
Compressive Strength (3d)	MPa	33.1	≥ 27.0
Compressive Strength (28d)	MPa	60.5	≥ 52.5
Flexural Strength (3d)	MPa	6.6	/
Flexural Strength (28d)	MPa	9.1	/

Safety & Compliance

Item	Value
Water-soluble Cr (VI)	5.5 mg/kg
Internal Radiation Index	0.4
External Radiation Index	0.3
Heavy Metals	Qualified

Conclusion

This batch of clinker meets the requirements of GB/T 21372-2024. All tested indicators comply with standard specifications.

Disclaimer: This datasheet is based on test results of a specific batch and is for reference only. Final specifications shall be subject to contract.