GBFS Technical Datasheet

森澜商贸
SENLAN TRADING

Manufacturer	Tangshan Senlan Commerce and Trade Co., Ltd.	**Document**	GBFS Technical Data Sheet
Product	Granulated Blast Furnace Slag (GBFS)	**Form**	Water-Granulated Slag
Sample	GBFS / Water Slag	**Reference**	Internal test data + translated lab sheet

Detailed Chemical Analysis

Chemical Item	Value
Glass Content (%)	98.1
Moisture Content (%)	9.40
0–10 mm Fraction (%)	99.86
Appearance	Granular / Water-Granulated
Color	Light gray to off-white
Loss on Ignition (LOI, %)	0.34
CaO (%)	39.07
SiO_2 (%)	33.21
Al_2O_3 (%)	16.02
Fe_2O_3 (%)	0.99
MgO (%)	9.62
SO_3 (%)	0.09
K_2O (%)	0.26
Na_2O (%)	0.41
R_2O (%)	0.58
Cl^- (%)	0.02
MnO (%)	0.32
TiO_2 (%)	0.45

Remarks

The above moisture and size tests were performed by SGS-CSTC Tianjin laboratory. Glass content testing by XRD analysis was performed by SGS-CSTC Beijing Mineral Laboratory. This datasheet combines screening/lab sheet data and internal chemical analysis for commercial reference.

Quality Control & Authorization

Quality Status	Issued By
For customer reference and technical communication	Tangshan Senlan Commerce and Trade Co., Ltd.

Disclaimer: This datasheet is provided for reference only. The values above are compiled from specific sample test records and internal analysis data and may vary depending on source, moisture condition, processing, and shipment lot. Final specifications and acceptance criteria shall be subject to the signed contract and mutually agreed inspection method.