GGBFS Technical Datasheet

森澜商贸
SENLAN TRADING

Manufacturer	Tangshan Senlan Commerce and Trade Co., Ltd.	**Document**	GGBFS Quality Test Report (S95)
Product	Ground Granulated Blast Furnace Slag (GGBFS)	**Grade**	S95
Sample	GGBFS Powder	**Standard**	As per reported test standard

Key Highlights (Quick View)

Specific Surface Area	427 m^2/kg	**Glassy Phase Content**	97%
Activity Index (7d)	85%	**Activity Index (28d)**	100%
Density	2.9 g/cm^3	**Fluidity Ratio**	100%

Note: Values are extracted from the original quality test report for S95 grade GGBFS and presented in English for customer reference.

Technical Properties

Physical Properties

Test Item	Value
Fluidity Ratio (%)	100
Moisture Content (%)	0.1
Density (g/cm^3)	2.9
Specific Surface Area (m^2/kg)	427
Initial Setting Time Ratio (%)	125
Glassy Phase Content (%)	97

Chemical / Quality Indicators

Component / Item	Value
Chloride Ion (%)	0.03
Sulfur Trioxide, SO_3 (%)	0.1
Loss on Ignition (LOI, %)	0.6
Insoluble Matter (%)	1.3

Performance and Compliance

Test Item	Value
Activity Index (7 days, %)	85
Activity Index (28 days, %)	100
Internal Irradiation Index	0.3
External Exposure Index	0.5
Test Conclusion	Meet Standard

Reported Standard Requirements vs. Test Results

Test Item	Unit	Requirement	Result
Fluidity Ratio	%	≥ 95	100
Moisture Content	%	≤ 1.0	0.1
Chloride Ion	%	≤ 0.06	0.03
Sulfur Trioxide (SO_3)	%	≤ 4.0	0.1
Loss on Ignition (LOI)	%	≤ 1.0	0.6
Density	g/cm^3	≥ 2.8	2.9
Insoluble Matter	%	≤ 3.0	1.3
Initial Setting Time Ratio	%	≤ 200	125
Internal Irradiation Index	/	≤ 1.0	0.3
External Exposure Index	/	≤ 1.0	0.5
Glassy Phase Content	%	≥ 85	97
Activity Index (7d)	%	≥ 70	85
Activity Index (28d)	%	≥ 95	100
Specific Surface Area	m^2/kg	≥ 400	427

Quality Control & Authorization

Quality Status	Issued By
All reported items meet S95 test requirements	Tangshan Senlan Commerce and Trade Co., Ltd.

Disclaimer: This datasheet is provided for reference only. The above values are based on the submitted quality test report of a specific sample/batch of S95 GGBFS and may vary depending on production and shipment conditions. Final specifications, inspection method, and commercial terms shall be subject to the signed contract.