

Technical report by sample - Percentage of total photons:

(color coded titles refer to their respective line on the spectral chart)

	Cu	Zn	Sn	Pb	Fe	Se
CENTER TOP SPINE	97.170%	0.249%	2.075%	0.072%	0.434%	0.000%
LEFT SIDE OF TAIL	96.053%	0.486%	1.654%	0.143%	1.664%	0.000%
BASE BY LEFT PAW	96.214%	0.335%	2.206%	0.086%	1.072%	0.087%
UNDERBASE SCRAPE SIDE	98.045%	0.195%	1.705%	0.019%	0.032%	0.003%

Stalking Panther Large, BBCW A,1

Trace amounts of iron. Trace amounts of selenium found on the patina of the base.

No significant amounts of iron found on the sample spot "UNDERBASE SCRAPE SIDE" compared to the rest of sample spots.

Copper-tin alloy with iron-lead patina. Consistent except for selenium on base.