

1243I - VL 54 - Mixes

Last Updated: 11/14/2023

Domain	Submittal	Mix	28D Design Strength (PSI)	Slump (in)	W / CM Ratio
Civil					
Street/ Concrete Base	4.3	Central - 704CC	5000	4 ±1	0.44
Parking Strip/ Curb and Gutter	4.3	Central - 604	4000	4 ±1	0.50
Sidewalks	4.4	Central - 564LB	3000	4 ±1	0.50
Bus Pads	4.4	Central - 66G1R5P1	6000	4 ±1	0.40
Curb Ramps	4.5	Central - 554	3000	4 ±1	0.55
Sewer					
Manhole Footing	4.3	Central - 6012	4000	4 ±1	0.49
Manhole Mortarting	7.1	Parson CA Liner 100	9000		
Misc.					
2SK Sand Slurry – F20100FX	4.2	Central - F20100FX	100	8 ±1	2.40

Domain	Submittal	Mix - Identification Number	Type/Grading	Location
Civil				
ACWS	5.0	GraniteRock - 323	1/2" HMA	South SF / Redwood City
ACWS	5.0	GraniteRock - 803	1/2" HMA	South SF / Redwood City
ACWS	5.0	GraniteRock - SS1- H- Emulsion	1/2" HMA	South SF / Redwood City
ACWS	5.0	GraniteRock - 323	1/2" HMA	South SF / Redwood City
ACWS	5.0	GraniteRock - 803	1/2" HMA	South SF / Redwood City
ACWS	110.0	GraniteRock - 788	1/2" HMA	South SF / Redwood City
ACWS	110.0	GraniteRock - 784	1/2" HMA	South SF / Redwood City
ACWS	110.0	GraniteRock - 103	1/2" HMA	South SF / Redwood City