



**MICROTOP**

# MICROTOP® TW NSD

**MICROSILICA-MODIFIED SHOTCRETE MOTAR  
WITH HIGH CONTENT OF BLAST FURNACE CEMENT  
FOR WET-MIX-PNEUMATIC COVEYING AND DENSE-PHASE  
METHOD  
IN THE DRINKING WATER DOMAIN**

## DESCRIPTION

**MICROTOP TW NSD** is a pure mineral, hydraulic binding, microsilica-modified cement shotcrete mortar.

**MICROTOP TW NSD** is a mortar of concrete strength class C30/37, for the drinking water domain.

**MICROTOP TW NSD** complies with the demands of DVGW work sheets W 300 and W 347. Granulometric composition 0 - 3 mm.

## APPLICATION

**MICROTOP TW NSD** is used for the production of shotcrete mortar in wet-mix pneumatic conveying and dense phase method: It is used for the re-profiling and coating of surfaces, the increase of concrete covers and the finishing in the drinking water domain for average coat thickness of 25 mm.

**MICROTOP TW NSD** can easily be ground and smoothed. Smaller areas can be processed manually.

## PROPERTIES

- microsilica-modified
- low rebound
- low dust development
- open to steam diffusion
- water-impermeable
- chloride-free
- can be ground and smoothed

## PROCESSING

### Sub-base:

Load-bearing concrete and firmly adherent existing plasters with a bond strength of min. 1,5 N/mm<sup>2</sup>.

### Processing:

Clean surface from loose particles such as dust and cement slurry down to the load-bearing sub-base.

If necessary, carry out roughening.

The sub-base always has to be cleaned e.g. by high-pressure water or sand-blasting.

The day before application the concrete surfaces have to be dampened until capillary saturation is achieved. The surfaces must be matt-damp when the application takes place.

**MICROTOP TW NSD** is mixed with approx. 2,25 l water per 25 kg bag. Application of the basic mixture in wet-mix-pneumatic-conveyance or dense-phase method using suitable mixing technique.

The temperature on the sub-base must be min. 5 °C and must not fall below.

### After-treatment:

By the use of humidifiers the relative air humidity after the application must be kept at 95 % for at least 10 days. The heat input must not exceed 20 °C. Air draught and stronger air movements have to be avoided.

## PRODUCTION /CONTROL

Producer:

KORODUR Westphal Hartbeton GmbH & Co. KG, works Wattenscheid. Internal and external control.

**Certification: DIN EN ISO 9001:2008**

## SUPPLY / DELIVERY

25 kg special paper bags

## STORAGE

Dry, like cement.

Shelf-life approx. 6 months.

## HINTS

This product contains cement and has an alkaline reaction with moisture/water. Therefore protect skin and eyes. In case of contact with eyes consult a doctor. The afore-mentioned data, processing and use of our products are based on our experience. Taking into consideration the differences and deviations in materials, sub-bases and working conditions, a guarantee for working results cannot be given nor any reliability, regardless the legal relationship, whether referred to these hints nor to given verbal advice, unless we are charged of having acted on purpose or gross negligence. In such case the applicator has to furnish evidence that he had forwarded to us in good time, completely and in written form, any information required for proper and promising judgment. Protective rights of third parties have to be observed. In any case the latest technical data sheet refers.

per April 2015



**KORODUR International GmbH**

**Head Office:**

Wernher-von-Braun-Str. 4

92224 Amberg

P.O. Box 1653 • 92206 Amberg

Phone: +49 (0) 96 21 / 47 59 – 0

Telfax: +49 (0) 96 21 / 3 23 41

info@korodur.de

[www.korodur.de](http://www.korodur.de)

**Bochum Wattenscheid Works:**

Hohensteinstr. 19

44866 Bochum

P.O. Box 60 02 48 • 44842 Bochum

Phone: +49 (0) 23 27 / 94 57 – 0

Telefax: +49 (0) 23 27 / 32 10 84

wattenscheid@korodur.de

