





SILVER 95 C

Silver 95 C films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. Solar glare is greatly diminished and its one-way mirror aspect guarantees privacy from prying eyes, whilst affording a modern feel to the exterior of a building.



Warranty 12 YEARS



Fire-resistance rating



Storage from -5°C to +40°C **3 YEARS**



REACH RoHS compliant RESPECTED

WIDTHS AVAILABLE:



152 cm

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	<1 %
Visible light transmission	5 %
Reflection of external visible light	60 %
Reflection of internal visible light	60 %
Total solar energy rejected	87 %
Total solar energy rejected 2*	83 %
Solar ratio:	
Solar energy reflection	62 %
Solar energy absorption	33 %
Solar energy transmission	4 %
Reduction in Solar Glare	96 %
g-value	0.09
u-value	5.1
Shading coefficient	0.1
Installation type: Interior	
Roll length	30,5 m
Film composition	PET

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

eu		
Clear single pane	V	
Tinted single pane	Ţ	
Reflective tinted single pane	~	
Clear double pane	Ţ	
Tinted double pane	×	
Reflective tinted double pane	~	
Gas-filled double pane - Low E	×	
STADIP EXT. clear double pane	I	
STADIP INT. clear double pane	×	

Caution X Not ✓ Yes recommended

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.

CONSTRUCTION

Thickness

- 1. Hard scratch resistant layer, for durability and ease of
- maintenance during window cleaning
 2. High optical quality polyester, with anti IR metal particles deposit
- **3.** Bonding adhesive

Colour from the outside: SILVER

- High optical quality polyester
 Protection release liner, disposable after installation

MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

60 μ

Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.