

FILMS SOLAR FILM DATA SHEET **EXTERIOR INNOVATIVE**



SPECTRA 22 XC

Derived from the latest technologies, the Spectra 22 XC film incorporates a ceramic compound which enables it to reduce solar heat gain whilst remaining transparent. Our External Spectrally Selective films (Spectra 22 XC, 333 XC & 44 XC) are made from ceramic construction and are then considered as metal free window films.



Warranty See the notice



Fire-resistance rating M1



Storage from -5°C to +40°C

3 YEARS



REACH RoHS compliant

RESPECTED

WIDTHS AVAILABLE:

152 cm

183 cm

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	<1 %
Visible light transmission	78 %
Reflection of external visible light	9 %
Reflection of internal visible light	9 %
Total solar energy rejected	45 %
Total solar energy rejected 2*	48 %
Solar ratio:	
Solar energy reflection	10 %
Solar energy absorption	46 %
Solar energy transmission	44 %
Reduction in Solar Glare	18 %
g-value	0.55
u-value	5.08
Rejected Infrared (760-2500 nm)	+/- 77 %
Shading coefficient	0.6
Installation type: Exterior	
Roll length	30,5 m
Film composition	PET
Thickness	60 μ

Colour from the outside: HIGHLY

NEUTRAL

CONSTRUCTION

- 1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
- 2. High optical quality polyester with anti IR
- **3.** Bonding adhesive
- 4. High optical quality polyester5. PS adhesive, glass polymerization within 15 days
- **6.** Protection release liner, disposable after installation


INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	~
Tinted single pane	Ţ
Reflective tinted single pane	~
Clear double pane	~
Tinted double pane	Ţ
Reflective tinted double pane	~
Gas-filled double pane - Low E	Ţ
STADIP EXT. clear double pane	Ţ
STADIP INT. clear double pane	~



*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data. We reserve the right to modify the composition of our films at any time, Consult our warranty documents.