

# **DESIGN AND ANALYSIS OF LENGTHWISE GRADIENT HONEYCOMB CORE FOR OBTAINING GRADED BEAM PROPERTIES**

**A CAPSTONE PROJECT REPORT**

*Submitted in partial fulfillment of the  
requirement for the award of the  
Degree of*

**BACHELOR OF TECHNOLOGY  
IN  
MECHANICAL ENGINEERING**

*by*

**PERI SHANMUKHA RAM (17BME7047)**

*Under the Guidance of*

**Dr. P S RAMA SREEKANTH**



**VIT-AP  
UNIVERSITY**

**SCHOOL OF MECHANICAL ENGINEERING  
VIT-AP UNIVERSITY  
AMARAVATI- 522237**

*DECEMBER 2020*

## **CERTIFICATE**

This is to certify that the Capstone Project work titled "**DESIGN AND ANALYSIS OF LENGTHWISE GRADIENT HONEYCOMB CORE FOR OBTAINING GRADED BEAM PROPERTIES**" that is being submitted by **PERI SHANMKHA RAM (17BME7047)** is in partial fulfilment of the requirements for the award of Bachelor of Technology, is a record of bonafide work done under my guidance. The contents of this Project work, in full or in parts, have neither been taken from any other source nor have been submitted to any other Institute or University for the award of any degree or diploma and the same is certified.

**Dr. P S Rama Sreekanth**  
**Guide**

**The thesis is satisfactory / unsatisfactory**

**Internal Examiner**

**External Examiner**

**Approved by**

**PROGRAM CHAIR**

B. Tech. MECH

**DEAN**

School of Mechanical Engineering

## **ACKNOWLEDGEMENTS**

I would like to express my sincere gratitude to several individuals and organizations for supporting me throughout my four years of Under graduation. First, I wish to express my sincere gratitude to my project guide, Professor P S Rama Sreekanth, for his enthusiasm, patience, insightful comments, helpful information, practical advice and unceasing ideas that have helped me tremendously at all times in my research and writing of this thesis. His immense knowledge, profound experience and professional expertise in Honeycomb technology has enabled me to complete this research successfully. Without his support and guidance, this project would not have been possible. I could not have imagined having a better supervisor in my study.

Besides my guide, I would like to thank the rest of my thesis committee: Prof. Manikanta Ravindra Kumar Vakkalagadda, Prof. Pankaj Tambe and, Prof.Amit kumar for their encouragement, insightful comments and hard questions.

## **ABSTRACT**

In this paper different types of honeycomb structures are designed and are different properties are compared like total deformation of structure when fixed at one end and a point load is acted on free end. Also, a gradient Honeycomb structure is designed to check whether the gradient cell honeycomb structure (along length) offers more bending resistance or not. This Gradient honeycomb structure is compared within different cell-oriented structures and also compared with different regular honeycomb structure to prove that gradient honeycomb structure deforms less comparatively to regular honeycomb structure. Modal Analysis is also performed on both vertical and horizontal cell oriented gradient honeycomb structures to study the dynamic characteristics of a structure under vibrational excitation. Natural frequencies, mode shapes and mode vectors of a structure were found out using modal analysis. Gradient honeycomb structures are tested for impact loading on the free end of structure at three different speeds i.e., 40kmph, 20kmph and 10kmph to extract energy absorption graphs.

## TABLE OF CONTENTS

S.No.	Chapter	Title	Page Number
1.		<b>Acknowledgement</b>	2
2.		<b>Abstract</b>	3
3.		<b>List of Figures and Table</b>	6
4.	1	<b>Introduction</b>	20
	1.1	<b>Organization of the Report</b>	24
5.	2	<b>Background and Literature Survey</b>	25
	2.1	<b>Objectives</b>	26
6.	3	<b>Design and analysis of lengthwise gradient honeycomb core for obtaining graded beam properties</b>	27
	3.1	<b>Proposed System</b>	27
	3.2	<b>Working Methodology</b>	28
	3.3	<b>Design of Honeycomb Structure</b>	28
	3.4	<b>Vertical cell orientation</b>	29
	3.5	<b>Horizontal cell orientation</b>	32
	3.6	<b>Boundary conditions</b>	34
	3.7	<b>Deformation of regular Honeycomb structure (Vertical and Horizontal cell orientation).</b>	35
	3.8	<b>End cell deformation (Vertical and Horizontal cell orientation)</b>	41

	<b>3.9</b>	<b>Mid-Cell deformation (Vertical and horizontal cell orientation)</b>	<b>47</b>
<b>7</b>	<b>4.</b>	<b>Design of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation)</b>	<b>53</b>
	<b>4.1</b>	<b>Deformation of Gradient Honeycomb structure (Vertical cell orientation and horizontal cell orientation)</b>	<b>55</b>
	<b>4.2</b>	<b>End cell deformation of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation)</b>	<b>56</b>
	<b>4.6</b>	<b>Mid-cell deformation of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation)</b>	<b>57</b>
	<b>4.4</b>	<b>Modal Analysis of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation)</b>	<b>58</b>
	<b>4.5</b>	<b>Deformation of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation) at impact loads.</b>	<b>69</b>
	<b>4.6</b>	<b>Energy absorption of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation) at impact loads.</b>	<b>72</b>
<b>8.</b>	<b>5</b>	<b>Results and Inferences</b>	<b>78</b>
<b>9.</b>	<b>6</b>	<b>Conclusion and Future Works</b>	<b>80</b>
<b>10.</b>	<b>7</b>	<b>References</b>	<b>81</b>

## **List of Tables**

<b>Table No.</b>	<b>Title</b>	<b>Page No.</b>
1.	Honeycomb Properties	24
2.	Honeycomb Dimensions	29
3.	Types of modes and frequency For gradient honeycomb structures	68
4.	Observation vs inference table for Regular honeycomb structure	81

## **List of Figures**

<b>Figure No.</b>	<b>Title</b>	<b>Page No.</b>
1	Honeycomb Structures with kinds of inside cells.	20
2	Honeycomb terminology	21
3	Vertical cell-oriented honeycomb structure	22
4	Horizontal cell-oriented honeycomb structure	23
5	System block diagram	27
6	Cell dimensions of regular honeycomb structure	28
7	Honeycomb structure (vertical cell orientation) 12,1.2	29

8	Honeycomb structure (vertical cell orientation) 12,1	30
9	Honeycomb structure (vertical cell orientation) 15,1.2	30
10	Honeycomb structure (vertical cell orientation) 15,1	30
11	Honeycomb structure (vertical cell orientation) 21,1.2	31
12	Honeycomb structure (vertical cell orientation) 21,1	31
13	Honeycomb structure (Horizontal cell orientation) 12,1.2	32
14	Honeycomb structure (Horizontal cell orientation) 12,1	32
15	Honeycomb structure (Horizontal cell orientation) 15,1.2	33
16	Honeycomb structure (Horizontal cell orientation) 15,1	33
17	Honeycomb structure (Horizontal cell orientation) 21,1.2	33
18	Honeycomb structure (Horizontal cell orientation) 21,1	34

19	Honeycomb Structure (Vertical cell- orientation), fixed at one end (Cantilever beam)	34
20	Honeycomb Structure (Vertical cell- orientation), Applying point load (100N) at free end	34
21	Deformation of regular vertical cell orientation honeycomb structure (12,1.2)	35
22	Deformation of regular vertical cell orientation honeycomb structure (12,1)	35
23	Deformation of regular vertical cell orientation honeycomb structure (15,1)	36
24	Deformation of regular vertical cell orientation honeycomb structure (15,1.2)	36
25	Deformation of regular vertical cell orientation honeycomb structure (21,1)	37
26	Deformation of regular vertical cell orientation honeycomb structure (21,1.2)	37
27	Deformation of regular Horizontal cell orientation honeycomb structure (12,1.2)	38

28	Deformation of regular Horizontal cell orientation honeycomb structure (12,1)	38
29	Deformation of regular Horizontal cell orientation honeycomb structure (15,1)	39
30	Deformation of regular Horizontal cell orientation honeycomb structure (15,1.2)	39
31	Deformation of regular Horizontal cell orientation honeycomb structure (21,1)	40
32	Deformation of regular Horizontal cell orientation honeycomb structure (21,1.2)	40
33	End cell deformation of regular vertical cell orientation honeycomb structure (12,1.2)	41
34	End cell deformation of regular vertical cell orientation honeycomb structure (12,1)	41
35	End cell deformation of regular vertical cell orientation honeycomb structure (15,1)	42
36	End cell deformation of regular vertical cell orientation honeycomb structure (15,1.2)	42

37	End cell deformation of regular vertical cell orientation honeycomb structure (21,1)	43
38	End cell deformation of regular vertical cell orientation honeycomb structure (21,1.2)	43
39	End cell deformation of regular Horizontal cell orientation honeycomb structure (12,1.2)	44
40	End cell deformation of regular vertical call orientation honeycomb structure (12,1)	44
41	End cell deformation of regular vertical call orientation honeycomb structure (15,1)	45
42	End cell deformation of regular vertical call orientation honeycomb structure (15,1.2)	45
43	End cell deformation of regular vertical call orientation honeycomb structure (21,1)	46
44	End cell deformation of regular vertical call orientation honeycomb structure (21,1.2)	46
45	Mid-cell deformation of regular vertical cell	47

	orientation honeycomb structure (12,1.2)	
46	Mid-cell deformation of regular vertical cell orientation honeycomb structure (12,1)	47
47	Mid-cell deformation of regular vertical cell orientation honeycomb structure (15,1)	48
48	Mid-cell deformation of regular vertical cell orientation honeycomb structure (15,1.2)	48
49	Mid-cell deformation of regular vertical cell orientation honeycomb structure (21,1)	49
50	Mid-cell deformation of regular vertical cell orientation honeycomb structure (21,1.2)	49
51	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (12,1.2)	50
52	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (12,1)	50
53	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (15,1)	51

54	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (15,1.2)	51
55	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (21,1)	52
56	Mid-cell deformation of regular horizontal cell orientation honeycomb structure (21,1.2)	52
57	Cell dimensions of vertical cell oriented gradient honeycomb structure	53
58	Vertical cell oriented gradient honeycomb structure	53
59	Cell dimensions of horizontal cell oriented gradient honeycomb structure	54
60	Horizontal cell oriented gradient honeycomb structure	54
61	Total deformation of gradient honeycomb structure (Vertical cell orientation)	55
62	Total deformation of gradient honeycomb structure (Horizontal cell orientation)	55
63	End cell deformation of gradient honeycomb	56

	structure (Vertical cell orientation)	
64	End cell deformation of gradient honeycomb structure (Horizontal cell orientation)	56
65	Mid-cell deformation of gradient honeycomb structure (Vertical cell orientation)	57
66	Mid-cell deformation of gradient honeycomb structure (Horizontal cell orientation)	57
67	First modal shape deformation of gradient honeycomb structure (vertical cell orientation)	58
68	Second modal shape deformation of gradient honeycomb structure (vertical cell orientation)	58
69	Third modal shape deformation of gradient honeycomb structure (vertical cell orientation)	58
70	Fourth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	59
71	Fifth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	59
72	Sixth modal shape deformation of gradient	59

	honeycomb structure (vertical cell orientation)	
73	Seventh modal shape deformation of gradient honeycomb structure (vertical cell orientation)	60
74	Eighth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	60
75	Ninth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	60
76	Tenth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	61
77	Eleventh modal shape deformation of gradient honeycomb structure (vertical cell orientation)	61
78	Twelfth modal shape deformation of gradient honeycomb structure (vertical cell orientation)	61
79	First modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	62
80	Second modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	62
81	Third modal shape deformation of gradient	62

	honeycomb structure (horizontal cell orientation)	
82	Fourth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	66
83	Fifth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	63
84	Sixth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	63
85	Seventh modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	64
86	Eighth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	64
87	Ninth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	64
88	Tenth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	65

89	Eleventh modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	65
90	Twelfth modal shape deformation of gradient honeycomb structure (Horizontal cell orientation)	65
91	Total deformation of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 40KMPH.	69
92	Total deformation of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 20KMPH	69
93	Total deformation of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 10KMPH	70
94	Total deformation of honeycomb gradient (Horizontal cell orientation) when impacted with a sphere with 40KMPH	70
95	Total deformation of honeycomb gradient (Horizontal cell orientation) when impacted with a sphere with 20KMPH	71

96	Total deformation of honeycomb gradient (Horizontal cell orientation) when impacted with a sphere with 10KMPH	71
97	Energy probe of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 40KMPH	72
98	Energy vs time graph of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 40KMPH	72
99	Energy probe of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 20KMPH	73
100	Energy vs time graph of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 20KMPH	73
101	Energy probe of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 10KMPH	74
102	Energy vs time graph of honeycomb gradient (vertical cell orientation) when impacted with a sphere with 10KMPH	74
103	Energy probe of honeycomb gradient (horizontal cell orientation) when	75

	impacted with a sphere with 40KMPH	
104	Energy vs time graph of honeycomb gradient (horizontal cell orientation) when impacted with a sphere with 40KMPH	75
105	Energy probe of honeycomb gradient (horizontal cell orientation) when impacted with a sphere with 20KMPH	76
106	Energy vs time graph of honeycomb gradient (horizontal cell orientation) when impacted with a sphere with 20KMPH	76
107	Energy probe of honeycomb gradient (horizontal cell orientation) when impacted with a sphere with 10KMPH	77
108	Energy vs time graph of honeycomb gradient (horizontal cell orientation) when impacted with a sphere with 10KMPH	77
109	Total deformation vs cell diagonal length graph for vertical cell oriented regular honeycomb structures	78
110	Total deformation vs cell diagonal length graph for 18	79

Horizontal cell oriented  
regular honeycomb  
structures

111

Honeycomb panels in  
AUDI R7S

81

# CHAPTER 1

## INTRODUCTION

Honeycomb Structures are natural or man-made structures that have the geometry of a honeycomb which allows the utilization of material to be minimum. There are different types of geometry for honeycomb structures but the common feature of all such structures is an array of hollow cells formed between thin vertical walls. The most common type is hexagonal cell shape honeycomb. However, to meet different engineering applications triangular cells, square cells, and circular-cored hexagonal cells, and circular-cored square cells are also used.




Figure 1 Honeycomb Structures with kinds of inside cells.

- a. General Structure
- b. Triangular
- c. Double hexagonal
- d. Inside circular
- e. Full double hexagonal
- f. Full insider circular

A honeycomb shaped structure provides a material with minimal density and relatively high out-of-plane compression properties and out-of-plane shear properties. Honeycomb structural material between two thin layers that provide strength in tension. This forms a plate-like assembly. Honeycomb materials are widely used where flat or slightly curved surfaces are in need and they have high specific strength. They are widely used in the aerospace industry for this reason,

and honeycomb materials in aluminum, fiberglass and advanced composite materials have been featured in aircraft and rockets since 1950's.

Man-made honeycomb structures include sandwich-structured composites with honeycomb cores. Man-made honeycomb structures are manufactured by using a variety of different materials, depending on the intended application and required characteristics, from paper or thermoplastics, used for low strength and stiffness for low load applications, to high strength and stiffness for high performance applications, from aluminum or fiber reinforced plastics. There are five basic ways of making honeycomb: adhesive bonding, resistance welding, brazing, diffusion bonding and thermal fusion. These methods are based on how the nodes are attached. By far the most common manufacturing method is adhesive bonding; perhaps as much as 95% of the honeycomb cores are made this way. Resistance welding, brazing or diffusion bonding are only used on cores that must see high temperatures or severe environmental conditions as it is much more expensive to manufacture core by these processes.





Figure 2 Honeycomb terminology

- Honeycomb density - the weight of one cubic foot of core, expressed in pounds per cubic foot (pcf) or the weight of one cubic meter of core, expressed in kilograms per cubic meter ( $\text{kg/m}^3$ ).
- Cell - a single honeycomb unit, usually a hexagon.
- Ribbon - the flat sheet material constituting the honeycomb, also referred to as web.


- Node - the bonded portion of adjacent ribbon sheets, double sheets.
- Free wall - cell wall sections of single unbonded sheets.
- L direction - the core ribbon direction, the direction of continuous sheets.
- R direction - the core ribbon direction, same as the L direction.
- W direction - the direction in which the core is expanded or perpendicular to the ribbon direction.
- T direction - the core direction parallel with the cell openings.
- HOBE - Honeycomb Before Expansion, the solid block of bonded sheets.
- CUE - Core Unexpanded, the solid block of bonded sheets.

### **Project Terminology:**



**Figure 3 Honeycomb Structure (Vertical cell-orientation)**

- Vertical cell-oriented Honeycomb Structure



**Figure 4 Honeycomb Structure (Horizontal cell-orientation)**

- Horizontal cell-oriented Honeycomb Structure
- The basic honeycomb element consists of one edge and two free walls. The various parameters that are derived from geometry of honeycomb given in the following table and are derived as follows:

- Honeycomb density ( $HD$ ) = 
$$\frac{2(q + p) t \rho_s}{(q + p \cos \theta) (2p \sin \theta)}$$
- Cells per honeycomb surface area ( $C/HSA$ ) = 
$$\frac{1}{(q + p \cos \theta) (2p \sin \theta)}$$
- Exposed foil area per honeycomb volume ( $EF\ A/HV$ ) = 
$$\frac{2(q + 2p)}{(q + p \cos \theta) (2p \sin \theta)}$$
- Foil edge area per honeycomb surface area ( $FEA/HSA$ ) = 
$$\frac{2(q + p) t}{(q + p \cos \theta) (2p \sin \theta)}$$

- where,  $p$ =free wall length,  $q$ =node width,  $\theta$  =expansion angle,  $t$ = web thickness,  $\rho_s$  = web density.
- Web density of PCTPE nylon filament is  $0.0011\text{gm/mm}^3$  or  $1.1\text{kg/m}^3$ .
- As cell's longest diagonal length decreases along rows i.e., each column will have same cell size, the properties such as Honeycomb density, Cells per honeycomb surface area, foil edge area per honeycomb surface area, exposed foil area per honeycomb volume decrease.

Cell longest diagonal (mm)	Free wall length (a)mm	Node width (b)mm	Expansion angle (degrees)	Web thickness (t)mm	Web density Gm/mm <sup>3</sup>	Honeycomb density (HD)kg/m <sup>3</sup>	C/HAS Cells per honeycomb surface area Cells/mm <sup>2</sup>	FEA/HSA Foil edge area per honeycomb surface area Mm <sup>2</sup> /mm <sup>2</sup>	EFA/HV Exposed foil area per honeycomb volume Mm <sup>2</sup> /mm <sup>3</sup>
12	6	6	60	1.2	0.0011	0.3388	0.0106837	0.25667	2.6
15	7.5	7.5	60	1.2	0.0011	0.27104	0.006833376	0.2533	2.08
21	10.5	10.5	60	1.2	0.0011	0.1936	0.00348857	0.146667	1.47571

Table 1 Honeycomb properties

### 1.3 Organization of the Report

The remaining chapters of the project report are described as follows:

- Chapter 2 contains the background and literature survey and objectives of project
- Chapter 3. proposed system, and hardware and software details, Design of regular Honeycomb structure, boundary conditions, methodology, deformation of regular honeycomb structures, deformation of different cells in regular honeycomb structure.
- Chapter 4 gives designs, boundary conditions, methodology, and design of gradient honeycomb structure, deformation, modal analysis, and impact analysis.
- Chapter 5 discusses the results and inferences obtained after the project was implemented.

- Chapter 6 concludes the project and discusses about future work.
- Chapter 7 gives references.

## **Chapter 2**

### **Background and Literature Survey**

The book titled “Tom Bitzer auth. Honeycomb Technology Materials, Design, Manufacturing, Applications and Testing.” Through this book, we get fundamentals of honeycomb structure, terminology, different web materials, honeycomb types, cell configurations, materials used, manufacturing processes, applications, evolution of applications of honeycomb structures in different fields of study. Particularly I had referred the manufacturing methods of honeycomb structures section. There are five processes, namely, Adhesive bonding, resistance welding, brazing, diffusion bonding and thermal fusion. Depending on web material, manufacturing process is selected. For instance, brazing and resistance welding is only used on cores that see high temperatures or severe environmental conditions. This book also insights about all strength and compares honeycomb structures with different plane panels to prove its maximum strength.

The first paper I referred was “Design and Analysis of Honey Comb Structures with Different Cases.” Authored by Shaik.Nazeer and Shaik Allabakshu from department of aerospace engineering, Nirma Institute of Science and Technology. It discussed a case, in which a honeycomb structure was designed of length 0.085m, width of 0.115m and thickness of 0.0007m. One side of Honeycomb structure was fixed and pressure was applied on face panel of structure. Total deformation, stress and strain was found out using Ansys workbench with different material assigned. This paper gave more insights on design methodology, material selection and also explained different phases of design of honeycomb structure.

So, from the above paper and book the understanding is that Honeycomb structures have a wide range of applications. Secondly, the use of honeycomb structures can reduce the weight by certain amount by offering more strength. All the papers, I referred had regular honeycomb structures used for experiments and analyzing results. If we decrease cell size gradually in length direction, the cell wall thickness along length direction also increases resulting in more resistance

than the previous cell as the cell wall thickness of right most cell has more thickness than the left cells to it.

The third paper was authored by Santosh kumar sahu, Nitesh Dhar Badgayan from department of Mechanical Engineering, Amrita School of Engineering and North Eastern Regional Institute of Science and Technology respectively. This paper is titled “Influence of cell size on out of plane stiffness and in-plane compliance character of the sandwich beam made with tunable PCTPE nylon honeycomb core and hybrid polymer nanocomposite skin.” This paper talks about fabrication of hybrid sandwich beams made with PCTPE nylon. Some part of this paper deals with honeycomb core geometry and fabrication section to understand parameters derived from geometry such as Honeycomb density, cells per honeycomb surface area, exposed foil area per honeycomb volume, foil edge area per honeycomb surface area. As I started working on to decrease cell size along length, I had to work on these properties for different dimensions to observe the trend for gradient honeycomb structure.

The fourth paper, “Modal Analysis and Harmonic Response Analysis of a Crankshaft” authored by Dr.C.M Ramesha, Abhijith KG, Department of Mechanical Engineering, M.S.R.I.R Bangalore, India. I used this paper as reference for modal analysis of honeycomb structure. Although this paper was not related to honeycomb structure but, modal analysis part of this paper was used to understand and study the dynamic characteristics of gradient honeycomb structure under vibrational excitation.

## **1.1 Objectives**

The following are the objectives of this project:

- To design Honeycomb Structure of varying diagonal length cell size by keeping cell size constant along length direction.
- To evaluate and compare deformation of regular honeycomb structure and varying cell honeycomb structure.
- To evaluate and compare deformation of different honeycomb structures with different cell orientation (Regular and varying structures).
- To evaluate and compare deformation and energy absorption of varying cell honeycomb structures (Sleeping and standing cell-oriented structures) at different cases.

- To perform modal analysis to determine the vibrational characteristics of honeycomb structure

## CHAPTER 3

# DESIGN AND ANALYSIS OF LENGTHWISE GRADIENT HONEYCOMB CORE FOR OBTAINING GRADED BEAM PROPERTIES

This Chapter describes the proposed system working methodology, software and hardware details.

## 2.1 Proposed System

The following block diagram (figure 2) shows the system architecture of this project.




Figure 5 System Block Diagram

## 2.2 Working Methodology

Whole project was implemented in software by simulations. Firstly, Honeycomb Structures of different cell sizes and cell wall thickness are designed and are simulated to find out deformation of total structure and deformation of different cells in honeycomb when one side of structure is fixed. Secondly, after observing and inferring the relation between dimensions and deformation, gradient honeycomb structure along ribbon direction is designed. Again, the gradient structures are simulated to find out deformation of structure and then compare with regular honeycomb.

To conduct impact loading simulation, a sphere is designed on top plane of honeycomb structure. Before simulating, the sphere is given certain velocity and made it to impact honeycomb structure. This process is repeated for at different velocities and energy graphs are extracted.

### Design of Honeycomb Structure (Vertical cell orientation and horizontal cell orientation)





Figure 6 Cell dimensions of Regular Honeycomb Structure

- In total, twelve regular honeycomb structures were designed with different dimensional combinations. All the structure core has approximated length of 220mm, width of 50mm and thickness of 30mm.
- All the twelve different honeycomb structures dimensions are listed in below table.

Cell orientation	Cell diagonal size (mm)	Cell wall thickness (mm)
Vertical	21	1.2
Vertical	15	1.2
Vertical	12	1.2
Vertical	21	1
Vertical	15	1
Vertical	12	1
Horizontal	21	1.2
Horizontal	15	1.2
Horizontal	12	1.2
Horizontal	21	1
Horizontal	15	1
Horizontal	12	1


**Table 2 Honeycomb Dimensions**

## **Vertical cell orientation**




**Figure 7 Honeycomb Structure (Vertical cell-orientation). 12,1.2**

- Cell diagonal-12mm, Cell wall thickness -1.2mm




**Figure 8 Honeycomb Structure (Vertical cell-orientation). 12,1**

- Cell diagonal-12mm, Cell wall thickness -1mm




**Figure 9 Honeycomb Structure (Vertical cell-orientation). 15,1.2**

- Cell diagonal-15mm, Cell wall thickness -1.2mm




**Figure 10 Honeycomb Structure (Vertical cell-orientation). 15,1**

- Cell diagonal-15mm, Cell wall thickness -1mm



**Figure 11 Honeycomb Structure (Vertical cell-orientation). 21,1.2**


- Cell diagonal-21mm, Cell wall thickness -1.2mm



**Figure 12 Honeycomb Structure (Vertical cell-orientation). 21,1**


- Cell diagonal-21mm, Cell wall thickness -1mm

## Horizontal cell orientation




**Figure 13 Honeycomb Structure (Horizontal cell-orientation). 12,1.2**

- Cell diagonal-12mm, Cell wall thickness -1.2mm




**Figure 14 Honeycomb Structure (Horizontal cell-orientation). 12,1**

- Cell diagonal-12mm, Cell wall thickness -1mm




**Figure 15 Honeycomb Structure (Horizontal cell-orientation). 15,1.2**

- Cell diagonal-15mm, Cell wall thickness -1.2mm




**Figure 16 Honeycomb Structure (Horizontal cell-orientation). 15,1**

- Cell diagonal-15mm, Cell wall thickness -1mm



**Figure 17 Honeycomb Structure (Horizontal cell-orientation). 21,1.2**


- Cell diagonal-21mm, Cell wall thickness -1.2mm




**Figure 18 Honeycomb Structure (Horizontal cell-orientation). 21,1**

- Cell diagonal-21mm, Cell wall thickness -1mm

## Boundary Conditions:



**Figure 19 Honeycomb Structure (Vertical cell-orientation), fixed at one end (Cantilever beam).**




**Figure 20 Honeycomb Structure (Vertical cell-orientation), Applying point load (100N) at free end.**

- Honeycomb Structure is fixed at one end and 100N force is applied on the other end of structure.
- Total deformation of structure and cell deformation of different cells in different columns were found out in ANSYS.
- Element type- Linear tetrahedral
- All the simulations are performed at ambient temperature (22 °C)


## Deformation of regular Honeycomb Structures

- Vertical Cell Orientation.




**Figure 21 Deformation of regular Vertical cell-orientation Honeycomb Structure (12,1.2)**

- Minimum Deformation-0m
- Maximum Deformation-5.7111e-004 m
- Average Deformation-2.1381e-004 m




**Figure 22 Deformation of regular Vertical cell-orientation Honeycomb Structure (12,1)**

- Minimum Deformation-0m
- Maximum Deformation-1.0768e-003 m
- Average Deformation-4.0268e-004 m




**Figure 23 Deformation of regular Vertical cell-orientation Honeycomb Structure (15,1)**

- Minimum Deformation-0m
- Maximum Deformation-1.04e-003 m
- Average Deformation-3.8921e-004 m




**Figure 24 Deformation of regular Vertical cell-orientation Honeycomb Structure (15,1.2)**

- Minimum Deformation-0m
- Maximum Deformation-2.042e-003 m
- Average Deformation-7.6092e-004 m



**Figure 25 Deformation of regular Vertical cell-orientation Honeycomb Structure (21,1)**


- Minimum Deformation-0m
- Maximum Deformation-2.8549e-003 m
- Average Deformation-1.0764e-003 m



**Figure 26 Deformation of regular Vertical cell-orientation Honeycomb Structure (21,1.2)**


- Minimum Deformation-0m
- Maximum Deformation-2.1956e-003 m
- Average Deformation-8.1628e-004 m

- **Horizontal Cell Orientation**




**Figure 27 Deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1.2)**

- Minimum Deformation-0m
- Maximum Deformation-8.6549e-004 m
- Average Deformation-3.1971e-004 m




**Figure 28 Deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1)**

- Minimum Deformation-0m
- Maximum 2.1972e-003 m
- Average Deformation-8.1239e-004 m



**Figure 29 Deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1)**

- Minimum Deformation-0m
- Maximum Deformation-2.6044e-003 m
- Average Deformation-9.6152e-004 m



**Figure 30 Deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1.2)**

- Minimum Deformation-0m
- Maximum Deformation-1.5782e-003 m
- Average Deformation-5.8187e-004 m




Figure 31 Deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1)

- Minimum Deformation-0m
- Maximum Deformation-5.2423e-003 m
- Average Deformation-1.9082e-003 m




Figure 32 Deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1.2)

- Minimum Deformation-0m
- Maximum Deformation-3.1268e-003 m
- Average Deformation-1.1405e-003 m

## End cell deformation (Vertical cell orientation)




Figure 33 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (12,1.2)

- Minimum Deformation- 5.2245e-004 m
- Maximum Deformation-5.7111e-004 m
- Average Deformation- 5.4967e-004 m




Figure 34 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (12,1)

- Minimum Deformation- 9.8952e-004 m
- Maximum Deformation-1.0768e-003 m
- Average Deformation- 1.0385e-003 m




Figure 35 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (15,1)

- Minimum Deformation- 9.3053e-004m
- Maximum Deformation-1.04e-003 m
- Average Deformation- 9.9345e-004 m




Figure 36 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (15,1.2)

- Minimum Deformation- 1.8474e-003 m
- Maximum Deformation-2.042e-003 m
- Average Deformation- 1.9544e-003 m




Figure 37 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (21,1)

- Minimum Deformation- 2.4476e-003 m
- Maximum Deformation-2.8549e-003 m
- Average Deformation- 2.6949e-003 m




Figure 38 End cell deformation of regular Vertical cell-orientation Honeycomb Structure (21,1.2)

- Minimum Deformation- 1.9098e-003 m
- Maximum Deformation-2.1956e-003 m
- Average Deformation- 2.0818e-003 m

- End cell deformation (Horizontal cell orientation)




Figure 39 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1.2)

- Minimum Deformation- 7.789e-004 m
- Maximum Deformation-8.499e-004 m
- Average Deformation- 8.155e-004 m






Figure 40 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1)

- Minimum Deformation- 1.9831e-003 m
- Maximum Deformation- 2.1621e-003 m
- Average Deformation- 2.0774e-003 m




**Figure 41 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1)**

- Minimum Deformation- 2.2966e-003 m
- Maximum Deformation-2.546e-003 m
- Average Deformation- 2.4248e-003 m




**Figure 42 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1.2)**

- Minimum Deformation- 1.3915e-003 m
- Maximum Deformation-1.5434e-003 m
- Average Deformation- 1.4707e-003 m



**Figure 43 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1)**

- Minimum Deformation- 4.3913e-003 m
- Maximum Deformation-5.0783e-003 m
- Average Deformation- 4.7529e-003 m



**Figure 44 End cell deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1.2)**

- Minimum Deformation- 2.6189e-003 m
- Maximum Deformation-3.0301e-003 m
- Average Deformation- 2.8349e-003 m

## Mid-Cell deformation

- Vertical Cell Orientation




Figure 45 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (12,1.2)

- Minimum Deformation-1.9738e-004 m
- Maximum Deformation - 2.3621e-004 m
- Average Deformation- 2.175e-004 m






Figure 46 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (12,1)

- Minimum Deformation-3.3845e-004 m
- Maximum Deformation - 4.0655e-004 m
- Average Deformation- 3.7415e-004 m




**Figure 47 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (15,1)**

- Minimum Deformation-3.2983e-004 m
- Maximum Deformation - 4.1293e-004 m
- Average Deformation- 3.7429e-004 m




**Figure 48 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (15,1.2)**

- Minimum Deformation-6.2041e-004 m
- Maximum Deformation - 7.8001e-004 m
- Average Deformation- 7.0279e-004 m



**Figure 49 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (21,1)**

- Minimum Deformation- 7.2028e-004 m
- Maximum Deformation-1.043e-003 m
- Average Deformation- 8.9446e-004 m



**Figure 50 Mid-Cell deformation of regular Vertical cell-orientation Honeycomb Structure (21,1.2)**

- Minimum Deformation- 6.6462e-004 m
- Maximum Deformation-9.0082e-004 m
- Average Deformation- 7.8991e-004 m

- Horizontal cell orientation




Figure 51 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1.2)

- Minimum Deformation-2.4417e-004 m
- Maximum Deformation - 2.9679e-004 m
- Average Deformation- 2.7226e-004 m






Figure 52 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (12,1)

- Minimum Deformation-6.1454e-004 m
- Maximum Deformation - 7.4801e-004 m
- Average Deformation- 6.897e-004 m




**Figure 53 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1)**

- Minimum Deformation-7.3013e-004 m
- Maximum Deformation - 9.1366e-004 m
- Average Deformation- 8.269e-004 m




**Figure 54 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (15,1.2)**

- Minimum Deformation-4.4249e-004 m
- Maximum Deformation - 5.5461e-004 m
- Average Deformation- 5.032e-004 m



**Figure 55 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1)**

- Minimum Deformation- 1.7144e-003 m
- Maximum Deformation-2.2629e-003 m
- Average Deformation- 2.0138e-003 m



**Figure 56 Mid-Cell deformation of regular Horizontal cell-orientation Honeycomb Structure (21,1.2)**

- Minimum Deformation- 1.0234e-003 m
- Maximum Deformation-1.3518e-003 m
- Average Deformation- 1.2022e-003 m

## Chapter 4

### Design of Gradient Honeycomb Structure

- Vertical cell orientation




Figure 57 Cell dimensions of Vertical cell oriented Gradient Honeycomb Structure.

- The total length and width of structure are 127.33 mm and 52.5mm respectively. The thickness of whole structure is 30mm.
- Along the length, diagonal length of hexagonal cell is decreased uniformly by 0.5mm by keeping cell size constant i.e., 21mm.






Figure 58 Vertical cell oriented Gradient Honeycomb Structure

- **Horizontal cell orientation**



**Figure 59 Cell dimensions of Horizontal cell oriented Gradient Honeycomb Structure.**

- The total length and width of structure are 107.25 mm and 60.6mm respectively. The thickness of whole structure is 30mm.
- Along the length, diagonal length of hexagonal cell is decreased uniformly by 0.5mm by keeping cell size constant i.e., 21mm.



**Figure 60 Horizontal cell oriented Gradient Honeycomb Structure**

## Deformation of Gradient Honeycomb structure (Vertical and Horizontal cell orientation).




Figure 61 Total Deformation of Gradient Honeycomb Structure (Vertical cell orientation)

- Maximum Deformation=0.00040467m
- Average deformation= 0.00016616m
- Minimum Deformation =0m





Figure 62 Total Deformation of Gradient Honeycomb Structure (Horizontal cell orientation)


- Maximum Deformation=0.00052312
- Average deformation=0.00020044
- Minimum Deformation =0m

## End cell Deformation in Gradient Honeycomb Structures



**Figure 63 End cell Deformation of Gradient Honeycomb Structure (Vertical cell orientation)**


- Maximum Deformation=0.00040467m
- Average deformation=0.00037639m
- Minimum Deformation =0.00033413m



**Figure 64 End cell Deformation of Gradient Honeycomb Structure (Horizontal cell orientation)**


- Maximum Deformation=0.00049291m
- Average deformation= 0.00043414m
- Minimum Deformation =0.0003787m

## Mid-cell Deformation in Gradient Honeycomb Structures



**Figure 65** Mid-cell Deformation of Gradient Honeycomb Structure (Vertical cell orientation)

- Maximum Deformation=0.00018976m
- Average deformation=0.00015174m
- Minimum Deformation =0.0001115m



**Figure 66** Mid-cell Deformation of Gradient Honeycomb Structure (Horizontal cell orientation)

- Maximum Deformation=0.00022795m
- Average deformation=0.00017764m
- Minimum Deformation =0.00012406m

## Modal Analysis of Gradient Honeycomb Structure

- Vertical cell orientation




Figure 67 First modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 68 Second modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 69 Third modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 70 Fourth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 71 Fifth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 72 Sixth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 73 Seventh modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 74 Eight modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 75 Ninth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 76 Tenth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 77 Eleventh modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)




Figure 78 Twelfth modal shape deformation of gradient Honeycomb Structure (Vertical cell orientation)

- Horizontal Cell orientation




Figure 79 First modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 80 Second modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 81 Third modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 82 Fourth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 83 Fifth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 84 Sixth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 85 Seventh modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 86 Eighth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 87 Ninth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 88 Tenth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)



Figure 89 Eleventh modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)




Figure 90 Twelfth modal shape deformation of gradient Honeycomb Structure (Horizontal cell orientation)

**Vertical Cell Orientation****Horizontal Cell Orientation**

<b>Mode</b>	<b>Frequency (HZ)</b>	<b>Type of Mode</b>	<b>Mode</b>	<b>Frequency (HZ)</b>
1	399.27	Bending	1	527.01
2	444.36	Bending	2	621.75
3	879.68	Bending	3	1233.4
4	1555.5	Bending +Torsion	4	2626.9
5	2197.5	Bending +Torsion	5	2834.3
6	2688.5	Bending	6	3159.2
7	3196.3	Bending	7	4156.4
8	3311.3	Bending + Torsion	8	4253
9	3686.7	Bending + Torsion	9	5458.1
10	4695.9	Bending + Torsion	10	5946.5
11	5023.6	Bending	11	6371
12	5421.3	Bending	12	6570.6

**Table 3 Types of mode and frequency table for gradient Honeycomb structures**

- Modal analysis is a technique to study the dynamic characteristics of a structure under vibrational excitation. Natural frequencies, mode shapes and mode vectors of a structure can be determined using modal analysis.

- The modal shape represents the way a structure can deflect. Modal shape for lowest frequency indicates the lower energy state.
- Therefore, if you provide very little input to a system it will deflect as mode shape 1. If you continue increasing energy input it will show two, three or next modal shape depending on the energy. The higher modal shapes require very high energy state which a structure or system may not face in its entire life.

## **Boundary Conditions**

- Honeycomb Structure is fixed at one end and 100N force is applied on the other end of structure.
- Total deformation of structure and cell deformation of different cells in different columns were found out in ANSYS.
- Element type- Linear tetrahedral
- All the simulations are performed at ambient temperature (22 °C)
- Sphere material Properties:



## Structural Steel



Fatigue Data at zero mean stress comes from 1998 ASME BPV Code, Section 8, Div 2, Table 5-110.1

Density

7850 kg/m<sup>3</sup>

### Structural



#### ▼ Isotropic Elasticity

Derive from	Young's Modulus and Poisson's Ratio
Young's Modulus	2e+11 Pa
Poisson's Ratio	0.3
Bulk Modulus	1.6667e+11 Pa
Shear Modulus	7.6923e+10 Pa
Isotropic Secant Coefficient of Thermal Expansion	1.2e-05 1/°C
Compressive Ultimate Strength	0 Pa
Compressive Yield Strength	2.5e+08 Pa

- Honeycomb Structure material properties:



## Aluminum



Density

2710 kg/m<sup>3</sup>

### Structural



#### ▼ Isotropic Elasticity

Derive from	Young's Modulus and Poisson's Ratio
Young's Modulus	6.8e+10 Pa
Poisson's Ratio	0.32
Bulk Modulus	6.2963e+10 Pa
Shear Modulus	2.5758e+10 Pa

## Deformation of Gradient Honeycomb Structure at impact loads

- Vertical cell orientation




Figure 91 Total Deformation of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 40KMPH

- Minimum Deformation-0m
- Maximum Deformation-3.3406e-002 m
- Average Deformation-8.1439e-003 m




Figure 92 Total Deformation of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 20KMPH

- Minimum Deformation-0m

- Maximum Deformation-2.7946e-002 m
- Average Deformation-6.983e-003 m




Figure 93 Total Deformation of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 10KMPH

- Minimum Deformation-0m
- Maximum Deformation-2.2249e-002 m
- Average Deformation-5.3843e-003 m

### • Horizontal cell orientation




Figure 94 Total Deformation of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 40KMPH

- Minimum Deformation-0m
- Maximum Deformation-3.3334e-002 m
- Average Deformation-1.2691e-002 m




Figure 95 Total Deformation of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 20KMPH

- Minimum Deformation-0m
- Maximum Deformation-0.11245 m
- Average Deformation-5.4481e-003 m





Figure 96 Total Deformation of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 10KMPH


- Minimum Deformation-0m
- Maximum Deformation-0.1232 m
- Average Deformation-4.2916e-003 m.

## **Energy absorption of Gradient Honeycomb Structure (Vertical cell orientation and horizontal cell orientation) at impact loads**

- Vertical Cell orientation




**Figure 97 Energy probe of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 40KMPH**




**Figure 98 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 40KMPH**

- Sphere speed- 11.11mps

- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 3.8042 J, Minimum Kinetic Energy= 1.8878 J
- Maximum Internal Energy = 3.1788 J, Minimum Internal Energy = 0J
- The blue line Indicates total Energy. Maximum total energy is 6.983J




**Figure 99 Energy probe of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 20KMPH**




**Figure 100 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 20KMPH**

- Sphere speed- 5.555mps

- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 1.0296 J, Minimum Kinetic Energy= 0.47204 J
- Maximum Internal Energy = 0.88873 J, Minimum Internal Energy = 0J
- The blue line Indicates total Energy. Maximum total energy is 1.9183 J




**Figure 101 Energy probe of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 10KMPH**




**Figure 102 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 10KMPH**

- Sphere speed- 2.5557mps
- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 24.784 J, Minimum Kinetic Energy= 0.11849 J
- Maximum Internal Energy = 21.744 J, Minimum Internal Energy = 0J
- The blue line Indicates total Energy. Maximum total energy is 29.026 J

- **Horizontal cell orientation**




**Figure 103 Energy probe of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 40KMPH**




**Figure 104 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 40KMPH**

- Sphere speed- 11.11mps
- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 4.9037 J, Minimum Kinetic Energy= 1.7479 J
- Maximum Internal Energy = 3.7992 J, Minimum Internal Energy = 0J
- The blue line Indicates total Energy. Maximum total energy is 8.7029J




**Figure 105 Energy probe of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 20KMPH**




**Figure 106 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 20KMPH**

- Sphere speed- 5.555mps

- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 52.996 J, Minimum Kinetic Energy= 0.47398 J
- Maximum Internal Energy = 45.936 J, Minimum Internal Energy = 0J
- The blue line Indicates total Energy. Maximum total energy is 62.851 J



**Figure 107 Energy probe of Honeycomb Gradient (Horizontal cell orientation) when impacted with a sphere with 10KMPH**



**Figure 108 Energy vs time graph of Honeycomb Gradient (Vertical cell orientation) when impacted with a sphere with 10KMPH**

- Sphere speed- 2.5557mps

- The graph illustrates Kinetic and Internal energy absorbed during the impact. The green line and pink line represent kinetic and internal energy respectively.
- Maximum Kinetic Energy = 24.784 J, Minimum Kinetic Energy= 0.11849 J
- Maximum Internal Energy = 21.744 J, Minimum Internal Energy = 0J.
- The blue line Indicates total Energy. Maximum total energy is 29.026 J.

## Results and Inferences

- As cell's longest diagonal length decreases along rows i.e., each column will have same cell size, the properties such as Honeycomb density, Cells per honeycomb surface area, foil edge area per honeycomb surface area, exposed foil area per honeycomb volume decrease.





Figure 109 Total Deformation vs Cell diagonal length graph for Vertical Cell Oriented Regular Honeycomb Structure



**Figure 110 Total Deformation vs Cell diagonal length graph for Vertical Cell Oriented Regular Honeycomb Structure**

Observations	Inferences
<ul style="list-style-type: none"> <li>As cell diagonal length increased, total deformation also increased.</li> </ul>	<ul style="list-style-type: none"> <li>For lowest diagonal length in a cell of honeycomb Structure, has high resistance.</li> </ul>
<ul style="list-style-type: none"> <li>As wall thickness increases, total deformation decreased.</li> </ul>	<ul style="list-style-type: none"> <li>Cell wall thickness increases moment of inertia which will decrease deflection.</li> </ul>
<ul style="list-style-type: none"> <li>Except for 15mm,1mm Structure, in which total deformation is lesser than the structure with 15mm and 1.2mm as diagonal length of cell and cell wall thickness respectively.</li> </ul>	<ul style="list-style-type: none"> <li>This is because of total length of structure, as it is to be maintained approximately 220mm length and 50mm width.</li> </ul>

**Table 4 Observation vs Inference table of regular honeycomb structures**

- For almost all the modes, Vertical cell oriented Gradient Honeycomb Structure deforms less than Horizontal cell oriented Gradient Honeycomb Structure.
- But, for all the mode type of Bending +Torsion, Horizontal cell oriented Gradient Honeycomb Structure's maximum deformation is very high.
- The higher modal shapes require very high energy state which a structure or system may not face in its entire life.
- Vertical cell-oriented Honeycomb Structures offer higher bending resistance than Horizontal cell-oriented Honeycomb Structures.
- Gradient Vertical cell-oriented Honeycomb Structures offer higher bending resistance than Gradient Horizontal cell-oriented Honeycomb Structures.
- Maximum deformation occurs at end cell of Honeycomb structure.
- Gradient Honeycomb Structure offers more bending resistance than the regular Honeycomb Structure because of gradual increment in cell wall thickness for a given number of cells.
- Horizontal cell oriented gradient Honeycomb Structure fails at 40 KMPH speed impact load.
- For vertical cell orientated Honeycomb Structure, failure occurs at all the three cases. This is because of resistance offered by Honeycomb cell due to its orientation.
- Horizontal cell-oriented Honeycomb Structure can be used wherever low speed impacts at free end are applied.
- At low speeds Horizontal cell-oriented Honeycomb Structure absorbs more energy than the vertical cell-oriented Honeycomb Structure.

## **Conclusions and Future works**

- Vertical cell-oriented honeycomb structure offers more bending resistance than horizontal cell orientated honeycomb structures.
- Increasing cell diagonal along length increases bending resistance than regular honeycomb structure. (Both for horizontal and vertical cell oriented)
- Compression test on adhesive bonded Honeycomb Sandwiches can also be a future work.
- In future, this can be experimented on cars front exterior as gradient honeycomb structures can sustain impact loading (sudden brakes or speed breaker jerks during drive).



**Figure 111 Honeycomb panels assembled in AUDI R7S**

- Harmonic Analysis and Random Vibration analysis can be done in future to determine the response of the structure under a steady-state sinusoidal (harmonic) loading at a given frequency and to determine structure response at random loading respectively

## References

- Tom Bitzer, Honeycomb Technology, First edition, Hexcel Corporation Dublin, CA USA, 1997
- Khan MK, Baig T, Mirza S. Experimental investigation of in-plane and out-of-plane crushing of aluminum honeycomb. Mater Sci Eng A 2012; 539:135–42
- Gong X. Vibration and acoustic performance of in-plane honeycomb sandwich panels [dissertation]. Clemson University; 1998.
- Sahu, Santosh & Badgayan, Nitesh & Samanta, Sutanu & Sahu, Duryodhan & Sreekanth, P S. (2018). Influence of cell size on out of plane stiffness and in-plane compliance character of the sandwich beam made with tunable PCTPE nylon honeycomb core and hybrid polymer

nanocomposite skin. International Journal of Mechanical Sciences. 148.

10.1016/j.ijmecsci.2018.08.011.

- Shaik.Nazeer “Design and Analysis of Honey Comb Structures with Different Cases.”
- Amin Ajdari “Mechanical properties and energy absorption of heterogeneous and functionally graded cellular structures.”
- Pagadala Bhavek, A. Soma Sundar, Kalapala Prasad. Design and analysis of honeycomb structures. (ISSN-2455-6300).
- H.Salem, Dijali Boutchincha, Abdelmadjid Boudjemai. Modal analysis of the multi-shaped coupled honeycomb structures used in satellites structural design
- O.S. Es-Said. Theoretical design and analysis of a honeycomb panel sandwich structure loaded in pure bending.
- Nurashikin Sawal, Abdul Basit Mohd Nazri, Hazizan Md Akil-“Effect of Cell Size Material on the Mechanical Properties of Honeycomb Core Structure”, International Journal of Science and Research (IJSR).
- Pizhong Qiao, Mijia Yang. Impact analysis of fiber reinforced polymer honeycomb composite sandwich beams.