LIQUI-GEM SAPPHIRE

Crosslinked Acrylic Floor Finish

Form: Liquid

Color: Opaque White

Odor: Mild **pH:** 8.0 - 8.75

Polymer Type: Zinc Crosslinked Acrylic

Solids Content: 22%

Solubility (in water): Soluble **(in mineral spirits):** Insoluble

Flash Point (ASTM D-7821): None Specific Gravity: $0.97 \text{ g/cm}^3 \pm 0.05$

Density: $8.09 \pm 0.05 \, \text{lbs/gal}$

Storage Stability (at 70°F): Minimum 1 year

(at 0°F): Damaged by Freezing

<u>Ingredients</u>	C.A.S. #
Water	7732-18-5
Diethylene Glycol Methyl Ether	111-77-3
Zinc Ammonium Carbonate	38714-47-5
Dibutyl Phthalate	84-74-2
Tributoxyethyl Phosphate	78-51-3

Other Uses...

- Terrazzo Finish
- Desk Top Sealer
- Wood Floor Sealer
- Wood Wall Sealer
- Mold Release Agent
- Concrete Floor Finish
- Quarry Tile Polish
- Marble Polish

APPLICATION: Remove old wax or finish using either LIQUI-GEM MARQUISE CUT or LIQUI-GEM PRINCESS CUT. Rinse floor several times with clean water. Then use LIQUI-GEM BALANCE to neutralize excess alkalinity, rinse floor with water and allow floor to dry thoroughly. Apply smooth even coats of LIQUI-GEM SAPPHIRE using a previously rinsed cotton string mop or lambswool applicator. Allow 30 minutes for drying before applying the next coat of LIQUI-GEM SAPPHIRE.

HMIS				NFPA
	Severe	4	Extreme	
Health1	Serious	3	High	Health1
Flammability0	Moderate	2	Moderate	Flammability0
Reactivity0	Slight	1	Slight	Reactivity0
Personal ProtectionX	Minimal	0	Insignificant	Special Precautions None

KEEP FROM FREEZING