

THE EVOLUTION AND OPTIMIZATION OF ORTHODONTIC BONDING: A COMPREHENSIVE EVIDENCE-BASED SYNTHESIS AND CLINICAL PROTOCOL

Authors:

Maen Mahfouz^{1+*}, Eman Alzaben²

Affiliations:

¹ Private Orthodontic Clinic, Ministry of Health, Ramallah, Palestine.

² Private Dental Clinic, Jerusalem, Palestine.

⁺ Former Lecturer, Department of Orthodontics and Pediatric Dentistry, Faculty of Dentistry, Arab American University Palestine (AAUP), Jenin, Palestine.

*Correspondence to: Dr. Maen Mahfouz, mnnm0599@gmail.com

ORCID iDs:

Maen Mahfouz: 0000-0001-9669-9984

Eman Alzaben: 0009-0000-2829-6833

Abstract

Background: Orthodontic bonding has evolved through seven distinct generations, from early failed attempts to sophisticated multi-modal systems. Despite advancements, clinicians face persistent challenges balancing mechanical efficacy with biological preservation.

Objective: To synthesize historical development, current evidence, and future directions of orthodontic bonding, culminating in the introduction of the Biologically-Attentive Precision Bonding (BAPB) protocol—a comprehensive clinical framework for optimized adhesive selection and technique.

Methods: This comprehensive review integrates foundational studies, contemporary systematic reviews, and clinical trials to analyze key aspects of bonding: historical evolution, shear bond strength parameters, polymerization science, contamination management, and substrate-specific

protocols.

Results: Evidence establishes a therapeutic window for shear bond strength (8-13 MPa) that balances retention with enamel safety. The 1:10 energy rule provides reliable polymerization guidance when combined with proper light positioning. Moisture control remains paramount, with contamination reducing bond strength by 30-50%. Contemporary evidence clarifies optimal techniques, including avoiding sealant pre-curing and standardized protocols for bonding to restorations.

Conclusions: Successful bonding requires moving beyond material selection to embrace integrated clinical protocols. The BAPB protocol provides a scenario-based decision matrix that addresses enamel integrity, caries risk, and restorative context. Future directions include bioactive "smart" materials and AI-enhanced digital workflows, all guided by the principle of achieving sufficient, rather than maximal, bond strength while prioritizing enamel preservation.

Keywords: Orthodontic Bonding, Shear Bond Strength, Adhesive Protocols, Bioactive Materials, Enamel Preservation, Digital Bonding, Evidence-Based Dentistry.

1. Introduction

The paradigm shift from circumferential banding to direct enamel bonding in the 1970s revolutionized fixed appliance therapy, offering improved aesthetics, enhanced patient comfort, and clinical applicability to partially erupted teeth. This transition, however, exchanged one set of challenges for another, centering treatment success on the integrity of the adhesive-enamel interface.

Five decades of relentless innovation have produced seven generations of bonding systems, each addressing limitations in strength, moisture sensitivity, or clinical efficiency. Despite this progress, fundamental clinical dilemmas persist. Should clinicians choose the proven robustness of total-etch techniques or the efficiency of self-etch systems? How does one balance the therapeutic benefits of fluoride-releasing adhesives against their potentially lower bond strength? What protocols ensure reliable bonding to the increasingly prevalent ceramic and composite restorations in adult orthodontics?

This manuscript provides a critical, evidence-based synthesis of orthodontic bonding science, from historical foundations to contemporary protocols. Beyond mere cataloging, we introduce the **Biologically-Attentive Precision Bonding (BAPB) protocol**—an original clinical framework that integrates material science with patient-specific factors to optimize both mechanical efficiency and enamel health preservation. This protocol represents not merely a technique, but a holistic philosophy for bonding in modern orthodontic practice.

2. Historical Evolution: Seven Generations of Progress

Understanding bonding's historical context illuminates the principles behind contemporary materials and explains why certain techniques failed. The progression through seven generations reveals a clear trajectory toward simplification, moisture tolerance, and clinical reliability.

Table 1: The Generational Evolution of Orthodontic Bonding Systems

Generation	Era	Key Characteristics & Chemistry	Representative Example(s)	Primary Advancement/Limitation
1st (G1)	1960s	No enamel etching; cyanoacrylates.	Eastman 910	First direct bonding attempt; obsolete due to extremely poor bond strength.
2nd (G2)	Early 1970s	Early acrylic resins (Polymethylmethacrylate).	Sevriton	High polymerization shrinkage, poor adhesion.
3rd (G3)	Mid-1970s – 1990s	Etch-rinse technique established. Bis-GMA composite resin.	Concise™ (3M)	Foundation of modern bonding; moisture-sensitive but reliable.
4th (G4)	1990s	Self-Etching Primers (SEP) introduced. Combines weak acid & primer.	Transbond™ SEP (3M)	Simplified technique; early formulations less reliable.
5th (G5)	Mid-1990s	Moisture-Insensitive Primers (MIP). Hydrophilic monomers.	Transbond™ MIP (3M)	Improved performance in humid fields.

6th (G6)	Late 1990s	No-Mix Adhesives. Predosed, auto-mix systems.	Rely-a-Bond®	Simplified dispensing, reduced waste.
7th (G7)	2000s	Refined SEP Systems. Improved acidity and stability.	Greengloo™ (Ormco)	Current clinical standard for 1-step bonding.
Universal	2010s +	Multi-Mode Adhesives. Versatile for etch-rinse, self-etch, or selective-etch.	Assure® Plus (Reliance)	Growing adoption for complex scenarios.

The critical turning point was **Reynolds' (1975)** demonstration that a bond strength of **6-8 MPa** was sufficient for clinical success, establishing that maximal strength was neither necessary nor desirable. This principle continues to guide development, shifting focus toward handling characteristics, biological compatibility, and clinical efficiency.

3. Core Scientific Principles

3.1. Shear Bond Strength: The Therapeutic Window

Shear bond strength (SBS) remains the primary metric for evaluating adhesive performance. The foundational work of Reynolds (1975) and Retief (1974) establishes clear parameters:

- **Minimum Adequacy:** 6-8 MPa (withstands clinical forces)
- **Enamel Fracture Threshold:** 13.5-15 MPa (cohesive enamel strength)
- **Therapeutic Window:** 8-13 MPa (optimal balance of retention and safety)

SBS values must be interpreted alongside the **Adhesive Remnant Index (ARI)**, which scores adhesive left on enamel post-debond (0-3). An ideal outcome combines SBS within the therapeutic window with an ARI of 1-2, indicating adequate strength with failure at the interface rather than within enamel.

3.2. The Polymerization Equation: The 1:10 Energy Rule

For light-cured adhesives, adequate polymerization depends on total energy delivered:

$$\text{Energy Density (J/cm}^2\text{)} = \text{Intensity (W/cm}^2\text{)} \times \text{Time (s)}$$

Research indicates 10-12 J/cm² achieves optimal conversion. Thus:

$$\text{Time (s)} = 10 / \text{Intensity (W/cm}^2\text{)}$$

This "1:10 Rule" provides practical guidance but requires regular radiometer verification of light output and strict attention to light-tip distance (<1 mm), as distance exponentially reduces energy delivery.

3.3. Contamination: The Non-Negotiable Factor

Moisture or blood contamination reduces SBS by 30-50% (Hobson et al., 2001), often pushing strength below clinical adequacy. Meticulous isolation—using cheek retractors, dry angles, and high-volume suction—is fundamental, not optional. This is particularly critical for self-etch primers, which lack the rinsing step that helps displace contaminants in total-etch protocols.

4. The Biologically-Attentive Precision Bonding (BAPB) Protocol

We propose the BAPB protocol as an integrated, scenario-based approach that synthesizes historical wisdom with contemporary evidence.

Core Philosophy: The bonding appointment represents an opportunity to establish both mechanical efficiency and proactive enamel preservation through precision technique and material selection tailored to individual patient factors.

4.1. Pre-Bonding Assessment Matrix

Before adhesive selection, clinicians evaluate:

1. **Enamel Integrity:** Sound vs. Compromised (fluorosis, hypoplasia, white spot lesions)
2. **Caries Risk Profile:** Low vs. High (based on history, hygiene, diet)
3. **Restorative Context:** Virgin enamel vs. Existing restorations (composite, ceramic)

4.2. BAPB Decision Algorithm & Technical Protocol

Step 1: Universal Preparation

- Meticulous isolation with cheek retractors and high-volume suction
- Pumice prophylaxis (mandatory for SEP systems, recommended for all)
- Assessment using the above matrix

Step 2: Scenario-Based Protocol Selection

Table 2: BAPB Clinical Decision Matrix

Scenario	Enamel & Risk Profile	Adhesive System	Key Technique	Evidence-Based Rationale
A	Sound Enamel, Low Caries Risk	Conventional Composite or SEP	Operator preference	Maximizes efficiency with proven strength.
			(Total-etch or SEP). Do NOT pre-cure sealant (Hoppe et al., 2022).	
B	Sound Enamel, High Caries Risk	Bioactive Composite or RMGIC	Selective-Etch with Universal Adhesive: Etch perimeter only (15 sec), apply universal adhesive, then bioactive paste.	Balances mechanical retention (peripheral etch) with therapeutic ion release.
C	Compromised Enamel (Fluorosis, Hypoplasia)	RMGIC (First-line)	Condition with polyacrylic acid,	Chemical adhesion more reliable than micromechanical

			lightly dry, place RMGIC.	retention on poorly prismatic enamel.
D	Bonding to Composite Restorations	Composite + Universal Adhesive	1. Roughen with fine diamond bur. 2. Clean with 37% phosphoric acid (15-20 sec). 3. Apply 2-3 coats universal adhesive, cure. 4. Bond with composite (Buyukcavus et al., 2022).	Combined mechanical/chemical approach ensures reliable adhesion to resin-based substrates.
E	Bonding to Ceramic/Zirconia	Composite + Specialized Primers	Ceramic: Hydrofluoric acid etch, silane application. Zirconia: Air- abrasion, 10- MDP primer application.	Addresses unique surface chemistry of prosthetic materials.

Step 3: Meticulous Adhesive Management

- Apply adhesive sparingly to bracket base
- Immediately remove gross flash with sharp probe before curing
- Cure according to 1:10 rule with optimal light positioning

Step 4: Conservative Debonding Protocol

- Use debonding pliers applying shear force at bracket-adhesive interface

- Remove residual adhesive with **12-18 fluted tungsten carbide bur at low speed** using peeling motion
- Final polish with rubber cup and fine paste to preserve enamel surface

5. Discussion: Integrating Evidence into Clinical Wisdom

5.1. Resolving Historical Debates

The **total-etch vs. SEP** debate is clinically settled: systematic reviews show no significant difference in clinical failure rates. The BAPB protocol allocates them based on scenario—SEP for routine efficiency (Scenario A), while total-etch finds targeted application in selective-etch techniques (Scenario B).

5.2. Contemporary Evidence Integration

Recent systematic reviews provide crucial clarifications:

- **Sealant Pre-Curing:** Hoppe et al. (2022) confirm **no benefit to pre-curing** the sealant layer, supporting BAPB's streamlined "wet-bonding" technique that enhances interfacial cohesion.
- **Restorative Bonding:** Buyukcavus et al. (2022) provide evidence-based specifics for bonding to composites, transforming a clinical challenge into a standardized protocol within Scenario D.

5.3. The Triad of Bonding Success

BAPB operationalizes three evidence-based pillars:

1. **Immaculate Moisture Control** (Hobson et al., 2001)
2. **Adequate Polymerization** (1:10 Rule with proper positioning)
3. **Scenario-Appropriate Materials & Techniques**

Failure in any pillar compromises outcomes, regardless of material quality.

5.4. The Sufficient Strength Paradigm

The pursuit of ever-higher bond strength is misguided and potentially harmful. The goal is **sufficient, reliable strength** within the therapeutic window (8-13 MPa), coupled with favorable failure modes (ARI 1-2) and enamel-preserving debonding characteristics.

6. Future Directions

6.1. Material Innovations

- **Bioactive "Smart" Adhesives:** Next-generation materials with pH-responsive ion release, antibacterial properties, and enhanced remineralization capacity.
- **Debonding-on-Demand:** Adhesives weakened by specific light wavelengths for safer removal.

6.2. Digital Integration

- **AI-Enhanced Positioning:** Machine learning algorithms for optimal bracket placement based on tooth morphology and planned occlusion.
- **Robotic Assistance:** Automated adhesive dispensing and bracket placement for ultimate precision.

6.3. Biological Optimization

- **Gene Expression Analysis:** Understanding cellular responses to bonding materials to optimize biocompatibility.
- **Nano-Engineering:** Materials designed at molecular level for ideal mechanical and biological properties.

7. Conclusion

Orthodontic bonding has evolved from a technique of high failure to one of predictable, evidence-based success. The contemporary challenge transcends mere adhesion to encompass integrated optimization of mechanical efficiency, biological preservation, and clinical practicality.

The **Biologically-Attentive Precision Bonding (BAPB) protocol** provides a comprehensive framework for this optimization, translating five decades of innovation into actionable clinical decisions. By emphasizing scenario-based selection, precision technique, and enamel preservation, it elevates bonding from routine procedure to cornerstone of biologically respectful orthodontic therapy.

As materials and technologies advance, the fundamental principle remains: successful bonding achieves **sufficient strength** through **appropriate materials** applied with **meticulous technique**—always prioritizing the long-term health of the enamel substrate. The BAPB protocol embodies this principle, offering a dynamic framework ready to incorporate future innovations while grounded in proven scientific evidence.

8. References

1. Reynolds, I. R. (1975). A review of direct orthodontic bonding. *British Journal of Orthodontics*, 2(3), 171-178.
2. Retief, D. H. (1974). The mechanical bond. *International Journal of Orthodontics*, 12(2), 137-148.
3. Hobson, R. S., Ledvinka, J., & Meechan, J. G. (2001). The effect of moisture and blood contamination on bond strength of a new orthodontic bonding material. *American Journal of Orthodontics and Dentofacial Orthopedics*, 120(1), 54-57.
4. Cacciafesta, V., Sfondrini, M. F., Scribante, A., Boehme, A., & Jost-Brinkmann, P. G. (2005). Effect of light-tip distance on the shear bond strengths of composite resin. *The Angle Orthodontist*, 75(3), 386-391.
5. Artun, J., & Bergland, S. (1984). Clinical trials with crystal growth conditioning as an alternative to acid-etch enamel pretreatment. *American Journal of Orthodontics*, 85(4), 333-340.
6. Hoppe, J., Lehmann, T., Hennig, C. L., Schulze-Späte, U., & Jacobs, C. (2022). Shear bond strength after using sealant before bonding: a systematic review and meta-analysis of in vitro studies. *Clinical Oral Investigations*, 26(1), 1-11.

7. Buyukcavus, E., Ugurlu, M., & Buyukcavus, M. H. (2022). Shear bond strength of orthodontic molar tubes to composite restoration bonded with particular adhesives after different surface pre-treatments. *Orthodontics & Craniofacial Research*, 25(4), 541-548.
8. Bishara, S. E., Ajlouni, R., Soliman, M. M., Oonsombat, C., Laffoon, J. F., & Warren, J. (2005). Evaluation of a new curing light on the shear bond strength of orthodontic brackets. *The Angle Orthodontist*, 75(3), 410-413.
9. Eliades, T., & Brantley, W. A. (2000). The inappropriateness of conventional orthodontic bond strength assessment protocols. *European Journal of Orthodontics*, 22(1), 13-23.
10. Fox, N. A., McCabe, J. F., & Gordon, P. H. (1991). Bond strengths of orthodontic bonding materials: an in vitro study. *British Journal of Orthodontics*, 18(2), 125-130.
11. Rueggeberg, F. A. (2011). State-of-the-art: dental photopolymerization—a review. *Dental Materials*, 27(1), 39-52.
12. Oesterle, L. J., Newman, S. M., & Shellhart, W. C. (2001). Rapid curing of composite with a high-intensity light: an in vitro study. *The Angle Orthodontist*, 71(5), 383-388.
13. Sondhi, A. (2015). Efficient and effective indirect bonding. *Journal of Clinical Orthodontics: JCO*, 49(4), 239-250.
14. Millett, D. T., Glenny, A. M., Mattick, C. R., Hickman, J., & Mandall, N. A. (2017). Orthodontic bonding: a systematic review. *Journal of Orthodontics*, 44(2), 79-87.
15. Wiegand, A., Buchalla, W., & Attin, T. (2022). Bioactive dental materials: State of the art and future perspectives. *Dental Materials*, 38(1), 1-12.

Author Contributions: M.M. conceived the BAPB protocol framework and led manuscript synthesis. E.A. conducted evidence analysis, contributed to protocol detailing and critical revisions. Both authors approved the final manuscript.

Disclosure Statement: The authors declare no potential conflicts of interest regarding the research, authorship, or publication of this article.

Funding Statement: No external funding was received for the preparation of this manuscript.