



CharCoat SC

PRODUCT DESCRIPTION

CharCoat SC Structural Steel Fire Protection is the pinnacle of technology and performance in Thin Film Intumescent Fireproofing.

SC can be applied to steelwork in interior or covered exterior applications. SC fireproofing coating is spray applied and offers up to 150 minutes fire protection under UL263 and BS476: Part 21. There is no reinforcement or mesh required.

SC can be applied in residential, commercial and industrial applications where architectural designs call for a thin-film, aesthetic, highly decorative finish.

Semi exterior or covered areas can also be completed using a urethane, epoxy or water based topcoat to seal the fireproofing system. With SC's low spread rate, higher than average solids and extremely low DFT's, we can provide the most cost effective solution for all of your steel fireproofing needs.

FEATURES AND BENEFITS

- Fire rates steelwork up to 150 minutes
- Low VOC
- 20 to 30 times typical intumescent expansion
- Extremely low DFT's
- Water based intumescent coatings
- Non-Toxic / Non-Hazardous (water based)
- Most steelwork 1 or 2 coat application
- Permanent cost effective solution
- Zero maintenance required
- Single component (stir and spray)
- Brush application also available

APPLICATION AREAS

- Airports
- Stadiums and Leisure Facilities
- Office Buildings
- Retail Complexes
- Cinemas
- Residential Low and Highrise Apartments
- Atriums
- Warehousing
- Powerstations
- Mines
- Smelters
- Shipyards
- Swimming Pools (C4 topcoat)



TDS

AUTHOR	SEAN RITCHIE
VERSION	2.0
PURPOSE/CHANGES	TECHNICAL
DATE PUBLISHED	JUNE 2026

TECHNICAL DATA

Composition	Low VOC, Waterbased, NON-DG
Certification	BS476, Part 21 UL 263 GB14907-2018
Building Classification	C1 and C2 Environments
Specific Gravity	1.30 ± 0.01kg/L (25°C)
Volume Solids	69% ± 3%
VOC	1 g/L
Theoretical Coverage	1800g/m ² based on an applied @ 1.0mm DFT
Colour	White / matte
Primer	Epoxy Zinc Primer or similar
Topcoat	Water-based topcoats (interior if required)
Drying Time at 25°C	2 hours (touch) 4 hours (hard dry) 72 hours full cure
Coating Intervals at 25°C	Spray min. 4-6 hours

PLEASE CONTACT US FOR OTHER PROPERTIES

PACKAGING

- 25 kg Drum
- Plastic pails
- Other sizes on request

TRANSPORT / STORAGE

Transport and storage free from frost- preferably at a minimum of +5°C to a maximum of +35°C.

SHELF LIFE

When stored at the recommended conditions, unopened pails have a shelf life of 12 months from date of manufacture.

APPLICATION GUIDELINES

For Interior applications, use SC (up to 150 minutes). Topcoats are not required for interior works, but may be needed simply for colour. For covered external works, topcoats are required. Water based topcoats, urethane or epoxy topcoats are acceptable. SC will last the life time of the steelwork if properly maintained.

GUARANTEE / WARRANTY

Please refer to our full Terms and Conditions of sale.

No liability can be accepted for the information provided in this document although it is published in good faith and believed to be correct. CharCoat Passive Fire Protection reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

PRODUCT

SC

FIRE RATING (MINUTES)

up to 150 minutes

APPROVALSBS476, Part 21
UL 263**DESCRIPTION**120 minutes - Structural Steelwork
150 minutes - Structural Steelwork

CHARCOAT

Suite 301 – 220 Brew Street, Port Moody, BC V3H 0H6 Canada

☎ +1 604 941 1001

✉ mail@CharCoat.com

🌐 www.CharCoat.com

charcoatpfp



Disclaimer: The above data, particularly the recommendations for the application and use of Charcoat Passive Fire Protection products are based on the manufacturer's knowledge and experience. Due to different materials and conditions of application, which are beyond our control, we recommend in any case to carry out sufficient tests in order to ensure that Charcoat Passive Fire Protection products are suitable for the intended purpose and applications. Therefore, any liability for such recommendations or any oral advice is expressly excluded unless we have acted willfully or by gross negligence. It is always the responsibility of the installer / purchaser to guarantee correct preparation, DFT (Charcoat Coatings) and thickness (Charcoat Firestop Products) of all Charcoat Passive Fire Protection products. Charcoat Passive Fire Protection is not liable for installation or faulty installation. It is always the responsibility of the installer / purchaser to guarantee and certify the installation of materials.

