Electronic Structure of Graphene Nanoribbons in the Tight-Binding Model

Elsie Sheldrake
Department of Physics, University of Bath, Bath BA2 7AY, United Kingdom
Date submitted: 13/03/2026

Abstract

In this article a computational study of the electronic properties of graphene nanoribbons using a nearest-neighbour tight-binding model is presented. The geometry of graphene nanoribbons comes in two distinct types: *armchair* and *zigzag* nanoribbons of varying width are constructed numerically and their Bloch Hamiltonians are diagonalised to obtain the band structure and density of states. The calculations reproduce the width-dependence in band gap behaviour of armchair nanoribbons, as well as the characteristic edge states of zigzag ribbons. Numerical convergence tests and recovery of the graphene Dirac dispersion serve to demonstrate the reliability of the computational approach. These results illustrate how tight-binding calculations can predict electronic behaviour of graphene nanostructures beyond what can be obtained analytically.

1. Introduction

Graphene is a single layer of carbon atoms in a two-dimensional hexagonal lattice. Considerable interest has manifest in graphene science since its experimental isolation in 2004 by Andre Geim and Konstantin Novoselov [7] due to its exotic electronic properties and applications in nanoelectronics [2]. The charge carriers in graphene behave as massless Dirac fermions, leading to exceptionally high carrier mobility and atypical transport behaviour [3]. These properties make graphene a promising platform for the next generation of electronic and molecular devices.

When graphene is confined to a narrow strip it is known as a graphene nanoribbon (GNR), a quasi-one-dimensional structure with strong quantum confinement effects [3]. This significantly modifies the electronic structure compared to bulk graphene, particularly the sensitive dependence on both ribbon width and edge geometry [2, 3]. The two most notable common edge geometries are armchair and zigzag nanoribbons, which exhibit markedly different properties, such as in their band structure and transport behaviour [6].

An understanding of how the electronic properties of graphene nanoribbons depend on their geometry is a crucial problem in device design and nanoscale physics [2]. Notable analytic approaches have provided insight for idealised systems [1, 3], however numerical methods are often required to study realistic nanostructures. In this work, a tight-binding computational model is implemented in order to investigate the electronic band structure and density of states for graphene nanoribbons of different edge geometries and widths. The numerical results are then analysed to determine how the ribbon structure influences the presence of band gaps and other key features of the electronic properties of GNRs.

2. Tight-Binding Model

The true Hamiltonian for a GNR consists of an infinite sum of contributions over the periodic lattice, which is computationally intractable. To progress, this work employs the tight-binding approach [2, 3].

2.1 Graphene Lattice

The two-dimensional honeycomb lattice of carbon atoms can be viewed as two interpenetrating triangular sublattices, labelled A and B. Each atom has three nearest neighbours at a distance a, the carbon-carbon bond length. The structure of graphene is not a Bravais lattice, instead accurately described as a triangular lattice with a two-atom basis per unit cell. The lattice vectors

$$\boldsymbol{a_1} = \frac{a}{2}(3, \sqrt{3}), \quad \boldsymbol{a_2} = \frac{a}{2}(3, -\sqrt{3}), \tag{1}$$

and reciprocal lattice vectors,

$$\boldsymbol{b_1} = \frac{2\pi}{3a}(1, \sqrt{3}), \quad \boldsymbol{b_2} = \frac{2\pi}{3a}(1, -\sqrt{3}) \tag{2}$$

are shown in Figure 1. Here, $a \approx 1.42$Å is the carbon-carbon distance [2].

Of interest are the two points K and K' in the Brillouin zone (BZ), these are known as the Dirac points. The electronic properties around the Fermi level are dominated by p_z orbitals perpendicular to the graphene plane. These orbitals form a π-electron system, able to be approximated by the tight-binding model, in which electrons hop only between nearest-neighbouring atomic sites [2, 3].



Figure 1. Taken from [2]. Left: The lattice structure of graphene, constructed of two overlapping triangular lattices. Here, $\mathbf{a_1}$ and $\mathbf{a_2}$ are the lattice unit vectors, $\boldsymbol{\delta_i}$ (i = 1,2,3) are the nearest-neighbour vectors. Right: The Brillouin zone. The reciprocal lattice vectors $\mathbf{b_1}$ and $\mathbf{b_2}$ are shown in the above. The Dirac cones appear at the K and K' points.

2.2 Tight-Binding Hamiltonian

In the tight-binding model, expanding the Hamiltonian for electron hopping in graphene to next-nearest-neighbour order ($\hbar = 1$) reads [2, 3]:

$$H = -t \sum_{\langle i,j \rangle, \sigma} \left(a_{\sigma,i}^{\dagger} b_{\sigma,j} + \text{h.c.} \right) \qquad (3)$$
$$-t' \sum_{\langle\langle i,j \rangle\rangle, \sigma} \left(a_{\sigma,i}^{\dagger} a_{\sigma,j} + b_{\sigma,i}^{\dagger} b_{\sigma,j} + \text{h.c.} \right).$$

In (3), the sum is over products involving the operators $a_{\sigma,i}$ ($a_{\sigma,i}^{\dagger}$) and $b_{\sigma,i}$ ($b_{\sigma,i}^{\dagger}$), which annihilate (create) an electron with spin σ on site $\boldsymbol{R_i}$ on sublattice A and B, respectively. H.c. refers to the Hermitian conjugate of the preceding expression. Here, t (≈ 2.7 eV to 2.8 eV) and t' (≈ 0.2 eV) are the nearest and next-nearest neighbour hopping energies, respectively. The band structure can be derived analytically [2]:

$$E_{\pm}(\boldsymbol{k}) = \pm t\sqrt{3 + f(\boldsymbol{k})} - t' f(\boldsymbol{k}),$$
$$f(\boldsymbol{k}) = 2\cos\left(\sqrt{3}k_y a\right) + 4\cos\left(\frac{\sqrt{3}}{2}k_y a\right)\cos\left(\frac{3}{2}k_x a\right). \quad (4)$$

Here, the +/− signs correspond to the upper (π) and lower (π*) bands, respectively. It is worth noting that in the nearest neighbour approximation ($t' = 0$), the spectrum becomes symmetric around zero energy. For finite values of t' the electron-hole symmetry is broken. See Figure 7 in section 4 for an example of this effect on the band gap of zigzag nanoribbons.

2.3 Graphene Nanoribbons

As stated in section 1, graphene nanoribbons come in two typical shapes, armchair (AGNR) and zigzag (ZGNR), which drastically alter the π electronic structures [3].

Figure 2 shows a simple model to study these edge states and size effects. In this work, N is defined as a width parameter, equal to the number of dimer (two carbon sites) lines for the armchair ribbon and by the number of zigzag lines for the zigzag ribbon. The dangling bonds at the ends of these GNRs are not considered, with the ribbon modelled as periodic along the ribbon axis.



Figure 2. Taken from [3], with relabelling. The above shows the structure of graphene nanoribbons. *Left:* armchair nanoribbon. *Right:* zigzag nanoribbon. The lattice constant in the figure is denoted by d, and N defines the ribbon width, while D is the width of the unit cell for AGNRs. Sites with dashed lines indicate missing carbon atoms for the boundary condition of the massless Dirac equation.

The electronic properties of nanoribbons have strong dependence on both width and edge orientation. AGNRs may be either metallic or semiconducting, depending on their width, whereas ZGNRs exhibit characteristic edge states which govern their electronic structure [2, 3]. To see how these effects are demonstrated in this work, see Section 4.

2.4 Bloch Hamiltonian

Given the ribbon is periodic along its length, Bloch's theorem can be applied in this direction. The electronic wavefunctions hence are of Bloch form,

$$\psi_{n,k}(r) = e^{ikr} u_{n,k}(r), \qquad (5)$$

where k is crystal momentum along the ribbon axis, r is the direction along the ribbon axis. It is clear from (5) that the Hamiltonian can hence be written as a k-dependent matrix $H(k)$.

Therefore, for each k value, the electronic energies are obtained by solving the eigenvalue equation

$$H(k)\psi_n(k) = E_n(k)\psi_n(k). \qquad (6)$$

Sampling k across the one-dimensional BZ produces the band structure $E_n(k)$, see Section 4 for further details.

2.5 Density of States

The electronic density of states (DoS) describing the number of available states at a particular energy is given by

$$D(E) = \sum_n \int dk\, \delta\big(E - E_n(k)\big), \qquad (7)$$

with the integral taken over all k. In a (quasi-)one-dimensional system like a graphene nanoribbon, the DoS possesses *van Hove singularities* at band extrema [3]. These appear as sharp peaks in the DoS, providing a reliable method to analyse their electronic structures.

In numerical calculations, the delta function is replaced by a small Gaussian broadening, yielding a smooth approximation of the DoS able to be computed directly from the band energies, see Sections 4.2 and 4.3.

3. Computational Implementation

This section outlines the methodology of the approach, making frequent reference to appendices A, B and C.

3.1 Lattice Construction

The GNR geometries are constructed by imposing finite boundaries on a honeycomb lattice along one direction, while maintaining periodicity along the axis of the ribbon, from input parameters N and a (only the value $a = 1.42$ Å is used in what follows).

For the two edge geometries considered here, the unit cell is constructed with this in mind. Atomic positions

and nearest neighbour connections are stored for later use in building the tight-binding Hamiltonian. This procedure is outlined in Appendix A.

3.2 Hamiltonian Construction

The calculations employ the standard form for the NN tight-binding Hamiltonian, equivalent to setting $t' = 0$ in (3). For some calculations (see Figures 3 and 7), a finite t' is implemented to demonstrate particle-hole symmetry breaking and the slight shift in Dirac point energy.

The tight-binding Hamiltonian is constructed by assigning hopping terms between NN lattice sites. For each NN pair i, j, the hopping value t is added to the Hamiltonian matrix, with the value $t \approx 2.7$ eV used throughout.

Accounting for the periodic nature of the ribbon, the hopping terms connecting atoms in neighbouring unit cells acquire a phase factor e^{ikT}, where T the translation length of the unit cell. The Hamiltonian is then written:

$$H(k) = -t \sum_{\langle i,j \rangle, n} e^{iknT} \, |i\rangle\langle j| \; + \text{h.c.} \; .$$

This Hamiltonian is expressed in the basis of atomic p_z orbitals within a single unit cell, yielding an $M \times M$ matrix, with M the number of atoms per unit cell.

The pipeline includes two extensions to the tight-binding model. The first is the addition of NNN terms, mentioned already. The second is the inclusion of a staggered onsite potential,

$$H_\Delta = \Delta \sum_i \xi_i a_i^\dagger a_i \, , \tag{8}$$

where $\xi_i = \pm 1$, $+$ and $-$ corresponding to the A and B sublattices respectively. It is seen in Section 4.1 that the inclusion of this term breaks sublattice symmetry, opening a band gap. Further detail of the implementation is discussed in Appendix B.

3.3 Band Structure Calculation

The electronic band structure of the ribbons is obtained by solving the eigenproblem (6) at many values of crystal momentum k. The BZ of the one-dimensional ribbon is uniformly sampled using a grid of k-points.

For each k-point, the Hamiltonian matrix is numerically diagonalised to obtain the energy eigenvalues $E_n(k)$. The collection of eigenvalues across the BZ forms the band structure of the nanoribbon. These eigenvalue calculations are performed using standard numerical linear algebra methods.

3.4 Density of States

To compute the density of states, the delta function in (7) must be approximated numerically. This work approximates the delta function by a Gaussian of finite width σ. Therefore, each eigenvalue contributes a Gaussian peak to the DoS.

The spectrum output is then evaluated on a finite grid to produce a smooth DoS curve. This approach allows for the characteristic van Hove singularities to be clearly identified. Further methodological details are provided in Appendix C.

3.5 Validation and Numerical Convergence

In the interest of ensuring reliable numerical calculations, two validation tests were performed.

Firstly, convergence of the computed band gap with respect to the count of sampled k-points was validated. The band gap was evaluated for increasing N_k for a set of test armchair and zigzag nanoribbons. The results showed that calculated gaps converge rapidly as k-point sampling became sufficiently dense, while metallic systems remain gapless within the numerical precision governed by the convergence criterion,

$$\frac{\left|E_g(N_k) - E_g^{\text{ref}}\right|}{E_g^{\text{ref}}} < 0.1\ \%,$$

in which $E_g(N_k)$ is the computed band gap energy for N_k and E_g^{ref} is the computed band gap energy of highest precision. In this work, the highest precision E_g^{ref} is that computed from the densest k-point sampling, $N_k = 1001$ in this work.

Secondly, the validity of the implementation of the tight-binding model was verified by investigating whether a sufficiently wide GNR reproduces the linear Dirac dispersion expected for bulk graphene. For a GNR of appropriate width, bands near the Fermi level were fitted to the relation:

$$E_{+,-}(k) = \pm \hbar v_F k.$$

Here, v_F is the Fermi velocity. The fitted value was found to agree with the theoretical prediction $\hbar v_F = 3ta/2$ within a tolerance of 1%, confirming the ability of the implementation to reproduce the known low-energy electronic structure of graphene.

4. Electronic Properties of Graphene Nanoribbons

In this section, the computational approaches taken to model the physics described in Section 3 are performed and compared with that in the current literature.

4.1 Armchair Nanoribbon Band Structures

The electronic band structures for GNRs of both edge types were computed using the tight-binding method, outlined in section 3. Figure 3 shows graphically the obtained band structures for ribbons of different widths.



Figure 3. Band structures of armchair nanoribbons for ribbon widths $N = 8, 9, 10$ calculated using the nearest neighbour tight-binding model with hopping parameter $t = 2.7$ eV. The figure illustrates the strong dependence of the band structure on ribbon width, due to quantum confinement [3, 4]. The second $N = 10$ graph (*bottom-left)* shows the affect the staggered potential Δ, set at 1eV for illustration, has on the band structure as the band gap is widened.

Included in Figure 3 is a graph of the AGNR band structure when subjected to the staggered onsite potential H_Δ, discussed in 3.2. This potential opens the band gap, serving to mimic the effects of boron nitride-type symmetry breaking [3].

Unlike bulk graphene, which is gapless due to Dirac points, AGNRs have a width-dependent gap due to quantum confinement in the transverse direction. Confinement quantises the allowed transverse wave vectors, modifying the electronic dispersion relative to the two-dimensional graphene sheet.

Armchair ribbons of width $N = 3m + 2$ display metallic behaviour, while ribbons with $N = 3m$ or $N = 3m + 1$ possess finite band gaps. This pattern is apparent in Figure 3, and aligns with the current literature [2-4].

As ribbon width increases, band spacing decreases. In the $N \to \infty$ limit, the band structure for bulk graphene is recovered. This reflects the weakening quantum confinement effects on the system, as it approaches the two-dimensional limit [2, 3].

4.2 Zigzag Edge States

ZGNRs have very different electronic behaviour to that of AGNRs due to the distinct boundary conditions of their edge geometry. In the NN tight-binding model, zigzag edges support electronic states localised at the ribbon boundaries [2]. These near-dispersionless bands close to the Fermi energy are not present in AGNRs. As a first demonstration of their considerably different properties, Figure 4 shows the band structure of a typical zigzag ribbon.



Figure 4. Computed band structure of a zigzag nanoribbon for width parameter $N = 8$, $t = 2.7$ eV. The flat bands near $E = 0$ and degeneracy at the BZ edge are clearly visible, in stark contrast with the band structure of AGNRs (Figure 3)

The resulting band structure in Figure 4 contrasts with that of AGNRs (Figure 3) with a pair of near-flat bands appearing in the vicinity of the Fermi level. These bands extend over a finite region of the BZ, indicating states of low group velocity. This dispersionless property is characteristic of spatially localised electronic states, as is the case in ZGNRs.

To verify the edge-localised nature of these states, the distribution of the relevant eigenstate was examined. Figure 5 shows the probability density of the state at $k = \pi/T$, where the flat band becomes maximally localised. Wavefunction amplitude is then dominantly concentrated on the outermost atoms of the ZGNR, decreasing exponentially towards the centre. This verifies the notion that flat bands originate in the confinement of the electronic states to the zigzag edges.

The consequence of this on the spectral signature for these edges is visible in the DoS, shown in Figure 6. The peak appearing near the Fermi energy arises from the large number of degenerate states from the flat band [3, 4]. In contrast with AGNRs, where the DoS vanishes inside the band gap, ZGNRs are characterised by a high DoS at zero energy. Figure 6 also shows the resultant van Hove singularities, appearing as sharp peaks in the DoS vs energy plot.

The extent of the metallic properties of ZGNRs is further examined by extending the tight-binding model to include NNN hopping by including $t' = 0.2$ eV. This leads to a small band gap for the zigzag ribbon, which can be seen from the band gap vs ribbon width plot in Figure 7. While zigzag ribbons are metallic in the NN approximation, the inclusion of t' in (3) breaks the electron-hole symmetry and a small band gap is produced, larger for narrow ribbons [4]. This demonstrates how modifications to the tight-binding model can influence the low-energy electronic structure.



Figure 5. Plots of probability density over the width direction y of a ZGNR, with width parameter $N = 8$, $t = 2.7$ eV at $k = \pi/T$. *Top:* the probability density on individual lattice sites, colours indicating the two sublattices for graphene. *Bottom:* the summed probability density across the transverse direction. The wavefunction amplitude is strongly localised at the ribbon edges, decaying rapidly into the interior.



Figure 6. The results of the computation of the density of states for a ZGNR of width $N = 8$, $t = 2.7$ eV. Here, the deviation σ of the Gaussian approximation of the delta function appearing in the equation for the DoS (7) is set at $\sigma = 0.05$ eV. This value was chosen to provide sufficient smoothing to suppress discretisation artefacts while preserving the key spectral features.



Figure 7. The computed band gap for the ZGNRs of varying widths N at $t = 2.7$eV. *Top:* the band gap in the NN approximation ($t' = 0$). As expected, no band gap emerges regardless of ribbon width. *Bottom:* the band gap computing in the NNN regime ($t' = 0.2$eV). Inclusion of this term breaks electron-hole symmetry, producing a small band gap for narrow ribbons, decreasing with ribbon width [3].

4.3 Width Dependence of the Band Gap for Armchair Ribbons

As mentioned, quantum confinement effects cause a strong width-dependence on the band gap for AGNRs. To this end, the band gap E_g was calculated for armchair nanoribbons of varying width N. For each ribbon, the band structure was computed via the tight-binding Hamiltonian in the NN regime, as described in section 3. The band gap was then determined as the energy difference between the lowest conducting band and highest valence band.

The resultant N-dependence of the band gap is shown in Figure 8. As ribbon width increases, the band gap exposits a monotonic decrease, arising from the reduction of quantum confinement as the system approaches the bulk graphene limit. The most significant band gaps are hence present for narrower ribbons, given the stronger confinement of electronic states in the transverse direction [5].



Figure 8. The band gap energies for a variety of armchair nanoribbons are displayed for linear (*top*) and logarithmic (*bottom*) scaling of the band gap. For the metallic $N = 3m + 2$ family, the band gap remains at 0 within the NN tight-binding model, while the semiconducting families $3p$ and $3p + 1$ show a monotonic decrease in band gap energy as ribbon width increases.

As mentioned in section 4.1, AGNRs are classified into 3 families according to their width N. Ribbons satisfying $N = 3m + 2$ possess small or vanishing band gaps due to their metallic nature, while the remaining families are semiconducting [2-4]. The results in Figure 8 reproduce this behaviour, demonstrating significant differences in electronic properties between these families given their geometric structure. These width-dependent band gaps are of particular interest in nanoelectronic applications, in which engineering band gap control becomes important [2].

4.4 Density of States of Armchair Ribbons

The DoS provides complementary information on the band structure, indicating the amount of electronic states at each energy. Using the eigenvalues obtained from tight-binding calculations, the DoS was computed following the procedure in Section 3.4.

Density of states for three armchair nanoribbons of different families is shown in Figure 9. A band gap for the two semiconducting families is visible around the Fermi energy, consistent with the semiconducting band structure discussed in Section 4.1. The van Hove singularities appear as sharp peaks in the spectrum, just as with the ZGNR in Figure 6.

In contrast to the armchair ribbon DoS, the ZGNR case discussed in Section 4.2 displays a sharp central peak in the DoS at the Fermi level. These, as mentioned, arise from the flat edge bands corresponding to edge-localised states.



Figure 9. Density of states for representatives of the three AGNR families. For the semiconducting families $N = 9, 10$ (*top*) in the figure, a clear band gap is present around the Fermi energy. For the metallic $N = 11$ armchair ribbon, this band gap is no longer empty, in accordance with its metallic nature.

5. Conclusions

In this work, electronic properties of graphene nanoribbons were reproduced computationally in the tight-binding approximation. For both armchair and zigzag nanoribbons, the momentum-dependent Hamiltonian was successfully constructed, with the resulting eigenproblem (6) being solved across the Brillouin zone.

The results of Section 4 demonstrate robustly the substantial dependence on the specific geometry when studying the electronic properties of graphene nanoribbons. The known width-dependence for the band gaps of AGNRs arising from quantum confinement [3-5] were successfully reproduced. The influence of a staggering potential on the band structure of AGNRs [4] was also successfully reproduced computationally by an extension to the NN tight-binding model. The near-flat bands of ZGNRs at the Fermi level associated with edge-localisation were reproduced. Such edge states were verified through calculations of the spatial probability density over the transverse direction, showing significant localisation at the ribbon boundaries.

The DoS reveals these features further, showcasing the van Hove singularities of the one-dimensional GNR systems, with a pronounced peak at the Fermi energy for zigzag ribbons. In summary, the computational approach successfully and robustly reproduces the key theoretical predictions for graphene nanoribbons, demonstrating the capability of numerical methods to explore electronic behaviour of nanoscale materials.

References:

[1] P. R. Wallace, The Band Theory of Graphite, Phys. Rev. 71 (1947) 622–634

[2] A. H. Castro Neto, F. Guinea, N. M. R. Peres, K. S. Novoselov and A. K. Geim, The Electronic Properties of Graphene, Rev. Mod. Phys. 81 (2009) 109–162

[3] K. Wakabayashi, K. I. Sasaki, T. Nakanishi and T. Enoki, Electronic States of Graphene Nanoribbons and Analytical Solutions, Sci. Technol. Adv. Mater. 11 (2010) 054504

[4] Y.-W. Son, M. L. Cohen and S. G. Louie, Energy Gaps in Graphene Nanoribbons, Phys. Rev. Lett. 97 (2006) 216803

[5] M. Ezawa, Peculiar Width Dependence of the Electronic Properties of Carbon Nanoribbons, Phys. Rev. B 73 (2006) 045432

[6] S. Datta, Electronic Transport in Mesoscopic Systems, Cambridge University Press (1995)

[7] K. S. Novoselov, A. K. Geim, S. V. Morozov, D. Jiang, Y. Zhang, S. V. Dubonos, I. V. Grigorieva and A. A. Firsov, Electric Field Effect in Atomically Thin Carbon Films, Science 306 (2004) 666–669

Appendix A: Nanoribbon lattice generation.

The lattice geometry necessary for this work is generated with the script `lattice_generator.py`. The program constructs atomic positions for the GNR unit cell, determines NN connections for downstream usage in building the tight-binding Hamiltonian, and exports the lattice data for use later.

A.1 Unit Cell Construction
Atomic positions for AGNRs and ZGNRs are generated by separate routines. Below is shown the case for zigzag geometry:

```
def build_zigzag(N: int, a: float):
        T = np.sqrt(3) * a
        positions, labels = [], []
        y = 0.0
        for n in range(N):
                if n % 2 == 0:
                        positions.append([0.0, y])
                        positions.append([T / 2.0, y + a / 2.0])
                else:
                        positions.append([T / 2.0, y])
                        positions.append([0.0, y + a / 2.0])

                labels += [0, 1]
                y += a / 2.0 + a

        positions = np.array(positions)
        labels = np.array(labels, dtype=int)

        a1 = np.array([T, 0.0])
        a2 = np.array([0.0, 0.0])

        return positions, labels, a1, a2
```

This routine generates the atomic coordinate for a ZGNR containing N zigzag chains. The translation vector of the unit cell is $T = \sqrt{3}a$ along the ribbon axis. Each unit cell contains $2N$ atoms belonging to the two sublattices. A similar procedure is employed for ZGNRs.

A.2 Nearest Neighbour Identification
Nearest neighbour pairs are found by comparing atomic separations with the bond length a. Interactions with atoms in neighbouring cells are also included per the NNN extension.

```
def find_neighbors(positions: np.ndarry, labels, a1: np.darray, a: float,
                        tol: float = 0.05):

    bond_len = a
    M = len(positions)
    neighbors = []

    for cell_image in [0, 1, -1]:
        shift = cell_image * a1

        for i in range(M):
            for j in range(M):

                if labels[i] == labels[j]:
                    continue
                if cell_image == 0 and i >= j:
                    continue

                disp = positions[j] + shift - positions[i]
                dist = np.linalg.norm(disp)
```

```
            if abs(dist - bond_len) < tol * bond_len:
                neighbors.append(dict(
                    i=i,
                    j=j,
                    cell=cell_image,
                    dx=float(disp[0]),
                    dy=float(disp[1]),
                ))
```

Appendix B: Hamiltonian Construction

The Bloch Hamiltonian used to compute band structures is implemented in `hamiltonian_k.py`. This script loads the generated lattice data and constructs the k-dependent tight-binding Hamiltonian. The Bloch Hamiltonian is built from summing NN hopping terms with a phase factor corresponding to the periodic boundary conditions of the GNRs.

```
def build_Hk(lattice, t, k, t2, delta):

    M = lattice["M"]
    T = lattice["T"]
    neighbors = lattice["neighbors"]

    H = np.zeros((M, M), dtype=np.complex128)

    for nb in neighbors:
        i, j, n = nb["i"], nb["j"], nb["cell"]
        phase = np.exp(1j * k * n * T)

        H[i, j] += -t * phase

        if n == 0:
            H[j, i] += -t * np.conj(phase)

    if delta != 0.0:
        labels = lattice["labels"]
        for i in range(M):
            H[i, i] += delta * (1 if labels[i] == 0 else -1)

    return H
```

The Hamiltonian includes the standard NN hopping parameter t, along with the optional extensions of NNN hopping from t' (t2 in the above) and a staggered on-site potential Δ that breaks the sublattice symmetry.

Eigenvalues $E_n(k)$ of $H(k)$ are obtained using `numpy.linalg.eigvalsh`, yielding the band structure of the nanoribbon.

Appendix C: Density of States

The DoS is computed from band energies via the script `dos.py`. The program reads band structure output from `bandstructure.py` and evaluates the DoS on a finite energy grid using Gaussian broadening.

The delta function in (7) is replaced by a Gaussian of width σ:

```
def dos_gaussian(bands, E_grid, sigma):

    Nk  = bands.shape[0]
    dos = np.zeros(len(E_grid))

    inv_s   = 1.0 / (sigma * np.sqrt(2*np.pi))
    inv_2s2 = 1.0 / (2*sigma**2)
```

```
    for ik in range(Nk):
        evals = bands[ik, :]
        dE = E_grid[:, np.newaxis] - evals[np.newaxis, :]
        dos += (inv_s * np.exp(-dE**2 * inv_2s2)).sum(axis=1)

    dos /= Nk
    return dos
```

Each eigenvalue $E_n(k)$ contributes a Gaussian peak centred at its energy value. The subsequent spectrum produces the smooth approximation of the DoS, while preserving the characteristic van Hove singularities present in the band structure.