

ALUNOVA ALUMINIUM COMPOSITE MATERIAL Built For America				TECHNICAL DATA SHEET	
				EBI/TDS/002 Rev 6 date:20.05.2024	
				ALLOY SERIES: 1) 1100 H16 /H18 2) 3105/3003 H16	
S.NO	PROPERTIES	STANDARD	UNIT/REF	2mm*	
General Properties					
1	Skin thickness	EN485-4	mm	0.18 mm	
2	Core material		-	Durable LDPE Mineral Core	
3	Standard Width		Inch	48" / 49"	
4	Standard length		Inch	78"/84"/90.5"/96"-Standards / Any length up to 197"	
5	Surface Finish		-	PVDF/HDPE/PE	
Mechanical Properties					
6	Peel Strength	ASTM D903	N/mm	>5	
7	Flexural Strength	ASTM C393	N/mm	≥100	
8	Impact Resistance	ASTM D5420	-	High	
9	Tensile Strength	ASTM E8	N/mm	≥130	
Environmental Resistance					
10	U V Resistance	ASTM G154	-	Excellent	
11	Temperature Resistance	ISO 4892-2	-	-50°C - + 80°C	
12	Humidity Resistance	ASTM D2247	-	Excellent	
13	Salt Spray Resistance	ASTM B117	-	Excellent	
Surface Finish Properties					
14	Gloss @ 60°C	ECCA T2	%	30-45/20-80	
15	Pencil Hardness	ECCA T4		Min HB	
Product Tolerances					
16	Width		mm	± 2	
17	Length		mm	±4	
18	Thickness		mm	±0.2	
19	Squareness		mm	Max 5	
20	Bow		%	±0.8	
	Alunova Middle East P.O. Box 30103, Ajman, UAE Tel: +971-6-7487677 Fax: +971-6-7425196 U.S.A : +1 (765) 491-2190 Georgia region : +1 912 381 0417				