The Microbial Challenge of a Plastic Planet: Decoding and Engineering the Biodegradation of Polyethylene

Abstract

Polyethylene (PE), the world's most produced polymer, represents an environmental paradox: its chemical inertness makes it an ideal material for countless applications but also a uniquely persistent pollutant. Microbial biodegradation offers a sustainable route for PE waste management, yet progress is hampered by the polymer's profound recalcitrance. This review critically examines the complex interplay between PE's physicochemical properties and the microbial mechanisms evolved or engineered to deconstruct it. We dissect the multi-stage biodegradation cascade, from essential abiotic priming to the enzymatic toolkit of oxidoreductases that initiate polymer chain cleavage, and the subsequent metabolic assimilation of degradation products. We survey the key microbial players—from single strains of *Rhodococcus* and *Bacillus* to synergistic consortia and novel insect gut microbiomes—and critically appraise the analytical methodologies used to evidence degradation, highlighting common pitfalls and the necessity of definitive techniques like isotopic labeling. Major knowledge gaps are identified, including the incomplete understanding of enzymatic pathways, the slow reaction kinetics, and the challenge of achieving complete mineralization. Finally, we provide a forward-looking perspective on how synthetic biology, enzyme engineering, and metagenomic discovery are poised to transform PE biodegradation from a slow, natural process into a viable, engineered solution for a circular bio-economy.

1. Introduction: The Polyethylene Paradox

The Global Scale of PE Production and Waste

Polyethylene (PE) stands as the most produced and consumed synthetic polymer globally, a cornerstone of modern industrial society. Its annual production exceeded 100 million metric tons in 2024, constituting more than one-third of the total global plastic demand.[1] The market, valued at over USD 120 billion in 2024, continues an aggressive growth trajectory, with projections indicating a compound annual growth rate (CAGR) of over 5% to surpass USD 165 billion by 2030.[1] This expansion is propelled by PE's unmatched versatility, durability, and cost-effectiveness, making it indispensable in sectors such as packaging—its largest consumer—as well as construction, automotive, and healthcare.[1] This immense production volume, now part of an overall annual plastic output exceeding 400 million tonnes, has inevitably led to a commensurate waste crisis of planetary scale.[4]

The management of this waste remains a critical global failure. An alarming small fraction of all plastic waste ever produced, estimated at a mere 9%, has been recycled.[5] The remainder, over 90%, is either incinerated, accumulates in landfills, or is mismanaged, ultimately leaking into natural ecosystems.[6] This results in an estimated 11 million tonnes of plastic entering the oceans each year, a figure that is forecasted to triple by 2060 if current production and waste management trends persist.[6] This disparity between production and effective end-of-life management underscores the inadequacy of current recycling infrastructures, particularly for post-consumer PE films and mixed plastic streams, thereby creating an urgent need for alternative solutions. The economic forces driving PE's market success, especially in rapidly developing regions like Asia-Pacific which accounts for over half the global market, are the very same forces compounding the environmental burden, creating a fundamental tension between economic growth and ecological sustainability.[2]

The Duality of PE: Indispensable Material vs. Persistent Pollutant

The core of the polyethylene paradox lies in its defining chemical characteristics. The properties that render PE an exemplary material for a vast array of applications are precisely those that make it an exceptionally persistent environmental pollutant.[9] Its structure consists of a long hydrocarbon backbone of repeating ethylene units, $(C_2H_4)_n$, held together by strong, non-polar carbon-carbon single bonds. This simple, robust structure imparts excellent chemical resistance, moisture barrier properties, and durability.[9] However, the absence of hydrolyzable functional groups, such as the ester bonds found in polyethylene terephthalate (PET), makes the PE backbone highly resistant to enzymatic attack by microorganisms.[13] This inherent recalcitrance means that PE persists in the environment for time scales estimated to be in the hundreds or even thousands of years.[15] Over time, it does not mineralize but instead fragments through abiotic processes into progressively smaller particles—microplastics and

nanoplastics—which are now ubiquitous contaminants in soil, water, air, and have infiltrated the global food web, with unknown but concerning consequences for ecosystem and human health.[7]

Microbial Biodegradation as a Solution

In response to this escalating crisis, microbial biodegradation has emerged as a compelling and potentially sustainable strategy for managing PE waste.[18] Unlike energy-intensive conventional disposal methods such as landfilling, which merely contains the problem, or incineration, which can release greenhouse gases and toxic byproducts like polycyclic aromatic hydrocarbons and dioxins, biodegradation offers the prospect of a low-energy, environmentally benign process.[20] The central premise is that microbial communities can utilize the carbon skeleton of the PE polymer as a substrate for metabolism, ultimately mineralizing it into carbon dioxide (CO_2), water, and new biomass.[18] This would effectively close the loop, returning the carbon sequestered in the plastic to the biological carbon cycle. However, transforming this potential into a practical, scalable technology is a formidable scientific and engineering challenge. It requires a profound understanding of the physicochemical barriers that make PE so resilient and the discovery, characterization, and engineering of biological systems—both enzymes and whole organisms—capable of systematically dismantling this synthetic fortress.[10] This review will critically assess the current state of this endeavor, from fundamental mechanisms to future biotechnological prospects.

2. The Fortress of Recalcitrance: Physicochemical Barriers to PE Degradation

The extraordinary persistence of polyethylene in the environment is not accidental but is a direct consequence of its fundamental physicochemical properties. Overcoming these barriers is the central challenge in developing effective biodegradation strategies.

The Inert C-C Backbone

The primary molecular feature conferring recalcitrance upon PE is its backbone, composed

exclusively of repeating ethylene units ($(-CH_2-CH_2-)_n$) linked by strong, non-polar carbon-carbon single bonds.[9] Unlike natural polymers such as cellulose or even synthetic polyesters like PET, which contain heteroatoms (e.g., oxygen) that create polar, hydrolytically susceptible ester or glycosidic linkages, the PE backbone is a uniform hydrocarbon chain. This structure lacks a "handle" for the hydrolytic enzymes that are common in microbial degradative pathways.[14] Consequently, the degradation of PE cannot proceed via simple hydrolysis. Instead, it must be initiated by an oxidative attack that cleaves either a C-H or a C-C bond. This initial oxidation is an energetically demanding, high-activation-energy step, representing the principal rate-limiting barrier to the entire biodegradation process.[25]

The Role of Molecular Weight and Branching

Polyethylene is not a single, uniform substance but a family of semi-crystalline polymers whose physical properties, and thus their susceptibility to degradation, are profoundly influenced by their molecular weight and degree of chain branching.[28] High molecular weights, often in the range of tens to hundreds of thousands of grams per mole, render the polymer chains far too large for direct uptake and intracellular metabolism by microorganisms, mandating an extracellular enzymatic strategy.[28] The degree of branching further dictates how these long chains can pack together, defining the polymer's crystallinity and density (Table 1).

Table 1: Physicochemical Properties of Common Polyethylene Types and Their Implications for Biodegradation

Polymer Type	Typical Density (g/cm3)	Degree of Branching	Degree of Crystallinity (%)	Melting Point (°C)	Implications for Biodegradation
HDPE	0.941–0.965	Minimal (linear chains)	High (>90%)	120–130	Highly resistant. Tightly packed crystalline regions are sterically inaccessibl

					e to enzymes. Requires significant abiotic pre-treatment.
LDPE	0.910–0.940	High (long and short chains)	Low (50–60%)	105–115	More susceptible than HDPE. Larger amorphous regions provide greater access for enzymatic attack.
LLDPE	0.915–0.925	Moderate (short chains)	Intermediate	120–125	Susceptibility is intermediate between LDPE and HDPE. Linear backbone but short branches disrupt crystalline packing.
Data synthesized from.[12]					

High-density polyethylene (HDPE) consists of linear chains that pack efficiently, resulting in a highly ordered, crystalline structure that is rigid and dense. In contrast, the extensive branching in low-density polyethylene (LDPE) disrupts this packing, creating a more disordered, amorphous structure that is flexible and less dense.[12] This structural difference is

a critical determinant of biodegradability.

Crystallinity and Hydrophobicity

The semi-crystalline nature and hydrophobicity of PE present formidable physical barriers to microbial attack.

- **Crystallinity:** Microbial enzymes are large, complex biomolecules that require physical access to the polymer chains to function. The tightly packed, ordered lamellae of the crystalline regions are sterically hindered and largely inaccessible to these enzymes.[30] Degradation is therefore believed to occur preferentially, if not exclusively, within the more disordered, flexible, and accessible amorphous regions.[15] This explains the general observation that LDPE, with its lower crystallinity, is more amenable to biodegradation than HDPE.[15] This also implies a potential negative feedback mechanism: as microbes consume the accessible amorphous material, the remaining polymer becomes progressively more crystalline and, therefore, more resistant to further degradation.
- **Hydrophobicity:** The non-polar hydrocarbon nature of PE makes its surface intensely hydrophobic. This property repels the aqueous medium in which microbial life and its water-soluble extracellular enzymes operate.[13] This presents a major challenge for the first crucial step of biodegradation: microbial colonization. Successful degradation requires microorganisms to overcome this hydrophobic barrier to adhere to the surface and establish a biofilm, a process that is significantly hindered.[32]

Impact of Polymer Additives

Commercial PE products are complex formulations, not pure polymers. They contain a suite of chemical additives designed to improve processability, performance, and lifespan, which can have confounding effects on biodegradation.[34]

- **Inhibitory Additives:** Antioxidants and UV stabilizers are ubiquitous in commercial PE. Their express purpose is to prevent oxidative degradation by quenching the very free-radical chain reactions that are essential for both abiotic weathering and the initial enzymatic attack by oxidoreductases.[13] Thus, the chemical makeup of most real-world PE waste is intentionally designed to resist the primary mechanism of biodegradation.
- **Pro-degradant Additives:** In response to environmental concerns, so-called "oxo-degradable" plastics have been developed, which incorporate pro-oxidant additives (e.g., salts of iron, manganese, or cobalt).[35] These additives are designed to accelerate

abiotic photo- and thermo-oxidation, promoting chain scission and fragmentation of the polymer into smaller pieces that are theoretically more bioavailable.[35] However, the efficacy and environmental benefit of this approach are highly controversial. There is significant concern that these additives may only hasten the fragmentation of macroplastics into microplastics without ensuring complete microbial mineralization, potentially exacerbating the problem of microplastic pollution.[38] Indeed, some comprehensive studies have found no evidence that these additives significantly enhance the ultimate biodegradation (i.e., mineralization) of PE in various environments.[39] This controversy highlights a critical need for rigorous, standardized testing that distinguishes between mere fragmentation and true biodegradation.

3. The Biodegradation Cascade: A Stepwise Deconstruction

The microbial degradation of polyethylene is not a single event but a complex, multi-stage process that can be conceptualized as a cascade (Figure 1). Each stage presents its own set of challenges and requires specific biological or environmental facilitators. True biodegradation is only achieved when the polymer is fully mineralized, meaning its carbon is converted into inorganic forms like CO_2.[34]

!(https://i.imgur.com/example-figure-1.png "Figure 1: The Four Stages of Polyethylene Biodegradation")

Priming the Attack: The Essential Role of Abiotic Factors

For pristine, unweathered PE, the rate of microbial degradation is often immeasurably slow.[10] A critical prerequisite for effective biodegradation is an initial abiotic priming or "weathering" phase, which modifies the polymer's surface to make it more amenable to microbial attack. This can be achieved through several mechanisms:

- **Photo-oxidation:** Exposure to ultraviolet (UV) radiation, primarily from sunlight, is a key initiator of PE degradation. The energy from UV photons can generate free radicals on the polymer backbone, triggering a cascade of auto-oxidative reactions in the presence of oxygen. This process leads to two crucial changes: (i) chain scission, which reduces the polymer's molecular weight, and (ii) the introduction of oxygen-containing functional groups, such as carbonyl ($>C=O$), carboxyl ($-COOH$), and hydroxyl ($-OH$)

moieties, onto the polymer surface.[40] These new polar groups decrease the surface hydrophobicity, facilitating microbial attachment, and provide potential sites for enzymatic attack.[15]

- **Thermo-oxidation:** Elevated temperatures can also induce thermal degradation through similar free-radical mechanisms, breaking down the polymer chains and promoting oxidation.[40]
- **Synergistic Pre-treatments:** In both natural environments and laboratory settings, the combination of multiple abiotic factors acts synergistically. Many experimental protocols explicitly use pre-treatments—such as UV irradiation, heat, or chemical oxidation with agents like nitric acid or potassium permanganate—to accelerate the initial degradation phase and enhance the susceptibility of PE to subsequent microbial action.[13]

Phase 1: Biodeterioration (Colonization and Biofilm Formation)

This is the first truly biological stage, where microorganisms physically interact with the plastic surface. Overcoming PE's hydrophobicity is the initial challenge. Microorganisms with inherently hydrophobic cell surfaces (e.g., *Rhodococcus*) or those that can secrete biosurfactants to reduce surface tension are better equipped to adhere.[32] Once attached, successful colonizers proliferate and secrete a matrix of extracellular polymeric substances (EPS)—a mixture of polysaccharides, proteins, and DNA—to form a biofilm.[18]

This biofilm is more than just a layer of cells; it is a structured community that creates a unique microenvironment at the polymer-water interface. Within the biofilm, extracellular enzymes can be concentrated to high levels, water can be retained, and the products of degradation can be captured for efficient uptake by the cells. This microbial habitat that forms on plastic surfaces in the environment has been termed the "Plastisphere," a novel ecological niche with distinct community structures.[37]

Phase 2: Biofragmentation (Enzymatic Depolymerization)

This stage involves the core biochemical reactions where the large, insoluble polymer chains are cleaved into smaller, soluble fragments. Given the inert nature of PE's C-C backbone, this process is initiated by powerful extracellular oxidoreductases (Table 3). The enzymatic strategy for PE degradation appears to be an exaptation of machinery evolved for breaking down other recalcitrant natural polymers, most notably lignin.[48]

Table 3: Major Enzyme Classes Involved in the Initial Oxidation of Polyethylene

Enzyme Class	EC Number	Catalytic Action	Cofactors/Requirements	Microbial Source Examples
Laccases	1.10.3.2	One-electron oxidation of phenolic and non-phenolic substrates, generating radicals that can attack the polymer backbone.	O_2, Copper ions	*Rhodococcus ruber*, *Trametes versicolor*, *Aspergillus* spp.
Peroxidases	1.11.1.x	Oxidation of substrates using hydrogen peroxide (H_2O_2) as an oxidant.	H_2O_2, Heme	*Phanerochaete chrysosporium* (LiP, MnP), various fungi and bacteria.
Alkane Monooxygenases	1.14.15.3 (AlkB-type)	Introduction of a hydroxyl group onto an alkane chain, converting an inert hydrocarbon into an alcohol.	O_2, Rubredoxin, NAD(P)H	*Pseudomonas* spp., *Rhodococcus* spp., *Acinetobacter* spp.
Data synthesized from.[48]				

The action of these enzymes introduces oxygen into the hydrocarbon chain, breaking its chemical inertness. This initial oxidation is the crucial, rate-limiting step that triggers depolymerization, resulting in a complex mixture of shorter-chain alkanes, alcohols, ketones,

and carboxylic acids.[40]

Phases 3 & 4: Assimilation and Mineralization

The smaller, more soluble molecules produced during biofragmentation are then small enough to be transported across the cell membrane into the microbial cytoplasm.

- **Assimilation:** Once inside the cell, these fragments are channeled into central metabolic pathways. Long-chain alkanes and fatty acids are typically catabolized via the **β-oxidation pathway**. This iterative process shortens the carbon chain by two carbons at a time, generating acetyl-CoA.[46]
- **Mineralization:** The acetyl-CoA produced from β-oxidation enters the **tricarboxylic acid (TCA) cycle**, where it is completely oxidized to generate cellular energy (in the form of ATP) and reducing power (NADH, $FADH_2$). The final products of this complete aerobic respiration are CO_2, water, and new microbial biomass.[55] The release of CO_2 derived from the polymer's carbon atoms is the definitive hallmark of mineralization, signifying that the plastic has been fully integrated into the biological carbon cycle and removed from the environment as a pollutant.[21] This entire cascade illustrates that PE biodegradation is a complex relay race, likely requiring a diverse team of enzymes and organisms to carry out the distinct steps from surface attack to final mineralization.

4. The Microbial Vanguard: Key Players and Communities

The search for organisms capable of degrading polyethylene has spanned diverse ecosystems, from industrial waste sites to pristine natural environments. This bioprospecting has revealed a wide array of bacteria and fungi with at least some capacity to attack PE, as well as complex symbiotic systems in insect guts that exhibit remarkable efficiency.

A Catalogue of Cultured Degraders

While hundreds of species have been anecdotally associated with plastic degradation, several

genera consistently emerge in laboratory studies as key players.

- **Bacteria:**
  - ***Rhodococcus* species:** This genus is arguably the most promising group of bacterial PE degraders identified to date. Strains like *Rhodococcus ruber* C208 exhibit a highly hydrophobic cell surface, which promotes strong adhesion to the PE surface and facilitates the formation of dense, robust biofilms—a critical first step in degradation.[45] Genomic and proteomic analyses have confirmed that *Rhodococcus* species possess a formidable arsenal of relevant oxidative enzymes, including laccases, alkane monooxygenases (AlkB), and cytochrome P450 hydroxylases, which are upregulated during growth on PE.[52] Studies have demonstrated measurable weight loss and surface deterioration of PE films incubated with *Rhodococcus* strains, solidifying their status as model organisms for PE biodegradation research.[33]
  - ***Bacillus* species:** Members of the genus *Bacillus*, such as *B. subtilis*, *B. cereus*, and *B. siamensis*, are frequently isolated from plastic-polluted soils and landfills.[21] Their ability to form resilient endospores allows them to survive harsh conditions, and they are known to secrete a wide variety of extracellular enzymes. Numerous studies have reported significant weight loss of PE films (ranging from a few percent to over 20% in some cases) after incubation with *Bacillus* strains, accompanied by clear evidence of surface erosion and chemical modification.[61]
  - ***Pseudomonas* species:** This metabolically versatile genus, including species like *P. aeruginosa* and *P. putida*, is well-known for its ability to degrade a wide range of organic pollutants, including hydrocarbons. They have been shown to form biofilms on PE surfaces and induce chemical changes, although reported degradation rates are often lower than those for *Rhodococcus* or *Bacillus*.[61]
- **Fungi:** Filamentous fungi are particularly well-adapted for degrading solid, insoluble substrates. Their exploratory hyphal growth allows them to physically penetrate the polymer matrix, while they secrete powerful cocktails of extracellular enzymes, often the same ones used to decompose recalcitrant plant matter like lignin and cellulose.[18]
  - ***Aspergillus* and *Penicillium* species:** Fungi from these two genera, such as *A. niger*, *A. flavus*, and *P. simplicissimum*, are among the most commonly reported PE degraders.[67] They have been isolated from various environments, including marine water and landfill soil, and have demonstrated the ability to use PE as a sole carbon source, leading to significant weight loss and surface fragmentation in laboratory assays.

Table 2: Key Microbial Genera Implicated in Polyethylene Biodegradation

Microbial Group	Genus	Notable Species	Typical Isolation Source	Key Reported Enzymes/Mechanisms

Bacteria	*Rhodococcus*	*R. ruber*, *R. erythropolis*	Soil, Plastic waste	Laccases, Alkane monooxygenases, Biofilm formation
	Bacillus	*B. subtilis*, *B. cereus*, *B. siamensis*	Landfill soil, Mangrove soil, Compost	Hydrolases, Oxidoreductases, Spore formation
	Pseudomonas	*P. aeruginosa*, *P. putida*	Contaminated soil, Water	Alkane monooxygenases, Lipases, Biofilm formation
	Acinetobacter	*A. baumannii*	Insect gut, Soil	Multicopper oxidases
Fungi	*Aspergillus*	*A. niger*, *A. flavus*	Landfill soil, Marine water	Laccases, Peroxidases, Hydrolases
	Penicillium	*P. simplicissimum*	Mangrove soil, Marine water	Oxidoreductases
	Fusarium	*F. oxysporum*	Landfill soil	Hydrolases
Data compiled from.[13]				

Novel Ecosystems: The Insect Gut Microbiome

One of the most significant recent breakthroughs in the field has been the discovery of "plastivorous" insect larvae that can consume and rapidly metabolize PE. Larvae of the greater wax moth (*Galleria mellonella*) and various mealworms (*Tenebrio molitor*, *Zophobas atratus*) have been observed to chew through and ingest PE films, mineralizing a substantial

fraction to CO_2 at rates far exceeding those seen in microbial monocultures.[73]

This high efficiency is not solely a property of the insect or its microbes but appears to be a powerful synergy between them. The insect acts as a mechanical and chemical "pre-treatment bioreactor": its mandibles physically shred the plastic, vastly increasing its surface area, while the chemical environment of its gut may further prime the polymer for microbial attack.[73] The gut microbiome, enriched with bacteria such as *Acinetobacter*, *Bacillus*, and *Enterococcus*, then carries out the biochemical heavy lifting.[72] This discovery has opened up a new and exciting avenue for bioprospecting, as the insect gut represents a highly selective environment for enriching potent plastic-degrading microorganisms and enzymes.[46]

Strength in Numbers: Synergistic Microbial Consortia

In nature, microorganisms rarely exist as pure cultures. They form complex, interacting communities, and this community-level action is proving to be far more effective for degrading complex substrates like PE than the efforts of any single strain.[77] While a single microbe may possess only a partial enzymatic toolkit, a consortium can bring together a diverse array of capabilities that work in synergy.[47]

This synergy manifests in several ways:

- **Division of Labor:** Different species can specialize in different stages of the degradation cascade. For instance, one species may excel at initial surface colonization and oxidation, producing intermediates that are then consumed by other community members.[77] This prevents the accumulation of potentially inhibitory byproducts and creates a more efficient metabolic pipeline.[81]
- **Enhanced Biofilm Formation:** In some consortia, certain species may not directly degrade the plastic but instead contribute to the production of EPS, creating a more robust biofilm structure that benefits the primary degraders.[82]
- **Increased Resilience:** Diverse communities are generally more stable and resilient to environmental perturbations than monocultures, making them better suited for real-world applications.[84]

Recognizing this, research is shifting from isolating single "super-bugs" to understanding and engineering microbial consortia. This involves both "top-down" approaches (studying and optimizing naturally occurring communities from the Plastisphere) and "bottom-up" approaches (rationally constructing synthetic microbial consortia with defined species and functions) to create a microbial "dream team" for PE degradation.[49]

5. A Critical Lens on Methodology: Proving Biodegradation

A significant challenge impeding progress in the field of PE biodegradation is the lack of standardized methodologies and the frequent misinterpretation of analytical data. Many published studies provide evidence that is merely consistent with biodegradation but fall short of providing definitive proof, leading to a literature landscape that is difficult to navigate and compare.[10] A clear hierarchy of evidence is needed to critically evaluate claims of degradation.

Indirect and Qualitative Methods (Circumstantial Evidence)

These methods are often the first line of investigation but are highly susceptible to artifacts and should be interpreted with caution.

- **Weight Loss:** While intuitive and widely used, gravimetric analysis is perhaps the most misleading metric when used in isolation. Apparent weight loss can result from the leaching of soluble additives, plasticizers, or residual monomers from the polymer matrix, or from the physical abrasion and loss of small, non-degraded fragments, rather than true microbial consumption of the polymer backbone.[10] Without corroborating data, it provides no information on the ultimate fate of the polymer's carbon.
- **Microscopy (SEM/AFM):** Scanning Electron Microscopy (SEM) and Atomic Force Microscopy (AFM) are invaluable for visualizing changes in the surface topography of the plastic. The appearance of pits, cracks, cavities, and general surface erosion, along with visible microbial colonization and biofilm formation, provides strong evidence of biodeterioration.[13] However, these observations are qualitative. They do not quantify the extent of degradation, nor can they definitively distinguish between biotic effects and abiotic weathering, which can produce similar morphological changes. Furthermore, they are surface-limited techniques and provide no information about changes in the bulk polymer.[89]
- **Spectroscopy (FTIR/XPS):** Fourier-Transform Infrared (FTIR) spectroscopy is a powerful and sensitive technique for detecting changes in the chemical bonding within the polymer. The appearance of new absorption bands in the carbonyl ($~1715 cm^{-1}$) and hydroxyl ($~3300 cm^{-1}$) regions is often cited as key evidence of polymer oxidation.[10] X-ray Photoelectron Spectroscopy (XPS) provides similar, but more surface-sensitive,

information about elemental composition and chemical states.[91] The critical, and frequently overlooked, pitfall of these techniques is **biomass contamination**. Residual microbial biofilm, which is composed of proteins (amide bonds), lipids (ester bonds), and polysaccharides (hydroxyl and ether bonds), has strong spectral signatures that overlap directly with the signals expected from polymer oxidation. Inadequately cleaned samples can therefore lead to false-positive results, where the spectrum of the biofilm is mistaken for the spectrum of the degraded polymer.[92]

Quantitative and Confirmatory Methods (Strong Evidence)

These techniques provide quantitative data on changes to the polymer or its breakdown products.

- **Gel Permeation Chromatography (GPC):** GPC (also known as Size Exclusion Chromatography, SEC) is the standard method for measuring the molecular weight distribution of a polymer. A decrease in the average molecular weight (M_w and M_n) provides clear evidence of polymer chain scission (biofragmentation), a key step in degradation.[55]
- **Chromatography-Mass Spectrometry (GC-MS/LC-MS):** These hyphenated techniques are used to identify and quantify the low-molecular-weight products of degradation that are released into the culture medium. Detecting a series of oligomers, alkanes, fatty acids, or other intermediates can help elucidate the degradation pathway.[55] However, this method is also subject to a critical artifact: the potential presence of low-molecular-weight additives or manufacturing residues (e.g., oligomers, alkanes) in the starting plastic material. A recent study demonstrated that a common commercial PE powder contained significant amounts of alkanes and ketones, which, if detected after incubation, could be erroneously attributed to biodegradation.[94]

Definitive Methods (The Gold Standard)

Only methods that directly track the fate of the polymer's carbon atoms can provide unambiguous proof of biodegradation.

- **Respirometry:** This method quantifies mineralization by measuring the cumulative production of gaseous end-products over time. In aerobic systems, this involves trapping and measuring the evolved CO_2; in anaerobic systems, both CO_2 and methane (CH_4) are measured.[34] This directly assesses the conversion of organic carbon to

inorganic carbon. Its main limitation is ambiguity if other organic carbon sources (e.g., from the culture medium, or from dead microbial biomass) are present and being mineralized simultaneously.[58]

- **Stable Isotope Tracing:** This is the most rigorous and definitive method for proving and quantifying biodegradation.[13] The experiment is conducted using PE synthesized from a ^{13}C-labeled precursor (e.g., ^{13}C-ethylene). By tracing the heavy carbon isotope, the fate of the polymer can be followed with absolute certainty.
    - **Proof of Mineralization:** Detection of ^{13}C-labeled CO_2 ($^{13}CO_2$) via Isotope Ratio Mass Spectrometry (IRMS) provides incontrovertible proof that the carbon in the evolved gas originated from the PE polymer.[58]
    - Proof of Assimilation: By extracting and analyzing microbial biomass components (e.g., phospholipid fatty acids, PLFAs; or DNA) for ^{13}C enrichment, it is possible to prove that carbon from the PE was incorporated into the cells of the degrading microorganisms.95

      This approach elegantly bypasses all the artifacts associated with other methods, such as biomass contamination or degradation of trace nutrients, and represents the gold standard for biodegradation research.

Table 4: A Comparative Analysis of Analytical Techniques for Measuring PE Biodegradation

Technique	Information Provided	Advantages	Critical Limitations & Potential Artifacts	Level of Evidence
Weight Loss	Net change in mass of the polymer sample.	Simple, inexpensive, widely used.	Non-specific. Can be caused by leaching of additives or physical fragmentation, not just mineralization.	Circumstantial
SEM / AFM	Surface morphology (cracks, pits, erosion), biofilm	High-resolution imaging of surface biodeterioration.	Qualitative, surface-only. Cannot distinguish from abiotic	Circumstantial

	visualization.		weathering. Provides no chemical information.	
FTIR / XPS	Changes in chemical functional groups (e.g., formation of C=O, -OH).	Sensitive to chemical changes indicating oxidation.	Highly prone to false positives from residual biofilm contamination, which has similar spectral signatures.	Circumstantial
GPC / SEC	Changes in molecular weight distribution.	Quantitative measure of polymer chain scission (biofragmentation).	Does not confirm mineralization. Can be complex for cross-linked polymers.	Confirmatory
GC-MS / LC-MS	Identification of low-molecular-weight degradation products.	Provides insight into metabolic intermediates and pathways.	Can be confounded by pre-existing oligomers or additives in the virgin plastic.	Confirmatory
Respirometry	Measurement of CO_2 (aerobic) or CH_4 (anaerobic) evolution.	Direct quantification of mineralization.	Can be ambiguous if other carbon sources are present in the system, leading to overestimation.	Definitive (with proper controls)
^{13}C Isotopic	Unambiguous tracking of	The "gold standard."	Complex, requires	Definitive

Tracing	polymer carbon into CO_2 and biomass.	Eliminates all ambiguity and artifacts. Provides definitive proof of both mineralization and assimilation.	custom synthesis of ^{13}C-labeled polymer, expensive analytical equipment (IRMS).	
A critical synthesis based on.[10]				

6. Grand Challenges and Uncharted Territory

Despite decades of research, the field of polyethylene biodegradation is still in its infancy, facing several fundamental challenges that limit its practical application. Progress is constrained by knowledge gaps in core biochemistry, process kinetics, and methodological standards.

The Rate-Limiting Step Controversy

While it is widely accepted that the initial oxidation of the inert hydrocarbon backbone is the primary bottleneck for PE degradation, the precise enzymatic reaction that constitutes this rate-limiting step remains poorly understood and debated.[27] Is it the initial hydroxylation of a C-H bond, likely catalyzed by a monooxygenase like AlkB or a cytochrome P450? Or is it the direct cleavage of a C-C bond, perhaps mediated by the powerful, non-specific radicals generated by ligninolytic enzymes like laccases and peroxidases? The biochemical evidence for either pathway as the definitive initiating event is incomplete. This lack of clarity is a major obstacle, as identifying this crucial first step is essential for rationally designing or engineering more efficient enzymes. The search for a single "PEase" analogous to the well-characterized PETase for polyester degradation may be misguided; it is more likely that a multi-enzyme pathway is required, where the initial oxidative "key" has yet to be definitively identified and characterized.[26]

The Elusive Goal of Complete Mineralization

A consistent theme across the literature is the report of only partial degradation. Most laboratory studies, even those running for several weeks or months, report PE weight loss in the single-digit or low double-digit percentage range.[10] Achieving high levels of conversion, let alone complete mineralization, remains an elusive goal. Several factors likely contribute to this challenge. As discussed, the preferential degradation of amorphous regions may leave behind a more crystalline, and thus more recalcitrant, polymer residue. Another possibility is the accumulation of metabolic intermediates that are either toxic to the microorganisms or are themselves recalcitrant to further breakdown, causing the process to stall.[27] Furthermore, the long-term stability and activity of the requisite extracellular enzymes in the culture environment are often unknown. Understanding and overcoming these barriers to complete conversion is a grand challenge for the field.[49]

The Lab-to-Field Gap

There is a vast chasm between the optimized, controlled conditions of a laboratory flask and the complex, fluctuating environments of a landfill, soil, or the ocean.[101] Laboratory studies typically employ pre-treated plastics, pure or defined microbial cultures, and nutrient-rich media at a constant, optimal temperature and pH. In contrast, real-world environments are characterized by variable temperatures, nutrient limitations, competition from a complex native microbiome, and the presence of a heterogeneous mix of plastic types and contaminants.[38] A microbial strain or consortium that performs well under ideal lab conditions may fail completely in the field. Bridging this lab-to-field gap will require a shift towards testing in more realistic microcosm or mesocosm systems and developing microbial solutions that are not only effective but also robust and competitive in complex environments.

Lack of Standardized Protocols

As detailed in the previous section, the field is hampered by a fundamental lack of standardization. The use of widely varying types of PE (films, powders, pellets; different densities; with and without undefined additives), different and often inadequate analytical methods, and inconsistent reporting metrics makes it nearly impossible to compare results

across different studies meaningfully.[23] What one paper reports as a 5% degradation based on weight loss could be an artifact of additive leaching, while another paper's 1% mineralization measured by isotopic tracing represents a more significant, albeit smaller, true result. This absence of a common framework—including standard reference materials, a consensus on the "gold standard" of proof (i.e., mineralization), and clear reporting guidelines—severely impedes cumulative scientific progress and fosters an environment where claims can be difficult to validate.[99]

7. Outlook and Perspectives: Engineering a Biological Solution

The challenges facing polyethylene biodegradation are formidable, but the convergence of powerful new technologies in biology and engineering offers a clear path forward. The future of the field lies in moving beyond the passive observation of natural degradation processes and toward the active design and engineering of robust biological systems for plastic waste management. This transition will transform PE biodegradation from a scientific curiosity into a viable industrial process.

Discovery Engine: Mining the Global Metagenome

The vast majority of microbial life on Earth cannot be cultured using standard laboratory techniques, meaning that traditional bioprospecting has only accessed a tiny fraction of the planet's genetic and enzymatic diversity. Metagenomics—the direct sequencing of DNA from environmental samples—provides a culture-independent window into this "microbial dark matter".[104] Environments where plastics accumulate, such as landfills, marine plastispheres, and the guts of plastivorous insects, represent evolutionary hotspots where microbes are under selective pressure to metabolize synthetic polymers. By applying shotgun metagenomic sequencing to these samples, researchers can identify novel genes and reconstruct entire metabolic pathways for plastic degradation.[106] Combined with advanced bioinformatic tools, such as hidden Markov models trained on the sequences of known plastic-degrading enzymes and machine learning algorithms, this approach can rapidly sift through terabases of sequence data to pinpoint high-potential candidate enzymes ("plastizymes") for experimental validation.[104]

Designer Microbes and Enzymes: The Synthetic Biology Revolution

Once novel enzymes and pathways are discovered, the tools of synthetic biology can be used to optimize them for industrial application.

- **Rational Protein Engineering:** The performance of a natural enzyme is rarely optimal for an industrial process. Using techniques like site-directed mutagenesis and computational protein design, enzymes can be re-engineered for higher catalytic activity, improved thermal stability to allow for reactions at elevated temperatures (which increases polymer chain mobility), and broadened substrate specificity. The remarkable success in engineering PET-degrading enzymes, such as the development of the highly efficient FAST-PETase and HotPETase variants, provides a clear blueprint for what is possible for PE-degrading oxidoreductases.[111]
- **Metabolic Engineering and Synthetic Consortia:** Rather than relying on a single organism, entire multi-step degradation pathways can be rationally designed and constructed. This can involve engineering a single robust microbial chassis, such as *E. coli* or *Pseudomonas putida*, to express all the necessary enzymes for the complete conversion of PE fragments to a desired product.[113] Alternatively, synthetic microbial consortia (SynComs) can be built, where the complex metabolic task is divided among several specialist strains that are engineered to work together synergistically. This modular approach allows for greater control and optimization of the overall process.
- **Directed Evolution:** For enzymes or pathways where the mechanism is poorly understood, directed evolution offers a powerful, data-driven optimization strategy. By creating large libraries of enzyme variants and subjecting them to high-throughput screening under selective pressure, it is possible to rapidly evolve proteins with dramatically improved properties without a priori knowledge of their structure-function relationships.[83]

Process Engineering: From the Flask to the Bioreactor

For biodegradation to be a scalable solution, it must move out of the laboratory flask and into industrial-scale bioreactors. This presents significant process engineering challenges.[117] A successful PE bioreactor will likely be a multi-stage system that integrates:

1. **Mechanical and Physicochemical Pre-treatment:** To maximize surface area and bioavailability, the plastic waste will first need to be shredded or milled into a fine powder. This may be combined with a rapid thermal or UV treatment to initiate surface

oxidation.[85]

2. **Controlled Biological Reaction:** The pre-treated plastic would then be fed into a bioreactor—likely a stirred-tank or fluidized-bed reactor for submerged liquid fermentation—containing the engineered microbial consortium. Critical parameters such as temperature, pH, aeration, and nutrient levels would be tightly controlled to ensure maximal and sustained microbial activity.[101]

The Circular Bio-Economy: Beyond Degradation to Upcycling

The most transformative vision for the future of PE biodegradation is not merely its disposal but its valorization. Instead of complete mineralization to low-value CO_2, engineered metabolic pathways could be designed to convert the breakdown products of PE into high-value chemicals. This concept, known as "upcycling," would reframe plastic waste as a valuable carbon feedstock for a new circular bio-economy.[100] For example, the acetyl-CoA generated from PE degradation could be channeled into biosynthetic pathways to produce biodegradable polymers like polyhydroxyalkanoates (PHAs), specialty lipids, or platform chemicals.[20] Achieving this would create a powerful economic incentive for plastic waste collection and recycling, providing a market-driven solution to pollution that is far more sustainable than disposal. This represents the ultimate goal: a hybrid technological and biological system that closes the loop on the polyethylene life cycle.

References

- [1] Virtue Market Research. (n.d.). *Polyethylene Market*. Retrieved from https://virtuemarketresearch.com/report/polyethylene-market
- [2] Precedence Research. (n.d.). *Polyethylene Market*. Retrieved from https://www.precedenceresearch.com/polyethylene-market
- [3] Future Market Insights. (n.d.). *Polyethylene Market*. Retrieved from https://www.futuremarketinsights.com/reports/polyethylene-market
- [4] Plastics Europe. (2024). *Plastics – the fast Facts 2024*. Retrieved from https://plasticseurope.org/wp-content/uploads/2024/11/PE_TheFacts_24_digital-1pager.pdf
- [125] Argus Media. (2025). *Polyethylene model update: Key insights on 2024 PE market trends*. Retrieved from https://www.argusmedia.com/en/news-and-insights/market-opinion-and-analysis-blog/polyethylene-model-update-2024-takeaways

- [126] Plastics Europe. (n.d.). *Plastics – the fast Facts 2024*. Retrieved from https://plasticseurope.org/knowledge-hub/plastics-the-fast-facts-2024/
- [127] U.S. Environmental Protection Agency. (n.d.). *Plastics: Material-Specific Data*. Retrieved from https://www.epa.gov/facts-and-figures-about-materials-waste-and-recycling/plastics-material-specific-data
- [6] Wastedirect. (n.d.). *Plastic Waste Statistics*. Retrieved from https://wastedirect.co.uk/blog/plastic-waste-statistics/
- [7] European Environment Agency. (n.d.). *Plastics*. Retrieved from https://www.eea.europa.eu/en/topics/in-depth/plastics
- [8] United Nations Environment Programme. (n.d.). *Plastic pollution*. Retrieved from https://www.unep.org/topics/chemicals-and-pollution-action/plastic-pollution
- [128] Greenmatch. (n.d.). *10 Countries Producing Most Plastic Waste*. Retrieved from https://www.greenmatch.co.uk/blog/10-countries-producing-most-plastic-waste
- [5] Our World in Data. (n.d.). *Plastic Pollution*. Retrieved from https://ourworldindata.org/plastic-pollution
- [9] Wikipedia. (n.d.). *Polyethylene*. Retrieved from https://en.wikipedia.org/wiki/Polyethylene
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [24] Britannica. (n.d.). *polyethylene*. Retrieved from https://www.britannica.com/science/polyethylene
- [12] SpecialChem. (n.d.). *Polyethylene (PE) Plastic*. Retrieved from https://www.specialchem.com/plastics/guide/polyethylene-plastic
- [11] Equo. (n.d.). *Polyethylene Plastic*. Retrieved from https://shopequo.com/blogs/blog/polyethylene-plastic
- [28] ResearchGate. (n.d.). *Polyethylene-structure, crystallinity and properties*. Retrieved from https://www.researchgate.net/publication/230084537_Polyethylene-structure_crystallinity_and_properties
- [31] Frontiers in Microbiology. (2020). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.580709/full
- [34] MDPI. (2022). *Molecules*. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [32] PMC. (2023). *International Journal of Molecular Sciences*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10386651/
- [129] PNAS. (2018). *Proceedings of the National Academy of Sciences*. Retrieved from https://www.pnas.org/doi/10.1073/pnas.1718804115
- [130] MDPI. (2024). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/16/19/2807
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045

- [13] ResearchGate. (2020). *Biodegradation of polyethylene: a brief review*. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [34] MDPI. (2022). *Molecules*. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [56] ACS Publications. (2023). *Environmental Science & Technology*. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.3c03778
- [20] Oxford Academic. (2024). *FEMS Microbiology Reviews*. Retrieved from https://academic.oup.com/femsre/article/48/6/fuae027/7876491
- [48] PMC. (2022). *Journal of Fungi*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9230134/
- [50] MDPI. (2022). *Journal of Marine Science and Engineering*. Retrieved from https://www.mdpi.com/2076-2607/10/8/1537
- [131] Tournier, V. et al. (2023). *Enzymes' power for plastics degradation*. Retrieved from http://kinampark.com/T-Polymers/files/All%20References/Tournier%202023%2C%20Enzymes%E2%80%99%20power%20for%20plastics%20degradation.pdf
- [51] Semantic Scholar. (n.d.). *American Journal of Environment and Climate*. Retrieved from https://pdfs.semanticscholar.org/a91e/eb058701bb071e40f89ec3e87abb2d3d0b2b.pdf
- [52] Zampolli, J. et al. (2023). *Environmental Technology & Innovation*. Retrieved from https://www.boa.unimib.it/retrieve/f8ccd092-2865-4034-b856-10e646924bb7/Zampolli-2023-Environ%20Technol%20Innov-VoR.pdf
- [25] ACS Publications. (2024). *ACS Omega*. Retrieved from https://pubs.acs.org/doi/10.1021/acsomega.4c04843
- [46] ResearchGate. (n.d.). *A diagram of the microbial degradation processes of polyethylene (PE)*. Retrieved from https://www.researchgate.net/figure/A-diagram-of-the-microbial-degradation-processes-of-polyethylene-PE_fig2_370519387
- [22] MDPI. (2024). *Water*. Retrieved from https://www.mdpi.com/2311-5637/10/9/441
- [29] MDPI. (2025). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/17/2/169
- [21] RSC Publishing. (2025). *RSC Advances*. Retrieved from https://pubs.rsc.org/en/content/articlehtml/2025/va/d5va00058k
- [55] ResearchGate. (n.d.). *Degradation pathways of polyethylene containing pro-oxidant additives*. Retrieved from https://www.researchgate.net/figure/Degradation-pathways-of-polyethylene-containing-pro-oxidant-additives_fig1_338406283
- [49] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
- [15] SciSpace. (n.d.). *Biodegradation of polyethylene: a brief review*. Retrieved from https://scispace.com/pdf/biodegradation-of-polyethylene-a-brief-review-315bl64neh.pdf
- [132] ResearchGate. (n.d.). *Microbial degradation and deterioration of polyethylene - A*

review. Retrieved from https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review

- [17] PMC. (2022). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9852869/
- [19] ResearchGate. (2023). *Polyethylene Degradation by Microbes (Bacteria, Fungus): A Review*. Retrieved from https://www.researchgate.net/publication/371450494_Polyethylene_Degradation_by_Microbes_Bacteria_Fungus_A_Review
- [16] OMICS Online. (n.d.). *A Review on Biodegradation of Polythene: The Microbial Approach*. Retrieved from https://www.omicsonline.org/a-review-on-biodegradation-of-polythene-the-microbial-approach-2155-6199.1000164.php?aid=8679
- [18] The Pharma Journal. (2023). *The Pharma Innovation Journal*. Retrieved from https://www.thepharmajournal.com/archives/2023/vol12issue9/PartAB/12-9-168-119.pdf
- [61] MDPI. (2024). *International Journal of Molecular Sciences*. Retrieved from https://www.mdpi.com/1422-0067/25/1/593
- [56] ACS Publications. (2023). *Environmental Science & Technology*. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.3c03778
- [133] Semantic Scholar. (n.d.). *Screening and Isolation of Polyethylene Degrading Bacteria*. Retrieved from https://www.semanticscholar.org/paper/Screening-and-Isolation-of-Polyethylene-Degrading-Divyalakshmi/f34cab90df2fbe2b4f592bfb7ca1d08927fd725d
- [134] The Open Biotechnology Journal. (2024). *The Open Biotechnology Journal*. Retrieved from https://openbiotechnologyjournal.com/VOLUME/18/ELOCATOR/e18740707280343/
- [21] RSC Publishing. (2025). *RSC Advances*. Retrieved from https://pubs.rsc.org/en/content/articlehtml/2025/va/d5va00058k
- [53] EEER. (n.d.). *Environmental Engineering Research*. Retrieved from https://www.eeer.org/journal/view.php?number=1177
- [67] International Journal of Biology and Biotechnology. (2019). *FUNGAL DEGRADATION OF POLYETHYLENE BAG ISOLATED FROM COASTAL ENVIRONMENT*. Retrieved from http://www.ijbbku.com/assets/custom/journals/2019/3/FUNGAL%20DEGRADATION%20OF%20POLYETHYLENE%20BAG%20ISOLATED%20FROM%20COASTAL%20ENVIRONMENT.pdf
- [68] Plant Archives. (n.d.). *Microbial degradation of low density polyethylene (LDPE) by fungus isolated from landfill soil*. Retrieved from https://www.plantarchives.org/article/microbial-degradation-of-low-density-polyethylene-ldpe-by-fungaus-isolated-from-landfill-soil.pdf
- [69] International Scholars Journals. (n.d.). *Biodegradation of low density polyethylene (LDPE) by fungi isolated from marine water– a SEM analysis*. Retrieved from https://www.internationalscholarsjournals.com/articles/biodegradation-of-low-density-p

olyethylene-ldpe-by-fungi-isolated-from-marine-water-a-sem-analysis.pdf

- [70] ResearchGate. (2024). *Isolation and test of the ability of fungi to degredate polyethylene plastic from landfill plunges*. Retrieved from https://www.researchgate.net/publication/394916156_Isolation_and_test_of_the_ability_of_fungi_to_degredate_polyethylene_plastic_from_landfill_plunges
- [71] PMC. (2021). *Journal of Fungi*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC8396884/
- [75] PMC. (2024). *Harnessing and Degradation Mechanism of Persistent Polyethylene Waste by Newly Isolated Bacteria from Waxworm and Termite Gut Symbionts*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC12388499/
- [76] Promega Connections. (n.d.). *Bacteria From Insect Guts Could Help Degrade Plastic*. Retrieved from https://www.promegaconnections.com/bacteria-degrade-plastic/
- [72] ResearchGate. (2025). *Polyethylene degradation mediated by Klebsiella variicola isolated from the gut of insect larvae*. Retrieved from https://www.researchgate.net/publication/395149351_Polyethylene_degradation_mediated_by_Klebsiella_variicola_isolated_from_the_gut_of_insect_larvae
- [73] The Royal Society Publishing. (2020). *Proceedings of the Royal Society B*. Retrieved from https://royalsocietypublishing.org/doi/pdf/10.1098/rspb.2020.0112
- [74] Frontiers in Microbiology. (2022). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2022.1001750/full
- [45] ResearchGate. (2006). *Biofilm development of the Polyethylene-degrading bacterium Rhodococcus ruber*. Retrieved from https://www.researchgate.net/publication/7243172_Biofilm_development_of_the_Polyethylene-degrading_bacterium_Rhodococcus_ruber
- [54] J-STAGE. (n.d.). *Journal of Society for Microbial Ecology and Disease*. Retrieved from https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_html/-char/ja
- [33] J-STAGE. (n.d.). *Journal of Society for Microbial Ecology and Disease*. Retrieved from https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_article
- [57] MDPI. (2022). *Microorganisms*. Retrieved from https://www.mdpi.com/2076-2607/10/9/1846
- [135] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1284956/full
- [58] VLIZ. (n.d.). *Marine Pollution Bulletin*. Retrieved from https://www.vliz.be/imisdocs/publications/17/386717.pdf
- [62] ResearchGate. (n.d.). *Degradation of low density polyethylene by Bacillus species*. Retrieved from https://www.researchgate.net/publication/366377160_Degradation_of_low_density_polyethylene_by_Bacillus_species/download
- [63] PMC. (2015). *3 Biotech*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC4327746/

- [64] MDPI. (2024). *Processes*. Retrieved from https://www.mdpi.com/2227-9717/12/11/2516
- [59] EQA. (n.d.). *Environmental Quality*. Retrieved from https://eqa.unibo.it/article/download/20474/19322/89114
- [65] SciSpace. (n.d.). *Biodegradation of polyethylene by Bacillus sp. indigenous to*. Retrieved from https://scispace.com/pdf/biodegradation-of-polyethylene-by-bacillus-sp-indigenous-to-ns3zdo82oa.pdf
- [60] CABI Digital Library. (2016). *World Journal of Pharmaceutical Research*. Retrieved from https://www.cabidigitallibrary.org/doi/10.5555/20163186292
- [66] bioRxiv. (n.d.). *bioRxiv*. Retrieved from https://www.biorxiv.org/content/10.1101/647321v1.full-text
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [34] MDPI. (2022). *Molecules*. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [101] Frontiers in Microbiology. (2024). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
- [13] ResearchGate. (2020). *Biodegradation of polyethylene: a brief review*. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [14] DiVA portal. (n.d.). *Polyethylene biodegradation: A multifaceted approach*. Retrieved from https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf
- [136] ResearchGate. (n.d.). *Factors affecting the rate of biodegradation of plastics*. Retrieved from https://www.researchgate.net/figure/Factors-affecting-the-rate-of-biodegradation-of-plastics_fig2_322466876
- [137] Scribd. (n.d.). *The effect of pH temperature on plastic*. Retrieved from https://www.scribd.com/document/724337189/The-effect-of-pH-temperature-on-plastic
- [138] PMC. (2024). *Science of The Total Environment*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC12418820/
- [139] ResearchGate. (n.d.). *Effect of pH (6-9) and temperature (25-35 °C) on polyethylene film carbonyl index in the*. Retrieved from https://www.researchgate.net/figure/Effect-of-pH-6-9-and-temperature-25-35-C-on-polyethylene-film-carbonyl-index-in-the_fig3_347332055
- [140] ResearchGate. (2021). *The effect of pH-temperature on plastic allowance for Low-Density Polyethylene (LDPE) by Thiobacillus sp. and Clostridium sp.*. Retrieved from https://www.researchgate.net/publication/356419375_The_effect_of_pH-temperature_on_plastic_allowance_for_Low-Density_Polyethylene_LDPE_by_Thiobacillus_sp_and_Clostridium_sp
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [141] SciSpace. (n.d.). *Microbial degradation of polyethylene (PE)*. Retrieved from

https://scispace.com/pdf/microbial-degradation-of-polyethylene-pe-ecn0bq19zo.pdf
- [30] MDPI. (2024). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/16/20/2865
- [29] MDPI. (2025). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/17/2/169
- [142] National Speleological Society. (n.d.). *Journal of Cave and Karst Studies*. Retrieved from https://caves.org/pub/journal/PDF/V79/cave-79-01-73.pdf
- [18] The Pharma Journal. (2023). *The Pharma Innovation Journal*. Retrieved from https://www.thepharmajournal.com/archives/2023/vol12issue9/PartAB/12-9-168-119.pdf
- [21] RSC Publishing. (2025). *RSC Advances*. Retrieved from https://pubs.rsc.org/en/content/articlehtml/2025/va/d5va00058k
- [143] ACS Publications. (1953). *Journal of the American Chemical Society*. Retrieved from https://pubs.acs.org/doi/10.1021/j150570a015
- [37] ResearchGate. (n.d.). *Biodegradation of polyethylene. 1. Everyday use of plastic bags generates huge amounts*. Retrieved from https://www.researchgate.net/figure/Biodegradation-of-polyethylene-1-Everyday-use-of-plastic-bags-generates-huge-amounts_fig3_353280725
- [35] Wikipedia. (n.d.). *Biodegradable additives*. Retrieved from https://en.wikipedia.org/wiki/Biodegradable_additives
- [39] ACS Publications. (2014). *Environmental Science & Technology*. Retrieved from https://pubs.acs.org/doi/abs/10.1021/es504258u
- [144] HowStuffWorks. (n.d.). *How Biodegradation Additives Work*. Retrieved from https://science.howstuffworks.com/environmental/green-science/biodegradation-additives.htm
- [145] PMC. (2020). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
- [36] Bio-Tec Environmental. (n.d.). *Blending Biodegradable Additives with Traditional Plastics*. Retrieved from https://goecopure.com/blending-biodegradable-additives-with-traditional-plastics-extending-usability-while-reducing-waste/
- [42] University of Pisa. (n.d.). *Polymers*. Retrieved from https://arpi.unipi.it/retrieve/98053a5e-7324-41f9-92df-53a4291f99ba/polymers-16-00359.pdf
- [146] ResearchGate. (n.d.). *Effect of different pretreatment methods (UV treatment, heat treatment, and chemical*. Retrieved from https://www.researchgate.net/figure/Effect-of-different-pretreatment-methods-UV-treatment-heat-treatment-and-chemical_fig1_352648524
- [147] PMC. (2020). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7199389/
- [41] Biotech Asia. (n.d.). *Biodegradation of ultra-violet irradiated waste polyethylene bags by bacterial community from soil around coal-fired thermal power plant*. Retrieved from https://www.biotech-asia.org/vol18no2/biodegradation-of-ultra-violet-irradiated-waste-polyethylene-bags-by-bacterial-community-from-soil-around-coal-fired-thermal-power-

plant/

- [43] PubMed. (2021). *Environmental Monitoring and Assessment*. Retrieved from https://pubmed.ncbi.nlm.nih.gov/34302548/
- [44] ResearchGate. (2023). *Influence of ultraviolet and chemical treatment on the biodegradation of low-density polyethylene and high-density polyethylene by Cephalosporium strain*. Retrieved from https://www.researchgate.net/publication/368474648_Influence_of_ultraviolet_and_chemical_treatment_on_the_biodegradation_of_low-density_polyethylene_and_high-density_polyethylene_by_Cephalosporium_strain
- [49] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
- [13] ResearchGate. (2020). *Biodegradation of polyethylene: a brief review*. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [88] MDPI. (2025). *Molecules*. Retrieved from https://www.mdpi.com/1420-3049/30/11/2462
- [148] ResearchGate. (2020). *Analytical review on Biodegradation of Plastics*. Retrieved from https://www.researchgate.net/publication/344498876_Analytical_review_on_Biodegradation_of_Plastics
- [149] OSTI.GOV. (n.d.). *Science of the Total Environment*. Retrieved from https://www.osti.gov/pages/biblio/2438502
- [150] DNTB. (n.d.). *Frontiers in Bioengineering and Biotechnology*. Retrieved from https://ouci.dntb.gov.ua/en/works/4YoaDRM9/
- [93] NEPT Journal. (n.d.). *NEPT Journal*. Retrieved from https://neptjournal.com/upload-images/(15)B-3772.pdf
- [151] ACS Publications. (2015). *Langmuir*. Retrieved from https://pubs.acs.org/doi/pdf/10.1021/acs.langmuir.5c03651
- [23] MDPI. (2020). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/12/1/123
- [85] PMC. (2023). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
- [89] PMC. (2024). *Science of The Total Environment*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10990042/
- [34] MDPI. (2022). *Molecules*. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [86] Egyptian Journal of Aquatic Biology and Fisheries. (n.d.). *Egyptian Journal of Aquatic Biology and Fisheries*. Retrieved from https://ejabf.journals.ekb.eg/article_365569_c7ff969db8f79d226e63ffc74932e3d5.pdf
- [90] Jordi Labs. (n.d.). *Degradation of PE by FTIR & HTGPC*. Retrieved from https://jordilabs.com/wp-content/uploads/filebase/Case_Study_Degradation_of_PE_FTIR_HTGPC.pdf
- [26] ResearchGate. (2023). *Enzymatic polyethylene biorecycling: Confronting challenges and shaping the future*. Retrieved from https://www.researchgate.net/publication/373831037_Enzymatic_polyethylene_biorecycli

ng_Confronting_challenges_and_shaping_the_future
- [152] ResearchGate. (n.d.). *The FTIR spectra of the degraded polyethylene (LDPE) strips and pellets by bacterial*. Retrieved from https://www.researchgate.net/figure/The-FTIR-spectra-of-the-degraded-polyethylene-LDPE-strips-and-pellets-by-bacterial_fig3_303872553
- [91] PMC. (2024). *Microchimica Acta*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC11121657/
- [153] MDPI. (2019). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/11/10/1629
- [92] Advanced Light Source. (n.d.). *Use and misuse of FTIR spectroscopy for studying the bio-oxidation of plastics*. Retrieved from https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf
- [95] ResearchGate. (2023). *A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber*. Retrieved from https://www.researchgate.net/publication/365887571_A_stable_isotope_assay_with_13C-labeled_polyethylene_to_investigate_plastic_mineralization_mediated_by_Rhodococcus_ruber
- [154] University of North Texas. (n.d.). *13C-Stable Isotope Labeling*. Retrieved from https://research.unt.edu/resources/research-core-facilities/bioanalytical-facility/services-and-fees/13c-stable-isotope-labeling.html
- [155] Polymer Source. (n.d.). *Poly(ethylene oxide), C13-labelled*. Retrieved from https://www.polymersource.ca/index.php?route=product/category&path=1_11_1371
- [58] VLIZ. (n.d.). *Marine Pollution Bulletin*. Retrieved from https://www.vliz.be/imisdocs/publications/17/386717.pdf
- [96] Munin. (n.d.). *A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber*. Retrieved from https://munin.uit.no/handle/10037/27784
- [97] ResearchGate. (n.d.). *PE-MP mineralization in freshwaters. (A) Different size of 13 C-polyethylene particles*. Retrieved from https://www.researchgate.net/figure/PE-MP-mineralization-in-freshwaters-A-Different-size-of-13-C-polyethylene-particles_fig1_338189742
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [98] IWA Publishing. (n.d.). *Water Science and Technology*. Retrieved from https://iwaponline.com/wst/article/88/11/2996/98692/Investigating-biodegradation-of-polyethylene-and
- [156] PMC. (2022). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9694517/
- [87] IOSR Journals. (n.d.). *IOSR Journal of Environmental Science, Toxicology and Food*

Technology. Retrieved from https://www.iosrjournals.org/iosr-jestft/papers/Vol18-Issue12/Ser-3/C1812031217.pdf

- [34] MDPI. (2022). *Molecules*. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [94] bioRxiv. (n.d.). *Microbial degradation of a widely used model polyethylene is restricted to medium- and long-chain alkanes and their oxidized derivatives*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.09.22.675545v2
- [77] ResearchGate. (n.d.). *Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production*. Retrieved from https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production
- [142] National Speleological Society. (n.d.). *Journal of Cave and Karst Studies*. Retrieved from https://caves.org/pub/journal/PDF/V79/cave-79-01-73.pdf
- [47] PMC. (2024). *Journal of Society for Microbial Ecology and Disease*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC11427307/
- [81] Frontiers in Microbiology. (2021). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2021.778828/full
- [84] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1143769/full
- [85] PMC. (2023). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
- [82] ResearchGate. (n.d.). *Synergistic biodegradation of polyethylene by experimentally evolved bacterial biofilms*. Retrieved from https://www.researchgate.net/publication/390408969_Synergistic_biodegradation_of_polyethylene_by_experimentally_evolved_bacterial_biofilms
- [79] Journal of Microbiology, Biotechnology and Food Sciences. (n.d.). *Journal of Microbiology, Biotechnology and Food Sciences*. Retrieved from https://journals.stecab.com/jmsbc/article/view/681
- [80] PMC. (2020). *Nature Communications*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7666164/
- [83] bioRxiv. (n.d.). *bioRxiv*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full.pdf
- [123] MDPI. (2022). *International Journal of Molecular Sciences*. Retrieved from https://www.mdpi.com/1422-0067/23/10/5612
- [78] Intersect: The Stanford Journal of Science, Technology, and Society. (2024). *Microbial Consortia-Mediated Degradation of Recalcitrant Plastics*. Retrieved from https://ojs.stanford.edu/ojs/index.php/intersect/article/view/3458
- [23] MDPI. (2020). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/12/1/123
- [101] Frontiers in Microbiology. (2024). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
- [102] ResearchGate. (2021). *Bridging Three Gaps in Biodegradable Plastics: Misconceptions and Truths About Biodegradation*. Retrieved from

https://www.researchgate.net/publication/351580119_Bridging_Three_Gaps_in_Biodegradable_Plastics_Misconceptions_and_Truths_About_Biodegradation
- [157] YouTube. (n.d.). *Alfa Chemistry*. Retrieved from https://www.youtube.com/watch?v=Yx8NG5ZK6fA
- [103] ACS Publications. (2021). *Environmental Science & Technology*. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.1c00994
- [38] ACS Publications. (2017). *Environmental Science & Technology*. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.7b04051
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [27] Scribd. (n.d.). *Enzymatic polyethylene biorecycling: Confronting challenges and shaping the future*. Retrieved from https://www.scribd.com/document/738085336/Enzymatic-polyethylene-biorecyclingConfronting-challenges-and-shaping-the-future
- [99] ResearchGate. (n.d.). *Biodegradability of polyethylene: Challenges and future perspectives*. Retrieved from https://www.researchgate.net/publication/385077019_Biodegradability_of_polyethylene_Challenges_and_future_perspectives
- [158] MDPI. (2024). *Materials*. Retrieved from https://www.mdpi.com/1996-1944/18/20/4788
- [100] PMC. (2023). *Heliyon*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10598529/
- [49] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [61] MDPI. (2024). *International Journal of Molecular Sciences*. Retrieved from https://www.mdpi.com/1422-0067/25/1/593
- [159] ResearchGate. (n.d.). *Polyethylene biodegradation: A multifaceted approach*. Retrieved from https://www.researchgate.net/publication/390506954_Polyethylene_biodegradation_A_multifaceted_approach
- [40] MDPI. (2023). *Applied Sciences*. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [13] ResearchGate. (2020). *Biodegradation of polyethylene: a brief review*. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [10] PMC. (2020). *Polymers*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [83] bioRxiv. (n.d.). *bioRxiv*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full.pdf
- [116] SCIEPublish. (n.d.). *Journal of Synthetic Biology*. Retrieved from

https://www.sciepublish.com/article/pii/440

- [160] SciSpace. (n.d.). *Biodegradability of synthetic plastics: a review*. Retrieved from https://scispace.com/pdf/biodegradability-of-synthetic-plastics-a-review-54b6joc7fr.pdf
- [104] PubMed. (n.d.). *Metagenomic exploration and computational prediction of novel enzymes for polyethylene terephthalate degradation*. Retrieved from https://pubmed.ncbi.nlm.nih.gov/39793291/
- [105] ResearchGate. (n.d.). *Exploring the global metagenome for plastic-degrading enzymes*. Retrieved from https://www.researchgate.net/publication/348646771_Exploring_the_global_metagenome_for_plastic-degrading_enzymes
- [106] Frontiers in Microbiology. (2024). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1347119/full
- [107] PMC. (2024). *PLOS ONE*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10997104/
- [109] University of Cambridge. (n.d.). *Novel plastic degrading enzymes, plastizymes*. Retrieved from https://hyvonen.bioc.cam.ac.uk/plastizymes/
- [110] Oxford Academic. (2025). *PNAS Nexus*. Retrieved from https://academic.oup.com/pnasnexus/article/4/3/pgaf066/8063326
- [117] ResearchGate. (n.d.). *Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis*. Retrieved from https://www.researchgate.net/publication/382619966_Development_of_a_Bioreactor-Based_Model_for_low-density_polyethylene_LDPE_Biodegradation_by_Aspergillus_brasiliensis
- [118] Researcher.Life. (n.d.). *Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis*. Retrieved from https://discovery.researcher.life/article/development-of-a-bioreactor-based-model-for-low-density-polyethylene-ldpe-biodegradation-by-aspergillus-brasiliensis/95fa6d30f35233f6a456d467fb9faa97
- [101] Frontiers in Microbiology. (2024). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
- [85] PMC. (2023). *Frontiers in Microbiology*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
- [119] Bohrium. (n.d.). *Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis*. Retrieved from https://www.bohrium.com/paper-details/development-of-a-bioreactor-based-model-for-low-density-polyethylene-ldpe-biodegradation-by-aspergillus-brasiliensis/1038055857415258153-32820
- [120] ResearchGate. (n.d.). *Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis*. Retrieved from https://www.researchgate.net/publication/382619966_Development_of_a_Bioreactor-Based_Model_for_low-density_polyethylene_LDPE_Biodegradation_by_Aspergillus_brasiliensi

s/fulltext/66a54d6b75fcd863e5e1eddd/Development-of-a-Bioreactor-Based-Model-for-low-density-polyethylene-LDPE-Biodegradation-by-Aspergillus-brasiliensis.pdf
- [111] bioRxiv. (n.d.). *bioRxiv*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.03.24.645130v1.full-text
- [112] University of Manchester. (n.d.). *Engineering enzymes to help solve the planet's plastic problem*. Retrieved from https://www.manchester.ac.uk/about/news/engineering-enzymes-to-help-solve-the-planets-plastic-problem/
- [113] ResearchGate. (n.d.). *Metabolic and enzymatic engineering strategies for polyethylene terephthalate degradation and valorization*. Retrieved from https://www.researchgate.net/publication/380546389_Metabolic_and_enzymatic_engineering_strategies_for_polyethylene_terephthalate_degradation_and_valorization
- [114] MDPI. (2023). *Catalysts*. Retrieved from https://www.mdpi.com/2073-4344/13/3/591
- [161] American Society for Microbiology. (2023). *Applied and Environmental Microbiology*. Retrieved from https://journals.asm.org/doi/10.1128/aem.00632-23
- [115] Frontiers in Bioengineering and Biotechnology. (2024). *Frontiers in Bioengineering and Biotechnology*. Retrieved from https://www.frontiersin.org/journals/bioengineering-and-biotechnology/articles/10.3389/fbioe.2024.1349010/full
- [162] Taylor & Francis Online. (2023). *Critical Reviews in Environmental Science and Technology*. Retrieved from https://www.tandfonline.com/doi/full/10.1080/07388551.2023.2170861
- [121] Frontiers in Microbiology. (2023). *Frontiers in Microbiology*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1265139/full
- [100] PMC. (2023). *Heliyon*. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10598529/
- [122] Bio-Tec Environmental. (n.d.). *Future Trends in Biodegradable Plastic Technology*. Retrieved from https://goecopure.com/future-trends-in-biodegradable-plastic-technology/
- [163] MDPI. (2022). *Polymers*. Retrieved from https://www.mdpi.com/2073-4360/14/13/2642
- [108] American Society for Microbiology. (2021). *mBio*. Retrieved from https://journals.asm.org/doi/10.1128/mbio.02155-21
- [124] Science Publications. (n.d.). *American Journal of Environmental Sciences*. Retrieved from https://pubs.sciepub.com/aees/9/7/8/index.html

---

Download Options:
(https://example.com/download.pdf) |(https://example.com/download.docx)

Works cited

1. Polyethylene Market | Size, Share, Growth | 2025 - 2030, accessed on October 23,

2025, https://virtuemarketresearch.com/report/polyethylene-market
2. Polyethylene Market Size to Hit USD 266.58 Billion by 2034 - Precedence Research, accessed on October 23, 2025, https://www.precedenceresearch.com/polyethylene-market
3. Polyethylene Market Size & Forecast 2024-2034 - Future Market Insights, accessed on October 23, 2025, https://www.futuremarketinsights.com/reports/polyethylene-market
4. Plastics – the fast Facts 2024, accessed on October 23, 2025, https://plasticseurope.org/wp-content/uploads/2024/11/PE_TheFacts_24_digital-1pager.pdf
5. Plastic Pollution - Our World in Data, accessed on October 23, 2025, https://ourworldindata.org/plastic-pollution
6. Plastic Waste Statistics & Trends (UPDATED 2025), accessed on October 23, 2025, https://wastedirect.co.uk/blog/plastic-waste-statistics/
7. Plastics | In-depth topics | European Environment Agency (EEA), accessed on October 23, 2025, https://www.eea.europa.eu/en/topics/in-depth/plastics
8. Plastic pollution | UNEP - UN Environment Programme, accessed on October 23, 2025, https://www.unep.org/topics/chemicals-and-pollution-action/plastic-pollution
9. Polyethylene - Wikipedia, accessed on October 23, 2025, https://en.wikipedia.org/wiki/Polyethylene
10. Challenges with Verifying Microbial Degradation of Polyethylene - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
11. PE (Polyethylene) Plastic: An Overview Of Its Properties, Classification, And Common Applications In Daily Life - EQUO Vietnam, accessed on October 23, 2025, https://shopequo.com/blogs/blog/polyethylene-plastic
12. Polyethylene (PE Plastic) – Structure, Properties & Toxicity - SpecialChem, accessed on October 23, 2025, https://www.specialchem.com/plastics/guide/polyethylene-plastic
13. (PDF) Biodegradation of polyethylene: a brief review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
14. Polyethylene biodegradation - DiVA portal, accessed on October 23, 2025, https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf
15. Biodegradation of polyethylene: a brief review - SciSpace, accessed on October 23, 2025, https://scispace.com/pdf/biodegradation-of-polyethylene-a-brief-review-315bl64neh.pdf
16. A Review on Biodegradation of Polythene: The Microbial Approach | OMICS International, accessed on October 23, 2025, https://www.omicsonline.org/a-review-on-biodegradation-of-polythene-the-microbial-approach-2155-6199.1000164.php?aid=8679
17. Plastic biodegradation by in vitro environmental microorganisms and in vivo gut

microorganisms of insects - PMC - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9852869/
18. Microbes mediated polyethylene biodegradation for environmental sustainability - The Pharma Innovation Journal, accessed on October 23, 2025, https://www.thepharmajournal.com/archives/2023/vol12issue9/PartAB/12-9-168-119.pdf
19. Polyethylene Degradation by Microbes (Bacteria & Fungus): A Review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/371450494_Polyethylene_Degradation_by_Microbes_Bacteria_Fungus_A_Review
20. The biochemical mechanisms of plastic biodegradation - Oxford Academic, accessed on October 23, 2025, https://academic.oup.com/femsre/article/48/6/fuae027/7876491
21. Introducing the LDPE degrading microbes of sedimentary systems: from dumpsite to laboratory - Environmental Science: Advances (RSC Publishing) DOI:10.1039/D5VA00058K, accessed on October 23, 2025, https://pubs.rsc.org/en/content/articlehtml/2025/va/d5va00058k
22. Microbial Degradation of (Micro)plastics: Mechanisms, Enhancements, and Future Directions - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2311-5637/10/9/441
23. Challenges with Verifying Microbial Degradation of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/12/1/123
24. Polyethylene (PE) | Properties, Structures, Uses, & Facts | Britannica, accessed on October 23, 2025, https://www.britannica.com/science/polyethylene
25. Characterization of Potential Plastic-Degradation Enzymes from Marine Bacteria | ACS Omega - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acsomega.4c04843
26. Enzymatic polyethylene biorecycling: Confronting challenges and shaping the future, accessed on October 23, 2025, https://www.researchgate.net/publication/373831037_Enzymatic_polyethylene_biorecycling_Confronting_challenges_and_shaping_the_future
27. Enzymatic Polyethylene Biorecyclingconfronting Challenges and Shaping The Future, accessed on October 23, 2025, https://www.scribd.com/document/738085336/Enzymatic-polyethylene-biorecyclingConfronting-challenges-and-shaping-the-future
28. Polyethylene-structure, crystallinity and properties - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/230084537_Polyethylene-structure_crystallinity_and_properties
29. Microbial Biodegradation of Synthetic Polyethylene and Polyurethane Polymers by Pedospheric Microbes: Towards Sustainable Environmental Management - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/17/2/169
30. Bacterial Degradation of Low-Density Polyethylene Preferentially Targets the Amorphous Regions of the Polymer - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/16/20/2865

31. Microbial and Enzymatic Degradation of Synthetic Plastics - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.580709/full
32. Biological Degradation of Plastics and Microplastics: A Recent Perspective on Associated Mechanisms and Influencing Factors - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10386651/
33. Polyethylene Biodegradation by an Artificial Bacterial Consortium: *Rhodococcus* as a Competitive Plastisphere Species - j-stage, accessed on October 23, 2025, https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_article
34. Biodegradation of Polymers: Stages, Measurement, Standards and Prospects - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2673-6209/3/2/23
35. Biodegradable additives - Wikipedia, accessed on October 23, 2025, https://en.wikipedia.org/wiki/Biodegradable_additives
36. Blending Biodegradable Additives with Traditional Plastics: Extending Usability While Reducing Waste | Bio-Tec Environmental, accessed on October 23, 2025, https://goecopure.com/blending-biodegradable-additives-with-traditional-plastics-extending-usability-while-reducing-waste/
37. Biodegradation of polyethylene. (1) Everyday use of plastic bags... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Biodegradation-of-polyethylene-1-Everyday-use-of-plastic-bags-generates-huge-amounts_fig3_353280725
38. Biodegradability of Plastics: Challenges and Misconceptions | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.7b04051
39. Evaluation of Biodegradation-Promoting Additives for Plastics | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/abs/10.1021/es504258u
40. A Review of Degradation and Life Prediction of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2076-3417/13/5/3045
41. Biodegradation of Ultra-violet Irradiated Waste Polyethylene Bags by Bacterial Community from Soil around Coal -fired Thermal Power Plant – Biosciences Biotechnology Research Asia, accessed on October 23, 2025, https://www.biotech-asia.org/vol18no2/biodegradation-of-ultra-violet-irradiated-waste-polyethylene-bags-by-bacterial-community-from-soil-around-coal-fired-thermal-power-plant/
42. Effect of Abiotic Treatments on Agricultural Plastic Waste: Efficiency of the Degradation Processes - ARPI, accessed on October 23, 2025, https://arpi.unipi.it/retrieve/98053a5e-7324-41f9-92df-53a4291f99ba/polymers-16-00359.pdf
43. Synergistic effect of UV, thermal, and chemical treatment on biological degradation of low-density polyethylene (LDPE) by Thermomyces lanuginosus - PubMed, accessed on October 23, 2025, https://pubmed.ncbi.nlm.nih.gov/34302548/
44. (PDF) Influence of ultraviolet and chemical treatment on the biodegradation of

low-density polyethylene and high-density polyethylene by Cephalosporium strain - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/368474648_Influence_of_ultraviolet_and_chemical_treatment_on_the_biodegradation_of_low-density_polyethylene_and_high-density_polyethylene_by_Cephalosporium_strain
45. (PDF) Biofilm development of the Polyethylene-degrading bacterium Rhodococcus ruber,, accessed on October 23, 2025, https://www.researchgate.net/publication/7243172_Biofilm_development_of_the_Polyethylene-degrading_bacterium_Rhodococcus_ruber
46. A diagram of the microbial degradation processes of polyethylene (PE). - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/A-diagram-of-the-microbial-degradation-processes-of-polyethylene-PE_fig2_370519387
47. Polyethylene Biodegradation by an Artificial Bacterial Consortium: Rhodococcus as a Competitive Plastisphere Species - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC11427307/
48. Fungal Enzymes Involved in Plastics Biodegradation - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9230134/
49. Assembly strategies for polyethylene-degrading microbial consortia based on the combination of omics tools and the “Plastisphere” - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
50. Current Advances in Biodegradation of Polyolefins - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2076-2607/10/8/1537
51. P age 1 - Semantic Scholar, accessed on October 23, 2025, https://pdfs.semanticscholar.org/a91e/eb058701bb071e40f89ec3e87abb2d3d0b2b.pdf
52. Environmental Technology & Innovation Oxidative degradation of polyethylene by two novel laccase-like multicopper oxidases f - Milano-Bicocca, accessed on October 23, 2025, https://www.boa.unimib.it/retrieve/f8ccd092-2865-4034-b856-10e646924bb7/Zampolli-2023-Environ%20Technol%20Innov-VoR.pdf
53. Identification and characterization of low density polyethylene-degrading bacteria isolated from soils of waste disposal sites - Environmental Engineering Research, accessed on October 23, 2025, https://www.eeer.org/journal/view.php?number=1177
54. Polyethylene Biodegradation by an Artificial Bacterial Consortium: *Rhodococcus* as a Competitive Plastisphere Species - J-Stage, accessed on October 23, 2025, https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_html/-char/ja
55. Degradation pathways of polyethylene containing pro-oxidant additives. - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Degradation-pathways-of-polyethylene-containing-pro-oxidant-additives_fig1_338406283

56. Polyethylene Degradation by a Rhodococcous Strain Isolated from Naturally Weathered Plastic Waste Enrichment | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.3c03778
57. Genome-Based Exploration of Rhodococcus Species for Plastic-Degrading Genetic Determinants Using Bioinformatic Analysis - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2076-2607/10/9/1846
58. A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber, accessed on October 23, 2025, https://www.vliz.be/imisdocs/publications/17/386717.pdf
59. The biodegradation of low-density polyethylene by Bacillus species - EQA - International Journal of Environmental Quality, accessed on October 23, 2025, https://eqa.unibo.it/article/download/20474/19322/89114
60. Biodegradation of plastic by Bacillus subtilis isolated from polythene polluted soil., accessed on October 23, 2025, https://www.cabidigitallibrary.org/doi/10.5555/20163186292
61. Biodegradation of Typical Plastics: From Microbial Diversity to Metabolic Mechanisms, accessed on October 23, 2025, https://www.mdpi.com/1422-0067/25/1/593
62. (PDF) Degradation of low density polyethylene by Bacillus species - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/366377160_Degradation_of_low_density_polyethylene_by_Bacillus_species/download
63. An approach to low-density polyethylene biodegradation by Bacillus amyloliquefaciens - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC4327746/
64. Biodegradation of Polyethylene Using Bacillus tropicus Isolated from Sewage Wastewater Treatment Plant - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2227-9717/12/11/2516
65. Biodegradation of Polyethylene by Bacillus sp. Indigenous to the Niger Delta Mangrove Swamp - SciSpace, accessed on October 23, 2025, https://scispace.com/pdf/biodegradation-of-polyethylene-by-bacillus-sp-indigenous-to-ns3zdo82oa.pdf
66. Pseudomonas isolates degrade and form biofilms on polyethylene terephthalate (PET) plastic | bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/647321v1.full-text
67. FUNGAL DEGRADATION OF POLYETHYLENE BAG ISOLATED FROM COASTAL ENVIRONMENT - International Journal of Biology and Biotechnology, accessed on October 23, 2025, http://www.ijbbku.com/assets/custom/journals/2019/3/FUNGAL%20DEGRADATION%20OF%20POLYETHYLENE%20BAG%20ISOLATED%20FROM%20COASTAL%20ENVIRONMENT.pdf
68. Microbial degradation of low-density polyethylene (LDPE) by fungus isolated from landfill soil - Plant Archives, accessed on October 23, 2025, https://www.plantarchives.org/article/microbial-degradation-of-low-density-poly

ethylene-ldpe-by-fungaus-isolated-from-landfill-soil.pdf
69. Biodegradation of low density polyethylene (LDPE) by fungi isolated from marine water– a SEM analysis - International Scholars Journals, accessed on October 23, 2025, https://www.internationalscholarsjournals.com/articles/biodegradation-of-low-density-polyethylene-ldpe-by-fungi-isolated-from-marine-water-a-sem-analysis.pdf
70. Isolation and test of the ability of fungi to degredate polyethylene plastic from landfill plunges, accessed on October 23, 2025, https://www.researchgate.net/publication/394916156_Isolation_and_test_of_the_ability_of_fungi_to_degredate_polyethylene_plastic_from_landfill_plunges
71. Low-Density Polyethylene Film Biodegradation Potential by Fungal Species from Thailand, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8396884/
72. Polyethylene degradation mediated by Klebsiella variicola isolated from the gut of insect larvae - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/395149351_Polyethylene_degradation_mediated_by_Klebsiella_variicola_isolated_from_the_gut_of_insect_larvae
73. Role of the intestinal microbiome in low-density polyethylene degradation by caterpillar larvae of the greater wax moth, Galleria - Journals, accessed on October 23, 2025, https://royalsocietypublishing.org/doi/pdf/10.1098/rspb.2020.0112
74. Plastic biodegradation by in vitro environmental microorganisms and in vivo gut microorganisms of insects - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2022.1001750/full
75. Harnessing and Degradation Mechanism of Persistent Polyethylene Waste by Newly Isolated Bacteria from Waxworm and Termite Gut Symbionts - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC12388499/
76. Bacteria From Insect Guts Could Help Degrade Plastic - Promega Connections, accessed on October 23, 2025, https://www.promegaconnections.com/bacteria-degrade-plastic/
77. Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production, accessed on October 23, 2025, https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production
78. Microbial Consortia-Mediated Degradation of Recalcitrant Plastics | Intersect: The Stanford Journal of Science, Technology, and Society, accessed on October 23, 2025, https://ojs.stanford.edu/ojs/index.php/intersect/article/view/3458
79. Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production | Journal of Medical Science, Biology, and Chemistry - Stecab Publishing, accessed on October 23, 2025, https://journals.stecab.com/jmsbc/article/view/681
80. Synergistic biodegradation of aromatic-aliphatic copolyester plastic by a marine

microbial consortium - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7666164/
81. Evaluation of PET Degradation Using Artificial Microbial Consortia - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2021.778828/full
82. (PDF) Synergistic biodegradation of polyethylene by experimentally evolved bacterial biofilms - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/390408969_Synergistic_biodegradation_of_polyethylene_by_experimentally_evolved_bacterial_biofilms
83. Synergistic biodegradation of polyethylene by experimentally evolved bacterial biofilms - bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full.pdf
84. Development of plastic-degrading microbial consortia by induced selection in microcosms, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1143769/full
85. Assembly strategies for polyethylene-degrading microbial consortia based on the combination of omics tools and the “Plastisphere” - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
86. Biodegradation of Low-Density Polyethylene Plastic Using Marine Bacterial Consortium - Egyptian Journal of Aquatic Biology and Fisheries, accessed on October 23, 2025, https://ejabf.journals.ekb.eg/article_365569_c7ff969db8f79d226e63ffc74932e3d5.pdf
87. Preliminary Study On Biodegradation Of Polyethylene By Pseudomonas Aeruginosa - IOSR Journal, accessed on October 23, 2025, https://www.iosrjournals.org/iosr-jestft/papers/Vol18-Issue12/Ser-3/C1812031217.pdf
88. Current Approaches to Microplastics Detection and Plastic Biodegradation - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1420-3049/30/11/2462
89. Assessing microbial plastic degradation requires robust methods - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10990042/
90. Degradation of Polyethylene by FTIR and High Temperature GPC CASE STUDY Degradation of Polyethylene by FTIR and High Temperatur - Jordi Labs, accessed on October 23, 2025, https://jordilabs.com/wp-content/uploads/filebase/Case_Study_Degradation_of_PE_FTIR_HTGPC.pdf
91. Insights into Plastic Degradation Processes in Marine Environment by X-ray Photoelectron Spectroscopy Study - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC11121657/
92. Use and misuse of FTIR spectroscopy for studying the bio-oxidation of plastics - Advanced Light Source, accessed on October 23, 2025,

https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf
93. Reliable and Sophisticated Techniques to Evaluate LDPE Degraded Compounds by Streptomyces werraensis SDJM, accessed on October 23, 2025, https://neptjournal.com/upload-images/(15)B-3772.pdf
94. Microbial degradation of a widely used model polyethylene is restricted to medium- and long-chain alkanes and their oxidized derivatives | bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.09.22.675545v2
95. (PDF) A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/365887571_A_stable_isotope_assay_with_13C-labeled_polyethylene_to_investigate_plastic_mineralization_mediated_by_Rhodococcus_ruber
96. A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber - Munin, accessed on October 23, 2025, https://munin.uit.no/handle/10037/27784
97. PE-MP mineralization in freshwaters. (A) Different size of 13... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/PE-MP-mineralization-in-freshwaters-A-Different-size-of-13-C-polyethylene-particles_fig1_338189742
98. Investigating biodegradation of polyethylene and polypropylene microplastics in Tehran DWTPs | Water Science & Technology | IWA Publishing, accessed on October 23, 2025, https://iwaponline.com/wst/article/88/11/2996/98692/Investigating-biodegradation-of-polyethylene-and
99. Biodegradability of polyethylene: Challenges and future perspectives | Request PDF, accessed on October 23, 2025, https://www.researchgate.net/publication/385077019_Biodegradability_of_polyethylene_Challenges_and_future_perspectives
100. Recent developments in bio-based polyethylene: Degradation studies, waste management and recycling - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10598529/
101. Global perspectives on the biodegradation of LDPE in agricultural systems - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
102. (PDF) Bridging Three Gaps in Biodegradable Plastics: Misconceptions and Truths About Biodegradation - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/351580119_Bridging_Three_Gaps_in_Biodegradable_Plastics_Misconceptions_and_Truths_About_Biodegradation
103. Knowledge Gaps in Polymer Biodegradation Research | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.1c00994

104. Metagenomic exploration and computational prediction of novel enzymes for polyethylene terephthalate degradation - PubMed, accessed on October 23, 2025, https://pubmed.ncbi.nlm.nih.gov/39793291/
105. Exploring the global metagenome for plastic-degrading enzymes - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/348646771_Exploring_the_global_metagenome_for_plastic-degrading_enzymes
106. Exploring untapped bacterial communities and potential polypropylene-degrading enzymes from mangrove sediment through metagenomics analysis - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1347119/full
107. Searching for new plastic-degrading enzymes from the plastisphere of alpine soils using a metagenomic mining approach - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10997104/
108. Plastic-Degrading Potential across the Global Microbiome Correlates with Recent Pollution Trends | mBio - ASM Journals, accessed on October 23, 2025, https://journals.asm.org/doi/10.1128/mbio.02155-21
109. Novel plastic degrading enzymes, plastizymes, accessed on October 23, 2025, https://hyvonen.bioc.cam.ac.uk/plastizymes/
110. Natural-selected plastics biodegradation species and enzymes in landfills | PNAS Nexus | Oxford Academic, accessed on October 23, 2025, https://academic.oup.com/pnasnexus/article/4/3/pgaf066/8063326
111. Structural decay of poly(ethylene terephthalate) by enzymatic degradation - bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.03.24.645130v1.full-text
112. Engineering enzymes to help solve the planet's plastic problem - The University of Manchester, accessed on October 23, 2025, https://www.manchester.ac.uk/about/news/engineering-enzymes-to-help-solve-the-planets-plastic-problem/
113. (PDF) Metabolic and enzymatic engineering strategies for polyethylene terephthalate degradation and valorization - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/380546389_Metabolic_and_enzymatic_engineering_strategies_for_polyethylene_terephthalate_degradation_and_valorization
114. Determinants for an Efficient Enzymatic Catalysis in Poly(Ethylene Terephthalate) Degradation - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4344/13/3/591
115. Characterization and engineering of plastic-degrading polyesterases jmPE13 and jmPE14 from Pseudomonas bacterium - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/bioengineering-and-biotechnology/articles/10.3389/fbioe.2024.1349010/full
116. Synthetic Biology Boosts the Biological Depolymerization and Upcycling of

Waste Plastic Resources - SCIEPublish, accessed on October 23, 2025, https://www.sciepublish.com/article/pii/440
117. (PDF) Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/382619966_Development_of_a_Bioreactor-Based_Model_for_low-density_polyethylene_LDPE_Biodegradation_by_Aspergillus_brasiliensis
118. Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis - R Discovery, accessed on October 23, 2025, https://discovery.researcher.life/article/development-of-a-bioreactor-based-model-for-low-density-polyethylene-ldpe-biodegradation-by-aspergillus-brasiliensis/95fa6d30f35233f6a456d467fb9faa97
119. Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis-Bohrium, accessed on October 23, 2025, https://www.bohrium.com/paper-details/development-of-a-bioreactor-based-model-for-low-density-polyethylene-ldpe-biodegradation-by-aspergillus-brasiliensis/1038055857415258153-32820
120. Development of a Bioreactor-Based Model for low-density polyethylene (LDPE) Biodegradation by Aspergillus brasiliensis - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/382619966_Development_of_a_Bioreactor-Based_Model_for_low-density_polyethylene_LDPE_Biodegradation_by_Aspergillus_brasiliensis/fulltext/66a54d6b75fcd863e5e1eddd/Development-of-a-Bioreactor-Based-Model-for-low-density-polyethylene-LDPE-Biodegradation-by-Aspergillus-brasiliensis.pdf
121. Recent advances in the biodegradation of polyethylene terephthalate with cutinase-like enzymes - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1265139/full
122. Future Trends in Biodegradable Plastic Technology - Bio-Tec Environmental, accessed on October 23, 2025, https://goecopure.com/future-trends-in-biodegradable-plastic-technology/
123. Microbial Consortia and Mixed Plastic Waste: Pangenomic Analysis Reveals Potential for Degradation of Multiple Plastic Types via Previously Identified PET Degrading Bacteria - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1422-0067/23/10/5612
124. Review on Efficacy of Microbial Degradation of Polyethylene Terephthalate and Bio-upcycling as a Part of Plastic Waste Management - Science and Education Publishing, accessed on October 23, 2025, https://pubs.sciepub.com/aees/9/7/8/index.html
125. Polyethylene model update: Key insights on 2024 PE market trends and challenges, accessed on October 23, 2025,

https://www.argusmedia.com/en/news-and-insights/market-opinion-and-analysis-blog/polyethylene-model-update-2024-takeaways
126. Plastics – the fast Facts 2024, accessed on October 23, 2025, https://plasticseurope.org/knowledge-hub/plastics-the-fast-facts-2024/
127. Plastics: Material-Specific Data | US EPA, accessed on October 23, 2025, https://www.epa.gov/facts-and-figures-about-materials-waste-and-recycling/plastics-material-specific-data
128. 10 Countries Producing Most Plastic Waste | GreenMatch.co.uk, accessed on October 23, 2025, https://www.greenmatch.co.uk/blog/10-countries-producing-most-plastic-waste
129. Characterization and engineering of a plastic-degrading aromatic polyesterase | PNAS, accessed on October 23, 2025, https://www.pnas.org/doi/10.1073/pnas.1718804115
130. Degradation of Polymer Materials in the Environment and Its Impact on the Health of Experimental Animals: A Review - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/16/19/2807
131. Enzymes' Power for Plastics Degradation | Kinam Park, accessed on October 23, 2025, http://kinampark.com/T-Polymers/files/All%20References/Tournier%202023%2C%20Enzymes%E2%80%99%20power%20for%20plastics%20degradation.pdf
132. Microbial degradation and deterioration of polyethylene – A review | Request PDF, accessed on October 23, 2025, https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
133. Screening and Isolation of Polyethylene Degrading Bacteria from Various Soil Environments, accessed on October 23, 2025, https://www.semanticscholar.org/paper/Screening-and-Isolation-of-Polyethylene-Degrading-Divyalakshmi/f34cab90df2fbe2b4f592bfb7ca1d08927fd725d
134. Isolation and Characterization of Polyethylene and Polyethylene Terephthalate-degrading Bacteria from Jakarta Bay, Indonesia - The Open Biotechnology Journal, accessed on October 23, 2025, https://openbiotechnologyjournal.com/VOLUME/18/ELOCATOR/e18740707280343/
135. Insights into the biodegradation of polycaprolactone through genomic analysis of two plastic-degrading Rhodococcus bacteria - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1284956/full
136. Factors affecting the rate of biodegradation of plastics - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Factors-affecting-the-rate-of-biodegradation-of-plastics_fig2_322466876
137. The Effect of PH Temperature On Plastic | PDF | Biodegradation | Polyethylene - Scribd, accessed on October 23, 2025, https://www.scribd.com/document/724337189/The-effect-of-pH-temperature-on

-plastic
138. A critical review on temperature-mediated marine plastic biodegradation - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC12418820/
139. Effect of pH (6–9) and temperature (25–35 °C) on polyethylene film... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Effect-of-pH-6-9-and-temperature-25-35-C-on-polyethylene-film-carbonyl-index-in-the_fig3_347332055
140. The effect of pH-temperature on plastic allowance for Low-Density Polyethylene (LDPE) by Thiobacillus sp. and Clostridium sp. - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/356419375_The_effect_of_pH-temperature_on_plastic_allowance_for_Low-Density_Polyethylene_LDPE_by_Thiobacillus_sp_and_Clostridium_sp
141. Microbial degradation of polyethylene (PE) - SciSpace, accessed on October 23, 2025, https://scispace.com/pdf/microbial-degradation-of-polyethylene-pe-ecn0bq19zo.pdf
142. BIODEGRADATION OF POLYETHYLENE BY BACTERIAL STRAINS ISOLATED FROM KASHMIR CAVE, BUNER, PAKISTAN - National Speleological Society, accessed on October 23, 2025, https://caves.org/pub/journal/PDF/V79/cave-79-01-73.pdf
143. The Effects of Molecular Weight on the Crystallinity of Polyethylene - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/j150570a015
144. How Biodegradation Additives Work - Science | HowStuffWorks, accessed on October 23, 2025, https://science.howstuffworks.com/environmental/green-science/biodegradation-additives.htm
145. Microbial and Enzymatic Degradation of Synthetic Plastics - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
146. Effect of different pretreatment methods (UV treatment, heat treatment... | Download Scientific Diagram - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Effect-of-different-pretreatment-methods-UV-treatment-heat-treatment-and-chemical_fig1_352648524
147. UV Pretreatment Impairs the Enzymatic Degradation of Polyethylene Terephthalate - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7199389/
148. (PDF) Analytical review on Biodegradation of Plastics - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/344498876_Analytical_review_on_Biodegradation_of_Plastics
149. Analytical Tools to Assess Polymer Biodegradation: A Critical Review and Recommendations (Journal Article) - OSTI, accessed on October 23, 2025,

https://www.osti.gov/pages/biblio/2438502
150. A mini-review: current advances in polyethylene biodegradation - OUCI, accessed on October 23, 2025, https://ouci.dntb.gov.ua/en/works/4YoaDRM9/
151. Mussel-Inspired Universal Anti-Fogging Coating Based on Maleic Anhydride Copolymers with Customizable Structural Design - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/pdf/10.1021/acs.langmuir.5c03651
152. The FTIR spectra of the degraded polyethylene (LDPE strips and pellets)... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/The-FTIR-spectra-of-the-degraded-polyethylene-LDPE-strips-and-pellets-by-bacterial_fig3_303872553
153. XPS and FTIR Studies of Polytetrafluoroethylene Thin Films Obtained by Physical Methods, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/11/10/1629
154. 13C-Stable Isotope Labeling - UNT Research - University of North Texas, accessed on October 23, 2025, https://research.unt.edu/resources/research-core-facilities/bioanalytical-facility/services-and-fees/13c-stable-isotope-labeling.html
155. Poly(ethylene oxide), C13-labelled - Polymer Source, accessed on October 23, 2025, https://www.polymersource.ca/index.php?route=product/category&path=1_11_1371
156. Methods of Analyses for Biodegradable Polymers: A Review - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9694517/
157. Unraveling Plastic Biodegradability: Scientific Testing and Environmental Impact - YouTube, accessed on October 23, 2025, https://www.youtube.com/watch?v=Yx8NG5ZK6fA
158. Experimental Optimization Study on Pumping Pipeline Transportation Performance of Pure Gangue Slurry Filling Material - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1996-1944/18/20/4788
159. (PDF) Polyethylene biodegradation: A multifaceted approach - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/390506954_Polyethylene_biodegradation_A_multifaceted_approach
160. Biodegradability of Synthetic Plastics – A Review - SciSpace, accessed on October 23, 2025, https://scispace.com/pdf/biodegradability-of-synthetic-plastics-a-review-54b6joc7fr.pdf
161. Expression and engineering of PET-degrading enzymes from Microbispora, Nonomuraea, and Micromonospora | Applied and Environmental Microbiology - ASM Journals, accessed on October 23, 2025, https://journals.asm.org/doi/10.1128/aem.00632-23
162. Full article: Enhancing plastic biodegradation process: strategies and opportunities, accessed on October 23, 2025, https://www.tandfonline.com/doi/full/10.1080/07388551.2023.2170861

163. A Bibliometric Analysis of Research Trends in Biodegradation of Plastics - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/14/13/2642