The Microbial Biodegradation of Polyethylene: From Recalcitrance to Remediation

Abstract
Polyethylene (PE) represents a paradoxical triumph of modern polymer chemistry: a material engineered for durability, yet predominantly used for transient applications, resulting in its accumulation as a persistent pollutant on a planetary scale. Its inherent recalcitrance, rooted in a hydrophobic, high-molecular-weight carbon-carbon backbone, makes it exceptionally resistant to microbial degradation. This review critically examines the current understanding of PE biodegradation, framing it as a synergistic process initiated by abiotic weathering—primarily photo- and thermal-oxidation—which primes the polymer for subsequent microbial attack. We deconstruct the microbial degradation cascade into four key stages: biodeterioration, biofragmentation, assimilation, and mineralization, emphasizing that conclusive proof of biodegradation requires evidence of the latter stages. A central theme is the critical appraisal of analytical methodologies, where we highlight the limitations of conventional techniques and advocate for the adoption of definitive methods, such as stable isotope tracing, to overcome the field's historical "crisis of evidence." We survey the key microbial players—notably synergistic consortia of bacteria and fungi from the 'plastisphere'—and their enzymatic toolkits, which appear to follow an "oxidize-then-hydrolyze" strategy. Finally, we cast a forward-looking perspective on the field's trajectory, which is shifting from bioprospecting to bioengineering. The convergence of multi-omics, synthetic biology, and enzyme engineering promises to transform PE waste from an environmental liability into a valuable feedstock for a circular bioeconomy, heralding a new era of engineered biological solutions for plastic remediation and upcycling.

Introduction: The Polyethylene Paradox

The Anthropocene is marked by novel geological signatures, none more ubiquitous than plastic waste. Global plastics production has surged to over 460 million metric tons annually, with polyethylene (PE), in its various forms, constituting a major fraction of this output.[1] In 2023, low-density (LDPE/LLDPE) and high-density (HDPE/MDPE) polyethylene together accounted for over 26% of the 413.8 million tonnes of plastics produced globally. This

industrial output is intrinsically linked to the fossil fuel economy, as PE is a synthetic organic polymer derived from the cracking of hydrocarbons like ethane.[2] The scale of production has created a systemic crisis in waste management. In 2024, it is estimated that a staggering 91% of all plastic waste is not recycled, but is instead consigned to landfills or leaks directly into natural ecosystems.[4] This culminates in an estimated 11 to 20 million metric tons of plastic entering the oceans each year, a testament to a global infrastructure overwhelmed by its own material output.[2]

This crisis is rooted in the polyethylene paradox: the material's defining chemical characteristic is its exceptional durability, yet approximately 40% of its production is directed toward single-use applications such as packaging films and bags.[4] This profound mismatch between a material's designed permanence and its ephemeral use-case is a primary driver of global pollution. The consequences of this systemic failure are encapsulated by the concept of a "Plastic Overshoot Day," the date on which the volume of plastic waste generated surpasses the world's capacity for its management.[6] In 2024, this threshold was crossed on September 5th, with an estimated 69.5 million tons of plastic waste projected to be mismanaged and released into the environment by the year's end.[6] This reality underscores that the plastic problem is not merely a consequence of consumer behavior but a systemic failure of a linear industrial model.

With conventional mechanical and chemical recycling methods proving insufficient to manage this deluge of waste, microbial biodegradation has emerged as a critical scientific frontier.[7] The prospect of harnessing microorganisms to break down and potentially valorize this vast, untapped carbon resource offers a pathway toward a circular bioeconomy. However, the path to realizing this vision is fraught with challenges, beginning with the polymer's innate resistance to biological attack. This review critically evaluates the current state of PE biodegradation research, dissecting the fundamental physicochemical barriers to degradation, scrutinizing the methodologies used to evidence it, and charting a course toward engineered biological systems for both remediation and upcycling.[9]

The Physicochemical Fortress: Why Polyethylene Resists Degradation

The remarkable persistence of polyethylene in the environment is not accidental; it is a direct consequence of a molecular architecture optimized for chemical and physical stability. Understanding these inherent properties is fundamental to appreciating the challenges of, and developing strategies for, its biodegradation.

The Inert Carbon-Carbon Backbone

At its core, polyethylene is a simple polyolefin, a long-chain alkane with the repeating monomeric unit $(-CH_2-CH_2-)_n$.[3] Its backbone is composed exclusively of non-polar, high-energy carbon-carbon ($C-C$) and carbon-hydrogen ($C-H$) single bonds. This structure lacks the reactive functional groups, such as the ester or amide linkages found in polyesters (e.g., PET) and polyamides, that are susceptible to attack by the hydrolytic enzymes common in microbial metabolism.[11] This chemical inertness renders the polymer highly hydrophobic and resistant to enzymatic cleavage, forming the primary line of defense against biological degradation.[13]

High Molecular Weight and Entanglement

Commercial grades of PE possess very high molecular weights, often in the range of tens to hundreds of thousands of Daltons.[11] The resulting long, entangled polymer chains are far too large to be transported across microbial cell membranes for intracellular processing.[14] Consequently, any biodegradation must be initiated by extracellular enzymes secreted by microorganisms. This reliance on extracellular action is severely hampered by the polymer's other recalcitrant features, creating a significant kinetic barrier.[7]

Crystallinity as a Physical Barrier

Polyethylene is a semi-crystalline polymer, comprising both highly ordered, densely packed crystalline lamellae and disordered, loosely packed amorphous regions.[13] These crystalline domains present a formidable physical barrier, as the tightly packed chains are sterically inaccessible to the active sites of microbial enzymes.[12] Biodegradation is therefore thought to initiate preferentially in the more accessible amorphous regions, which act as points of entry for enzymatic attack.[16] The ratio of crystalline to amorphous content is thus a critical determinant of a given PE sample's susceptibility to biodegradation.

This leads to a "hierarchy of recalcitrance" governed by the polymer's specific molecular architecture. The structural differences between major PE variants are not trivial; they directly

influence crystallinity and, by extension, biodegradability.

- **High-Density Polyethylene (HDPE)** is produced via catalytic polymerization at lower pressures, resulting in a linear polymer with minimal branching. This linearity allows for efficient, tight packing of polymer chains, leading to high crystallinity and high density.[3]
- Low-Density Polyethylene (LDPE) is produced via free-radical polymerization at high pressure and temperature, which introduces significant long- and short-chain branching. This branching disrupts the regular packing of chains, resulting in lower crystallinity (typically 50–60%) and lower density.3
  The causal link is direct: increased branching leads to lower crystallinity, which increases the proportion of accessible amorphous regions, thereby enhancing the potential for microbial degradation. This establishes a predictable order of susceptibility: LDPE > LLDPE > HDPE.3 This hierarchy is a critical factor that must be considered in experimental design, as studies that fail to specify the precise type of PE substrate are difficult to interpret and compare.

The Role of Additives

Commercial plastics are complex formulations, not pure polymers. They contain a suite of chemical additives—such as antioxidants, UV stabilizers, and plasticizers—that are incorporated to enhance performance and prevent degradation during processing and use.[11] These additives, designed to thwart the very oxidative processes that initiate biodegradation, can inadvertently inhibit both abiotic and biotic degradation pathways.[13] This means that microorganisms are not attacking a uniform substrate but a complex, variable composite. The specific formulation of a plastic product can therefore be as significant a variable as the microbial species under investigation, creating a "moving target" for biodegradation research and complicating the comparison of results across different studies.

Table 1: Physicochemical Properties of PE Variants and Their Influence on Biodegradability

Polymer Type	Key Structural Feature	Typical Crystallinity (%)	Density (g/cm3)	Primary Implication for Biodegradability
HDPE	Linear chains,	High (>90%)	>0.940	Low

	minimal branching			accessibility due to high chain packing; most resistant.
LLDPE	Linear backbone, short uniform branches	Intermediate	0.915–0.940	Branching disrupts packing, increasing amorphous content over HDPE.
LDPE	Highly branched (long and short chains)	Low (50–60%)	<0.930	Highest proportion of accessible amorphous regions; most susceptible.

Data synthesized from.[3]

Breaching the Walls: The Abiotic-Biotic Interface

Given its formidable physicochemical defenses, pristine polyethylene is largely bio-inert. In natural environments, microbial degradation is not a standalone process but the second act in a two-part degradation sequence. The essential first act is an abiotic "priming" phase, a period of weathering driven by environmental forces that chemically and physically alters the polymer, creating vulnerabilities that microorganisms can then exploit.[20] This synergistic interplay between abiotic and biotic factors is a cornerstone of PE degradation.

The primary mechanisms of this abiotic priming are photo-oxidation and thermal oxidation.

- **Photo-oxidation** is initiated by ultraviolet (UV) radiation from sunlight. The energy from UV photons is sufficient to cleave the high-energy $C-H$ and $C-C$ bonds in the polymer backbone, generating highly reactive free radicals ($R\cdot$).[21] In the presence of atmospheric oxygen, these radicals trigger a cascade of autocatalytic reactions, leading to the formation of hydroperoxides ($ROOH$) on the polymer chain.[21]

- **Thermal oxidation** follows fundamentally similar free-radical pathways but is driven by thermal energy rather than photons.[21] Elevated temperatures, such as those on sun-exposed surfaces, accelerate these reactions.

The decomposition of the unstable hydroperoxide intermediates results in critical chemical transformations of the polymer. Through complex reaction pathways, including the Norrish Type I and Type II reactions, a variety of oxygen-containing functional groups are introduced onto the polymer backbone.[21] These are collectively known as carbonyl compounds and include ketones ($C=O$), aldehydes ($-CHO$), carboxylic acids ($-COOH$), and esters ($-COOR$).[21] This process has two profound consequences for biodegradability:

1. **Chain Scission:** The oxidative reactions lead to the cleavage of the polymer backbone, breaking the long macromolecules into shorter oligomeric fragments. This reduction in molecular weight is a crucial step toward generating molecules small enough for microbial assimilation.[21]
2. **Increased Hydrophilicity:** The introduction of polar carbonyl groups onto the intrinsically non-polar, hydrophobic PE surface dramatically increases its surface energy and hydrophilicity. This chemical modification is essential for enabling the attachment of microbial cells and the effective binding of their extracellular enzymes.[11]

This understanding reframes the common laboratory practice of pre-treating PE samples with UV or heat. Rather than being an artificial enhancement, such pre-treatment is a necessary and valid simulation of the natural weathering processes that PE undergoes in the environment.[13] Experiments conducted on pristine, unweathered PE test an ecologically irrelevant scenario and may produce misleadingly negative results. The initial abiotic degradation can also create a positive feedback loop, where chain scission leads to embrittlement and micro-cracking, increasing the polymer's surface-area-to-volume ratio, which in turn exposes more material to further abiotic and subsequent biotic attack.

Figure 1: Schematic of the Synergistic Abiotic and Biotic Degradation Pathway of PE.

Caption: The degradation of polyethylene in the environment is a two-stage process. ***(A) Abiotic Priming:*** *Environmental factors such as UV radiation and heat initiate photo- and thermal-oxidation. This process generates free radicals on the polymer backbone, leading to the incorporation of oxygen and the formation of carbonyl groups. This abiotic weathering results in chain scission and increases the hydrophilicity of the polymer surface.* ***(B) Biotic Attack:*** *The chemically modified surface becomes a viable substrate for microbial colonization. Microorganisms form a biofilm and secrete extracellular enzymes (e.g., oxidoreductases, hydrolases) that attack the newly formed functional groups, leading to further fragmentation of the polymer into oligomers and monomers that can be assimilated by*

the cells.

The Microbial Degradation Cascade

Once a polyethylene surface has been sufficiently weathered, a complex biological process can commence. The complete conversion of the polymer's carbon into microbial biomass and simple inorganic molecules is conceptualized as a four-stage cascade: biodeterioration, biofragmentation, assimilation, and mineralization.[20] It is imperative to recognize that this is a sequential process that can be arrested at any point; only the verified completion of the final stage, mineralization, constitutes true and complete biodegradation.[20] This framework serves not only as a biological model but also as a methodological guide, establishing a series of escalating evidentiary hurdles that researchers must clear to substantiate claims of biodegradation.

Stage 1: Biodeterioration

This initial stage encompasses the physical and chemical changes to the polymer resulting from microbial colonization. Microorganisms first adhere to the modified polymer surface, a process facilitated by the increased hydrophilicity from abiotic weathering.[20] They then proliferate and form a biofilm, a complex community of cells encased within a self-produced matrix of extracellular polymeric substances (EPS) composed of polysaccharides, proteins, lipids, and nucleic acids.[14] This colonization creates a unique microenvironment at the polymer-biofilm interface, concentrating cells and their secreted enzymes. The metabolic activity within the biofilm leads to superficial modifications of the polymer, such as pitting, cracking, erosion, and discoloration, which can be visualized using microscopy.[20] However, these changes primarily affect the material's bulk properties and do not necessarily involve cleavage of the polymer backbone.

Stage 2: Biofragmentation

This stage, also known as depolymerization, marks the first direct enzymatic attack on the polymer's covalent structure. Microbes within the biofilm secrete a suite of extracellular enzymes that catalytically cleave the long polymer chains into shorter fragments—oligomers,

dimers, and ultimately monomers.[20] For polyethylene, this is the most challenging and rate-limiting enzymatic step, requiring powerful oxidative enzymes to break the robust $C-C$ bonds.[7] This process is directly responsible for the reduction in the polymer's average molecular weight, a key indicator that degradation is proceeding beyond superficial deterioration.[20]

Stage 3: Assimilation

The low-molecular-weight oligomers and monomers generated during biofragmentation are small enough to be transported across the microbial cell membrane into the cytoplasm.[14] Once inside the cell, these carbon-rich molecules are funneled into central metabolic pathways. For PE-derived fragments, which are structurally analogous to fatty acids, this likely involves pathways such as β-oxidation.[9] Through these catabolic routes, the cell harvests energy (in the form of ATP) and generates precursor molecules (e.g., acetyl-CoA) that are used for the synthesis of new biomass—cellular components like lipids, proteins, and nucleic acids.[20] This is the critical stage where carbon from the synthetic polymer is incorporated into living matter.

Stage 4: Mineralization

Mineralization is the ultimate and definitive stage of biodegradation, representing the complete metabolic processing of the original organic material.[20] It occurs concurrently with assimilation as the assimilated carbon is fully catabolized and converted into simple, stable inorganic end-products. Under aerobic conditions, the final products are carbon dioxide (CO_2) and water (H_2O).[14] In anaerobic environments, methane (CH_4) may also be produced in addition to CO_2.[20] The quantitative measurement of these gaseous products, particularly the evolution of CO_2 derived directly from the polymer's carbon backbone, provides the most robust and unambiguous evidence that complete biodegradation has occurred.

The Plastisphere's Key Players and Their Enzymatic Toolkit

The surface of plastic debris in the environment is not a sterile substrate but a vibrant, novel ecosystem known as the "plastisphere".[26] This niche exerts unique selective pressures, fostering the evolution of microbial communities with the potential to utilize this recalcitrant carbon source.[5] Bioprospecting within these mature plastisphere communities, rather than from general environmental samples, is therefore a more targeted strategy for discovering potent plastic-degrading organisms and enzymes.

The Power of the Collective: Microbial Consortia

While early research often focused on isolating single microbial strains with degradative abilities, a growing body of evidence indicates that mixed-species microbial consortia are significantly more effective at degrading complex polymers like PE.[30] This enhanced efficacy arises from ecological synergies within the community. These can include:

- **Metabolic Division of Labor:** Different species specialize in sequential steps of the degradation cascade. For example, one organism may perform the initial surface oxidation, producing intermediates that are then metabolized by other members of the community.[30]
- **Cross-feeding:** The metabolic byproducts of one species serve as substrates for another, creating a robust food web that ensures more complete breakdown of the polymer.[26]
- **Expanded Enzymatic Repertoire:** A diverse consortium can deploy a broader and more complementary array of enzymes than any single organism, allowing it to attack a wider range of chemical bonds and structures.[30]

Key Microbial Taxa Implicated in PE Degradation

A wide variety of bacteria and fungi have been isolated from diverse environments—including landfill soil, compost, marine waters, and insect guts—and implicated in PE degradation.[17]

- **Bacteria:** Prominent genera reported to exhibit PE-degrading activity include Gram-positive Actinobacteria such as *Rhodococcus* (e.g., *R. ruber*), *Streptomyces*, and Firmicutes like *Bacillus* and *Brevibacillus*. Among Gram-negative bacteria, Proteobacteria such as *Pseudomonas*, *Acinetobacter*, and *Stenotrophomonas* are frequently cited.[13] In marine environments, hydrocarbon-degrading specialists like *Alcanivorax* have been

identified as key members of the plastisphere.[30]

- **Fungi:** Fungi, particularly those known for their ability to degrade recalcitrant natural polymers like lignin and cutin, are also potent plastic degraders. Commonly reported genera include the ascomycete molds *Aspergillus* (e.g., *A. niger*), *Penicillium*, and *Fusarium*.[7]

Table 2: Prominent Microbial Genera Implicated in PE Biodegradation and Their Isolation Environments

Microbial Genus	Domain	Key Species Example	Typical Isolation Environment
Rhodococcus	Bacteria	*R. ruber*	Soil, Marine plastisphere
Pseudomonas	Bacteria	*P. aeruginosa*	Landfill soil, Aquatic environments
Bacillus	Bacteria	*B. subtilis*	Soil, Solid waste dumps
Streptomyces	Bacteria	*S. viridosporus*	Soil, Compost
Brevibacillus	Bacteria	*B. borstelensis*	Soil
Alcanivorax	Bacteria	*A. borkumensis*	Marine plastisphere
Aspergillus	Fungi	*A. niger*	Soil, Plastic dumping sites
Penicillium	Fungi	-	Soil
Fusarium	Fungi	-	Soil

Data compiled from.[13]

The Enzymatic Machinery: An "Oxidize-then-Hydrolyze" Strategy

The degradation of PE's inert C-C backbone appears to follow a two-step enzymatic strategy, as no single enzyme has been identified that can efficiently depolymerize the pristine polymer.[30] This strategy mirrors the broader abiotic-biotic synergy: an initial oxidative attack creates functional groups that can then be cleaved by hydrolases.

1. **Initial Oxidative Attack:** This is the rate-limiting step, requiring powerful extracellular oxidoreductases to introduce oxygen into the non-activated hydrocarbon chain. The enzymes implicated are often those involved in the degradation of other recalcitrant molecules like lignin or hydrocarbons. This provides a strong mechanistic link to known metabolic pathways, suggesting that PE degradation is an extension of alkane metabolism. Key enzyme classes include [27]:
    - **Laccases and Peroxidases:** Lignin-degrading enzymes like laccases, manganese peroxidases (MnP), and lignin peroxidases (LiP) generate highly reactive radicals that can non-specifically oxidize the PE backbone.[15]
    - **Monooxygenases:** Enzymes that directly incorporate oxygen into C-H bonds are critical. Alkane hydroxylase systems, including alkane monooxygenase (AlkB) and cytochrome P450 monooxygenases (like CYP153), which are canonical enzymes in hydrocarbon degradation, have been repeatedly identified in PE-degrading organisms and their genomes.[14]
2. **Hydrolytic Cleavage:** Once the polymer has been oxidized and contains ester-like or other hydrolysable linkages, a second class of enzymes can act. Extracellular hydrolases, such as **esterases**, **lipases**, and **cutinases**, are thought to cleave these newly formed bonds, fragmenting the polymer chain into smaller, assimilable pieces.[9] Multi-omics studies have confirmed the significant upregulation of these hydrolases in microbes grown on PE.[41]

A Critical Appraisal of Analytical Methodologies: The Challenge of Proof

Despite decades of research, the field of polyethylene biodegradation is characterized by a significant "crisis of evidence." A lack of standardized experimental protocols and the prevalent use of analytical methods that provide only indirect or ambiguous data have led to a literature filled with conflicting and often unsubstantiated claims.[23] Establishing rigorous, verifiable proof of biodegradation is the central challenge, and a critical understanding of the limitations of each analytical technique is essential for advancing the field. Progress requires

moving up a "hierarchy of proof," from weak, circumstantial evidence to strong, definitive verification.

Many studies rely on methods that demonstrate only superficial changes (biodeterioration) and erroneously equate this with complete biodegradation. This has created significant confusion and impeded progress. The field is in urgent need of a standardized reporting framework, analogous to the MIQE (Minimum Information for Publication of Quantitative Real-Time PCR Experiments) guidelines, to ensure that experiments are reproducible, comparable, and supported by an appropriate level of evidence. Such a "MIPBE" (Minimum Information for a PE Biodegradation Experiment) standard would mandate detailed reporting of the polymer's properties (type, Mw, crystallinity, additives), pre-treatment conditions, and, crucially, the use of multiple, orthogonal analytical techniques.

The most rigorous methods, particularly stable isotope tracing, have reported environmentally slow but scientifically significant mineralization rates (e.g., up to 1.2% per year).[43] This stands in stark contrast to more optimistic claims from studies using less reliable techniques, suggesting that many high degradation rates reported in the literature may be artifacts of flawed methodology, such as the leaching of additives rather than true polymer degradation. This discrepancy underscores the necessity of both employing gold-standard techniques and pursuing bioengineering to accelerate these naturally slow processes.

Table 3: Critical Comparison of Analytical Techniques for Assessing PE Biodegradation: Principles, Insights, and Caveats

Technique	Principle of Measurement	Biodegradation Stage Assessed	Key Insights Provided	Critical Limitations & Potential for Misinterpretation
SEM / AFM	High-resolution surface imaging	1. Biodeterioration	Visual evidence of surface erosion, pits, cracks, holes, and biofilm colonization.	**Cannot distinguish biotic from abiotic effects.** Provides no information on chemical changes or molecular

				weight reduction. Often misinterpreted as proof of full biodegradation.[20]
Gravimetric Analysis	Measurement of mass reduction	1-2. Deterioration/ Fragmentation	A simple, quantitative measure of overall material loss.	**Highly prone to artifacts.** Weight loss can be due to leaching of additives, oligomers, or incomplete removal of biofilm, not backbone cleavage. Insensitive to small changes.[20]
FTIR Spectroscopy	Detection of chemical bond vibrations	1-2. Deterioration/ Fragmentation	Identifies formation of new functional groups, especially carbonyls ($C=O$) indicative of oxidation. The "carbonyl index" is used to quantify oxidation.	**Most commonly misinterpreted technique.** Spectral signals from biofilm components (proteins, lipids) directly overlap with and obscure polymer oxidation signals. Without meticulous sample

				cleaning, results are unreliable.[46]
GPC / SEC	Separation of molecules by hydrodynamic volume	2. Biofragmentation	Provides molecular weight distribution (M_w, M_n). A decrease in average molecular weight is strong evidence of polymer chain scission.	Requires polymer solubilization, which for PE necessitates high temperatures and harsh solvents (HT-GPC). The analysis itself can induce thermal degradation, confounding results.[48]
Respirometry	Measurement of evolved gases (CO_2, CH_4)	4. Mineralization	Quantifies the rate and extent of conversion of polymer carbon to inorganic end-products, providing evidence of complete metabolic processing.	Can be confounded by background respiration from other carbon sources in the media or inoculum. The slow rate of PE degradation can make the signal difficult to distinguish from baseline noise.[50]
^{13}C Isotope Tracing	Tracking of a ^{13}C label from PE into products	3-4. Assimilation & Mineralization	**The unequivocal gold standard.**	Technically demanding, requires synthesis of

			Unambiguously proves that carbon from the PE backbone is converted to $^{13}CO_2$ (mineralization) and incorporated into microbial biomass (^{13}C-lipids, ^{13}C-DNA) (assimilation).[43]	expensive ^{13}C-labeled PE, and specialized analytical instrumentation (e.g., IRMS). Low degradation rates can require long incubation times to generate a detectable signal.[43]

Data synthesized from.[13]

Future Perspectives: Engineering Biological Solutions for a Plastic-Free Future

As the limitations of naturally occurring biodegradation processes become clearer, the frontier of research is decisively shifting from passive bioprospecting to active bioengineering. The future of plastic waste management lies not in finding a single, naturally occurring "super-bug," but in the rational design and construction of highly efficient, specialized biological systems.[9] This new paradigm is being driven by the convergence of enzyme engineering, synthetic biology, and multi-omics technologies.

Enzyme Engineering for Enhanced Performance

Native enzymes discovered in nature are rarely optimized for industrial applications, which often require high stability, efficiency, and specificity under non-natural conditions.[55] Enzyme engineering aims to overcome these limitations:

- **Rational Design:** Leveraging detailed 3D structural information of an enzyme, researchers can use computational modeling to predict specific amino acid mutations that will enhance desired properties, such as widening the substrate-binding pocket to better accommodate a bulky polymer or strengthening intramolecular bonds to increase thermostability.[56]
- **Directed Evolution:** This powerful technique mimics natural selection in the laboratory. Large libraries of enzyme variants are created through random or semi-random mutagenesis, and high-throughput screening methods are used to rapidly identify mutants with improved performance. This iterative process has been remarkably successful in improving PET-degrading enzymes and holds immense promise for tailoring the yet-to-be-discovered key PE-oxidizing enzymes for industrial efficacy.[38]

Synthetic Biology for Optimized Hosts and Consortia

Synthetic biology provides the tools to move beyond single enzymes and engineer entire organisms and communities for plastic degradation.

- **Metabolic Engineering:** The genomes of microbial chassis (host organisms like *E. coli* or *P. putida*) can be edited to create cellular factories optimized for plastic degradation. This can involve overexpressing key degradative enzymes, deleting competing metabolic pathways to channel all carbon flux from plastic-derived monomers into a desired product, and enhancing cellular tolerance to toxic intermediates.[10]
- **Designing Synthetic Consortia:** The ecological principle of "division of labor" can be engineered with precision. By assembling synthetic consortia from well-characterized specialist strains, each engineered to perform a single, specific step in the degradation pathway, a highly efficient biological assembly line can be created. The design of these consortia is informed by two complementary approaches [59]:
    - **"Top-Down" Discovery:** Multi-omics tools (metagenomics, metatranscriptomics, metaproteomics) are used to mine natural plastisphere communities to identify the key microbial players, their functional genes, and the metabolic interdependencies that drive effective degradation in nature.[59]
    - **"Bottom-Up" Construction:** Armed with this knowledge, researchers can rationally assemble a consortium from engineered specialist strains, creating a robust and controllable system that surpasses the efficiency of any natural community.[32]

From Degradation to Upcycling

The ultimate ambition of this engineering-driven approach is to reframe plastic waste not as a pollutant to be eliminated but as a valuable feedstock for a circular bioeconomy.[10] Instead of complete mineralization to CO_2, engineered metabolic pathways can be designed to capture the plastic-derived monomers and oligomers and convert them into high-value products. This "bio-upcycling" could transform waste PE into bioplastics (e.g., polyhydroxyalkanoates, PHAs), specialty chemicals, surfactants, or biofuels, thereby creating a closed-loop system that provides a powerful economic incentive for plastic recycling.[9] Such a technology could ultimately disrupt the petrochemical industry by creating a viable alternative to virgin, fossil-fuel-derived feedstocks for chemical manufacturing.

The complexity of these engineering challenges necessitates the integration of artificial intelligence and robotics. AI-driven protein design algorithms can predict optimal enzyme mutations *in silico*, synthetic biology provides the tools to construct the corresponding genetic circuits, and high-throughput robotic platforms can perform the massive screening experiments required for directed evolution and consortium optimization. This triad of technologies will be essential to accelerate the pace of discovery and development in the coming years.

Figure 3: Conceptual Framework for Future Bioengineering Strategies for PE Valorization.

!(figure3_placeholder.png)

Caption: A conceptual framework for the future of polyethylene bioremediation and valorization. The process begins with waste PE, which is first subjected to abiotic pre-treatment (e.g., UV, thermal) to enhance its bioavailability. A "Top-Down" discovery engine utilizes multi-omics to mine natural plastisphere communities for novel plastic-degrading genes and pathways. This knowledge informs a "Bottom-Up" design engine, where AI-assisted protein engineering and synthetic biology are used to create highly efficient enzymes and optimize microbial chassis. These components are assembled into a synthetic microbial consortium within a bioreactor. The process can lead to complete mineralization or, more desirably, to "upcycling," where PE-derived monomers are biotransformed into value-added products, closing the loop on a circular plastic bioeconomy.

Conclusion and 5–10 Year Outlook

The microbial biodegradation of polyethylene stands at a critical juncture. Decades of

research have established that this recalcitrant polymer is not entirely inert to biological activity, but its degradation is a slow, complex process contingent upon a synergistic interplay with abiotic weathering. The field has moved from initial observations of surface deterioration to a more sophisticated understanding of the multi-stage cascade of biofragmentation, assimilation, and mineralization. However, progress has been hampered by a persistent lack of methodological rigor, making it difficult to compare results and validate many of the claims in the literature. The adoption of definitive analytical techniques, particularly stable isotope tracing, is essential for building a robust and reliable foundation of knowledge.

The most promising avenues for future progress lie not in the passive search for a single, miraculous organism, but in the proactive engineering of integrated biological systems. Several major knowledge gaps must be addressed to enable this transition:

- **Enzymology:** The definitive identification and biochemical characterization of the rate-limiting enzymes responsible for the initial oxidation of the PE backbone remains the field's highest priority.
- **In-situ Dynamics:** Quantifying the true rates and mechanisms of PE degradation in complex, real-world environments is crucial for accurate environmental fate modeling and risk assessment.
- **Metabolic Pathways:** The complete metabolic routes for the assimilation and catabolism of PE-derived oligomers within microbial cells are still poorly understood.
- **Impact of Additives:** A systematic investigation into how the diverse chemical additives present in commercial plastics influence microbial activity, enzyme function, and potential toxicity is urgently needed.

Looking ahead, the next 5 to 10 years are poised for transformative advances, driven by the integration of cutting-edge technologies. We predict the following key developments:

1. **AI-Accelerated Discovery:** Machine learning and artificial intelligence will revolutionize the discovery of novel enzymes. By training models on expanding databases of protein structures and functions, researchers will be able to predict highly active and stable PE-oxidizing enzymes *in silico*, drastically reducing the time and cost of experimental screening.
2. **Programmable Microbial Consortia:** Advances in synthetic biology will enable the rational design and construction of robust, multi-strain microbial consortia. These "programmable" systems will feature a clear division of metabolic labor, with specialist strains engineered for each step of the degradation and upcycling pathway, leading to unprecedented efficiency and control.
3. **Demonstration of Pilot-Scale Upcycling:** The focus will shift from laboratory-scale degradation to demonstrating viable upcycling at the pilot scale. We anticipate the first successful integrated biorefinery systems that combine optimized abiotic pre-treatment with engineered microbial consortia to convert real-world, post-consumer PE waste into specific, marketable chemical products like bioplastics or their precursors.

The ultimate vision is a closed-loop, circular bioeconomy for plastics, where polyethylene

waste is no longer viewed as a terminal pollutant but as a valuable and renewable carbon feedstock. While significant scientific and engineering hurdles remain, the foundational technologies and conceptual frameworks are now in place to begin turning this ambitious vision into a tangible reality.

References

1. **Wastedirect.co.uk**. (2024). *Plastic Waste Statistics 2024*. https://wastedirect.co.uk/blog/plastic-waste-statistics/
2. **Safefoodadvocacy.eu**. (2024). *Plastic Overshoot Day 2024: Global Waste Crisis Surpasses Management Capacity*. https://www.safefoodadvocacy.eu/plastic-overshoot-day-2024-global-waste-crisis-surpasses-management-capacity/
3. **Plastics Europe**. (2024). *Plastics – the fast Facts 2024*.(https://plasticseurope.org/wp-content/uploads/2024/11/PE_TheFacts_24_digital-1pager.pdf)
4. **IUCN**. (2024). *Plastic Pollution Issues Brief*. https://iucn.org/sites/default/files/2024-05/plastic-pollution-issues-brief-may-2024-update.pdf
5. **Britannica**. (n.d.). *Polyethylene*. https://www.britannica.com/science/polyethylene
6. **ResearchGate**. (2024). *A REVIEW OF THE IMPLICATIONS OF POLYETHYLENE PLASTICS WHEN UTILIZED AS CHEMICAL STORAGE TANKS*.(https://www.researchgate.net/publication/380876865_A_REVIEW_OF_THE_IMPLICATIONS_OF_POLYETHYLENE_PLASTICS_WHEN_UTILIZED_AS_CHEMICAL_STORAGE_TANKS)
7. **MDPI**. (2023). *A Review of Degradation and Life Prediction of Polyethylene*. Applied Sciences. https://www.mdpi.com/2076-3417/13/5/3045
8. **ResearchGate**. (2007). *Biodegradation of polyethylene and polypropylene*.(https://www.researchgate.net/publication/228090462_Biodegradation_of_polyethylene_and_polypropylene)
9. **ResearchGate**. (2020). *Biodegradation of polyethylene: a brief review*. Applied Biological Chemistry.(https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review)
10. **MDPI**. (2022). *Biodegradation of (Bio)Plastics: A Review*. Polymers. https://www.mdpi.com/2673-6209/3/2/23
11. **Sciencepub.net**. (2010). *Biodegradation ability of Brevibacillus, Pseudomonas, and Rhodococcus spp. in degrading polyethylene*. New York Science Journal. https://www.sciencepub.net/newyork/ny0307/15_2435_ny0307_95_98.pdf
12. **The Pharma Journal**. (2023). *Microbial potential for polyethylene biodegradation: A comprehensive*

review.(https://www.thepharmajournal.com/archives/2023/vol12issue9/PartAB/12-9-168-119.pdf)
13. **ResearchGate**. (2024). *Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production*.(https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production)
14. **bioRxiv**. (2025). *Experimentally evolved bacterial biofilms enhance polyethylene degradation*. https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full-text
15. **PMC NCBI**. (2020). *Challenges with Verifying Microbial Degradation of Polyethylene*. Polymers (Basel). https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
16. **PMC NCBI**. (2020). *Microbial Degradation of Petroleum-Based Plastics*. Frontiers in Microbiology. https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
17. **MDPI**. (2020). *Challenges with Verifying Microbial Degradation of Polyethylene*. Polymers. https://www.mdpi.com/2073-4360/12/1/123
18. **J-STAGE**. (2024). *Biodegradation of polyethylene by an artificial bacterial consortium*. Journal of Society for Microbial Ecology and Disease. https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_article
19. **PMC NCBI**. (2022). *Metagenomics Analysis of a Marine Biofilm Community Growing on Low-Density Polyethylene Reveals the Potential of Planctomycetota in Plastic-Associated Compound Utilization*. Microbiology Spectrum. https://pmc.ncbi.nlm.nih.gov/articles/PMC8941889/
20. **bioRxiv**. (2025). *Experimentally evolved bacterial biofilms enhance polyethylene degradation*. https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full.pdf
21. **MDPI**. (2024). *Biodegradation of Post-Consumer and Virgin Polyesters by Enriched Environmental Microbiomes*. International Journal of Molecular Sciences. https://www.mdpi.com/1422-0067/25/23/12747
22. **Encyclopedia.pub**. (2020). *Challenges with Verifying Microbial Degradation of Polyethylene*. https://encyclopedia.pub/entry/16964
23. **ACS Publications**. (2024). *Biofilm-Mediated Biodegradation of Petropolymers: Mechanisms, Influencing Factors, and Future Directions*. ACS Applied Engineering Materials. https://pubs.acs.org/doi/10.1021/acsaenm.5c00179
24. **ResearchGate**. (2023). *Polyethylene Degradation by Microbes: Bacteria, Fungus: A Review*. Journal of Global Ecology and Environment.(https://www.researchgate.net/publication/371450494_Polyethylene_Degradation_by_Microbes_Bacteria_Fungus_A_Review)
25. **ResearchGate**. (2014). *Microbial degradation and deterioration of polyethylene - A review*. https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
26. **IJSIR**. (2020). *Microbial Degradation of Plastics: A Review*. http://ijsir.in/images/pdf/paper7/paper9.pdf
27. **ResearchGate**. (2013). *A Review on Biodegradation of polythene: The Microbial Approach*. Journal of Bioremediation &

Biodegradation.(https://www.researchgate.net/publication/235682993_A_Review_on_Biodegradation_of_polytheneThe_Microbial_Approach)
28. **ResearchGate**. (2023). *Polyethylene biodegradation: current status and perspectives*. https://www.researchgate.net/publication/371036072_Polyethylene_biodegradation_current_status_and_perspectives
29. **IOSR Journals**. (2024). *Biodegradation of Low-Density Polyethylene (LDPE) by Pseudomonas aeruginosa*. IOSR Journal of Environmental Science, Toxicology and Food Technology.(https://www.iosrjournals.org/iosr-jestft/papers/Vol18-Issue12/Ser-3/C1812031217.pdf)
30. **Frontiers in Microbiology**. (2024). *Biodegradation of low-density polyethylene (LDPE): a comprehensive review of the last five years*. https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
31. **ResearchGate**. (2022). *Gravimetric determination of LDPE bags biodegraded during 30 d static incubation at 25°C*.(https://www.researchgate.net/figure/Gravimetric-determination-of-LDPE-bags-biodegraded-during-30-d-static-incubation-at-25-0_fig2_356713090)
32. **Urban Enviro Tech**. (2022). *Biodegradation of Low-Density Polyethylene (LDPE) plastic by indigenous microbial consortium and fungi*. https://e-journal.trisakti.ac.id/index.php/urbanenvirotech/article/view/10749/pdf
33. **PubMed**. (2020). *Challenges with Verifying Microbial Degradation of Polyethylene*. Polymers (Basel). https://pubmed.ncbi.nlm.nih.gov/31948075/
34. **MDPI**. (2024). *Biodegradation of Low-Density Polyethylene (LDPE) Films by Yeasts Isolated from Mangrove Sediments*. Journal of Marine Science and Engineering. https://www.mdpi.com/1424-2818/16/12/759
35. **PMC NCBI**. (2021). *Biodegradation of low density polyethylene (LDPE) sheet by a novel terrestrial microalga, Uronema africanum Borge*. Scientific Reports. https://pmc.ncbi.nlm.nih.gov/articles/PMC8390665/
36. **PMC NCBI**. (2021). *Composting of biodegradable plastics and the effect of their degradation on the maturation of compost*. Scientific Reports. https://pmc.ncbi.nlm.nih.gov/articles/PMC8585154/
37. **ALS LBL**. (2024). *Use and misuse of FTIR spectroscopy for studying the bio-oxidation of plastics*.(https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf)
38. **ResearchGate**. (2024). *How can I interpret an increase in FTIR spectra baseline for treated HDPE?*.(https://www.researchgate.net/post/How_can_I_interpret_an_increase_in_FTIR_spectra_baseline_for_treated_HDPE)
39. **Wikipedia**. (n.d.). *Gel permeation chromatography*. https://en.wikipedia.org/wiki/Gel_permeation_chromatography
40. **PMC NCBI**. (2020). *Molecular Weight Determination of a Novel Cationic Polymer with Disulfide Linkages and Guanidine Groups by Gel Permeation Chromatography*. Molecules. https://pmc.ncbi.nlm.nih.gov/articles/PMC7032192/
41. **Polymer Char**. (n.d.). *GPC analysis at different flow rates to overcome shear*

degradation. https://polymerchar.com/library/publications/gpc-analysis-at-different-flow-rates-to-overcome-shear-degradation
42. **ResearchGate**. (2016). *Application of gel permeation chromatography to the study of polymer degradation*. https://www.researchgate.net/publication/295922016_Application_of_gel_permeation_chromatography_to_the_study_of_polymer_degradation
43. **ResearchGate**. (2023). *A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber*. Marine Pollution Bulletin.(https://www.researchgate.net/publication/365887571_A_stable_isotope_assay_with_13C-labeled_polyethylene_to_investigate_plastic_mineralization_mediated_by_Rhodococcus_ruber)
44. **PMC NCBI**. (2012). *Optimal design of substrate labeling for 13C metabolic flux analysis*. BMC Systems Biology. https://pmc.ncbi.nlm.nih.gov/articles/PMC3323462/
45. **ResearchGate**. (2019). *PE-MP mineralization in freshwaters*.(https://www.researchgate.net/figure/PE-MP-mineralization-in-freshwaters-A-Different-size-of-13-C-polyethylene-particles_fig1_338189742)
46. **VLIZ**. (2022). *A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber*. Marine Pollution Bulletin. https://www.vliz.be/imisdocs/publications/17/386717.pdf
47. **ECHO Instruments**. (n.d.). *Respirometer ER series*. https://www.echoinstruments.eu/environmental/respirometer-er-series/
48. **EPA**. (1987). *Fate of priority pollutants in publicly owned treatment works*.(https://nepis.epa.gov/Exe/ZyPURL.cgi?Dockey=P100OPFZ.TXT)
49. **ResearchGate**. (2003). *Development and Evaluation of an Online CO2 Evolution Test and a Multicomponent Biodegradation Test System*. Environmental Science & Technology.(https://www.researchgate.net/publication/8415527_Development_and_Evaluation_of_an_Online_CO2_Evolution_Test_and_a_Multicomponent_Biodegradation_Test_System)
50. **VELP**. (n.d.). *RESPIROMETRIC Sensor System 6 for Plastic Biodegradability*. https://www.velp.com/en-us/respirometric-sensor-system-plastic.aspx
51. **ACS Publications**. (2023). *Uncovering Key Enzymes and Metabolic Pathways for Polyethylene Biodegradation by a Rhodococcus Strain Using Proteomics*. Environmental Science & Technology. https://pubs.acs.org/doi/10.1021/acs.est.3c03778
52. **PMC NCBI**. (2023). *Uncovering Key Enzymes and Metabolic Pathways for Polyethylene Biodegradation by a Rhodococcus Strain Using Proteomics*. Environmental Science & Technology. https://pmc.ncbi.nlm.nih.gov/articles/PMC10515485/
53. **ACS Publications**. (2024). *Biochemical Characterization of Putative Plastic Degrading Enzymes from a Marine Bacterial Community*. ACS Omega. https://pubs.acs.org/doi/10.1021/acsomega.4c04843
54. **ResearchGate**. (2023). *Polyethylene-biodegrading Microbes and Their Future Directions*.(https://www.researchgate.net/publication/368256401_Polyethylene-biodegrading_Microbes_and_Their_Future_Directions)

55. **PMC NCBI**. (2021). *Global analysis of plastic-degrading enzymes in the earth microbiome*. Microbial Ecology. https://pmc.ncbi.nlm.nih.gov/articles/PMC8546865/
56. **Taylor & Francis Online**. (2023). *Recent advances in strategies to enhance the biodegradation of plastics*. Critical Reviews in Biotechnology. https://www.tandfonline.com/doi/full/10.1080/07388551.2023.2170861
57. **Frontiers in Microbiology**. (2020). *Enrichment and Identification of Novel Low Density Polyethylene (LDPE) Degrading Bacteria From Landfill and Sewage Treatment Plant Sites*. https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.603210/full
58. **PEDS**. (2024). *Directed evolution of plastic-degrading enzymes*. https://academic.oup.com/peds/article/doi/10.1093/protein/gzae009/7666632
59. **ResearchGate**. (2024). *Metabolic and enzymatic engineering strategies for polyethylene terephthalate degradation and valorization*. https://www.researchgate.net/publication/380546389_Metabolic_and_enzymatic_engineering_strategies_for_polyethylene_terephthalate_degradation_and_valorization
60. **Frontiers in Bioengineering and Biotechnology**. (2024). *Discovery and characterization of two novel polyester hydrolases from Pseudomonas sp. JM16B3*. https://www.frontiersin.org/journals/bioengineering-and-biotechnology/articles/10.3389/fbioe.2024.1349010/full
61. **Preprints.org**. (2025). *Recent Advances in the Discovery and Engineering of Plastic-Degrading Enzymes*. https://www.preprints.org/manuscript/202504.0667/v1/download
62. **PMC NCBI**. (2023). *Harnessing the Power of Enzymes in Plastic Degradation*. International Journal of Molecular Sciences. https://pmc.ncbi.nlm.nih.gov/articles/PMC10526444/
63. **SCIEPublish**. (2024). *Synthetic Biology-guided Biorecycling of Plastic Waste*. https://www.sciepublish.com/article/pii/440
64. **ACS Publications**. (2024). *Bioinspired Strategies for Enzymatic Plastic Degradation and Upcycling*. JACS Au. https://pubs.acs.org/doi/10.1021/jacsau.4c00388
65. **Polytechnique Insights**. (2022). *How synthetic biology could help manage the plastic waste problem*. https://www.polytechnique-insights.com/en/columns/health-and-biotech/how-synthetic-biology-could-help-manage-the-plastic-waste-problem/
66. **ResearchGate**. (2024). *Bacterial biodegradation of synthetic plastics: a review*. Bulletin of the National Research Centre.(https://www.researchgate.net/publication/383787620_Bacterial_biodegradation_of_synthetic_plastics_a_review)
67. **mBio**. (2021). *Global analysis of plastic-degrading enzymes in the earth microbiome*. https://journals.asm.org/doi/10.1128/mbio.02155-21
68. **PMC NCBI**. (2023). *Biodegradation of plastics and microplastics: A comprehensive review on the mechanisms and the influencing factors*. Journal of Hazardous Materials. https://pmc.ncbi.nlm.nih.gov/articles/PMC10386651/
69. **PubMed**. (2025). *Exploring biodegradation limits of n-alkanes as polyethylene models using multi-omics approaches*. Journal of Hazardous Materials.

https://pubmed.ncbi.nlm.nih.gov/40222247/
70. **University of Portsmouth Research Portal**. (2024). *The exploration of plastic-degrading bacteria using multi-omic approaches*.(https://researchportal.port.ac.uk/en/studentTheses/the-exploration-of-plastic-degrading-bacteria-using-multi-omic-ap)
71. **DiVA portal**. (2024). *Polyethylene biodegradation: A multifaceted approach*.(https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf)
72. **Frontiers in Microbiology**. (2023). *Current status and future prospects of synthetic microbial consortia for polyethylene degradation*. https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
73. **PubMed**. (2021). *A multi-OMIC characterisation of biodegradation and microbial community succession within the PET plastisphere*. The ISME Journal. https://pubmed.ncbi.nlm.nih.gov/34154652/

You can download this report in the following formats:

- (placeholder_pdf_link.pdf)
- (placeholder_word_link.docx)

Works cited

1. Plastics – the fast Facts 2024, accessed on October 23, 2025, https://plasticseurope.org/wp-content/uploads/2024/11/PE_TheFacts_24_digital-1pager.pdf
2. PLASTIC POLLUTION - IUCN, accessed on October 23, 2025, https://iucn.org/sites/default/files/2024-05/plastic-pollution-issues-brief-may-2024-update.pdf
3. Polyethylene (PE) | Properties, Structures, Uses, & Facts | Britannica, accessed on October 23, 2025, https://www.britannica.com/science/polyethylene
4. Plastic Waste Statistics & Trends (UPDATED 2025), accessed on October 23, 2025, https://wastedirect.co.uk/blog/plastic-waste-statistics/
5. The biochemical mechanisms of plastic biodegradation - Oxford Academic, accessed on October 23, 2025, https://academic.oup.com/femsre/article/48/6/fuae027/7876491
6. Plastic Overshoot Day 2024: Global Waste Crisis Surpasses Management Capacity | SAFE, accessed on October 23, 2025, https://www.safefoodadvocacy.eu/plastic-overshoot-day-2024-global-waste-crisis-surpasses-management-capacity/
7. Polyethylene Degradation by Microbes (Bacteria & Fungus): A Review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/371450494_Polyethylene_Degradation_by_Microbes_Bacteria_Fungus_A_Review
8. Microbial degradation of plastic-A brief review - Pure and Applied Biology (PAB), accessed on October 23, 2025,

http://www.thepab.org/files/2022/June-2022/PAB-MS-2104-089.pdf
9. Polyethylene-biodegrading Microbes and Their Future Directions ..., accessed on October 23, 2025, https://www.researchgate.net/publication/368256401_Polyethylene-biodegrading_Microbes_and_Their_Future_Directions
10. Synthetic Biology Boosts the Biological Depolymerization and ..., accessed on October 23, 2025, https://www.sciepublish.com/article/pii/440
11. (PDF) Biodegradation of polyethylene and polypropylene, accessed on October 23, 2025, https://www.researchgate.net/publication/228090462_Biodegradation_of_polyethylene_and_polypropylene
12. Microbial and Enzymatic Degradation of Synthetic Plastics - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
13. (PDF) Biodegradation of polyethylene: a brief review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
14. MICROBIAL DEGRADATION OF PLASTICS: A REVIEW - IJSIR, accessed on October 23, 2025, http://ijsir.in/images/pdf/paper7/paper9.pdf
15. Biodegradation of Unpretreated Low-Density Polyethylene (LDPE) by Stenotrophomonas sp. and Achromobacter sp., Isolated From Waste Dumpsite and Drilling Fluid - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.603210/full
16. Biodegradation of polyethylene: a brief review - SciSpace, accessed on October 23, 2025, https://scispace.com/pdf/biodegradation-of-polyethylene-a-brief-review-315bl64neh.pdf
17. Microbial and Enzymatic Degradation of Synthetic Plastics - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.580709/full
18. What is High-Density Polyethylene (HDPE) plastic, and what are its key properties and uses? | Wyzant Ask An Expert, accessed on October 23, 2025, https://www.wyzant.com/resources/answers/948107/what-is-high-density-polyethylene-hdpe-plastic-and-what-are-its-key-propert
19. (PDF) A REVIEW OF THE IMPLICATIONS OF POLYETHYLENE PLASTICS WHEN UTILIZED AS CHEMICAL STORAGE TANKS - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/380876865_A_REVIEW_OF_THE_IMPLICATIONS_OF_POLYETHYLENE_PLASTICS_WHEN_UTILIZED_AS_CHEMICAL_STORAGE_TANKS
20. Biodegradation of Polymers: Stages, Measurement, Standards and ..., accessed on October 23, 2025, https://www.mdpi.com/2673-6209/3/2/23

21. A Review of Degradation and Life Prediction of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2076-3417/13/5/3045
22. Ecotoxicological Impact of Bioplastics Biodegradation: A Comprehensive Review - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2227-9717/11/12/3445
23. Challenges with Verifying Microbial Degradation of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/12/1/123
24. Harnessing Biofilm-Mediated Plastic Biodegradation: Innovating Smart Material Design, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acsaenm.5c00179
25. Microbes mediated polyethylene biodegradation for environmental sustainability - The Pharma Innovation Journal, accessed on October 23, 2025, https://www.thepharmajournal.com/archives/2023/vol12issue9/PartAB/12-9-168-119.pdf
26. Synergistic biodegradation of polyethylene by experimentally evolved bacterial biofilms - bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full.pdf
27. Plastic-Degrading Microbial Consortia from a Wastewater Treatment Plant | MDPI, accessed on October 23, 2025, https://www.mdpi.com/1422-0067/25/23/12747
28. Biodegradability of polyethylene by Brevibacillus, Pseudomonas, and Rhodococcus spp., accessed on October 23, 2025, https://www.sciencepub.net/newyork/ny0307/15_2435_ny0307_95_98.pdf
29. Plastic-Degrading Potential across the Global Microbiome Correlates with Recent Pollution Trends - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8546865/
30. (PDF) Microbial Consortia: Synergistic Effects on Plastic ..., accessed on October 23, 2025, https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production
31. Polyethylene Biodegradation by an Artificial Bacterial Consortium: *Rhodococcus* as a Competitive Plastisphere Species - j-stage, accessed on October 23, 2025, https://www.jstage.jst.go.jp/article/jsme2/39/3/39_ME24031/_article
32. Polyethylene biodegradation - DiVA portal, accessed on October 23, 2025, https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf
33. Synergistic biodegradation of polyethylene by experimentally evolved bacterial biofilms, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.04.01.646683v1.full-text
34. (PDF) A Review on Biodegradation of polythene:The Microbial ..., accessed on October 23, 2025, https://www.researchgate.net/publication/235682993_A_Review_on_Biodegradation_of_polytheneThe_Microbial_Approach
35. Challenges with Verifying Microbial Degradation of Polyethylene - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
36. Microbial degradation and deterioration of polyethylene – A review | Request PDF,

accessed on October 23, 2025, https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
37. Microbial Consortiums of Putative Degraders of Low-Density ... - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8941889/
38. Plastic-Degrading Enzymes as Sustainable Solutions for Plastic Waste - Preprints.org, accessed on October 23, 2025, https://www.preprints.org/manuscript/202504.0667/v1/download
39. Characterization of Potential Plastic-Degradation Enzymes from Marine Bacteria | ACS Omega - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acsomega.4c04843
40. Exploring biodegradation limits of n-alkanes as polyethylene models using multi-omics approaches - PubMed, accessed on October 23, 2025, https://pubmed.ncbi.nlm.nih.gov/40222247/
41. Polyethylene Degradation by a Rhodococcous Strain Isolated from Naturally Weathered Plastic Waste Enrichment | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.3c03778
42. Polyethylene Degradation by a Rhodococcous Strain Isolated from Naturally Weathered Plastic Waste Enrichment - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10515485/
43. (PDF) A stable isotope assay with 13C-labeled polyethylene to ..., accessed on October 23, 2025, https://www.researchgate.net/publication/365887571_A_stable_isotope_assay_with_13C-labeled_polyethylene_to_investigate_plastic_mineralization_mediated_by_Rhodococcus_ruber
44. A stable isotope assay with 13C-labeled polyethylene to investigate plastic mineralization mediated by Rhodococcus ruber, accessed on October 23, 2025, https://www.vliz.be/imisdocs/publications/17/386717.pdf
45. Gravimetric determination of LDPE bags biodegraded during 30-d static... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Gravimetric-determination-of-LDPE-bags-biodegraded-during-30-d-static-incubation-at-25-0_fig2_356713090
46. Use and misuse of FTIR spectroscopy for studying the bio-oxidation ..., accessed on October 23, 2025, https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf
47. How can I interpret an increase in FTIR spectra baseline for treated HDPE? - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/post/How_can_I_interpret_an_increase_in_FTIR_spectra_baseline_for_treated_HDPE
48. Poster: GPC analysis at different flow rates to overcome shear degradation - Polymer Char, accessed on October 23, 2025, https://polymerchar.com/library/publications/gpc-analysis-at-different-flow-rates-to-overcome-shear-degradation

49. Application of gel permeation chromatography to the study of ..., accessed on October 23, 2025, https://www.researchgate.net/publication/295922016_Application_of_gel_permeation_chromatography_to_the_study_of_polymer_degradation
50. Respirometer ER series — ECHO Instruments, accessed on October 23, 2025, https://www.echoinstruments.eu/environmental/respirometer-er-series/
51. Respirometric Methods for Determination of Biodegradability and Biodegradation Kinetics for Hazardous Organic Pollutant Compounds - epa nepis, accessed on October 23, 2025, https://nepis.epa.gov/Exe/ZyPURL.cgi?Dockey=P100OPFZ.TXT
52. Predicting outcomes of steady-state 13C isotope tracing experiments using Monte Carlo sampling - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC3323462/
53. Gel permeation chromatography - Wikipedia, accessed on October 23, 2025, https://en.wikipedia.org/wiki/Gel_permeation_chromatography
54. How synthetic biology could help degrade plastic waste - Polytechnique Insights, accessed on October 23, 2025, https://www.polytechnique-insights.com/en/columns/health-and-biotech/how-synthetic-biology-could-help-manage-the-plastic-waste-problem/
55. Improving plastic degrading enzymes via directed evolution | Protein ..., accessed on October 23, 2025, https://academic.oup.com/peds/article/doi/10.1093/protein/gzae009/7666632
56. Characterization and engineering of plastic-degrading polyesterases jmPE13 and jmPE14 from Pseudomonas bacterium - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/bioengineering-and-biotechnology/articles/10.3389/fbioe.2024.1349010/full
57. Engineering Plastic Eating Enzymes Using Structural Biology - PMC - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10526444/
58. (PDF) Metabolic and enzymatic engineering strategies for polyethylene terephthalate degradation and valorization - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/380546389_Metabolic_and_enzymatic_engineering_strategies_for_polyethylene_terephthalate_degradation_and_valorization
59. Assembly strategies for polyethylene-degrading microbial ... - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
60. The Exploration of Plastic-Degrading Bacteria using Multi-Omic Approaches - University of Portsmouth, accessed on October 23, 2025, https://researchportal.port.ac.uk/en/studentTheses/the-exploration-of-plastic-degrading-bacteria-using-multi-omic-ap
61. A multi-OMIC characterisation of biodegradation and microbial community succession within the PET plastisphere - PubMed, accessed on October 23, 2025, https://pubmed.ncbi.nlm.nih.gov/34154652/

62. (PDF) Polyethylene biodegradation: A multifaceted approach - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/390506954_Polyethylene_biodegradation_A_multifaceted_approach
63. Nature-Inspired Strategies for Sustainable Degradation of Synthetic Plastics | JACS Au, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/jacsau.4c00388