# The Microbial Challenge of a Synthetic World: Deconstructing Polyethylene Biodegradation

**Abstract:** Polyethylene (PE), the world's most produced synthetic polymer, represents a monumental environmental challenge due to its extreme recalcitrance to natural degradation pathways. Its accumulation in terrestrial and marine ecosystems is a defining feature of the Anthropocene. While bioremediation through microbial action presents a conceptually sustainable solution, the field is characterized by slow progress, methodological inconsistencies, and a significant gap between laboratory findings and practical environmental application. This review critically assesses the current state of knowledge on the microbial biodegradation of PE. We first deconstruct the molecular basis of PE's durability, rooted in its stable carbon-carbon backbone, high molecular weight, and hydrophobicity. We then argue that effective biodegradation is a two-stage process, initiated by abiotic weathering that primes the polymer surface for subsequent microbial attack. A critical survey of the putative enzymatic toolkit reveals that while ligninolytic and alkane-degrading enzymes are leading candidates, definitive proof of an efficient "polyethylene-ase" remains elusive. We examine the key microbial players—from individual bacterial and fungal isolates to the synergistic power of consortia and insect gut microbiomes—highlighting a paradigm shift towards community-level functions. A cornerstone of this review is a rigorous appraisal of the analytical methodologies used to validate degradation, where we emphasize the critical distinction between true biodegradation (depolymerization and assimilation) and mere surface biodeterioration or fragmentation, which may inadvertently contribute to microplastic pollution. By synthesizing the major hurdles—including infinitesimally slow reaction rates and a crisis of experimental standardization—we identify the key knowledge gaps that impede progress. Finally, we offer a forward-looking perspective, envisioning a shift from the simple goal of mineralization to a more ambitious strategy of bio-upcycling, where engineered microbial systems, potentially in hybrid chemo-biological processes, transform PE waste into valuable platform chemicals and bioplastics, paving the way for a circular bio-economy.

## 1. Introduction: The Polyethylene Paradox—Ubiquity, Utility, and Environmental Persistence

The modern era is inextricably linked with the rise of synthetic polymers, and none is more emblematic of this relationship than polyethylene (PE). With global production exceeding 100 million metric tons in 2024 and a market valued at over USD 118 billion, PE accounts for more than one-third of the world's total plastic demand.[1] Its versatility, low cost, and durability have made it an indispensable material in sectors ranging from packaging—its largest consumer—to construction, automotive, and healthcare.[1] However, this utility is shadowed by a profound environmental paradox. The very chemical inertness that makes PE a superior material for protecting goods and ensuring safety also renders it exceptionally persistent upon disposal.[3]

The scale of the resulting pollution is staggering. Annually, over 460 million metric tons of plastic are produced, with an estimated 20 million metric tons leaking into the environment as mismanaged waste.[6] This burden is disproportionately driven by a small number of nations, with just 20 countries accounting for nearly 70% of plastic waste entering the environment.[7] Current end-of-life management strategies are woefully inadequate; globally, a mere 9% of all plastics are recycled each year, with the vast majority accumulating in landfills or natural ecosystems.[7] Once in the environment, PE is estimated to persist for hundreds, if not thousands, of years, fragmenting into micro- and nanoplastics that permeate every ecological niche, from the deepest oceans to arctic snow.[5]

This environmental crisis is compounded by a fundamental disconnect between economic drivers and ecological stewardship. The global PE market is projected to grow at a compound annual growth rate (CAGR) of approximately 5.5% through 2030, fueled by rising demand in emerging economies.[1] This robust economic engine for producing virgin polymer far outpaces the development and implementation of sustainable waste management infrastructure. This growing chasm ensures that the environmental burden of PE will intensify unless transformative solutions are developed.

In this context, microbial biodegradation has emerged as a compelling frontier of scientific inquiry. The prospect of harnessing natural biological systems to break down and metabolize this synthetic polymer offers the promise of a truly sustainable, circular solution.[10] However, the field is fraught with immense challenges. Reports of microbial activity on PE are numerous, yet progress is hampered by exceptionally slow degradation rates, a lack of standardized methodologies, and a scarcity of conclusive evidence for complete mineralization at an environmentally relevant scale.[9] This review aims to move beyond a simple cataloging of PE-degrading organisms to provide a critical analysis of the fundamental barriers, the proposed mechanisms, the key microbial and enzymatic players, and the analytical rigor required to validate claims of biodegradation. We will argue that overcoming the polyethylene challenge requires a systems-level understanding, from its molecular structure to the complex ecological interactions that govern its fate in the environment.

# 2. The Molecular Basis of Polyethylene's Recalcitrance

The extraordinary persistence of polyethylene is not an incidental property but is deeply rooted in its fundamental chemical structure and physical organization. Understanding these molecular-level defenses is paramount to devising strategies to overcome them. PE's recalcitrance is an emergent property arising from a hierarchy of features, from the strength of its covalent bonds to the architecture of its crystalline superstructure.

## The Fortress of the C-C Backbone

At its core, polyethylene is a simple homopolymer with the chemical formula $(C_2H_4)_n$, consisting of long chains of repeating ethylene units.[3] Its defining feature is a backbone composed exclusively of single carbon-carbon ($C-C$) and carbon-hydrogen ($C-H$) bonds. These non-polar, covalent bonds are characterized by high bond dissociation energies, making them thermodynamically stable and kinetically inert.[14] Unlike natural polymers such as cellulose (glycosidic bonds) or proteins (peptide bonds), or even other synthetic polymers like polyethylene terephthalate (PET) (ester bonds), the PE backbone lacks functional groups that are susceptible to attack by the common hydrolytic enzymes that drive most biological decomposition processes.[15] Consequently, the degradation of PE cannot proceed via hydrolysis; it necessitates an initial oxidative step to introduce reactive functional groups onto the polymer chain, a far more energetically demanding biochemical feat.

## Crystallinity and Branching as Architectural Barriers

Beyond its primary chemical structure, the physical arrangement of PE chains presents a formidable barrier to microbial attack. The degree to which these long chains can pack together determines the polymer's crystallinity, a key factor influencing its mechanical properties and its resistance to degradation. The major types of PE differ significantly in this regard (Table 1).

- **High-Density Polyethylene (HDPE):** Synthesized using catalysts that produce long, linear chains with minimal branching, HDPE molecules can pack together in a highly ordered, dense, and crystalline fashion. With a degree of crystallinity often reaching

70–90%, HDPE is rigid, strong, and highly resistant to chemical solvents and, by extension, enzymatic penetration.[13] The tightly packed crystalline lamellae are virtually inaccessible to extracellular enzymes.

- **Low-Density Polyethylene (LDPE):** Produced via a high-pressure polymerization process that introduces a significant number of both short and long side branches onto the polymer backbone. This branching disrupts the regular packing of the chains, resulting in a less ordered structure with a lower degree of crystallinity (typically 50–60%) and more amorphous regions.[13] These disordered, amorphous domains are considered to be more flexible and accessible, providing potential sites for an initial microbial assault. This structural difference is the primary reason why the majority of biodegradation studies focus on LDPE, as it presents a kinetically more favorable substrate.

## Insurmountable Physical Properties

Two final properties complete PE's molecular fortress. First, its high molecular weight, often ranging from tens to hundreds of thousands of Daltons (Da), makes the polymer chains far too large to be transported across microbial cell membranes for intracellular metabolism.[14] This dictates that any degradation must be initiated by extracellular enzymes secreted by the microorganisms. Second, the non-polar nature of its hydrocarbon backbone makes PE extremely hydrophobic and insoluble in water.[20] This creates a profound bioavailability challenge, as it hinders the effective interaction between the solid polymer surface and the aqueous-phase enzymes that must act upon it. Microorganisms must therefore employ strategies, such as producing biosurfactants or forming intimate biofilms, to overcome this interfacial barrier.[22]

Collectively, these multi-scale properties—a stable C-C backbone, high crystallinity, high molecular weight, and hydrophobicity—make PE one of the most recalcitrant synthetic materials ever created. Biodegradation is therefore not a simple process but a multi-faceted assault that must overcome chemical, physical, and interfacial barriers simultaneously.

**Table 1: Physicochemical Properties of Major Polyethylene Types and Their Implications for Biodegradability.**

| PE Type | Density (g/cm3) | Degree of Crystallinity (%) | Branching Structure | Typical Mw (Da) | Implications for Microbial Degradatio |
|---|---|---|---|---|---|

| | | | | | |
|---|---|---|---|---|---|
| | | | | | **n** |
| **LDPE** | 0.910–0.940 | 50–60% | Highly branched (short & long chains) | 40,000–50,000 | Higher amorphous content makes it more accessible to initial microbial attack. Most commonly studied.[18] |
| **LLDPE** | 0.915–0.925 | 60–70% | Linear with short, uniform branches | 50,000–150,000 | Properties between LDPE and HDPE; higher tensile strength than LDPE but still partially accessible.[4] |
| **HDPE** | 0.941–0.965 | 70–90% | Linear, minimal branching | 50,000–250,000 | High crystallinity and density create a significant physical barrier, making it highly recalcitrant.[13] |
| **UHMWPE** | >0.930 | ~85% | Extremely long linear | 3,000,000–6,000,00 | Extremely high molecular |

| | | | | | |
|---|---|---|---|---|---|
| | | | chains | 0 | weight and crystallinity render it virtually non-biodegradable.[13] |

# 3. A Two-Step Assault: The Synergy of Abiotic Weathering and Biotic Action

In natural environments, the microbial degradation of polyethylene is rarely, if ever, an isolated event acting on a pristine polymer. Instead, it is the culminating stage of a protracted degradation cascade that begins with the slow, relentless forces of abiotic weathering. This two-step process, involving an initial abiotic "priming" phase followed by a biotic colonization and degradation phase, is fundamental to understanding the fate of PE in the environment and the limitations of many laboratory-based studies.

## Step 1: Abiotic Priming of the Polymer Surface

Pristine polyethylene presents a chemically inert and hydrophobic surface that is largely unrecognizable to microbial enzymatic machinery.[3] Environmental factors must first breach this defense, creating chemical "handles" that facilitate microbial interaction. This abiotic activation is a critical, and often rate-limiting, prelude to biodegradation.

- **Photo-oxidation:** Exposure to ultraviolet (UV) radiation, particularly the UV-B component of sunlight, is a primary driver of PE weathering.[23] The absorption of UV energy can initiate free-radical chain reactions that lead to two crucial outcomes: chain scission, which reduces the polymer's molecular weight, and the incorporation of oxygen into the polymer backbone. This results in the formation of a variety of oxygen-containing functional groups, most notably carbonyls ($C=O$), but also carboxyls ($-COOH$) and hydroxyls ($-OH$).[23]
- **Thermo-oxidation:** Elevated temperatures, even those experienced during daily solar cycling, can significantly accelerate these oxidative reactions. The process is mechanistically similar to photo-oxidation, involving free-radical intermediates, and its effect is synergistic with UV exposure.[23]

The formation of these polar functional groups is the single most important event in the abiotic priming phase. It fundamentally alters the polymer surface, increasing its surface energy and reducing its hydrophobicity. This chemical modification makes the surface more wettable and creates anchor points for microbial adhesion, effectively bridging the gap between the inert polymer and the biological world.[20] This explains why many laboratory studies that aim to accelerate experiments employ artificial pre-treatments, such as exposure to UV lamps, high heat, or strong acids like nitric acid, to mimic the effects of years or decades of natural weathering in a matter of days or weeks.[19]

## Step 2: Biofilm-Mediated Biodegradation

Once the PE surface has been sufficiently oxidized, it becomes a viable substrate for microbial colonization. Microorganisms do not typically act as lone individuals but rather as organized communities within a biofilm.

- **Colonization and Biofilm Formation:** Pioneer microbial species adhere to the primed, more hydrophilic surface. These organisms begin to secrete a matrix of extracellular polymeric substances (EPS)—a complex mixture of polysaccharides, proteins, lipids, and nucleic acids.[14] This EPS matrix encases the microbial community, forming a mature biofilm.
- **The Biofilm as a Bioreactor:** The biofilm is not merely a passive attachment layer; it functions as a highly specialized microenvironment optimized for degrading a recalcitrant substrate. Within the biofilm, extracellular enzymes can be concentrated to high levels near the polymer surface, preventing their diffusion into the bulk environment. The matrix helps retain water, which is essential for enzymatic activity, and creates a diffusion barrier that can protect the community from external stressors.[27] Furthermore, the close proximity of different microbial species within the biofilm facilitates synergistic interactions, such as the exchange of metabolites, which is crucial for the complete breakdown of the polymer.[28] Some microbes within the biofilm may also produce biosurfactants, amphiphilic molecules that further reduce the surface tension between the hydrophobic polymer and the aqueous enzymatic solution, enhancing substrate bioavailability.[22]

This two-step model underscores a critical point: the rate of PE biodegradation in the environment is likely governed not by the metabolic potential of the local microbiome, but by the slow pace of the initial abiotic oxidation. Laboratory studies that bypass this step by using pre-treated PE may demonstrate the biochemical capability of microorganisms but can be misleading regarding the true environmental persistence of the material.

# 4. The Enzymatic Toolkit for PE Depolymerization

The central biochemical challenge in PE biodegradation is the enzymatic cleavage of its non-hydrolyzable, high-molecular-weight hydrocarbon backbone. Despite decades of research, the specific enzymes capable of efficiently catalyzing this process remain poorly understood, and a definitive "polyethylene-ase" has yet to be isolated, characterized, and validated *in vitro* on high-molecular-weight PE.[29] The current understanding is largely based on hypotheses derived from enzymes known to act on structurally analogous substrates.

## The Oxidative Vanguard: Ligninolytic Enzymes

Given that the initial attack on the PE backbone must be oxidative, enzymes involved in the degradation of lignin—a complex, aromatic, and highly recalcitrant natural polymer—are considered prime candidates. These enzymes are primarily secreted by fungi, particularly white-rot fungi.

- **Laccases and Peroxidases:** This group includes laccases (multicopper oxidases) and heme-containing peroxidases, such as Manganese Peroxidase (MnP) and Lignin Peroxidase (LiP).[31] These enzymes do not typically act directly on the bulky lignin polymer itself but work by generating small, highly reactive, and diffusible oxidizing agents. Laccases, in the presence of mediator compounds, and peroxidases, using hydrogen peroxide, produce powerful free radicals that can carry out a non-specific oxidative attack on a wide range of substrates.[32] It is hypothesized that these radicals could attack the $C-H$ bonds on the PE backbone, creating a polymer radical that can then react with oxygen, leading to the formation of hydroperoxides and subsequent chain scission.[31] Evidence for their involvement is largely correlational; their genes are often found in PE-colonizing communities, and their enzymatic activity is frequently detected in cultures that show signs of PE degradation.[31] However, direct evidence of these enzymes cleaving high-molecular-weight PE chains remains scarce.

## The Alkane Analogy: Hydrocarbon-Degrading Enzymes

The chemical structure of a linear PE chain is essentially that of a very long-chain alkane. This

has led researchers to investigate enzymes known to be involved in hydrocarbon metabolism, which are widespread in bacteria like *Pseudomonas* and *Rhodococcus*.

- **Alkane Monooxygenases (AlkB) and Cytochrome P450s (CYP153):** These are the best-characterized enzyme systems for initiating alkane degradation. They catalyze the terminal or sub-terminal hydroxylation of alkane chains, inserting an oxygen atom to form an alcohol.[26] This initial hydroxylation is the key activation step, as the resulting alcohol can be further oxidized by alcohol and aldehyde dehydrogenases to a fatty acid. This fatty acid can then be broken down into two-carbon units via the beta-oxidation pathway, feeding directly into central metabolism.[26] Metagenomic analysis of PE-colonizing biofilms has repeatedly identified genes encoding for AlkB and P450 systems, suggesting they play a role.[26] The prevailing hypothesis is that these enzymes could act on the ends of PE chains or on smaller oligomers released by an initial abiotic or enzymatic cleavage, initiating a stepwise degradation process.

## Controversial Players and a Critical Lack of Proof

The literature also contains reports of other enzymes, such as esterases and lipases, being involved in PE degradation.[35] This is mechanistically puzzling, as these enzymes catalyze the hydrolysis of ester bonds, which are absent in a pure PE backbone. Their detected activity may be explained by the hydrolysis of ester-based additives (e.g., plasticizers, slip agents) commonly found in commercial PE products, rather than an attack on the polymer itself.

This highlights a critical issue in the field: the reliance on analogy and correlation in the absence of direct biochemical proof. The enzymes currently under investigation are pursued because they degrade similar substrates (lignin, alkanes), not because they have been unequivocally shown to degrade PE. The observed degradation in microbial cultures could be the result of a complex, synergistic cascade of multiple enzymes that cannot be replicated by a single purified protein. A recent and particularly confounding finding revealed that a widely used commercial "model PE" substrate is, in fact, contaminated with significant quantities of medium- and long-chain alkanes and ketones.[38] Microbes grown on this substrate were found to be selectively degrading these low-molecular-weight contaminants, not the polymeric PE component. This discovery casts doubt on previous studies using similar substrates and underscores the urgent need for rigorous substrate characterization and direct biochemical validation of enzymatic activity on the polymer itself. The true PE-degrading enzymes may belong to entirely new, uncharacterized protein families, and their discovery is being hampered by these confounding factors.

# 5. The Key Microbial Players: From Single Strains to Complex Communities

The search for biological agents capable of degrading PE has uncovered a diverse array of bacteria and fungi isolated from various environments, from plastic-laden landfills to the depths of the ocean and the guts of insects. A clear and significant trend has emerged from this research: while individual microbial isolates can exhibit limited degradative capabilities, the most effective and robust biodegradation is consistently observed in complex microbial communities, or consortia. This suggests that PE degradation is not the work of a single "super-bug" but is rather a community-level function orchestrated by a network of interacting species.

## Bacterial Degraders

A number of bacterial genera are repeatedly implicated in PE degradation, often due to their metabolic versatility and their ability to form resilient biofilms on hydrophobic surfaces. Key players include:

- ***Rhodococcus***: Species like *Rhodococcus ruber* are frequently isolated from plastic-contaminated soils. They are known for their ability to degrade a wide range of hydrophobic compounds and are potent biofilm formers. Studies have shown that *Rhodococcus* strains can induce surface oxidation and measurable weight loss in PE films.[37]
- ***Bacillus***: This genus is ubiquitous in soil and compost environments. Species such as *Bacillus subtilis* and *Bacillus cereus* have been shown to colonize PE surfaces, produce biosurfactants that enhance bioavailability, and secrete oxidative enzymes like laccases, leading to surface deterioration and weight loss.[9]
- ***Pseudomonas***: Well-known for their metabolic prowess in degrading hydrocarbons, species like *Pseudomonas aeruginosa* are natural candidates. Genes for alkane-degrading enzymes are frequently detected in *Pseudomonas* strains associated with PE biofilms, and they are often key members of effective degrading consortia.[11]
- **Actinomycetes**: This group of filamentous bacteria, including genera like *Streptomyces*, is known for producing a vast array of extracellular enzymes and is often associated with the breakdown of complex organic matter in soil.[11]

## Fungal Degraders

Fungi, particularly filamentous fungi, are exceptionally well-equipped for degrading recalcitrant polymers like PE. Their hyphal mode of growth allows them to physically penetrate porous substrates, while their metabolic machinery is geared towards secreting powerful cocktails of extracellular oxidative enzymes to break down complex materials like lignin and cellulose. Genera such as ***Aspergillus***, ***Penicillium***, and ***Cladosporium*** have all been shown to grow on PE as a sole carbon source, secreting enzymes like laccases and peroxidases and causing significant structural and chemical changes to the polymer.[33]

**Table 2: Key Microbial Genera Implicated in Polyethylene Biodegradation.**

| Kingdom | Genus | Representative Species | Environmental Source | Key Putative Enzymes/ Mechanisms | Summary of Evidence |
|---|---|---|---|---|---|
| **Bacteria** | *Rhodococcus* | *R. ruber*, *R. jostii* | Soil, plastic waste | Multicopper oxidases, esterases, alkane hydroxylases | Strong biofilm former; evidence of surface oxidation and weight loss.[37] |
| **Bacteria** | *Bacillus* | *B. subtilis*, *B. cereus* | Soil, compost, insect gut | Laccases, lipases, biosurfactant production | Frequently isolated; confirmed weight loss and surface changes; some strains from waxworms.[9] |
| **Bacteria** | *Pseudomonas* | *P. aeruginosa*, | Landfills, marine | Alkane hydroxylase | Known hydrocarbo |

| | | | | | |
|---|---|---|---|---|---|
| | | *P. putida* | environments | s (AlkB), esterases | n degraders; metagenomic evidence from biofilms; used in consortia.[11] |
| **Fungi** | *Aspergillus* | *A. niger*, *A. flavus* | Landfills, marine sediments | Laccases, MnP, LiP, esterases | Powerful secretors of extracellular oxidative enzymes; significant weight loss reported.[34] |
| **Fungi** | *Penicillium* | *P. simplicissimum* | Soil, plastic waste | Laccases, peroxidases | Able to grow on PE as sole carbon source; evidence of chemical changes via FTIR.[33] |
| **Fungi** | *Cladosporium* | *Cladosporium sp.* | Soil | Laccases | Demonstrated degradation of heat-treated LDPE with surface changes confirmed by ESEM.[33] |

## The Power of Consortia and Insect Gut Microbiomes

The limitations of single-strain degradation have driven a paradigm shift towards studying microbial consortia. The evidence overwhelmingly indicates that mixed microbial communities outperform individual species. This synergy arises from several factors:

- **Metabolic Handoffs:** The complex, multi-step process of PE degradation can be divided among different species. One organism might perform the initial, difficult oxidative attack on the polymer, releasing smaller oligomers. These intermediates can then be readily metabolized by other members of the community that may lack the initial oxidative enzymes but are efficient at consuming the breakdown products.[28]
- **Niche Partitioning and Additive Degradation:** In real-world plastic waste, a consortium can partition its labor, with some species attacking the PE polymer while others specialize in degrading the various chemical additives present in the plastic formulation.[39]
- **Enhanced Resilience:** A diverse community is often more resilient to environmental fluctuations and can maintain functional stability better than a monoculture.

This concept of a synergistic, community-level function is perhaps best exemplified by the remarkable—and still debated—case of "plastivore" insect larvae. The larvae of the greater wax moth (*Galleria mellonella*) and the yellow mealworm (*Tenebrio molitor*) have been observed to consume and degrade PE and polystyrene at rates far exceeding those seen in microbial cultures.[43] The process begins with the crucial step of mechanical mastication, where the larvae chew the plastic into tiny fragments, vastly increasing its surface area. The subsequent biochemical degradation within the gut is a subject of intense research. It remains unclear whether the primary drivers are enzymes secreted by the insect itself, the specialized microbial community residing in its gut, or a complex host-microbe synergy.[36] Regardless of the precise mechanism, the insect gut represents a highly evolved natural bioreactor, combining physical pre-treatment with a dense, adapted microbial consortium. This model reinforces the idea that the most effective PE degradation strategies will likely involve integrated, multi-step processes rather than a single biological agent. The field is thus moving away from a search for a single "app" and towards understanding and engineering the entire "operating system" of a degrading community.

# 6. A Critical Appraisal of Analytical Methodologies: The Challenge of Proving Biodegradation

A significant impediment to progress in the study of PE biodegradation is the lack of standardized analytical methods and the frequent misinterpretation of experimental data. Many published studies make claims of "biodegradation" based on evidence that

demonstrates only superficial changes or physical fragmentation, processes that may not lead to the removal of plastic from the environment and could even exacerbate the problem by creating microplastics. A rigorous, multi-technique approach is essential to definitively validate true biodegradation, which involves both depolymerization and microbial assimilation.

The most common analytical techniques and their critical limitations are summarized in Table 3 and discussed below.

- **Weight Loss:** While intuitively simple, measuring the change in a sample's mass is notoriously unreliable. Inaccurate results can arise from the incomplete removal of the microbial biofilm, absorption of water by the polymer or biofilm, or the leaching of low-molecular-weight additives from the plastic matrix, all of which can confound the measurement.[12] At best, it is a preliminary indicator that requires corroboration by other methods.
- **Surface Imaging (SEM/AFM):** Scanning Electron Microscopy (SEM) and Atomic Force Microscopy (AFM) provide powerful, high-resolution images of the polymer surface. They can vividly show the effects of microbial colonization, such as the formation of pits, cracks, cavities, and general surface erosion.[14] While this provides compelling visual evidence of an interaction, it only demonstrates **biodeterioration**—a physical and chemical alteration of the surface. It does not prove that the polymer has been depolymerized or assimilated by the microbes.[51]
- **Chemical Analysis (FTIR Spectroscopy):** Fourier-Transform Infrared (FTIR) spectroscopy is an indispensable tool for detecting chemical changes on the polymer surface. It is highly sensitive to the formation of new functional groups resulting from oxidation, particularly the appearance of a characteristic carbonyl ($C=O$) absorption peak around 1715 $cm^{-1}$.[52] The calculation of a "carbonyl index" is a common way to quantify the extent of oxidation. However, like SEM, FTIR is primarily a surface-sensitive technique and provides no information about changes in the polymer's molecular weight, which is the true hallmark of degradation.[20]
- **Molecular Weight Analysis (GPC/SEC):** Gel Permeation Chromatography (GPC), also known as Size Exclusion Chromatography (SEC), is the **gold standard** for proving depolymerization. This technique separates polymer molecules based on their size in solution. A demonstrable shift in the molecular weight distribution towards lower values is unequivocal evidence that the long polymer chains have been cleaved into shorter ones.[51] This is a critical distinction: fragmentation can create smaller particles of the same high molecular weight, whereas biodegradation reduces the molecular weight itself. The technical challenge of solubilizing PE in high-temperature solvents has limited its use, but studies that lack GPC/SEC data should be interpreted with extreme caution, as they cannot confirm that true chain scission has occurred.
- **Product Identification (GC-MS/LC-MS):** Gas and Liquid Chromatography coupled with Mass Spectrometry are essential for identifying the low-molecular-weight products of degradation, such as oligomers, monomers, and other metabolic intermediates.[59] This provides crucial insight into the biochemical pathways at play and can help confirm that

the polymer is being broken down into smaller, assimilable units.

- **Proof of Mineralization (Respirometry/Isotope Tracing):** The ultimate proof of biodegradation is mineralization—the conversion of the polymer's carbon into metabolic end products like carbon dioxide ($CO_2$) or methane ($CH_4$). This can be measured through respirometry.[59] However, to be unambiguous, this requires the use of isotope-labeled PE (e.g., using $^{13}$C). By tracking the appearance of $^{13}CO_2$, researchers can definitively prove that the carbon from the polymer has been processed through microbial metabolism. This is a complex and expensive technique but provides the highest level of proof.
- **'Omics Approaches:** Modern molecular techniques like metagenomics, transcriptomics, and proteomics provide powerful tools for understanding the biological system. Metagenomics can identify all the potential degradation genes within a community, while proteomics can confirm which enzymes are actively being expressed in the presence of PE.[37] These methods are invaluable for generating hypotheses about mechanisms but do not directly measure the physical degradation of the polymer itself.

The pervasive issue in the literature is the conflation of biodeterioration and biofragmentation with true biodegradation. A study showing only surface cracks via SEM and an increased carbonyl index via FTIR has demonstrated that the plastic is being weathered and possibly fragmented into microplastics, but it has not proven that the plastic is being biologically removed from the environment. Adopting a more rigorous, multi-modal standard of proof—requiring, at minimum, evidence of chemical change (FTIR), surface change (SEM), and molecular weight reduction (GPC)—is critical for the field to advance and to avoid inadvertently promoting solutions that could worsen microplastic pollution.

**Table 3: Comparison of Analytical Techniques for Validating PE Biodegradation.**

| Technique | Principle | Information Provided | Critical Limitations / Potential for Misinterpretation |
|---|---|---|---|
| **Weight Loss** | Gravimetric measurement | Overall mass reduction of the sample. | Prone to error from biofilm residue, water absorption, or leaching of additives. Does not prove mineralization.[12] |
| **SEM / AFM** | Electron/Probe | High-resolution | Shows surface |

| | | | |
|---|---|---|---|
| | Microscopy | imaging of surface topography. | erosion (pits, cracks). Cannot distinguish biotic vs. abiotic causes. **Evidence of biodeterioration, not biodegradation**.[48] |
| **FTIR Spectroscopy** | Infrared light absorption by molecular bonds | Formation of new chemical functional groups (e.g., $C=O$, $-OH$). | Primarily a surface analysis. Confirms chemical oxidation but provides no information on molecular weight reduction.[20] |
| **GPC / SEC** | Chromatographic separation by hydrodynamic volume | Molecular weight distribution ($M_w$, $M_n$, PDI) of the polymer. | **Gold standard for proving depolymerization (chain scission).** Requires polymer solubilization, which can be difficult for cross-linked PE.[57] |
| **GC-MS / LC-MS** | Chromatographic separation and mass analysis | Identification and quantification of low-molecular-weight degradation products and metabolites. | Essential for elucidating metabolic pathways. Can be difficult to distinguish polymer-derived products from media components or cell metabolites.[59] |
| **Respirometry** | Measurement of $CO_2$ (aerobic) or $CH_4$ | Quantifies the extent of polymer mineralization. | **Definitive proof of ultimate biodegradation.** |

| | | | |
|---|---|---|---|
| | (anaerobic) evolution | | Requires isotope labeling (e.g., $^{13}$C-PE) to be unambiguous, which is expensive and complex.[49] |
| **Metagenomics / Proteomics** | DNA/protein sequencing and analysis | Identifies microbial taxa, functional genes, and expressed enzymes in a community. | Powerful for hypothesis generation (what *could* be happening). Does not directly measure polymer degradation itself.[61] |

# 7. Major Hurdles and Knowledge Gaps: Bridging Lab Curiosities and Environmental Solutions

Despite promising discoveries and growing research interest, the translation of microbial PE degradation from a laboratory curiosity into a viable environmental technology is hindered by several formidable challenges and fundamental knowledge gaps. The field appears to be caught in a "proof-of-concept" loop, repeatedly demonstrating that slow, partial degradation is possible under controlled conditions but failing to achieve the rates and scales necessary for practical application.

## The Overwhelmingly Slow Rate of Degradation

This remains the single greatest barrier to implementation. The most optimistic and credible laboratory studies report PE weight loss in the range of a few percent to perhaps 10-15% over incubation periods spanning several months, and in some cases, years.[9] While scientifically significant, these rates are orders of magnitude too slow to make a meaningful impact on the millions of tons of PE waste generated annually. Environmental degradation rates are even slower, with half-lives for common PE products estimated to be in the range of decades to centuries.[64] Accelerating this process by several orders of magnitude is the central challenge

for biotechnology.

## The Crisis of Standardization and Reproducibility

The field suffers from a profound lack of methodological consistency, making it nearly impossible to compare results across different studies and build a coherent body of knowledge. There is no universally accepted definition of what constitutes "biodegradation," leading to conflicting claims.[9] Furthermore, experiments vary widely in critical parameters, including the type and form of PE used (e.g., LDPE vs. HDPE, film vs. powder), the use and nature of pre-treatments (UV, heat, chemical), the composition of the culture media, and the duration of the experiment.[9] This heterogeneity prevents meaningful meta-analysis and slows collective progress.

## The "Pristine vs. Real-World Plastic" Problem

The vast majority of research is conducted using pure, clean, and often additive-free PE obtained from chemical suppliers. This bears little resemblance to post-consumer plastic waste, which is a complex and heterogeneous material. Commercial plastics contain a cocktail of chemical additives—such as stabilizers, plasticizers, antioxidants, and pigments—that are designed to prevent degradation and can be inhibitory or toxic to microorganisms.[51] Conversely, some additives may be more readily biodegradable than the polymer itself, acting as a preferential carbon source that confounds degradation measurements. This issue was starkly illustrated by the recent discovery that a common model PE substrate used in research contains non-polymeric alkanes and ketones, which microbes consume preferentially, leading to the erroneous conclusion that the polymer itself is being degraded.[38]

## The Scalability and Economic Chasm

Bridging the gap from a 250 mL laboratory flask to an industrial-scale bioreactor capable of processing tons of mixed, contaminated plastic waste represents a monumental engineering challenge.[12] Such a process would need to be robust, efficient, and, crucially, economically viable. The costs associated with building and operating large-scale bioreactors, producing the necessary enzymes in bulk, and managing the downstream processing of byproducts

must be competitive with the extremely low costs of landfilling or the established economics of mechanical recycling.[66] At present, biological methods are nowhere near this economic threshold.

### Fundamental Knowledge Gaps

Underpinning these practical hurdles are significant gaps in our fundamental understanding of the process:

- **The Enzymatic Pathway:** The complete, validated biochemical pathway for the cleavage of the PE backbone remains an enigma. The specific enzymes responsible, their mechanisms of action, and the sequence of reactions have not been fully elucidated.[29]
- **Metabolic Intermediates:** The identity, fate, and potential toxicity of the many low-molecular-weight intermediates generated during degradation are poorly understood.[68] Ensuring that the process does not release harmful byproducts into the environment is critical.
- **Ecology of Consortia:** While consortia are known to be more effective, the specific synergistic interactions, metabolic handoffs, and population dynamics that drive their enhanced performance are still largely a "black box." The principles for rationally designing stable, efficient synthetic consortia are in their infancy.[69]

To break out of the current cycle of incremental proofs-of-concept, the research community must shift its focus from simply discovering more organisms that can slowly degrade PE to tackling these fundamental rate-limiting steps and engineering challenges head-on.

## 8. Future Perspectives: Engineering a Bio-Based Circular Economy for Polyethylene

The path forward for PE biodegradation requires a strategic shift in both ambition and approach. The goal should evolve from simply making plastic waste disappear (mineralization) to a more sophisticated paradigm of bio-upcycling, where PE is viewed as a valuable carbon feedstock for a new circular bio-economy. Achieving this vision will require concerted efforts in foundational science, technology development, and systems integration over the next decade.

## The Next 5 Years: Foundational Science and Technology Development

The immediate future must focus on building the fundamental tools and knowledge base that are currently lacking.

- **Enzyme Discovery and Engineering:** The search for novel plastic-active enzymes (PAZymes) must accelerate. This will be driven by high-throughput functional metagenomic screening, which allows researchers to probe the genetic potential of entire microbial communities from plastic-polluted environments without the need for cultivation.[61] This discovery pipeline will be tightly integrated with artificial intelligence (AI) and machine learning-driven protein engineering. Predictive models will identify promising enzyme candidates from sequence data, and directed evolution or rational design will be used to dramatically improve their catalytic efficiency, thermal stability, and specificity.[70]
- **Standardization of Methods:** The research community must collaboratively establish and adopt a suite of standardized protocols. This includes using well-characterized reference PE materials (free of confounding contaminants), defining a minimal set of analytical techniques required to validate a claim of biodegradation (e.g., mandating GPC/SEC analysis), and standardizing reporting metrics. This will ensure that data generated across different laboratories is reproducible, comparable, and reliable.[21]
- **Rational Design of Synthetic Consortia:** Research will move beyond enriching for naturally occurring consortia towards a "bottom-up" synthetic biology approach. This involves rationally designing and constructing microbial consortia with defined metabolic divisions of labor. For example, a consortium might combine a bacterial strain engineered to secrete a powerful initial oxidative enzyme with another strain optimized to rapidly consume the resulting oligomers, preventing feedback inhibition and driving the reaction forward.[71]

## The Next 10 Years: Integration and Application

With a more powerful enzymatic toolkit and a deeper understanding of microbial consortia, the focus will shift towards integrating these biological modules into practical, scalable processes.

- **Hybrid Chemo-Enzymatic Processes:** A purely biological approach to degrading bulk PE is likely to remain too slow. The most promising pathway involves hybrid systems that couple an energy-efficient physical or chemical pre-treatment step with a subsequent

biological conversion. For instance, processes like mild pyrolysis or solvolysis could be used to rapidly and cost-effectively depolymerize PE waste into a liquid stream of smaller oligomers and waxes. This pre-processed feedstock would then be fed to engineered microbial consortia, which are far more efficient at metabolizing these smaller molecules than the solid polymer.[25]

- **From Biodegradation to Bio-Upcycling:** The ultimate goal must be to maximize resource efficiency. Mineralizing PE to $CO_2$ represents a complete loss of the valuable fixed carbon and embedded energy in the polymer. The future lies in redirecting the metabolic pathways of engineered microorganisms to convert PE-derived monomers and oligomers into high-value products. This could include platform chemicals (e.g., dicarboxylic acids for new polymer synthesis), biofuels, or biodegradable polymers like polyhydroxyalkanoates (PHAs).[72] This approach transforms plastic waste from an environmental liability into a sustainable feedstock, closing the loop and creating a true circular bio-economy.

## Concluding Vision

The journey to solve the polyethylene pollution crisis will not culminate in the discovery of a single "plastic-eating" microbe. Rather, it will be realized through the deliberate design and engineering of integrated, multi-stage systems where mechanical sorting, chemical depolymerization, and biological conversion work in concert. The critical role of microbiology and biotechnology will be to provide the highly specific, efficient, and robust catalytic modules that can take a heterogeneous waste stream and precisely transform it into a portfolio of valuable, sustainable products. This vision requires a shift in mindset from environmental remediation to resource valorization, positioning microbial communities not just as cleanup crews, but as the master chemists of a future circular economy.

---

## References


- [1] Virtue Market Research. (n.d.). *Polyethylene Market*. Retrieved from https://virtuemarketresearch.com/report/polyethylene-market
- [74] Grand View Research. (n.d.). *Low-density Polyethylene (LDPE) - Plastic Waste Management Market Statistics*. Retrieved from https://www.grandviewresearch.com/horizon/statistics/plastic-waste-management-market/polymer-type/low-density-polyethylene-ldpe/global

- [2] Future Market Insights. (n.d.). *Polyethylene Market Size and Share Forecast Outlook From 2024 to 2034*. Retrieved from https://www.futuremarketinsights.com/reports/polyethylene-market
- [75] Plastics Europe. (2024). *Plastics – the fast Facts 2024*. Retrieved from https://plasticseurope.org/knowledge-hub/plastics-the-fast-facts-2024/
- [6] IUCN. (2024). *Plastic pollution*. Retrieved from https://iucn.org/sites/default/files/2024-05/plastic-pollution-issues-brief-may-2024-update.pdf
- [7] Natural History Museum. (2024). *Almost 70% of all plastic waste is produced by just 20 countries*. Retrieved from https://www.nhm.ac.uk/discover/news/2024/september/almost-70-of-plastic-waste-produced-by-20-countries.html
- [3] Wikipedia. (n.d.). *Polyethylene*. Retrieved from https://en.wikipedia.org/wiki/Polyethylene
- [13] Exir Polymer. (n.d.). *All About Polyethylene*. Retrieved from https://exirpolymer.com/all-about-polyethylene/
- [4] Smart Turf. (n.d.). *Polyethylene Explained*. Retrieved from https://smartturf.com/polyethylene-explained
- [17] Reliance Foundry. (n.d.). *Polyethylene Plastic*. Retrieved from https://www.reliance-foundry.com/blog/polyethylene-plastic
- [18] SpecialChem. (n.d.). *Polyethylene (PE) Plastic*. Retrieved from https://www.specialchem.com/plastics/guide/polyethylene-plastic
- [15] Xometry. (n.d.). *What is Polyethylene?*. Retrieved from https://www.xometry.com/resources/materials/polyethylene/
- [8] U.S. Environmental Protection Agency. (n.d.). *Impacts of Plastic Pollution*. Retrieved from https://www.epa.gov/plastics/impacts-plastic-pollution
- [5] Eco_LifeMastery. (n.d.). *The Harmful Impact of Polyethylene: Understanding the Plastic Predicament*. Medium. Retrieved from https://medium.com/@Eco_LifeMastery/the-harmful-impact-of-polyethylene-understanding-the-plastic-predicament-697eb4d60ab2

- [76] POM Material. (n.d.). *Is Polyethylene Plastic?*. Retrieved from https://pom-material.com/blog/is-polyethylene-plastic/
- [77] National Center for Biotechnology Information. (n.d.). *Polyethylene terephthalate*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC8755403/
- [78] Accel Polymers. (2024). *Impact of HDPE Recycling on Our Environment*. Retrieved from https://accelpolymers.com/2024/02/01/impact-of-hdpe-recycling-on-our-environment/
- [24] National Center for Biotechnology Information. (n.d.). *The lifetime of plastics in the environment*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7334500/
- [20] Ghatge, S., et al. (2020). *Biodegradation of polyethylene: a brief review*. Applied Biological Chemistry. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [9] Restrepo-Flórez, J. M., et al. (2020). *Challenges in the microbial degradation of polyethylene*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [23] MDPI. (2023). *Degradation of Polyethylene Materials*. Applied Sciences. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [27] Frontiers in Microbiology. (2024). *Microbial degradation of plastics*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
- [10] OMICS International. (n.d.). *A Review on Biodegradation of Polythene: The Microbial Approach*. Journal of Bioremediation & Biodegradation. Retrieved from https://www.omicsonline.org/a-review-on-biodegradation-of-polythene-the-microbial-approach-2155-6199.1000164.php?aid=8679
- [11] Frontiers in Microbiology. (2022). *Degradation of polyethylene by soil microorganisms*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2022.1077588/full
- [37] ACS Publications. (2023). *Polyethylene Degradation by a Rhodococcus Strain*. Environmental Science & Technology. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.3c03778
- [71] Diva Portal. (2024). *Engineering microbial consortia for polyethylene degradation*. Retrieved from https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf

- [14] ResearchGate. (n.d.). *Evidence of Polyethylene Biodegradation by Bacterial Strains from the Guts of Plastic-Eating Waxworms*. Retrieved from https://www.researchgate.net/publication/268154348_Evidence_of_Polyethylene_Biodegradation_by_Bacterial_Strains_from_the_Guts_of_Plastic-Eating_Waxworms
- [37] ACS Publications. (2023). *Polyethylene Degradation by a Rhodococcus Strain Isolated from Naturally Weathered Plastic Waste Enrichment*. Environmental Science & Technology. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.3c03778
- [9] National Center for Biotechnology Information. (2020). *Microbial Degradation of Polyethylene: A Review*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [19] National Center for Biotechnology Information. (2017). *Biodegradation of high-density polyethylene by Klebsiella pneumoniae CH001*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC5603451/
- [40] MDPI. (2025). *Biodegradation of Low-Density Polyethylene and Polyurethane by Pedospheric Microbes*. Polymers. Retrieved from https://www.mdpi.com/2073-4360/17/2/169
- [79] The Open Biotechnology Journal. (2024). *Screening and Identification of Marine Bacteria for Polyethylene and Polyethylene Terephthalate Degradation*. Retrieved from https://openbiotechnologyjournal.com/VOLUME/18/ELOCATOR/e18740707280343/
- [34] MDPI. (2021). *Biodegradation of Low-Density Polyethylene by Endophytic Fungi*. Journal of Fungi. Retrieved from https://www.mdpi.com/2309-608X/7/8/594
- [33] MDPI. (2023). *Degradation of Low-Density Polyethylene by Cladosporium sp. CPEF-6*. Journal of Fungi. Retrieved from https://www.mdpi.com/2309-608X/9/6/605
- [80] bioRxiv. (2021). *A marine fungus Alternaria sp. FB1 degrades polyethylene*. Retrieved from https://www.biorxiv.org/content/10.1101/2021.11.19.469330.full
- [41] PLOS ONE. (2018). *Biodegradability of polyethylene by bacteria and fungi from Dandora dumpsite Nairobi-Kenya*. Retrieved from https://journals.plos.org/plosone/article?id=10.1371/journal.pone.0198446
- [81] Reddit. (n.d.). *There are 5 types of fungus that can eat plastic*. r/Anticonsumption. Retrieved from https://www.reddit.com/r/Anticonsumption/comments/1cw3riw/there_are_5_types_of_fung

us_that_can_eat_plastic/
- [35]
National Center for Biotechnology Information. (2024). *Fungi-Mediated Degradation of Plastics*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10991219/
- [28]
ResearchGate. (n.d.). *Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production*. Retrieved from https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production
- [26]
National Center for Biotechnology Information. (2022). *Metagenomic Analysis of a High-Density Polyethylene-Degrading Marine Prokaryotic Consortium*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC8941889/
- [42]
Frontiers in Microbiology. (2021). *Construction of an Artificial Microbial Consortium for PET Degradation*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2021.778828/full
- [72]
University of Illinois. (2023). *Harnessing microbial consortia to tackle plastic pollution*. Retrieved from https://dev-www.igb.illinois.edu/article/harnessing-microbial-consortia-tackle-plastic-pollution
- [82]
MDPI. (2024). *Microbial Degradation of Polyesters*. International Journal of Molecular Sciences. Retrieved from https://www.mdpi.com/1422-0067/25/23/12747
- [39]
Frontiers in Microbiology. (2023). *Selection and characterization of plastic-degrading microbial consortia*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1143769/full
- [43]
ACS Publications. (2020). *Biodegradation of Polyethylene and Polystyrene by Galleria mellonella Larvae*. Environmental Science & Technology. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.9b07044
- [83]
MDPI. (2024). *Enzymatic Degradation of Polystyrene by Galleria mellonella*. International Journal of Molecular Sciences. Retrieved from https://www.mdpi.com/1422-0067/25/3/1576
- [44]
The Royal Society Publishing. (2020). *The role of the gut microbiome in polyethylene degradation by Galleria mellonella*. Proceedings of the Royal Society B. Retrieved from https://royalsocietypublishing.org/doi/10.1098/rspb.2020.0112
- [36]

ResearchGate. (n.d.). *Multi-omics approach reveals new insights into the gut microbiome of Galleria mellonella exposed to polyethylene diet*. Retrieved from https://www.researchgate.net/publication/352154940_Multi-omics_approach_reveals_new_insights_into_the_gut_microbiome_of_Galleria_mellonella_LepidopteraPyralidae_exposed_to_polyethylene_diet

- [60]

ResearchGate. (n.d.). *Low and high-density polyethylene and expanded polystyrene biodegradation by the greater wax moth Galleria mellonella L reveals a key role of the gut microbiome*. Retrieved from https://www.researchgate.net/publication/390092565_Low_and_high-density_polyethylene_and_expanded_polystyrene_biodegradation_by_the_greater_wax_moth_Galleria_mellonella_L_reveals_a_key_role_of_the_gut_microbiome

- [45]

National Center for Biotechnology Information. (2022). *Gut Microbiota of the Greater Wax Moth (Galleria mellonella) Consuming Polyethylene and Polystyrene*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9294514/

- [31]

Fungal enzymes for the degradation of polyethylene: Molecular docking. (n.d.). Retrieved from http://uptlax.edu.mx/wp-content/uploads/2023/11/Fungal-enzymes-for-the-degradation-of-polyethylene-Molecular-docking-min.pdf

- [32]

National Center for Biotechnology Information. (2022). *Fungal Enzymes for Plastic Degradation*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9230134/

- [84]

Google Patents. (n.d.). *Method for degrading polyethylene by using bacillus extracellular laccase*. Retrieved from https://patents.google.com/patent/CN103980535A/en

- [61]

National Center for Biotechnology Information. (2020). *Metagenomic analysis of microbial population engaged in plastic biodegradation*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7521044/

- [85]

Oxford Academic. (2025). *Metagenomic analysis of plastisphere communities*. FEMS Microbiology Ecology. Retrieved from https://academic.oup.com/femsec/article/101/5/fiaf035/8104280

- [86]

OUCI. (n.d.). *Analytical methods for the analysis of biopolymers*. Retrieved from https://ouci.dntb.gov.ua/en/works/4gBygk07/

- [46]

MDPI. (2024). *Biodegradation of LDPE by Candida tropicalis and Rhodotorula mucilaginosa*. Journal of Marine Science and Engineering. Retrieved from https://www.mdpi.com/1424-2818/16/12/759

- [87] ResearchGate. (2021). *Analytical methods for the investigation of enzyme-catalyzed degradation of polyethylene terephthalate*. Retrieved from https://www.researchgate.net/publication/350556582_Analytical_methods_for_the_investigation_of_enzyme-catalyzed_degradation_of_polyethylene_terephthalate
- [59] NEPT Journal. (n.d.). *Biodegradation of LDPE by Streptomyces werraensis SDJM*. Retrieved from https://neptjournal.com/upload-images/(15)B-3772.pdf
- [88] Semantic Scholar. (2023). *Analytical method development, validation, and out-of-spec investigation for polyethylene glycol impurities*. Retrieved from https://www.semanticscholar.org/paper/Analytical-method-development%2C-validation%2C-and-for-Huang-Chu/a4139188a4b13518864042f1027c0f8bfc4ba57e
- [89] National Center for Biotechnology Information. (2022). *Analytical Methods for Biopolymer Analysis*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9694517/
- [48] ResearchGate. (n.d.). *SEM analysis of LDPE biodegradation*. Retrieved from https://www.researchgate.net/figure/SEM-analysis-of-LDPE-biodegradation-at-different-resolutions-500-2-500-a-control_fig4_364082699
- [49] International Scholars Journals. (n.d.). *Biodegradation of low density polyethylene (LDPE) by fungi isolated from marine water– a SEM analysis*. Retrieved from https://www.internationalscholarsjournals.com/articles/biodegradation-of-low-density-polyethylene-ldpe-by-fungi-isolated-from-marine-water-a-sem-analysis.pdf
- [50] Bioflux. (2024). *Biodegradation of low-density polyethylene by marine bacteria*. Retrieved from https://bioflux.com.ro/docs/2024.2735-2741.pdf
- [9] National Center for Biotechnology Information. (2020). *Microbial degradation of polyethylene: A review*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [90] IWA Publishing. (2023). *Investigating biodegradation of polyethylene and polypropylene microplastics*. Water Science & Technology. Retrieved from https://iwaponline.com/wst/article/88/11/2996/98692/Investigating-biodegradation-of-polyethylene-and
- [91] CET Journal. (2023). *Biodegradation of low-density polyethylene sheets using Aspergillus brasiliensis*. Retrieved from https://www.cetjournal.it/cet/23/99/067.pdf
- [52] ResearchGate. (n.d.). *The FTIR spectra of the degraded polyethylene (LDPE) strips and*

*pellets by bacterial*. Retrieved from https://www.researchgate.net/figure/The-FTIR-spectra-of-the-degraded-polyethylene-LDPE-strips-and-pellets-by-bacterial_fig3_303872553

- [53] The Madison Group. (n.d.). *Identifying Failures and Ensuring Quality of Plastics Using FTIR*. Retrieved from https://madisongroup.com/identifying-failures-and-ensuring-quality-of-plastic-materials/
- [54] MDPI. (2023). *FTIR Spectroscopy for Microplastic Analysis*. Polymers. Retrieved from https://www.mdpi.com/2073-4360/15/4/911
- [55] Jordi Labs. (n.d.). *Case Study: Degradation of PE by FTIR & HTGPC*. Retrieved from https://jordilabs.com/wp-content/uploads/filebase/Case_Study_Degradation_of_PE_FTIR_HTGPC.pdf
- [92] National Center for Biotechnology Information. (2021). *FTIR Analysis of Composted Materials*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC8585154/
- [56] ALS at LBL. (2024). *Use and misuse of FTIR spectroscopy for studying the bio-oxidation of plastics*. Retrieved from https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf
- [57] Agilent. (n.d.). *GPC/SEC Polymer Analysis Application Compendium*. Retrieved from https://www.agilent.com/cs/library/applications/5990-6970EN%20GPC%20SEC%20Polymers%20app%20compend.pdf
- [58] Technology Networks. (n.d.). *GPC/SEC Analysis of Polymer Degradation*. Retrieved from https://cdn.technologynetworks.com/tn/Resources/pdf/gpcsec-analysis-of-polymer-degradation.pdf
- [93] National Center for Biotechnology Information. (2021). *Photo-aged microplastics: Chemical characterization and degradation products*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC8234390/
- [51] MDPI. (2022). *Biodegradation of Plastics: A Review*. Applied Sciences. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [94] Sepscience. (n.d.). *GPC Analysis of Polymers: Measuring Molecular Weight and Distribution*. Retrieved from https://www.sepscience.com/gpc-analysis-of-polymers-measuring-molecular-weight-an

d-distribution-12025
- [95] ResearchGate. (n.d.). *Molecular weight analysis of the polymer*. Retrieved from https://www.researchgate.net/figure/Molecular-weight-analysis-of-the-polymer-aGPC-traces-of-the-polymer-before-sonication_fig9_369711714
- [62] ResearchGate. (n.d.). *Exploring the plastic degrading ability of microbial communities through metagenomic approach*. Retrieved from https://www.researchgate.net/publication/358887667_Exploring_the_plastic_degrading_ability_of_microbial_communities_through_metagenomic_approach
- [61] National Center for Biotechnology Information. (2020). *Metagenomic analysis of microbial population engaged in the plastic biodegradation*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7521044/
- [96] ResearchGate. (n.d.). *Review of microplastic degradation: Understanding metagenomic approaches for microplastic degrading organisms*. Retrieved from https://www.researchgate.net/publication/374243342_Review_of_microplastic_degradation_Understanding_metagenomic_approaches_for_microplastic_degrading_organisms
- [97] MDPI. (2025). *Biodegradation of Plastics by Halophilic Microbial Community*. Journal of Marine Science and Engineering. Retrieved from https://www.mdpi.com/2311-5637/11/4/227
- [85] Oxford Academic. (2025). *Metagenomic analysis of plastisphere communities*. FEMS Microbiology Ecology. Retrieved from https://academic.oup.com/femsec/article/101/5/fiaf035/8104280
- [29] NWO. (n.d.). *Unravelling and engineering a complete enzymatic degradation pathway for polyethylene*. Retrieved from https://www.nwo.nl/en/projects/apxwx12865
- [30] National Center for Biotechnology Information. (2024). *Re-evaluation of Putative Polyethylene Degrading Enzymes*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC11270687/
- [70] bioRxiv. (2025). *An AI-driven framework for the discovery and design of plastic-degrading enzymes*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.02.09.637306v1.full.pdf
- [98] Journal of Microbiology and Biotechnology. (2025). *A Cell-Free Protein Synthesis Platform for Rapid Screening of Plastic-Degrading Enzymes*. Retrieved from http://www.jmb.or.kr/journal/view.html?doi=10.4014/jmb.2503.03044

- [99] ACS. (n.d.). *Discovery of enzymes for biodegradation of polyethylene and polypropylene*. Retrieved from https://acs.digitellinc.com/p/s/discovery-of-enzymes-for-biodegradation-of-polyethylene-and-polypropylene-572172
- [100] ResearchGate. (n.d.). *Experimental investigations on polyethylene and polyethylene terephthalate microplastics' degradation: A review*. Retrieved from https://www.researchgate.net/publication/364700841_Experimental_investigations_on_polyethylene_and_polyethylene_terephthalate_microplastics'_degradation_A_review
- [69] ResearchGate. (n.d.). *Microbial degradation and deterioration of polyethylene - A review*. Retrieved from https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
- [25] Taylor & Francis Online. (2023). *Strategies to enhance the biodegradation of plastics*. Retrieved from https://www.tandfonline.com/doi/full/10.1080/07388551.2023.2170861
- [101] Frontiers in Microbiology. (2020). *Biodegradation of Low Density Polyethylene by Natural Bacteria*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.603210/full
- [73] Frontiers in Microbiology. (2023). *Engineering synthetic microbial consortia for polyethylene degradation*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
- [102] National Center for Biotechnology Information. (2023). *Recent advances in polyethylene degradation*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10598529/
- [9] National Center for Biotechnology Information. (2020). *Challenges in the microbial degradation of polyethylene*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
- [12] ResearchGate. (n.d.). *Biodegradability of polyethylene: Challenges and future perspectives*. Retrieved from https://www.researchgate.net/publication/385077019_Biodegradability_of_polyethylene_Challenges_and_future_perspectives
- [66] Sustainability Directory. (n.d.). *What challenges remain in scaling up production of plastic-eating enzymes?*. Retrieved from https://sustainability-directory.com/question/what-challenges-remain-in-scaling-up-prod

uction-of-plastic-eating-enzymes/

- [27] Frontiers in Microbiology. (2024). *Biodegradation of low-density polyethylene in agriculture*. Retrieved from https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
- [103] ACS Publications. (2018). *The Environmental Dilemma of Oxo-degradable and Biodegradable Plastics*. Environmental Science & Technology. Retrieved from https://pubs.acs.org/doi/10.1021/acs.est.7b04051
- [67] Sustainability Directory. (n.d.). *What are the key challenges to scaling up bioplastic production?*. Retrieved from https://sustainability-directory.com/question/what-are-the-key-challenges-to-scaling-up-bioplastic-production/
- [20] Ghatge, S., et al. (2020). *Biodegradation of polyethylene: a brief review*. Applied Biological Chemistry. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [51] MDPI. (2022). *Biodegradation of Plastics: A Review*. Applied Sciences. Retrieved from https://www.mdpi.com/2673-6209/3/2/23
- [21] MDPI. (2025). *Standardization of Methods for Plastic Biodegradation*. Molecules. Retrieved from https://www.mdpi.com/1420-3049/30/11/2462
- [104] ResearchGate. (n.d.). *Plastic Degradation: Challenges and Alternatives*. Retrieved from https://www.researchgate.net/publication/374388629_Plastic_Degradation_Challenges_and_Alternatives
- [105] National Center for Biotechnology Information. (2022). *Quantitative NMR for Microplastic Analysis*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC9919824/
- [106] ACS Publications. (2018). *Quantitative Assessment of Microplastics in Soil*. Analytical Chemistry. Retrieved from https://pubs.acs.org/doi/abs/10.1021/acs.analchem.8b00355
- [63] National Center for Biotechnology Information. (2020). *Biodegradation of Plastics in the Environment*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7023122/
- [64] ACS Publications. (2020). *Degradation Rates of Plastics in the Environment*. ACS Sustainable Chemistry & Engineering. Retrieved from https://pubs.acs.org/doi/10.1021/acssuschemeng.9b06635

- [47] IOSR Journals. (2024). *Biodegradation of Low-Density Polyethylene by Pseudomonas aeruginosa*. IOSR Journal of Environmental Science, Toxicology and Food Technology. Retrieved from https://www.iosrjournals.org/iosr-jestft/papers/Vol18-Issue12/Ser-3/C1812031217.pdf
- [38] bioRxiv. (2025). *Microbial degradation of a widely used model polyethylene is restricted to medium- and long-chain alkanes and their oxidized derivatives*. Retrieved from https://www.biorxiv.org/content/10.1101/2025.09.22.675545v2
- [65] MDPI. (2020). *Microbial Degradation of Polyethylene: A Review*. Polymers. Retrieved from https://www.mdpi.com/2073-4360/12/1/123
- [69] ResearchGate. (n.d.). *Microbial degradation and deterioration of polyethylene - A review*. Retrieved from https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
- [68] National Center for Biotechnology Information. (2023). *Microbial Degradation of Polyethylene: Mechanisms and Challenges*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
- [16] National Center for Biotechnology Information. (2020). *Microbial and Enzymatic Degradation of Petro-Polymers*. PMC. Retrieved from https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
- [107] Frontiers in Chemistry. (2021). *Biodegradable Plastics: Misconceptions and Truths*. Retrieved from https://www.frontiersin.org/journals/chemistry/articles/10.3389/fchem.2021.671750/full
- [23] MDPI. (2023). *Degradation of Polyethylene Materials*. Applied Sciences. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045
- [20] ResearchGate. (2020). *Biodegradation of polyethylene: a brief review*. Retrieved from https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
- [22] National Center for Biotechnology Information. (2020). *Challenges in the microbial degradation of polyethylene*. PMC. Retrieved from https://www.ncbi.nlm.nih.gov/pmc/articles/PMC7022683/
- [23] MDPI. (2023). *A comprehensive review of the different types of degradation that*

*polyethylene undergoes in the environment*. Applied Sciences. Retrieved from https://www.mdpi.com/2076-3417/13/5/3045

---

## Download Options

### Works cited

1. Polyethylene Market | Size, Share, Growth | 2025 - 2030, accessed on October 23, 2025, https://virtuemarketresearch.com/report/polyethylene-market
2. Polyethylene Market Size & Forecast 2024-2034 - Future Market Insights, accessed on October 23, 2025, https://www.futuremarketinsights.com/reports/polyethylene-market
3. Polyethylene - Wikipedia, accessed on October 23, 2025, https://en.wikipedia.org/wiki/Polyethylene
4. Understanding Polyethylene: Properties, Uses, and FAQs | Smart Turf® Artificial Grass, accessed on October 23, 2025, https://smartturf.com/polyethylene-explained
5. The Harmful Impact of Polyethylene: Understanding the Plastic Predicament - Medium, accessed on October 23, 2025, https://medium.com/@Eco_LifeMastery/the-harmful-impact-of-polyethylene-understanding-the-plastic-predicament-697eb4d60ab2
6. PLASTIC POLLUTION - IUCN, accessed on October 23, 2025, https://iucn.org/sites/default/files/2024-05/plastic-pollution-issues-brief-may-2024-update.pdf
7. Almost 70% of all plastic waste is produced by just 20 countries | Natural History Museum, accessed on October 23, 2025, https://www.nhm.ac.uk/discover/news/2024/september/almost-70-of-plastic-waste-produced-by-20-countries.html
8. Impacts of Plastic Pollution | US EPA, accessed on October 23, 2025, https://www.epa.gov/plastics/impacts-plastic-pollution
9. Challenges with Verifying Microbial Degradation of Polyethylene - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7022683/
10. A Review on Biodegradation of Polythene: The Microbial Approach | OMICS International, accessed on October 23, 2025, https://www.omicsonline.org/a-review-on-biodegradation-of-polythene-the-microbial-approach-2155-6199.1000164.php?aid=8679
11. Degradation of polyethylene plastic bags and bottles using microorganisms isolated from soils of Morogoro, Tanzania - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2022.1077588/full

12. Biodegradability of polyethylene: Challenges and future perspectives | Request PDF, accessed on October 23, 2025, https://www.researchgate.net/publication/385077019_Biodegradability_of_polyethylene_Challenges_and_future_perspectives
13. All About Polyethylene (PE): Structure, Properties & Uses - Exirpolymer, accessed on October 23, 2025, https://exirpolymer.com/all-about-polyethylene/
14. Evidence of Polyethylene Biodegradation by Bacterial Strains from the Guts of Plastic-Eating Waxworms - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/268154348_Evidence_of_Polyethylene_Biodegradation_by_Bacterial_Strains_from_the_Guts_of_Plastic-Eating_Waxworms
15. Polyethylene (PE): Structure, Properties, and Applications - Xometry, accessed on October 23, 2025, https://www.xometry.com/resources/materials/polyethylene/
16. Microbial and Enzymatic Degradation of Synthetic Plastics - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7726165/
17. You Use it Daily. But What IS Polyethylene Plastic? | Bollard Blog - Reliance Foundry, accessed on October 23, 2025, https://www.reliance-foundry.com/blog/polyethylene-plastic
18. Polyethylene (PE Plastic) – Structure, Properties & Toxicity - SpecialChem, accessed on October 23, 2025, https://www.specialchem.com/plastics/guide/polyethylene-plastic
19. Biodegradation of thermally treated high-density polyethylene (HDPE) by Klebsiella pneumoniae CH001 - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC5603451/
20. (PDF) Biodegradation of polyethylene: a brief review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/341433719_Biodegradation_of_polyethylene_a_brief_review
21. Current Approaches to Microplastics Detection and Plastic Biodegradation - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1420-3049/30/11/2462
22. Challenges with Verifying Microbial Degradation of Polyethylene ..., accessed on October 23, 2025, https://www.ncbi.nlm.nih.gov/pmc/articles/PMC7022683/
23. A Review of Degradation and Life Prediction of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2076-3417/13/5/3045
24. Opinion: We need better data about the environmental persistence of plastic goods - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7334500/
25. Full article: Enhancing plastic biodegradation process: strategies and opportunities, accessed on October 23, 2025, https://www.tandfonline.com/doi/full/10.1080/07388551.2023.2170861
26. Microbial Consortiums of Putative Degraders of Low-Density Polyethylene-Associated Compounds in the Ocean - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8941889/

27. Global perspectives on the biodegradation of LDPE in agricultural systems - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2024.1510817/full
28. Microbial Consortia: Synergistic Effects on Plastic Degradation and Enzyme Production, accessed on October 23, 2025, https://www.researchgate.net/publication/392897680_Microbial_Consortia_Synergistic_Effects_on_Plastic_Degradation_and_Enzyme_Production
29. Breaking the Unbreakable: Computational and Biochemical Identification of Polyethylene-Degrading Enzymes | NWO, accessed on October 23, 2025, https://www.nwo.nl/en/projects/apxwx12865
30. Characterization of Potential Plastic-Degradation Enzymes from Marine Bacteria - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC11270687/
31. Fungal enzymes for the degradation of polyethylene: Molecular docking simulation and biodegradation pathway proposal - Universidad Politécnica de Tlaxcala, accessed on October 23, 2025, http://uptlax.edu.mx/wp-content/uploads/2023/11/Fungal-enzymes-for-the-degradation-of-polyethylene-Molecular-docking-min.pdf
32. Fungal Enzymes Involved in Plastics Biodegradation - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9230134/
33. Biodegradation of Low Density Polyethylene by the Fungus Cladosporium sp. Recovered from a Landfill Site - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2309-608X/9/6/605
34. Low-Density Polyethylene Film Biodegradation Potential by Fungal Species from Thailand, accessed on October 23, 2025, https://www.mdpi.com/2309-608X/7/8/594
35. Biodegradation of plastic polymers by fungi: a brief review - PMC - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10991219/
36. (PDF) Multi-omics approach reveals new insights into the gut microbiome of Galleria mellonella (Lepidoptera:Pyralidae) exposed to polyethylene diet - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/352154940_Multi-omics_approach_reveals_new_insights_into_the_gut_microbiome_of_Galleria_mellonella_Lepidoptera_Pyralidae_exposed_to_polyethylene_diet
37. Polyethylene Degradation by a Rhodococcous Strain Isolated from Naturally Weathered Plastic Waste Enrichment | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.3c03778
38. Microbial degradation of a widely used model polyethylene is restricted to medium- and long-chain alkanes and their oxidized derivatives | bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.09.22.675545v2
39. Development of plastic-degrading microbial consortia by induced selection in

microcosms, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1143769/full
40. Microbial Biodegradation of Synthetic Polyethylene and Polyurethane Polymers by Pedospheric Microbes: Towards Sustainable Environmental Management - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/17/2/169
41. Biodegradability of polyethylene by bacteria and fungi from Dandora dumpsite Nairobi-Kenya | PLOS One - Research journals, accessed on October 23, 2025, https://journals.plos.org/plosone/article?id=10.1371/journal.pone.0198446
42. Evaluation of PET Degradation Using Artificial Microbial Consortia - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2021.778828/full
43. Biodegradation of Polyethylene and Polystyrene by Greater Wax Moth Larvae (Galleria mellonella L.) and the Effect of Co-diet Supplementation on the Core Gut Microbiome | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.9b07044
44. Role of the intestinal microbiome in low-density polyethylene degradation by caterpillar larvae of the greater wax moth, Galleria mellonella | Proceedings of the Royal Society B - Journals, accessed on October 23, 2025, https://royalsocietypublishing.org/doi/10.1098/rspb.2020.0112
45. The Bacterial and Fungal Gut Microbiota of the Greater Wax Moth, Galleria mellonella L. Consuming Polyethylene and Polystyrene - PMC - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9294514/
46. Assessing the Biodegradation of Low-Density Polyethylene Films by Candida tropicalis SLNEA04 and Rhodotorula mucilaginosa SLNEA05 - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1424-2818/16/12/759
47. Preliminary Study On Biodegradation Of Polyethylene By Pseudomonas Aeruginosa - IOSR Journal, accessed on October 23, 2025, https://www.iosrjournals.org/iosr-jestft/papers/Vol18-Issue12/Ser-3/C1812031217.pdf
48. SEM analysis of LDPE biodegradation at different resolutions (500×,... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/SEM-analysis-of-LDPE-biodegradation-at-different-resolutions-500-2-500-a-control_fig4_364082699
49. Biodegradation of low density polyethylene (LDPE) by fungi isolated from marine water– a SEM analysis - International Scholars Journals, accessed on October 23, 2025, https://www.internationalscholarsjournals.com/articles/biodegradation-of-low-density-polyethylene-ldpe-by-fungi-isolated-from-marine-water-a-sem-analysis.pdf
50. Low-density polyethylene biodegradation by the Pantoea sp. TR-C2 isolated from seabed sediment - Bioflux, accessed on October 23, 2025, https://bioflux.com.ro/docs/2024.2735-2741.pdf

51. Biodegradation of Polymers: Stages, Measurement, Standards and Prospects - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2673-6209/3/2/23
52. The FTIR spectra of the degraded polyethylene (LDPE strips and pellets)... - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/The-FTIR-spectra-of-the-degraded-polyethylene-LDPE-strips-and-pellets-by-bacterial_fig3_303872553
53. Identifying Failures and Ensuring Quality of Plastics Using FTIR - The Madison Group, accessed on October 23, 2025, https://madisongroup.com/identifying-failures-and-ensuring-quality-of-plastic-materials/
54. Fourier Transform Infrared Spectroscopy to Assess the Degree of Alteration of Artificially Aged and Environmentally Weathered Microplastics - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/15/4/911
55. Degradation of Polyethylene by FTIR and High Temperature GPC CASE STUDY Degradation of Polyethylene by FTIR and High Temperatur - Jordi Labs, accessed on October 23, 2025, https://jordilabs.com/wp-content/uploads/filebase/Case_Study_Degradation_of_PE_FTIR_HTGPC.pdf
56. Use and misuse of FTIR spectroscopy for studying the bio-oxidation of plastics - Advanced Light Source, accessed on October 23, 2025, https://als.lbl.gov/infrared-site/wp-content/uploads/sites/17/2024/03/Use-and-misuse-of-FTIR-spectroscopy-for-studying-the-bio-oxidation-of-plastics.pdf
57. Analysis of engineering polymers by GPC/SEC - Agilent, accessed on October 23, 2025, https://www.agilent.com/cs/library/applications/5990-6970EN%20GPC%20SEC%20Polymers%20app%20compend.pdf
58. GPC/SEC Analysis of Polymer Degradation - Technology Networks, accessed on October 23, 2025, https://cdn.technologynetworks.com/tn/Resources/pdf/gpcsec-analysis-of-polymer-degradation.pdf
59. Reliable and Sophisticated Techniques to Evaluate LDPE Degraded Compounds by Streptomyces werraensis SDJM, accessed on October 23, 2025, https://neptjournal.com/upload-images/(15)B-3772.pdf
60. Low and high-density polyethylene and expanded polystyrene biodegradation by the greater wax moth Galleria mellonella L reveals a key role of the gut microbiome | Request PDF - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/390092565_Low_and_high-density_polyethylene_and_expanded_polystyrene_biodegradation_by_the_greater_wax_moth_Galleria_mellonella_L_reveals_a_key_role_of_the_gut_microbiome
61. Metagenomic Exploration of Plastic Degrading Microbes for Biotechnological Application - PMC - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7521044/
62. Exploring the plastic degrading ability of microbial communities through metagenomic approach - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/358887667_Exploring_the_plastic_degr

ading_ability_of_microbial_communities_through_metagenomic_approach
63. Degradation of Plastics under Anaerobic Conditions: A Short Review - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC7023122/
64. Degradation Rates of Plastics in the Environment - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acssuschemeng.9b06635
65. Challenges with Verifying Microbial Degradation of Polyethylene - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2073-4360/12/1/123
66. What Challenges Remain in Scaling up Production of Plastic-Eating Enzymes? → Question, accessed on October 23, 2025, https://sustainability-directory.com/question/what-challenges-remain-in-scaling-up-production-of-plastic-eating-enzymes/
67. What Are the Key Challenges to Scaling up Bioplastic Production? - Sustainability Directory, accessed on October 23, 2025, https://sustainability-directory.com/question/what-are-the-key-challenges-to-scaling-up-bioplastic-production/
68. Assembly strategies for polyethylene-degrading microbial consortia based on the combination of omics tools and the “Plastisphere” - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10150012/
69. Microbial degradation and deterioration of polyethylene – A review | Request PDF, accessed on October 23, 2025, https://www.researchgate.net/publication/259995084_Microbial_degradation_and_deterioration_of_polyethylene_-_A_review
70. Protein language models accelerate the discovery of Plastic-Degrading Enzymes - bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2025.02.09.637306v1.full.pdf
71. Polyethylene biodegradation - DiVA portal, accessed on October 23, 2025, https://ltu.diva-portal.org/smash/get/diva2:1955313/FULLTEXT01.pdf
72. Harnessing microbial consortia to tackle plastic pollution, accessed on October 23, 2025, https://dev-www.igb.illinois.edu/article/harnessing-microbial-consortia-tackle-plastic-pollution
73. Assembly strategies for polyethylene-degrading microbial consortia based on the combination of omics tools and the “Plastisphere” - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2023.1181967/full
74. Low-density Polyethylene (LDPE) - Plastic Waste Management Market Statistics, accessed on October 23, 2025, https://www.grandviewresearch.com/horizon/statistics/plastic-waste-management-market/polymer-type/low-density-polyethylene-ldpe/global
75. Plastics – the fast Facts 2024, accessed on October 23, 2025, https://plasticseurope.org/knowledge-hub/plastics-the-fast-facts-2024/
76. Understanding Polyethylene Plastic: Properties, Uses, and Environmental Impact, accessed on October 23, 2025,

https://pom-material.com/blog/is-polyethylene-plastic/
77. Occurrence, toxicity and remediation of polyethylene terephthalate plastics. A review - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8755403/
78. Impact of HDPE Recycling On Our Environment - Accel Polymers llc., accessed on October 23, 2025, https://accelpolymers.com/2024/02/01/impact-of-hdpe-recycling-on-our-environment/
79. Isolation and Characterization of Polyethylene and Polyethylene Terephthalate-degrading Bacteria from Jakarta Bay, Indonesia - The Open Biotechnology Journal, accessed on October 23, 2025, https://openbiotechnologyjournal.com/VOLUME/18/ELOCATOR/e18740707280343/
80. A marine fungus efficiently degrades polyethylene - bioRxiv, accessed on October 23, 2025, https://www.biorxiv.org/content/10.1101/2021.11.19.469330.full
81. There are 5 types of fungus that can eat plastic : r/Anticonsumption - Reddit, accessed on October 23, 2025, https://www.reddit.com/r/Anticonsumption/comments/1cw3riw/there_are_5_types_of_fungus_that_can_eat_plastic/
82. Plastic-Degrading Microbial Consortia from a Wastewater Treatment Plant | MDPI, accessed on October 23, 2025, https://www.mdpi.com/1422-0067/25/23/12747
83. Biodegradation of Polystyrene by Galleria mellonella: Identification of Potential Enzymes Involved in the Degradative Pathway - MDPI, accessed on October 23, 2025, https://www.mdpi.com/1422-0067/25/3/1576
84. CN103980535A - Method of degrading polyethylene by extracellular laccase of bacillus - Google Patents, accessed on October 23, 2025, https://patents.google.com/patent/CN103980535A/en
85. Microplastic biofilms as potential hotspots for plastic biodegradation and nitrogen cycling: a metagenomic perspective | FEMS Microbiology Ecology | Oxford Academic, accessed on October 23, 2025, https://academic.oup.com/femsec/article/101/5/fiaf035/8104280
86. Methods of Analyses for Biodegradable Polymers: A Review - OUCI, accessed on October 23, 2025, https://ouci.dntb.gov.ua/en/works/4gBygk07/
87. Analytical methods for the investigation of enzyme-catalyzed degradation of polyethylene terephthalate - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/350556582_Analytical_methods_for_the_investigation_of_enzyme-catalyzed_degradation_of_polyethylene_terephthalate
88. Analytical method development, validation, and out-of-specification investigations for polyethylene glycol. | Semantic Scholar, accessed on October 23, 2025, https://www.semanticscholar.org/paper/Analytical-method-development%2C-validation%2C-and-for-Huang-Chu/a4139188a4b13518864042f1027c0f8bfc4ba57e
89. Methods of Analyses for Biodegradable Polymers: A Review - PMC - PubMed Central, accessed on October 23, 2025,

https://pmc.ncbi.nlm.nih.gov/articles/PMC9694517/
90. Investigating biodegradation of polyethylene and polypropylene microplastics in Tehran DWTPs | Water Science & Technology | IWA Publishing, accessed on October 23, 2025, https://iwaponline.com/wst/article/88/11/2996/98692/Investigating-biodegradation-of-polyethylene-and
91. Evaluation of the Biodegradation Process of Low-density Polyethylene by Aspergillus brasiliensis in Soil - Chemical Engineering Transactions, accessed on October 23, 2025, https://www.cetjournal.it/cet/23/99/067.pdf
92. Assessment of the Decomposition of Oxo- and Biodegradable Packaging Using FTIR Spectroscopy - PMC, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8585154/
93. A Systematic Study on the Degradation Products Generated from Artificially Aged Microplastics - PubMed Central, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC8234390/
94. GPC Analysis of Polymers: Measuring Molecular Weight and Distribution, accessed on October 23, 2025, https://www.sepscience.com/gpc-analysis-of-polymers-measuring-molecular-weight-and-distribution-12025
95. Molecular weight analysis of the polymer. a) GPC traces of the polymer... | Download Scientific Diagram - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/figure/Molecular-weight-analysis-of-the-polymer-aGPC-traces-of-the-polymer-before-sonication_fig9_369711714
96. (PDF) Review of microplastic degradation: Understanding metagenomic approaches for microplastic degrading organisms - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/374243342_Review_of_microplastic_degradation_Understanding_metagenomic_approaches_for_microplastic_degrading_organisms
97. New Halophilic Community Degrades Plastics: A Metagenomic Study - MDPI, accessed on October 23, 2025, https://www.mdpi.com/2311-5637/11/4/227
98. Rapid Screening of Plastic-Degrading Enzymes Using an Optimized Cell-Free Protein Synthesis Platform - Journal of Microbiology and Biotechnology, accessed on October 23, 2025, http://www.jmb.or.kr/journal/view.html?doi=10.4014/jmb.2503.03044
99. Discovery of enzymes for biodegradation of polyethylene and polypropylene, accessed on October 23, 2025, https://acs.digitellinc.com/p/s/discovery-of-enzymes-for-biodegradation-of-polyethylene-and-polypropylene-572172
100. Experimental investigations on polyethylene and polyethylene terephthalate microplastics' degradation. A review - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/364700841_Experimental_investigations_on_polyethylene_and_polyethylene_terephthalate_microplastics'_degradation_A_review

101. Biodegradation of Unpretreated Low-Density Polyethylene (LDPE) by Stenotrophomonas sp. and Achromobacter sp., Isolated From Waste Dumpsite and Drilling Fluid - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/microbiology/articles/10.3389/fmicb.2020.603210/full
102. Recent developments in bio-based polyethylene: Degradation studies, waste management and recycling - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC10598529/
103. Biodegradability of Plastics: Challenges and Misconceptions | Environmental Science & Technology - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/10.1021/acs.est.7b04051
104. Plastic Degradation: Challenges and Alternatives | Request PDF - ResearchGate, accessed on October 23, 2025, https://www.researchgate.net/publication/374388629_Plastic_Degradation_Challenges_and_Alternatives
105. Multi-Analytical Approach to Characterize the Degradation of Different Types of Microplastics: Identification and Quantification of Released Organic Compounds - PMC - NIH, accessed on October 23, 2025, https://pmc.ncbi.nlm.nih.gov/articles/PMC9919824/
106. Quantitative Analysis of Poly(ethylene terephthalate) Microplastics in Soil via Thermogravimetry–Mass Spectrometry | Analytical Chemistry - ACS Publications, accessed on October 23, 2025, https://pubs.acs.org/doi/abs/10.1021/acs.analchem.8b00355
107. Bridging Three Gaps in Biodegradable Plastics: Misconceptions and Truths About Biodegradation - Frontiers, accessed on October 23, 2025, https://www.frontiersin.org/journals/chemistry/articles/10.3389/fchem.2021.671750/full