



34% Triple Junction GaAs Solar Cell Assembly

Type: TJ Solar Cell Assembly 3T34A



This cell type is an InGaP/GaAs/Ge on Ge substrate triple junction solar cell (efficiency class 34%) with attached interconnectors and cover glass. The solar cell assembly has an improved grid-design and is equipped with an integrated bypass diode, which protects the adjacent cell in the string. Based on our space solar cell assemblies, the whole design of the 3T34A assembly was further developed and adapted to terrestrial application.



Copyright © 2015 AZUR SPACE Solar Power GmbH

DB 0003569-02-0 Issue: 2019-02-26 Page 1 of 2 Theresienstr. 2 74072 Heilbronn

phone: +49 7131 67 2603 telefax: +49 7131 67 2727 e-mail: info@azurspace.com website: www.azurspace.de Certified Company

ISO 9001 ISO 14001 OHSAS 18001

3T34A

34% Triple Junction GaAs Solar Cell Assembly

Type: TJ Solar Cell Assembly 3T34A



Design and Mechanical Data


| Base Material | GalnP/GaAs/Ge on Ge substrate |
|--|--|
| AR-coating | TiO _x /Al ₂ O ₃ |
| Dimensions | 40.15 x 80.15 mm ± 0.1 mm |
| Cell Area | 30.18 cm ² |
| Average Weight | ≤ 116 mg/cm² |
| Thickness | 280 ± 25 μm |
| Cover glass | CMX 100 |
| Cover glass thickness | 100μm |
| Interconnectors (3 x front side/ 1x diode) | Kovar, Ag |
| Dimensions (interconnector) | 6.5 x 7.53 mm |
| Interconnector thickness | 25 μm |
| | |



Electrical Data (SCA)

BOL Average Open Circuit Voc 2679 [mV] 441 Average Short Circuit Isc [mA] Voltage at max. Power V_{mp} [mV] 2440 Current at max. Power Imp [mA] 424 Power at MPP point P_{mp} [mW] 1035 34.3 Average Efficiency nbare [%]

EQE chart



Spectrum: AM1.5g ASTM-G173-03; 1000 W/m2; T=25°C

Acceptance Values (SCA)

| Voltage V _{op} | 2300 mV |
|---|---------|
| Min. average current I _{op avg} @ V _{op} | 435 mA |
| Min. individual current I _{op min} @ V _{op} | 420 mA |
| Min. averaged efficiency (lot) eta avg | 34.0 % |

Shadow protection (SCA)

| Integrated protection diode | $V_{forward}$ (500 mA) \leq 2.5 V |
|-----------------------------|-------------------------------------|
| T = 25°C ± 3°C | $I_{reverse}$ (2.8 V) \leq 1.0 mA |



Temperature Gradients (25°C - 80°C)

| | | | BOL | | | |
|-----------------------|-------------------------------------|---------|-------|--|--|--|
| Open Circuit Voltage | $\Delta V_{oc}/\Delta T \uparrow$ | [mV/°C] | - 6.0 | | | |
| Short Circuit Current | $\Delta I_{sc}/\Delta T \uparrow$ | [mA/°C] | 0.32 | | | |
| Voltage at max. Power | $\Delta V_{mp} / \Delta T \uparrow$ | [mV/°C] | - 6.1 | | | |
| Current at max. Power | $\Delta I_{mp}/\Delta T \uparrow$ | [mA/°C] | 0.28 | | | |



Threshold Values

| 11110011010 | |
|--------------|--|
| Absorptivity | ≤ 0.91 (with CMX 100 AR) |
| Pull Test | > 1.6 N with 12.5µm Ag stripes by pulling at 45° |

Copyright © 2015 AZUR SPACE Solar Power GmbH

DB 0003569-02-0 Issue: 2019-02-26 Page 2 of 2 **AZUR SPACE Solar Power GmbH**

Theresienstr. 2 74072 Heilbronn

phone: +49 7131 67 2603 telefax: +49 7131 67 2727 e-mail: info@azurspace.com website: www.azurspace.de Certified Company

ISO 9001 ISO 14001 OHSAS 18001

