

Perez Textile Conservation

Textile Conservation Studio
47 Pond Street (Ground Floor Studio), Jamaica Plain, MA 02130
(617) 555-3800 | jesse.perez@Finthesiss.ai

TREATMENT DOCUMENTATION RECORD

Studio project	PTC-2025-014	Object	Oaxacan handwoven wool textile, 19th century
Owner/Client	Private collection (via referral, Dr. Amina Rashid)	Conservator	Jesse Perez
Start date	January 5, 2026	Estimated completion	November 2026
Accession ref.	HARTWELL-OAX-01	Object dimensions	112 x 158 cm

OBJECT DESCRIPTION

19th century handwoven wool textile from Oaxaca, Mexico. Warp-faced plain weave with supplementary weft floats forming geometric banded patterning. Z-spun warp threads, estimated 22 per centimeter. Natural dye palette: red (likely cochineal, aluminium mordant), yellow (unidentified plant source, chromate mordant possible given post-1850 date range), indigo blue, natural cream.

CONDITION AT INTAKE

Overall condition: Fair. Warp thread loss in central field, approximately 8 percent of ground fabric affected across a 14 x 22 cm zone in the lower right quadrant. Some weft displacement adjacent to the loss zone. Light surface soiling throughout. Minor planar distortion at upper corners from previous storage folded. Dyes visually stable under examination light. UV fluorescence suggests possible chrome mordant in yellow areas (further analysis deferred).

TREATMENT PHASES

Phase	Description	Date	Status
1	Examination, photography, fiber and dye assessment	Jan 5-8, 2026	Complete
2	Surface cleaning, dry method, with low-suction aspirator	Jan 12-14, 2026	Complete
3	Humidification, localized, upper corners	Jan 19-22, 2026	Complete
4	Warp consolidation, Paraloid B-72 3% in ethanol, micro-dropper	Feb 3-14, 2026	In progress
5	Stitching consolidation - replacement warp supports	Feb 2026 to Oct 2026	Planned
6	Final photography and condition report	Nov 2026	Planned

MATERIALS USED

Paraloid B-72 (3% in ethanol) for thread consolidation. Linen thread 26/2 nm, natural undyed (lot 2025-T-14) for replacement warp supports. Hollytex polyester 3256 as working interleave. Deionized water for localized humidification via ultrasonic mist. No aqueous immersion or solvent cleaning due to uncharacterized yellow dye.

All materials are reversible or removable. No adhesives applied directly to textile surface.