



Powder



Applications

Recommended markets

No data available

Availability

 **Product Status:** COMMERCIAL

GrapheneBlack™ OX properties

Other properties

Supplier data

SI units

Imperial units

Properties	Value & unit	Test condition	Test method
Ash Content	2.85 %	Residue on Ignition, , Thermogravimetric Analysis. By Weight	
Carbon Content	> 95 %		
Decomposition Temperature	600 °C		
Density	2.2 g/cm³		
Density, Bulk	0.14 g/cm³		
Impurities	< 1 %		
Melting Point	4500 °C		
Moisture Content	< 0.6 %	Thermogravimetric Analysis. By Weight	
Number of Layers	6 – 10	Up to 90% of flakes	
Oxygen Content	3.5 %		
Particle Size	0.5 – 1 µm	Statistical TEM Analysis	
Particle Size Distribution, Median	13 µm	Laser Diffraction	
Sulfur Content	0.25 %		

GrapheneBlack™ OX

By [NANOXPLORE](#)

Related products

With Samples Available (3)



Type a product name, supplier or product family

For Suppliers



BIRLA CARBON

NC7000™
by Birla Carbon

[See the product →](#)

BIRLA CARBON

Elastocyl™ HTV1003
by Birla Carbon

[See the product →](#)



Epocyl™ 128-05
by Birla Carbon

[See the product →](#)

GrapheneBlack™ 0X

By [NANOXPLORE](#)



We resolve the complexity of your material selection thanks to Product Data, Knowledge and Assistance.

ABOUT

- Why SpecialChem?
- About Us
- For suppliers
- Career
- Join expert team
- Contact Us
- News
- Program Analytics

INDUSTRIES SERVED

- Plastic & Elastomers
- Coating Ingredients
- Polymer Additives
- Adhesives Ingredients
- Cosmetic Ingredients

Follow Us LinkedIn

[Terms and Conditions](#) [Privacy Policy](#) [Cookie Policy](#) @SpecialChem 2026