

INDUSTRIAL MINERALS / 05

Bentonite

Montmorillonite Clay

ORIGIN
India — Gujarat / Rajasthan
PRODUCT TYPE
Industrial Mineral
AVAILABLE TYPES
Sodium, Calcium
INCOTERMS
FOB, CIF
MOQ
1 x 20' FCL
LEAD TIME
Confirmed at Quotation

Other Incoterms (EXW, CFR, DDP) available on request. Lead time depends on destination, carrier schedules and each country's own import/customs rules — we confirm an exact shipment date once the destination port is known.

TECHNICAL SPECIFICATIONS

PARAMETER	SODIUM BENTONITE	CALCIUM BENTONITE
Swelling Index	15 ml/2g Min.	2 – 5 ml/2g
Montmorillonite Content	80% Min.	75% Min.
Moisture	Max. 12%	Max. 12%
Mesh	200 Mesh	200 Mesh

Values shown are commercial ranges. Sodium and Calcium Bentonite differ in exchangeable cation content. Swelling Index is the parameter drilling-fluid buyers check first.

PACKAGING

25 kg & 50 kg PP Woven Bags | 1000 kg Jumbo Bags

Other sizes and custom packaging are available on request.

DOCUMENTATION

Certificate of Analysis (COA) | Certificate of Origin

Additional certification available on request.

APPLICATIONS

- **Drilling Fluids** — Sodium type
- **Foundry** — Sand binder
- **Iron Ore Pelletizing** — Binder