

INDUSTRIAL MINERALS / 02

Potash Feldspar

K-Feldspar/Orthoclase

ORIGIN
India — Rajasthan
PRODUCT TYPE
Industrial Mineral
AVAILABLE FORMS
Lumps, Powder
INCOTERMS
FOB, CIF
MOQ
1 x 20' FCL
LEAD TIME
Confirmed at Quotation

Other Incoterms (EXW, CFR, DDP) available on request. Lead time depends on destination, carrier schedules and each country's own import/customs rules — we confirm an exact shipment date once the destination port is known.

TECHNICAL SPECIFICATIONS

PARAMETER	LUMPS	POWDER
K ₂ O	8% — 10%	8% — 10%
Fe ₂ O ₃	Max. 0.1%	Max. 0.1%
Al ₂ O ₃	18% — 20%	18% — 20%
Size / Mesh	10 — 40 mm	100 / 200 Mesh

Values shown are commercial ranges. K₂O content distinguishes this from Soda Feldspar and is the number ceramics and glaze formulators check first, since it directly affects firing temperature and the glassy phase a glaze develops. If you're unsure which of the two feldspars your formulation calls for, tell us the target firing range and we can recommend accordingly.

PACKAGING

25 kg & 50 kg PP Woven Bags | 1000 kg Jumbo Bags

Other sizes and custom packaging are available on request.

DOCUMENTATION

Certificate of Analysis (COA) | Certificate of Origin

Additional certification available on request.

APPLICATIONS

- **Ceramics** — Glaze, body flux
- **Glass Mfg.** — Flux material
- **Sanitaryware** — Vitrification