

INDUSTRIAL MINERALS / 03

Soda Feldspar

Sodium Feldspar | Albite



Soda Feldspar export from India. Lumps and Powder forms. Na₂O 8-10%. FOB/CIF Mundra, Kandla.

ORIGIN	PRODUCT TYPE	AVAILABLE TYPES
India — Rajasthan	Industrial Mineral	Lumps, Powder
INCOTERMS	MOQ	LEAD TIME
FOB, CIF	1 x 20' FCL	Confirmed at Quotation

Other Incoterms (EXW, CFR, DDP) available on request. Lead time depends on destination, carrier schedules and each country's own import/customs rules — we confirm an exact shipment date once the destination port is known.

Specifications by Form

PARAMETER	LUMPS	POWDER
Na₂O	8% — 10%	8% — 10%
Fe₂O₃	Max. 0.1%	Max. 0.1%
Al₂O₃	18% — 20%	18% — 20%
Size / Mesh	10 — 40 mm	100 / 200 Mesh

Values shown are commercial ranges. Na₂O content distinguishes this from Potash Feldspar and is the number glass and sanitaryware manufacturers check first, since sodium fluxes at a lower temperature than potassium and shifts the melting/firing curve. If you're unsure which of the two feldspars your formulation calls for, tell us the target firing range and we can recommend accordingly.

Packaging

25 kg & 50 kg PP Woven Bags · 1000 kg Jumbo Bags
Other sizes and custom packaging are available on request.

Documentation

Certificate of Analysis (COA) · Certificate of Origin
Additional certification available on request.

Applications

Glass Mfg. — Flux material

Ceramics — Glaze, body flux

Sanitaryware — Vitrification

Quality & Assurance

Agreed specification

Every shipment ships against an agreed spec and Certificate of Analysis.

Independent inspection

Third-party inspection (SGS/Intertek) at buyer's cost before loading.

Multiple sources

Multiple producers per product — spec matched to buyer, not one mill's output.