POLYMER-MODIFIED TILE ADHESIVE

# LIVO-FIX

## Premium Tile Adhesive

For interior floor and wall tile fixing

LIVO-FIX is a polymer-modified, cement-based tile adhesive for fixing ceramic, porcelain and vitrified tiles, and natural stone, on interior floors and walls. Its extended open time and slip resistance make it easy to use on vertical and horizontal surfaces, in wet and dry areas, in homes, commercial buildings and public spaces, and for tile-on-tile work.

| INDIAN STANDARD | EUROPEAN STANDARD |
|---|---|
| **IS 15477:2019** | **EN 12004** |
| **Type 2T** | **Class C2TE** |

Test results are given on page 2.




LIVO-FIX · 20 kg bag

## KEY FEATURES

**01** **High bond strength**
Tensile adhesion of 1.32 N/mm² or better at 28 days, tested to IS 15477:2019.

**02** **Extended open time (E)**
Minimum 30 minutes open time, with about 35 minutes of adjustability.

**03** **Slip and water resistant (T)**
Non-slip for vertical fixing. Tested after water immersion, heat ageing and freeze–thaw cycles.

**04** **Floors, walls and tile on tile**
Suits interior floors and walls in wet and dry areas, and fixing tile over existing tile.

## RECOMMENDED APPLICATIONS

| APPLICATION | SUITABLE FOR | NOTES |
|---|---|---|
| **Interior floors and walls** | Ceramic, porcelain and vitrified tiles; natural stone | For horizontal and vertical surfaces. |
| **Wet and dry areas** | Domestic, commercial and public spaces | Waterproof the substrate where the design requires. |
| **Tile on tile** | Over existing floor and wall tiles | Existing tiles must be sound, clean and firmly bonded. |

## APPLICATION PROPERTIES

| | |
|---|---|
| **Colour** | Grey and white |
| **Mixing ratio, powder : water** | 1 : 0.25–0.28 (grey) · 1 : 0.26–0.29 (white), by weight<br>Approx. 4–5 L of water per 20 kg bag |
| **Mixed density** | 1.7 – 1.85 kg/litre |
| **Open time** | Minimum 30 minutes |
| **Adjustability** | Approx. 35 minutes |
| **Pot life** | Approx. 120 minutes |
| **Application temperature** | 5 °C to 35 °C (substrate and material) |
| **Adhesive thickness** | 3 – 12 mm |
| **VOC content (EPA Method 24)** | < 1.2 g/kg |
| **Setting / trafficable / grouting time** | 24 hours |

## PERFORMANCE PROPERTIES

### A. EN 12004 and ISO 13007 — Class C2TE

| TEST PROPERTY | REQUIREMENT | TEST RESULT |
|---|---|---|
| Tensile adhesion strength, after 28 days | ≥ 1.0 N/mm² | **≥ 1.35 N/mm²** |
| Tensile adhesion strength after water immersion | ≥ 1.0 N/mm² | **≥ 1.1 N/mm²** |
| Tensile adhesion strength after heat ageing | ≥ 1.0 N/mm² | **≥ 1.18 N/mm²** |
| Tensile adhesion strength after freeze–thaw cycles | ≥ 1.0 N/mm² | **≥ 1.18 N/mm²** |
| Slip resistance (T) | ≤ 0.5 mm | **< 0.5 mm** |
| Extended open time (E), at 30 minutes | ≥ 0.5 N/mm² | **≥ 0.5 N/mm²** |

C = cementitious · 2 = improved · T = reduced slip · E = extended open time.

### B. IS 15477:2019 — Type 2T

| TEST PROPERTY | REQUIREMENT | TEST RESULT |
|---|---|---|
| Tensile adhesion, dry condition, after 28 days | ≥ 1.0 N/mm² | **≥ 1.32 N/mm²** |
| Tensile adhesion, wet condition | ≥ 1.0 N/mm² | **≥ 1.25 N/mm²** |
| Shear adhesion, dry condition | ≥ 1.25 N/mm² | **≥ 1.61 N/mm²** |
| Shear adhesion, wet condition | ≥ 1.0 N/mm² | **≥ 1.58 N/mm²** |
| Shear adhesion, heat ageing | ≥ 1.0 N/mm² | **≥ 1.62 N/mm²** |
| Slip resistance (T) | ≤ 0.5 mm | **< 0.5 mm** |

**Note.** Test results are indicative and follow the test methods in the relevant standards. They may vary with the substrate, site conditions and testing equipment. Field performance depends on installation methods and site conditions.

## SURFACE PREPARATION

- The substrate must be level, cured, sound, compact, rigid and dry, and free from dust, oil, paint or any other debonding agent, and from rising damp.
- Surfaces must be plumb and true to within 6 mm in 3 m (10 ft).
- Dampen dry or dusty surfaces with water and sweep off any excess water before applying the adhesive.
- Damp-cure new concrete slabs and allow them to reach 28 days before tiling, to reduce shrinkage movement at the tile bed.
- Provide expansion joints and fill them with a suitable sealant. Do not cover them with adhesive or tile.
- For wet areas, waterproof the substrate as the project design requires.

## MIXING AND APPLICATION

1. **Measure.** Pour approx. 4–5 litres of clean water per 20 kg bag into a clean container.
2. **Mix.** Add the powder gradually. Mix by hand trowel or with a slow-speed mixer to a smooth, uniform paste. Control the water ratio when mixing mechanically and do not add excess water.
3. **Mature.** Let the mix stand for 10–15 minutes, then remix before use.
4. **Apply.** Spread with the straight edge of a notched trowel, then comb with the notched side for an even thickness. Use a 6–10 mm notch as the tile requires.
5. **Fix.** Make sure the back of the tile is fully covered. Press the tile in, then tap all four corners and the centre with a rubber hammer or wooden roller to release trapped air and spread the adhesive evenly.
6. **Grout.** Grout after 24 hours, using a suitable cementitious or epoxy tile grout.

## COVERAGE & PACK

Approx. 5–6 m² per 20 kg bag at 3 mm thickness, using a 6 × 6 mm notch.

Coverage varies with notch size, tile type and the evenness of the substrate.

**Pack size:** 20 kg bag

## STORAGE & SHELF LIFE

**12 months** in the sealed original pack.

Store under cover, away from direct sunlight, in damp-proof conditions and protected from extremes of temperature.

## HEALTH & SAFETY

Keep out of reach of children. Wear protective clothing, gloves and eye/face protection. After skin contact, wash immediately with plenty of clean water. In case of eye contact, rinse immediately with plenty of clean water and seek medical advice. For professional use only. Refer to the Safety Data Sheet, available on request.

**LIVORA TECHNICAL SUPPORT**

Email livorachemicals@gmail.com

Web www.livorachemicals.com



Information in this data sheet is given in good faith, for guidance only. Site conditions vary; for work outside the stated applications, consult the LIVORA technical team. Always use the latest revision.