

An In-depth Technical Guide to the Safe Handling of Picryl Chloride for Researchers and Scientists

Author: BenchChem Technical Support Team. **Date:** April 2026

Compound of Interest

Compound Name: *Picryl chloride*

CAS No.: *88-88-0*

Cat. No.: *B1203447*

[Get Quote](#)

For Immediate Release

This technical guide provides a comprehensive overview of the safety and handling precautions for **Picryl chloride** (2-Chloro-1,3,5-trinitrobenzene), a highly explosive and toxic compound. This document is intended for researchers, scientists, and drug development professionals who may handle this hazardous material. Adherence to the following guidelines is critical to ensure laboratory safety.

Executive Summary

Picryl chloride is a powerful detonating explosive with high sensitivity to various stimuli. It is also classified as a toxic substance, fatal if swallowed, in contact with skin, or if inhaled. This guide summarizes the known explosive and physical properties of **Picryl chloride**, outlines detailed safety protocols for its handling and storage, and provides methodologies for key safety-related experiments.

Explosive and Physical Properties

Picryl chloride is a yellow crystalline solid that is highly explosive. While its shock sensitivity is comparable to TNT, it is extremely unstable when dry and can be initiated by friction, shock, or heat.^[1] Key quantitative data regarding its explosive and physical properties are summarized in the table below.

Property	Value	Source(s)
Explosive Properties		
Detonation Velocity	7,200 m/s	[2]
Impact Sensitivity (H50)	Data not available in search results	
Friction Sensitivity (BAM)	Data not available in search results	
Physical Properties		
Molecular Formula	C ₆ H ₂ ClN ₃ O ₆	[2]
Molar Mass	247.55 g/mol	[2]
Appearance	Light yellow needles	[1]
Melting Point	83 °C (181 °F)	[2]
Thermal Properties		
Decomposition Temperature	Data not available in search results	

Safety and Handling Precautions

Due to its hazardous nature, strict safety protocols must be followed when handling **Picryl chloride**.

Personal Protective Equipment (PPE)

A comprehensive range of PPE is mandatory when working with **Picryl chloride** to prevent accidental exposure through inhalation, ingestion, or skin contact.

- **Eye/Face Protection:** Chemical safety goggles and a face shield are essential.
- **Skin Protection:** A flame-retardant lab coat, along with chemical-resistant gloves (e.g., nitrile, neoprene, or Viton), should be worn. It is crucial to check the breakthrough time and permeation rate of the gloves for **Picryl chloride**.
- **Respiratory Protection:** A full-face respirator with appropriate cartridges should be used, especially when handling the powder or in case of potential aerosolization.

Engineering Controls

- **Ventilation:** All work with **Picryl chloride** must be conducted in a certified chemical fume hood with a tested and reliable exhaust system.
- **Isolation:** The experimental setup should be located in a designated area, away from incompatible materials and ignition sources.
- **Blast Shielding:** Use of a blast shield is highly recommended for any procedure involving the heating or agitation of **Picryl chloride**.

Handling and Storage

- **Wetting:** **Picryl chloride** should be kept wetted with at least 10% water by mass to reduce its sensitivity to shock and friction.^[1]
- **Avoidance of Stimuli:** Avoid grinding, scraping, or subjecting the material to any form of friction or impact. Use non-sparking tools.
- **Temperature Control:** Store in a cool, dry, and well-ventilated area, away from heat sources, open flames, and direct sunlight.
- **Grounding:** All equipment and containers should be properly grounded to prevent electrostatic discharge.

- Incompatible Materials: **Picryl chloride** is incompatible with strong oxidizing agents, nitrates, chlorates, and ammonia.[1] Contact with these materials can lead to violent reactions.

Spill and Emergency Procedures

- Evacuation: In case of a spill, evacuate the area immediately.
- Ignition Sources: Eliminate all sources of ignition.
- Containment: For small spills, carefully dampen the material with water and collect it with non-sparking tools into a sealed container for disposal.
- Fire: In case of fire, do not attempt to extinguish it. Evacuate the area and alert emergency services. There is a severe risk of explosion.

Experimental Protocols for Safety Assessment

Standardized tests are used to quantify the explosive properties of materials like **Picryl chloride**. The following are detailed methodologies for determining impact and friction sensitivity.

Impact Sensitivity: Drop Weight Test (ASTM E680)

The drop weight impact test determines the energy required to cause a material to react (explode or decompose) upon impact. The result is often expressed as the H50 value, which is the height from which a standard weight has a 50% probability of causing a reaction.

Methodology:

- Apparatus: A drop weight impact tester consists of a guided weight that can be dropped from a variable height onto a sample held in a standardized anvil assembly.
- Sample Preparation: A small, precisely measured amount of the dried explosive is placed in the sample holder.
- Procedure:
 - The weight is dropped from a predetermined height.

- The outcome (reaction or no reaction) is observed. A reaction is typically indicated by an audible report, flash, or smoke.
- The "up-and-down" or Bruceton method is commonly used to determine the H50 value. In this method, the height for the next drop is decreased after a reaction and increased after a non-reaction.
- A series of at least 20-30 drops is performed to obtain statistically significant data.
- Data Analysis: The H50 value and its standard deviation are calculated from the series of test results.

Friction Sensitivity: BAM Friction Test

The BAM (Bundesanstalt für Materialprüfung) friction test measures the sensitivity of a substance to frictional stimuli. The result is expressed as the load in Newtons (N) at which a reaction occurs.

Methodology:

- Apparatus: The BAM friction apparatus consists of a fixed porcelain pin and a movable porcelain plate. A weighted lever arm applies a known force to the pin, which is in contact with the sample on the plate.
- Sample Preparation: A small amount of the substance is spread on the porcelain plate.
- Procedure:
 - The porcelain plate is moved back and forth under the weighted porcelain pin.
 - The test is performed at various load levels.
 - The lowest load at which a flame, crackling, or detonation occurs in at least one of six trials is determined.
- Data Analysis: The friction sensitivity is reported as the lowest load at which a reaction was observed.

Material Compatibility


The choice of materials for handling and storing **Picryl chloride** is critical to prevent unintended reactions.

Material Category	Compatible	Incompatible
Metals	Stainless Steel (304, 316)	Copper, Brass, Bronze, Lead, Zinc
Plastics	Polytetrafluoroethylene (PTFE), Polyethylene (PE), Polypropylene (PP)	Polyvinyl chloride (PVC) may be less suitable due to potential for reaction with some nitro compounds.
Elastomers	Viton®, Kalrez®	Natural Rubber, Neoprene, Buna-N (Nitrile) may have limited compatibility and should be tested.

It is crucial to consult specific chemical compatibility charts and conduct testing for materials that will be in prolonged contact with **Picryl chloride**.


Signaling Pathways and Experimental Workflows

To visually represent the logical flow of safety procedures and experimental design, the following diagrams have been generated using Graphviz (DOT language).



[Click to download full resolution via product page](#)

Caption: Workflow for Safe Handling of **Picryl Chloride**.



[Click to download full resolution via product page](#)

Caption: Experimental Workflow for Drop Weight Impact Sensitivity Test.

Conclusion

Picryl chloride is a substance that demands the utmost respect and caution. The information provided in this guide is intended to supplement, not replace, comprehensive training and adherence to all institutional and regulatory safety protocols. Researchers must be thoroughly familiar with the hazards of **Picryl chloride** and the emergency procedures before commencing any work.

Need Custom Synthesis?

BenchChem offers custom synthesis for rare earth carbides and specific isotopic labeling.

Email: info@benchchem.com or [Request Quote Online](#).

References

- 1. calpaclab.com [calpaclab.com]
- 2. etusersgroup.org [etusersgroup.org]
- To cite this document: BenchChem. [An In-depth Technical Guide to the Safe Handling of Picryl Chloride for Researchers and Scientists]. BenchChem, [2026]. [Online PDF]. Available at: [<https://www.benchchem.com/product/b1203447/docs#an-in-depth-technical-guide-to-the-safe-handling-of-picryl-chloride-for-researchers-and-scientists>]

Disclaimer & Data Validity:

The information provided in this document is for Research Use Only (RUO) and is strictly not intended for diagnostic or therapeutic procedures. While BenchChem strives to provide accurate protocols, we make no warranties, express or implied, regarding the fitness of this product for every specific experimental setup.

Technical Support: The protocols provided are for reference purposes. Unsure if this reagent suits your experiment?

Need Industrial/Bulk Grade? [Request Custom Synthesis Quote](#)

BenchChem

Our mission is to be the trusted global source of essential and advanced chemicals, empowering scientists and researchers to drive progress in science and industry.

Contact

Address: 3281 E Guasti Rd

Ontario, CA 91761, United States

Phone: (601) 213-4426

Email: info@benchchem.com

[Contact our Ph.D. Support Team for a compatibility check](#)