




DATA SHEET

EP-20/H-97M

DESCRIPTION: EP-20/H97M is a fast gel time epoxy resin in a 1:1 mix ratio by volume, being a semi-rigid resin it provides good impact resistance, providing good adhesion to metals, plastics, wood, concrete, asphalts, etc.

SPECIFICATIONS

	EP - 20	H - 97M
Color	Black	Translucent
Mixing ratio by volume	100	100
Mixing ratio by weight	100	100
Specific weight @ 25°C	1.16	1.15
Viscosity, cps	11, 000 – 14, 000	10, 000 – 16, 000
Mixing viscosity, cps	10, 000 – 15, 000	
Gel time	18 – 20 minutes	



Note: the measurement tests were performed according to the temperatures of the graph with relative humidity percentages of 50%-80% (can be 40%-85%) as this does not affect the development of curing and properties.

PHYSICAL PROPERTIES:

Compression strength, psi, ASTM - D - 695	12, 500
Tension force, psi, ASTM - D - 638	8, 000
Elongation, ASTM - D - 638	7%
Hardness, ASTM - D - 2240	65 – 70 D



INSTRUCTIONS FOR USE

1. Clean the substrates, make sure they are free of dust and grease and/or any contaminant that may affect adhesion.
2. Measure components according to mixing ratio in volume or weight and mix the two components preferably in dispensing equipment.
3. Pour the mixture on the part to be bonded or repaired.
4. Do not expose the adhesive to temperatures below 15°C (59°F) for a prolonged period of time.
5. Do not expose the adhesive to direct sunlight or any other heat source higher than 30°C (86°F) minutes before using the adhesive.

CURING:

Initial cure is achieved in 16-24 hours at room temperature. Final cure takes at least 7-10 days at 25°C.

STORAGE REQUIREMENTS:

Store in a cool, dry place in a temperature range of 15°C- 40°C a maximum time of 24 months without having opened containers.

SAFETY:

Avoid inhaling mists and vapors, which may cause respiratory damage.
The use of gloves, protective goggles and mask is recommended for handling.
Try to work in areas with adequate ventilation to allow dissipation of chemical vapors that may arise.
If material enters the eyes, flush with plenty of water for fifteen minutes.
Avoid contact with skin, in case of contact wash with soap and water and rinse with clean water.
Observe all safety precautions.
For further information refer to the safety data sheet.

The information in this data sheet is based on our laboratory tests and our experience, however, because our products may be used under various conditions beyond our control, WE ARE NOT RESPONSIBLE FOR THEIR HANDLING AND APPLICATION. For this reason, we recommend that you perform the necessary analysis and evaluations to satisfy your requirements. Should you require further information, please contact our technical department.