

Role of mechanical stress localizations on the radiation hardness of AlGaIn/GaN high electron mobility transistors

Nahid Sultan Al-Mamun¹ , Abu Jafar Rasel¹, Zahabul Islam², Marian B Tzolov³ , Christopher M Smyth⁴, Aman Haque^{1,*} , Douglas E Wolfe⁵, Fan Ren⁶ and Stephen Pearton⁷ 

¹ Department of Mechanical Engineering, Penn State University, University Park, PA 16802, United States of America

² Mechanical and Manufacturing Engineering Program, School of Engineering, Bowling Green State University, Bowling Green, OH 43403, United States of America

³ Department of Biochemistry, Chemistry, Engineering and Physics, Commonwealth University of PA, Lock Haven, PA 17745, United States of America

⁴ Sandia National Laboratories, Albuquerque, NM 87123, United States of America

⁵ Department of Materials Science & Engineering, Penn State University, University Park, PA 16802, United States of America

⁶ Department of Chemical Engineering, University of Florida, Gainesville, FL 32611, United States of America

⁷ Department of Material Science and Engineering, University of Florida, Gainesville, FL 32611, United States of America

E-mail: mah37@psu.edu

Received 2 August 2024, revised 16 October 2024

Accepted for publication 25 October 2024

Published 6 November 2024



Abstract

Multi-material, multi-layered systems such as AlGaIn/GaN high electron mobility transistors (HEMTs) contain residual mechanical stresses that arise from sharp contrasts in device geometry and materials parameters. These stresses, which can be either tensile or compressive, are difficult to detect and eliminate because of their highly localized nature. We propose that their high-stored internal energy makes potential sites for defect nucleation sites under radiation, particularly if their locations coincide with the electrically sensitive regions of a transistor. In this study, we validate this hypothesis with molecular dynamic simulation and experiments exposing both pristine and annealed HEMTs to 2.8 MeV Au⁺³ irradiation. Our unique annealing process uses mechanical momentum of electrons, also known as the electron wind force (EWF) to mitigate the residual stress at room temperature. High-resolution transmission electron microscopy and cathodoluminescence spectra reveal the reduction of point defects and dislocations near the two-dimensional electron gas region of EWF-treated devices compared to pristine devices. The EWF-treated HEMTs showed relatively higher resilience with approximately 10% less degradation of drain saturation current and ON-resistance and 5% less degradation of peak transconductance. Both mobility and carrier

* Author to whom any correspondence should be addressed.



Original content from this work may be used under the terms of the [Creative Commons Attribution 4.0 licence](https://creativecommons.org/licenses/by/4.0/). Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI.