


REV. NO.	REVISION NOTE	DATE	NAME	CHECK
REV. B	UPDATED GEOMETRY	12.05.2016	E.Bugrova	J&J



Project name:	F-450 BAROM. STATION	J&J Jakopin
Lamination:	Open mould [WET] Simple surface	
Part weight:	2.7 kg	
Part area:	0.5 m <sup>2</sup>	5.9 lb
Average:	5.4 kg/m <sup>2</sup>	0.6 yd <sup>2</sup>
Average:	5.4 kg/m <sup>2</sup>	9.9 lb/yd <sup>2</sup>
Nominal fibre content by mass according to EN ISO 12215		

Area		0.238	0.27
	Ply	BASIC area	REINF area
	1	GC (type II)	GC (type II)
	2	CSM 300	CSM 300
	3	CSM 300	CSM 300
	4	EBX 600 M225	EBX 600 M225
	5		EBX 600 M225

EU	Total dry fibre:	2,471 g/m2	3,302 g/m2
	Total with resin:	4,500 g/m2	5,960 g/m2
	Thickness:	3.2 mm	4.1 mm
USA	Total w/dry:	72.9 oz/yd2	97.4 oz/yd2
	Total w/resin:	132.7 oz/yd2	175.8 oz/yd2
	Thickness:	0.12 in	0.16 in

INSTALLED material:	Weight:		Area:		Marq. [%]:
	[kg]	[lb]	[m <sup>2</sup> ]	[yd <sup>2</sup> ]	
GC (type II)	0.5	1.2	0.5	0.6	0
CSM 300	0.3	0.7	1.1	1.3	5
EBX 600 M225	0.7	1.5	0.8	1.0	5
POLYESTER (resin)	1.2	2.6			0
POLYESTER (hardener)	0.02	0.05			0
Total:	2.7 kg	5.9 lb	2.4 m2	2.8 yd2	

NEEDED material:	Weight:		Area:		Marq. [%]:
	[kg]	[lb]	[m <sup>2</sup> ]	[yd <sup>2</sup> ]	
GC (type II)	0.58	1.27	0.55	0.66	10
CSM 300	0.35	0.77	1.16	1.39	10
EBX 600 M225	0.74	1.63	0.89	1.06	10
POLYESTER (resin)	1.3	2.8			10
POLYESTER (hardener)	0.03	0.06			10
Total:	3.0 kg	6.5 lb	2.6 m2	3.1 yd2	

- Important:**
- during the lamination process environment temperature and humidity needs to be checked and recorded with temperature and humidity logger and comply with technical data sheets from suppliers
  - resin/hardener ratio needs to be correct for ambient temperature
  - all built in materials MUST have CE or similar certification
  - before secondary bonding or lamination surface must be sanded with GRIT 60 paper
  - Core must be sealed when hole is cut in to sandwich laminate or hole must be drilled to single skin area

Material:	Fibre orientation:	Resin uptake [g]:	Resin uptake [lb]:	Material description:
GC (type II)	SPRY application	0	0.00	GelCoat
CSM 300	RANDOM	700	1.54	Chopped strands matt
EBX 600 M225	[+45/-45 deg]	629	1.39	Double biaxial + matt
POLYESTER (resin)	0			Resin
POLYESTER (hardener)	0			Hardener

	Drawing name: <i>Barometric station</i>	Scale: <i>1:5</i>	Date: <i>7.4.2016</i>	Drawn by: <i>U.Mirjanic</i>	Page: <i>1 / 1</i>
	Subject: <i>F-450</i>				Page format: <i>A3</i>
File name: <i>F45000-00-ST-34-T01-ST-STD-3-EU-B-- Laminazione carter stazione barometrica- Barometric station lamination.dwg</i>					Approved: <i>J&amp;J</i>
THIS DRAWING IS PROTECTED BY COPYRIGHT AND IS SOLE PROPERTY OF FERRETTI spa. NO PART MAY BE COPIED OR REPRODUCED, MODIFIED OR USED IN ANY OTHER WAY WITHOUT WRITTEN PERMISSION. DO NOT MEASURE FROM DRAWING, IF IN DOUBT VERIFY WITH DESIGN OFFICE. BEFORE MANUFACTURING CHECK ALL DIMENSIONS WITH REFERENCING MODEL					