



WIRE ROPE & CABLE

IMPORTED

6x19 Class

6x36 Class

7x7 Galvanized

7x19 Galvanized


7x19 Vinyl Coated

7x7 Stainless – 304 & 316


7x19 Stainless – 304 & 316

CoreLifting.com


BRIGHT WIRE ROPE - 6 x 19 CLASS




6 x 25 FILLER WIRE
WITH FIBER CORE



6 x 19 SEALE
WITH IWRC




6 x 25 FILLER WIRE
WITH IWRC



6 x 26 WARRINGTON
SEALE WITH IWRC

FIBER CORE (EIPS)		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.105	3.01
5/16	0.164	4.69
3/8	0.236	6.71
7/16	0.320	9.10
1/2	0.420	11.80
9/16	0.530	14.90
5/8	0.660	18.40
3/4	0.950	26.20
7/8	1.290	35.40
1	1.680	46.00
1.1/8	2.130	57.90
1.1/4	2.630	71.10

IWRC (EIPS)**		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.116	3.40
5/16	0.180	5.27
3/8	0.260	7.55
7/16	0.350	10.20
1/2	0.460	13.30
9/16	0.590	16.80
5/8	0.720	20.60
3/4	1.040	29.40
7/8	1.420	39.80
1	1.850	51.70
1.1/8	2.340	65.00
1.1/4	2.890	79.90
1.3/8	3.500	96.00
1.1/2	4.160	114.00
1.5/8	4.880	132.00
1.3/4	5.670	153.00
2	7.390	198.00
2.1/4	9.360	247.00
2.3/8	10.400	274.00
2.1/2	11.600	302.00



**EIPS available in some sizes and constructions.


According to A.S.T.M. A1023/1023M Wire Rope for General Purposes and Federal Specification RR-W-410, current revision, as applicable. Meets the performance requirements of API-9A. Preformed, right regular lay.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.

NOTE: Lang lay, left lay, alternate lay, Seale available in some sizes. Heavy lubrication on request.





BRIGHT WIRE ROPE - 6 x 36 CLASS



**6 x 36 WARRINGTON
SEALE WITH FIBER CORE**

FIBER CORE (EIPS)		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.105	3.01
5/16	0.164	4.69
3/8	0.236	6.71
7/16	0.320	9.10
1/2	0.420	11.80
9/16	0.530	14.90
5/8	0.660	18.40
3/4	0.950	26.20
7/8	1.290	35.40
1	1.680	46.00
1.1/8	2.130	57.90
1.1/4	2.630	71.10



**6 x 36 WARRINGTON
SEALE WITH IWRC**

IWRC (EIPS)**		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.116	3.40
5/16	0.180	5.27
3/8	0.260	7.55
7/16	0.350	10.20
1/2	0.460	13.30
9/16	0.590	16.80
5/8	0.720	20.60
3/4	1.040	29.40
7/8	1.420	39.80
1	1.850	51.70
1.1/8	2.340	65.00
1.1/4	2.890	79.90
1.3/8	3.500	96.00
1.1/2	4.160	114.00
1.5/8	4.880	132.00
1.3/4	5.670	153.00
1.7/8	6.500	174.00
2	7.390	198.00
2.1/4	9.360	247.00
2.1/2	11.600	302.00
2.3/4	14.000	361.00
3	16.600	425.00
3.1/2	22.700	572.00


**EEIPS available in some sizes and constructions.

According to A.S.T.M. A1023/1023M Wire Rope for General Purposes and Federal Specification RR-W-410, current revision, as applicable. Meets the performance requirements of API-9A. Preformed, right regular lay.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.




GALVANIZED WIRE ROPE - 6 x 19 CLASS



**6 x 26 WARRINGTON
SEAL WITH FIBER CORE**

Drawn Galvanized FIBER CORE (EIPS)		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.105	3.01
3/8	0.236	6.71
7/16	0.320	9.10
1/2	0.420	11.80
9/16	0.530	14.90
5/8	0.660	18.40
3/4	0.950	26.20
7/8	1.290	35.40



**6 x 26 WARRINGTON
SEAL WITH IWRC**

Drawn Galvanized IWRC (EIPS)**		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
3/8	0.26	7.55
7/16	0.35	10.20
1/2	0.46	13.30
9/16	0.59	16.80
5/8	0.72	20.60
3/4	1.04	29.40
7/8	1.42	39.80
1	1.85	51.70
1.1/8	2.34	65.00
1.1/4	2.89	79.90
1.3/8	3.50	96.00
1.1/2	4.16	114.00
1.5/8	4.88	132.00
1.3/4	5.67	153.00
2	7.39	198.00

According to A.S.T.M. A1023/1023M Wire Rope for General Purposes and Federal Specification RR-W-410, current revision, as applicable. Meets the performance requirements of API-9A. Preformed, right regular lay.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.

** **EEIPS** available in some sizes and constructions.




GALVANIZED WIRE ROPE - 6 x 36 CLASS



**6 x 36 WARRINGTON
SEAL WITH FIBER CORE**

Drawn Galvanized FIBER CORE (EIPS)		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.105	3.01
3/8	0.236	6.71
1/2	0.420	11.80
9/16	0.530	14.90
5/8	0.660	18.40
3/4	0.950	26.20
7/8	1.290	35.40
1	1.680	46.00
1.1/8	2.130	57.90
1.1/4	2.630	71.10
1.3/8	3.180	85.50



**6 x 36 WARRINGTON
SEAL WITH IWRC**

Drawn Galvanized IWRC (EIPS)**		
Diameter in Inches	Approx. Weight per Foot in Pounds	Breaking Strength in Tons*
1/4	0.116	3.40
5/16	0.180	5.27
3/8	0.260	7.55
7/16	0.350	10.20
1/2	0.460	13.30
9/16	0.590	16.80
5/8	0.720	20.60
3/4	1.040	29.40
7/8	1.420	39.80
1	1.850	51.70
1.1/8	2.340	65.00
1.1/4	2.890	79.90
1.3/8	3.500	96.00
1.1/2	4.160	114.00
1.5/8	4.880	132.00
1.3/4	5.670	153.00
2	7.390	198.00
2.1/4	9.360	247.00
2.1/2	11.600	302.00
2.3/4	14.000	361.00
3	16.600	425.00
3.1/2	22.700	572.00

According to A.S.T.M. A1023/1023M Wire Rope for General Purposes and Federal Specification RR-W-410, current revision, as applicable. Meets the performance requirements of API-9A. Preformed, right regular lay.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.

** EEIPS available in some sizes and constructions.



GALVANIZED STEEL CABLE



7 x 7

7 x 7 GALVANIZED CABLE

Size in Inches	Approx. Wt. per 1000 Ft. in Pounds	Breaking Strength in Pounds*
1/16	7.5	480
5/64	11.0	650
3/32	16.0	920
1/8	28.0	1,700
5/32	43.0	2,600
3/16	62.0	3,700
1/4	106.0	6,100



7 x 19

7 x 19 GALVANIZED CABLE

Size in Inches	Approx. Wt. per 1000 Ft. in Pounds	Breaking Strength in Pounds*
3/32	17.4	1,000
1/8	29.0	2,000
5/32	45.0	2,800
3/16	65.0	4,200
7/32	86.0	5,600
1/4	110.0	7,000
5/16	173.0	9,800
3/8	243.0	14,400


Small diameter 7 x 7 and 7 x 19 construction cable is sometimes referred to as "aircraft cable".

It is not intended for aircraft use but designed for industrial and marine applications according to Federal Specification RR-W-410, current revision and A.S.T.M. A 1023/A 1023M, as applicable.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.



GALVANIZED STEEL CABLE




DISPLAY REELS

DISPLAY REELS - GALVANIZED CABLE

Size in Inches	Construction	Approx. Wt. per 1000 Ft. in Pounds	Display Reels Lengths Available in Feet	
1/16	7 x 7	7.5	500	250
3/32	7 x 7	16.0	500	250
1/8	7 x 7	28.0	500	250
5/32	7 x 7	43.0	500	250
3/16	7 x 7	62.0	500	250
1/8	7 x 19	29.0	500	250
5/32	7 x 19	45.0	500	250
3/16	7 x 19	65.0	500	250
1/4	7 x 19	110.0	500	250
5/16	7 x 19	173.0	500	200
3/8	7 x 19	243.0	500	200

VINYL COATED CABLE - GALVANIZED



7 x 7

CLEAR VINYL COATED CABLE, 7 x 7 - GALVANIZED


Cable Diameter in Inches	Coated To (in Inches)	Approx. Wt. per 1000 Ft. in Pounds	Breaking Strength in Pounds*	Construction
1/16	3/32	9.3	480	7 x 7
1/16	1/8	11.8	480	7 x 7
3/32	1/8	18.5	920	7 x 7
3/32	3/16	25.8	920	7 x 7
1/8	3/16	35.2	1,700	7 x 7
1/4	5/16	122.0	6,100	7 x 7

Small diameter 7 x 7 and 7 x 19 construction cable is sometimes referred to as "aircraft cable". *It is not intended for aircraft use* but designed for industrial and marine applications. When using wire rope clips with plastic coated cable, match clip size to uncoated cable diameter (3/16" cable coated to 1/4" takes 3/16" clip.) Strip plastic coating off cable where clips will be positioned for full holding power. Uncoated cable according to Federal Specification RR-W-410, current revision and A.S.T.M. A1023/1023M, as applicable.


* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.



VINYL COATED CABLE - GALV. & STAINLESS



7 x 7



7 x 19

CLEAR VINYL COATED CABLE, 7 x 19 - GALVANIZED

Cable Diameter in Inches	Coated To (in Inches)	Approx. Wt. per 1000 Ft. in Pounds	Breaking Strength in Pounds*	Construction
3/32	1/8	19.9	1,000	7 x 19
1/8	3/16	36.2	2,000	7 x 19
3/16	1/4	77.5	4,200	7 x 19
3/16	5/16	81.4	4,200	7 x 19
1/4	5/16	123.0	7,000	7 x 19
5/16	3/8	197.0	9,800	7 x 19
3/8	7/16	270.0	14,400	7 x 19

CLEAR VINYL COATED STAINLESS STEEL CABLE - TYPE 304

Cable Diameter in Inches	Coated To (in Inches)	Approx. Wt. per 1000 Ft. in Pounds	Breaking Strength in Pounds*	Construction
1/16	3/32	9.3	480	7 x 7
3/32	1/8	18.5	920	7 x 7
1/8	3/16	36.2	1,760	7 x 19
3/16	1/4	77.5	3,700	7 x 19
1/4	5/16	123.0	6,400	7 x 19
5/16	3/8	197.0	9,000	7 x 19
3/8	7/16	270.0	12,000	7 x 19



DISPLAY REELS

DISPLAY REELS - VINYL COATED GALVANIZED CABLE

Cable Diameter in Inches	Coated To (in Inches)	Approx. Wt. per 1000 Ft. in Pounds	Construction	Lengths Available in Ft.	
3/32	3/16	25.8	7 x 7	500	250
1/8	3/16	35.2	7 x 7	500	250
3/16	1/4	77.5	7 x 19	500	250
1/4	5/16	123.0	7 x 19	500	200
5/16	3/8	197.0	7 x 19	500	200

Small diameter 7 x 7 and 7 x 19 construction cable is sometimes referred to as "aircraft cable". *It is not intended for aircraft use* but designed for industrial and marine applications. When using wire rope clips with plastic coated cable, match clip size to uncoated cable diameter (3/16" cable coated to 1/4" takes 3/16" clip.) Strip plastic coating off cable where clips will be positioned for full holding power. Uncoated cable according to Federal Specification RR-W-410, current revision and A.S.T.M. A1023/1023M, as applicable.

Also available on special order: nylon and vinyl in various colors.

* Listed for comparison only. Actual operating loads should never exceed the recommended design factor or 20% of catalog Breaking Strength.

