



**PROTEX COATINGS OF CREATIVE BUSINESS SYSTEMS**

# Protolic RQD Paint

Single pack, air drying thermoplastic acrylic based finish paint

## FEATURES

- \* Fast drying property
- \* Quick, easy work & user's friendly application
- \* Can be apply in 0 to -10 C
- \* Very good moisture & water resistant
- > Poor solvent resistant

## TECHNICAL DATA

Type	: Thermoplastic resin with high class pigment		
Colour	: Range		
Finish	: Matt		
Mixing Ratio By Volume	: Single pack		
Induction Time	: N. A.		
Application Method	: Brush, Spray, Airless Spray		
Recommended DFT / Coat	: 25 - 35	Microns	
Theoretical Coverage	: 14.0 - 8.0	Sq. mtr.	
Pot Life 30 C	: N. A.		

**Drying time 30 C** : Touch Dry: 20 hours  
Handle: 4 hours  
Hard Dry: 12 hours  
Full Cure: 7 Days

**Overcoating Interval 30 C** : Minimum hours: 12  
Maximum Days: Unlimited

**Flash Point** : Above 28 C

**Storage Life** : 12 Months (30 C Room Temp. Cool & Dry)

**% Protex Thinner T - 800** : Brush 0-10, Spray 5-15, Airless Spray 0-5

**Health & Safety** : Please refer our MSDS

**Packing** : 20 Ltrs and 4 Ltrs

**Surface Preparation & Substrate Condition**

- \* Surface must be free from all contamination like oil, grease, carbon, moisture, rust, loose under coats, Dust etc.. in case of blasted metal surface gives excellent result, in case of old painted surface the old paint should be removed, for new surface it should be sufficiently roughed prior to painting.

**Notes**

- \* Stir all component separately, if settling is observed, loosen the settled material with the help of pneumatic stirrer followed by power driven stirrer for quick homogenous mixing. (After that mix both material, in case of two pack give induction time if applicable) then apply.
- \* Thinner is depend on application method & Dft requirement, in general condition, please conform with our technical team if your specific requirement.
- \* Do not apply when temperature below 10 C or arise above 50 C and when relative humidity rises above 85 % , Do not apply during Fog, Rain or Mist.
- \* Brushes and spray equipment should be cleaned with recommended PROTEX thinner.
- \* Viscosity may vary in case of temp. variation & volume of solid may 5 % (+, -) subject to shade to shade.

**Disclaimer**

The information contained with this technical data sheet based on information believed to be reliable at the time of preparation, since we have no control over the quality or condition of the substrate or the various factors affecting the use & application of product, we do not accept any responsibility or liability arising out of use of the product, we are authorised to change the data with out prior notice, we will issue new data sheet, the user should conform with Mfg./supplier before use.

Issue Date: 15th April 2010

# Creative Business Systems

7, Agrawal Estate, Gulab Nager Char Rasta, B/S Bhagirath-3, Amraiwadi, Ahmedabad-26  
M-9825008956, 9426386442 (F) 079-22742526 Website: [www.cretex.com](http://www.cretex.com)  
email id: [creativeprotex@gmail.com](mailto:creativeprotex@gmail.com) / [dhirentricoat@yahoo.com](mailto:dhirentricoat@yahoo.com)