



## PROTEX COATINGS OF CREATIVE BUSINESS SYSTEMS

### Protoxy Floor Primer

Epoxy Flooring High Build High Solid Primer

#### FEATURES

- \* High performance & high solid flooring clear pale yellow to brown primer
- \* Excellent bonding property with RCC & M. S. non porous floor
- \* Excellent abrasion resistant & impact resistant
- \* Excellent corrosion resistance on ferrous floor
- \* Surface sealer property & bond with surface as well as top coat

#### TECHNICAL DATA

|                        |  |                |
|------------------------|--|----------------|
| Type                   | : Epoxy resin - hardner with bonding additives |                |
| Colour                 | : Clear pale yellow to brownish                |                |
| Finish                 | : Glossy                                       |                |
| Mixing Ratio By Weight | : 2;1  | (Base:Hardner) |
| Induction Time         | : None   |                |
| Application Method     | : Brush, Airless Spray                         |                |
| Recommended DFT / Coat | : 75 - 125                                     | Microns        |
| Theoretical Coverage   | : 6.0 - 3.5                                    | Sq. mtr.       |
| Pot Life 30 C          | : 20 - 40                                      | Minutes        |
| Drying time 30 C       | : Touch Dry:                                   | 4 hours        |

Handle: 12 hours

Hard Dry: 24 hours

Full Cure: 7 Days

**Overcoating Interval 30 C** : Minimum hours: 3 (Applied on take free surface)  
Maximum hours: 5

**Flash Point** : Above 28 C

**Storage Life** : 12 Months (30 C Room Temp. Cool & Dry)

**% Protex Thinner T - 997** : Brush 0-5, Airless Spray 0-5

**Health & Safety** : Please refer our MSDS

**Packing** : 20 Kgs & 5 Kgs

**Surface Preparation & Substrate Condition**\_\_\_\_\_

- \* Surface must be free from all contamination like oil, grease, carbon, moisture, rust, loose under coats, Dust etc.. in case of blasted metal surface gives excellent result, in case of old painted surface the old paint should be removed, for new surface it should be sufficiently roughed prior to painting.

**Notes**\_\_\_\_\_

- \* Stir all component separately, if settling is observed, loosen the settled material with the help of pneumatic stirrer followed by power driven stirrer for quick homogenous mixing. (After that mix both material, in case of two pack give induction time if applicable) then apply.
- \* Thinner is depend on application method & Dft requirement, in general condition, please conform with our technical team if your specific requirement.
- \* Do not apply when temperature below 10 C or arise above 50 C and when relative humidity rises above 85 % , Do not apply during Fog, Rain or Mist.
- \* Brushes and spray equipment should be cleaned with recommended PROTEX thinner.
- \* Viscosity may vary in case of temp. variation & volume of solid may 5 % (+, -) subject to shade to shade.

**Disclaimer**\_\_\_\_\_

The information contained with this technical data sheet based on information believed to be reliable at the time of preparation, since we have no control over the quality or condition of the substrate or the various factors affecting the use & application of product, we do not accept any responsibility or liability arising out of use of the product, we are authorised to change the data with out prior notice, we will issue new data sheet, the user should conform with Mfg./supplier before use.

Issue Date: 15th April 2010

# Creative Business Systems

7, Agrawal Estate, Gulab Nager Char Rasta, B/S Bhagirath-3, Amraiwadi, Ahmedabad-26  
M-9825008956, 9426386442 (F) 079-22742526 Website: [www.cretex.com](http://www.cretex.com)  
email id: [creativeprotex@gmail.com](mailto:creativeprotex@gmail.com) / [dhirentricoat@yahoo.com](mailto:dhirentricoat@yahoo.com)