



Technical Data Sheet
技术指标

序号 No.	分析项目 Analysis Item	单位 Unit	N330	N326	N220	N550	N660	检测方法 Testing Methods
1	吸碘值 Iodine adsorption value	g/kg	82±6	82±6	121±6	39-47	32-40	GB/T 3780.1-2015
2	吸油值 Oil absorption value	10 ⁻⁵ m ³ /kg	102±6	72±6	114±6	116-126	85-95	GB/T 3780.2-2017
3	压缩试样吸油值 Absorption value for compressed sample	10 ⁻⁵ m ³ /kg	88±6	68±6	98±6	80-90	69-79	GB/T 3780.4-2017
4	着色强度 Tinctorial strength	%	104±8	111±8	116±8	/	/	GB/T 3780.6-2016
5	加热减量 Bulk, 125° C, 1hr	%	≤0.8	≤0.8	≤0.8	≤1.5	≤1.5	GB/T 3780.8-2019
6	灰分 Ash content	%	≤0.7	≤0.7	≤0.7	≤0.5	≤0.5	GB/T 3780.10-2017
7	45 μm水洗筛余物 45 μm sieve residue by water washing	ppm	≤500	≤500	≤500	≤500	≤500	GB/T 3780.21-2016
8	细粉含量 Finess content	%	≤7.0	≤7.0	≤7.0	≤10.0	≤7.0	GB/T 14853.2-2016
9	颗粒强度 Pallet hardness	cN	30±10	30±10	30±10	/	/	GB/T 14853.6-2013
10	比表面积 STSA		78±5					GB/T 10722-2014
11	PH值 PH value	/	5.0-9.0	5.0-9.0	5.0-9.0	5.0-9.0	6.0-10.0	GB/T 3780.7-2016
12	倾注密度 Pour density	kg/m ³	380±40	455±40	355±40	320-400	400-480	GB/T 14853.1-2013

Package: 25kg/bag, 500kg/bag, 1000kg/bag

Contact info: +86 13298417267, paloma@kygroup.ltd