



GLOBAL FLUX S.A.S.

TIANJIN BAOLAI FORTUNE TRADE CO.,LTD

ADDRESS: 04, 9TH FLOOR, NINGTAI PLAZA, NO.1 XIAGUANG ROAD,

NANKAI DISTRICT, TIANJIN, CHINA

MILL TEST CERTIFICATES

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

www.globalflux.com.co

REF NO: BLHJYP086C

DATE OF ISSUE: 4/Nov/2024

GOODS: ERW FIRE PIPES

SPECIFICATION: ASTM A795

INVOICE NO.HJYP086-GLOBAL

HEAT NO.	SIZE				AMOUNT PCS	THEORETICAL WEIGHT (MT)	CHEMICAL COMPOSITION (%)														TENSION TEST			PRESSURE	FLATTENING /BENDING TEST	NON-DESTRUCTIVE TEST	VISUAL DIMENSION
	SIZE MM	SIZE IN	W.T. SCH	LENGTH (M)			C	Mn	Si	P	S	Cu	Ni	V	Ti	Cr	Mo	Ni+V	Ni+V+Ti	Ce	T.S.	Y.P.	E.L.				
																					Mpa	Mpa	(%)				
4A-06957	48.3	1-1/2"	SCH10	5.80	300	5.411	0.26	1.11	0.12	0.012	0.009	0.004	0.002	0.006	0.006	0.004	0.008	0.014	0.159	433	249	31	1000	G	G	G	
4A-06957	60.3	2"	SCH10	5.80	200	4.559	0.26	1	0.13	0.01	0.008	0.006	0.002	0.005	0.006	0.007	0.004	0.007	0.013	0.15	426	245	30	1000	G	G	G
4C-07119	114.3	4"	SCH10	5.80	350	16.991	0.26	0.98	0.15	0.012	0.015	0.005	0.003	0.006	0.003	0.007	0.005	0.009	0.012	0.178	441	249	30	1200	G	G	G

COATING TEST (EPOXY POWDER)

Coating thickness ≥100μm	TEST ITEM	Cure time,min (232℃±3℃)		Gel time, s (205℃±3℃)		Paricle size /150μm,%		Paricle size /250μm,%		Thermal characteristics //Tg1, ℃ (20℃/min, N2)		Thermal characteristics //Tg2, ℃ (20℃/min, N2)		Thermal characteristics ΔH, J/g (20℃/min, N2)	
105	TEST METHOD	CSA Z245.20-2018/12.1		CSA Z245.20-2018/12.2		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7	
	TEST RESULT	0.5	G	14.90	G	0.46	G	0	G	63.9	G	101.2	G	42.4	G
TEST ITEM	Bending resistance (-30℃±3℃)		Abrasive resistance (CS-17, 1000g/1000r)		Chemical Resistance (PH2.5~3.0) (20℃±3℃, 90d)		Density, g/cm ³		Cathodic Disbondment, mm (24h,65℃±3℃, - 3.5±0.15V,3%NaCl, Saturated calomel reference electrode)		Adhesion, Rating (24h, 75℃±3℃)		Moisture content of the epoxy powder-Mass loss (105℃±3℃, 2h)		
TEST METHOD	SY/T4113.3-2019		GB/T 1768-2006		SY/T4113.9-2020		CSA Z245.20-2018/12.6		CSA Z245.20-2018/12.8		CSA Z245.20-2018/12.14		CSA Z245.20-2018/12.4		
TEST RESULT	G	69	G	G	1.466	G	1.1	G	1	G	0.38	G			

WE HEREBY CERTIFY THAT :

1. THE MATERIAL HEREIN HAS BEEN TESTED IN ACCORDANCE WITH ABOVE SPECIFICATIONS AND THE RESULTS OF ALL TESTS ARE ACCEPTABLE.

2. TESTING RESULTS SHOWED THAT THE COAT WAS EXCELLENT IN ABRASION RESISTANCE, CORROSION RESISTANCE, STAIN RESISTANCE AND SLIP RESISTANCE.

3. UNDER NORMAL CIRCUMSTANCES, THE LIFE OF THE GOODS IS 15 YEARS.

SIGNATURE



Typed by: 贾莹莹

Approved by

张立

Date 2024-11-04

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

www.globalflux.com.co

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

www.globalflux.com.co