



GLOBAL FLUX

TIANJIN BAOLAI FORTUNE TRADE CO.,LTD

ADDRESS: 04, 9TH FLOOR, NINGTAI PLAZA, NO.1 XIAGUANG ROAD,

NANKAI DISTRICT, TIANJIN, CHINA

MILL TEST CERTIFICATES

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS
www.globalflux.com.co

REF NO: BLHJYPO90C

DATE OF ISSUE: 23/Jan/2025

GOODS: ERW FIRE PIPES

SPECIFICATION: ASTM A795

INVOICE NO.: HJYPO90-GLOBAL

HEAT NO.	SIZE				AMOUNT PCS	THEORETICAL WEIGHT (MT)	CHEMICAL COMPOSITION (%)														TENSION TEST			PRESSURE	FLATTENING / BENDING TEST	NON-DESTRUCTIVE TEST	VISUAL DIMENSION
	SIZE MM	SIZE IN	W.T. SCH	LENGTH (M)			C	Mn	Si	P	S	Cu	Ni	V	Ti	Cr	Mo	Ni+V	Ni+V+Ti	Ce	T.S.	Y.P.	E.L.				
																					Mpa	Mpa	(%)				
4B-08219	33.4	1"	SCH40	5.80	37	0.537	0.28	0.99	0.13	0.01	0.009	0.006	0.004	0.005	0.006	0.008	0.006	0.009	0.015	0.175	437	254	30	700	G	G	G
4B-09167	48.3	1-1/2"	SCH10	5.80	200	3.608	0.27	1.03	0.13	0.012	0.011	0.006	0.002	0.006	0.004	0.006	0.006	0.008	0.012	0.173	429	247	30	1000	G	G	G
4C-08194	60.3	2"	SCH10	5.80	200	4.559	0.27	1.01	0.12	0.011	0.012	0.005	0.004	0.007	0.005	0.008	0.004	0.011	0.016	0.153	434	245	32	1000	G	G	G

COATING TEST (EPOXY POWDER)

Coating thickness ≥100μm	TEST ITEM	Cure time,min (232°C±3°C)		Gel time, s (205°C±3°C)		Paricle size //150μm,%		Paricle size //250μm,%		Thermal characteristics //Tg1, °C (20°C/min, N2)		Thermal characteristics //Tg2, °C (20°C/min, N2)		Thermal characteristics ΔH, J/g (20°C/min, N2)	
103	TEST METHOD	CSA Z245.20-2018/12.1		CSA Z245.20-2018/12.2		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7	
	TEST RESILT	0.5	G	14.90	G	0.46	G	0	G	63.9	G	101.2	G	42.4	G
TEST ITEM	Bending resistance (-30°C±3°C)		Abrasive resistance (CS-17, 1000g/1000r)		Chemical Resistance (PH2.5~3.0) (20°C±3°C, 90d)		Density, g/cm ³		Cathodic Disbondment, mm (24h,65°C±3°C, - 3.5±0.15V,3%NaCl, Saturated calomel reference electrode)		Adhesion, Rating (24h, 75°C±3°C)		Moisture content of the epoxy powder-Mass loss (105°C±3°C,2h)		
TEST METHOD	SY/T4113.3-2019		GB/T 1768-2006		SY/T4113.9-2020		CSA Z245.20-2018/12.6		CSA Z245.20-2018/12.8		CSA Z245.20-2018/12.14		CSA Z245.20-2018/12.4		
TEST RESILT	G	69	G	G	1.466	G	1.1	G	1	G	0.38	G			

WE HEREBY CERTIFY THAT:

1. THE MATERIAL HEREIN HAS BEEN TESTED IN ACCORDANCE WITH ABOVE SPECIFICATIONS AND THE RESULTS OF ALL TESTS ARE ACCEPTABLE.
2. TESTING RESULTS SHOWED THAT THE COAT WAS EXCELLENT IN ABRASION RESISTANCE, CORROSION RESISTANCE, STAIN RESISTANCE AND SLIP RESISTANCE.
3. UNDER NORMAL CIRCUMSTANCES, THE LIFE OF THE GOODS IS 15 YEARS.

SIGNATURE

天津宝来富特
国际贸易有限公司

Typed by: 贾莹莹

Approved by: 张立

Date: 2025-01-23

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS



GLOBAL FLUX

TIANJIN BAOLAI FORTUNE TRADE CO.,LTD

ADDRESS: 04, 9TH FLOOR, NINGTAI PLAZA, NO.1 XIAGUANG ROAD,

NANKAI DISTRICT, TIANJIN, CHINA

MILL TEST CERTIFICATES

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS
www.globalflux.com.co

REF NO: BLHJYPO90C

DATE OF ISSUE: 23/Jan/2025

GOODS: ERW FIRE PIPES

SPECIFICATION: ASTM A795

INVOICE NO.: HJYPO90-GLOBAL

HEAT NO.	SIZE				AMOUNT PCS	THEORETICAL WEIGHT (MT)	CHEMICAL COMPOSITION (%)														TENSION TEST			PRESSURE	FLATTENING /BENDING TEST	NON-DESTRUCTIVE TEST	VISUAL DIMENSION
	SIZE MM	SIZE IN	W.T. SCH	LENGTH (M)			C	Mn	Si	P	S	Cu	Ni	V	Ti	Cr	Mo	Ni+V	Ni+V+Ti	Ce	T.S.	Y.P.	E.L.				
							Mpa	Mpa	(%)	PSI																	
4A-09866	73	2-1/2"	SCH10	5.80	200	6.102	0.28	1	0.13	0.011	0.015	0.006	0.003	0.007	0.006	0.008	0.005	0.01	0.016	0.152	422	252	32	1000	G	G	G
4C-07895	88.9	3"	SCH10	5.80	100	3.747	0.29	1.11	0.14	0.01	0.014	0.005	0.002	0.005	0.005	0.009	0.005	0.007	0.012	0.168	432	248	31	1000	G	G	G
4A-08197	114.3	4"	SCH10	5.80	200	9.709	0.26	1.13	0.14	0.012	0.014	0.006	0.002	0.008	0.003	0.009	0.005	0.01	0.013	0.163	443	255	32	1200	G	G	G

COATING TEST (EPOXY POWDER)

Coating thickness ≥100μm	TEST ITEM	Cure time,min (232°C±3°C)		Gel time, s (205°C±3°C)		Paricle size //150μm,%		Paricle size //250μm,%		Thermal characteristics //Tg1, °C (20°C/min, N2)		Thermal characteristics //Tg2, °C (20°C/min, N2)		Thermal characteristics ΔH, J/g (20°C/min, N2)	
103	TEST METHOD	CSA Z245.20-2018/12.1		CSA Z245.20-2018/12.2		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7	
	TEST RESULT	0.5	G	14.90	G	0.46	G	0	G	63.9	G	101.2	G	42.4	G
TEST ITEM	Bending resistance (-30°C±3°C)		Abrasive resistance (CS-17, 1000g/1000r)		Chemical Resistance (PH2.5~3.0) (20°C±3°C, 90d)		Density, g/cm ³		Cathodic Disbondment, mm (24h,65°C±3°C, - 3.5±0.15V,3%NaCl, Saturated calomel reference electrode)		Adhesion, Rating (24h, 75°C±3°C)		Moisture content of the epoxy powder-Mass loss (105°C±3°C,2h)		
TEST METHOD	SY/T4113.3-2019		GB/T 1768-2006		SY/T4113.9-2020		CSA Z245.20-2018/12.6		CSA Z245.20-2018/12.8		CSA Z245.20-2018/12.14		CSA Z245.20-2018/12.4		
TEST RESULT	G		69	G	G		1.466	G	1.1	G	1	G	0.38	G	

WE HEREBY CERTIFY THAT:

1. THE MATERIAL HEREIN HAS BEEN TESTED IN ACCORDANCE WITH ABOVE SPECIFICATIONS AND THE RESULTS OF ALL TESTS ARE ACCEPTABLE.
2. TESTING RESULTS SHOWED THAT THE COAT WAS EXCELLENT IN ABRASION RESISTANCE, CORROSION RESISTANCE, STAIN RESISTANCE AND SLIP RESISTANCE.
3. UNDER NORMAL CIRCUMSTANCES, THE LIFE OF THE GOODS IS 15 YEARS.

SIGNATURE



Typed by: 贾莹莹

Approved by: 张立

Date: 2025-01-23

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS
www.globalflux.com.co



GLOBAL FLUX S.A.S.

TIANJIN BAOLAI FORTUNE TRADE CO.,LTD

ADDRESS: 04, 9TH FLOOR, NINGTAI PLAZA, NO.1 XIAGUANG ROAD,

NANKAI DISTRICT, TIANJIN, CHINA

MILL TEST CERTIFICATES

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS
www.globalflux.com.co

REF NO: BLHJYPO90C

DATE OF ISSUE: 23/Jan/2025

GOODS: ERW FIRE PIPES

SPECIFICATION: ASTM A795

INVOICE NO.: HJYPO90-GLOBAL

HEAT NO.	SIZE				AMOUNT PCS	THEORETICAL WEIGHT (MT)	CHEMICAL COMPOSITION (%)														TENSION TEST			PRESSURE	FLATTENING /BENDING TEST	NON-DESTRUCTIVE TEST	VISUAL DIMENSION
	SIZE MM	SIZE IN	W.T. SCH	LENGTH (M)			C	Mn	Si	P	S	Cu	Ni	V	Ti	Cr	Mo	Ni+V	Ni+V+Ti	Ce	T.S.	Y.P.	E.L.				
							Mpa	Mpa	(%)	PSI																	
4B-07892	168.3	6"	SCH10	5.80	35	2.807	0.26	0.97	0.12	0.015	0.009	0.006	0.002	0.005	0.003	0.007	0.004	0.007	0.01	0.154	448	246	33	1000	G	G	G

COATING TEST (EPOXY POWDER)

Coating thickness ≥100μm	TEST ITEM	Cure time,min (232°C±3°C)		Gel time, s (205°C±3°C)		Paricle size //150μm,%		Paricle size //250μm,%		Thermal characteristics //Tg1, °C (20°C/min, N2)		Thermal characteristics //Tg2, °C (20°C/min, N2)		Thermal characteristics ΔH, J/g (20°C/min, N2)	
103	TEST METHOD	CSA Z245.20-2018/12.1		CSA Z245.20-2018/12.2		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.5		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7		CSA Z245.20-2018/12.7	
	TEST RESULT	0.5	G	14.90	G	0.46	G	0	G	63.9	G	101.2	G	42.4	G
TEST ITEM	Bending resistance (-30°C±3°C)		Abrasive resistance (CS-17, 1000g/1000r)		Chemical Resistance (PH2.5~3.0) (20°C±3°C, 90d)		Density, g/cm ³		Cathodic Disbondment, mm (24h,65°C±3°C, - 3.5±0.15V,3%NaCl, Saturated calomel reference electrode)		Adhesion, Rating (24h, 75°C±3°C)		Moisture content of the epoxy powder-Mass loss (105°C±3°C,2h)		
TEST METHOD	SY/T4113.3-2019		GB/T 1768-2006		SY/T4113.9-2020		CSA Z245.20-2018/12.6		CSA Z245.20-2018/12.8		CSA Z245.20-2018/12.14		CSA Z245.20-2018/12.4		
TEST RESULT	G		69	G	G		1.466	G	1.1	G	1	G	0.38	G	

WE HEREBY CERTIFY THAT:

1. THE MATERIAL HEREIN HAS BEEN TESTED IN ACCORDANCE WITH ABOVE SPECIFICATIONS AND THE RESULTS OF ALL TESTS ARE ACCEPTABLE.
2. TESTING RESULTS SHOWED THAT THE COAT WAS EXCELLENT IN ABRASION RESISTANCE, CORROSION RESISTANCE, STAIN RESISTANCE AND SLIP RESISTANCE.
3. UNDER NORMAL CIRCUMSTANCES, THE LIFE OF THE GOODS IS 15 YEARS.

SIGNATURE



Typed by: 贾莹莹

Approved by: 张立

Date: 2025-01-23

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS

GLOBAL FLUX S.A.S.

SOLUCIONES PARA FLUIDOS