

A growing manufacturer of polymer compounds  
Tel No:-+91-11-49901800, Website: [www.peecopolytech.com](http://www.peecopolytech.com)

Date:- 31-08-2025

<b>Product Test Certificate</b>				
<b>Grade Name</b>		PPBPRAOE-01		
<b>Material Description</b>		ELV PP Parts Recycle		
<b>Batch No.</b>		B0225G004		
<b>Property</b>	<b>Unit</b>	<b>Test Method</b>	<b>Certified Specification</b>	<b>PPPL Results</b>
<b>Physical Properties</b>				
Density	gm/cc	ASTM D792	0.93 ~ 1.04	0.99
Melt Flow Rate @ 230°C / 2.16 kg	gm/10 min.	ASTM D1238	16 ~ 23	19.2
<b>Mechanical Properties</b>				
Tensile Strength @ Yield	Kg/cm <sup>2</sup>	ASTM D638	170 ~ 198	187.2
Elongation @ Yield	%	ASTM D638	6 ~ 8	6.5
Flexural strength	Kg/cm <sup>2</sup>	ASTM D790	240 ~ 424	370.8
Flexural modulus	Mpa	ASTM D790	870 ~ 2050	1740
Izod Impact (Notched @ 23°C)	Kg/cm <sup>2</sup>	ASTM D256	20 ~ 27	22.8
<b>Thermal Properties</b>				
Filler content (@650°C )	%	PPPL Method	10 ~ 16	14.5
Heat Deflection Temperature @ 455 Kpa	°C	ASTM D648	80 ~ 110	88
<b>Chemical Substances</b>				
Cd	PPM	XRF Screening	1000	Nd
Pb			100	32
Cr-VI			1000	Nd
Hg			1000	Nd
Br			1000	24

This is a computer- generated sheet which does not require any signature.

UNIT 1: A-88, DSIIDC NARELA INDUSTRIAL AREA, DELHI- 110040, INDIA

UNIT 2: 304, HSIIDC INDUSTRIAL AREA, REFINERY ROAD, PANIPAT, HARYANA- 132140, INDIA

UNIT 3: 537, BARHI INDUSTRIAL AREA, SONIPAT, HARYANA- 131101, INDIA